Molecularly Imprinted Polymers as new tool in proteomics: the case study of SCLC diagnosis

Thesis for the degree Philosophiae Doctor

by

Cecilia Rossetti

Department of Pharmaceutical Chemistry

School of Pharmacy

Faculty of Mathematics and Natural Sciences

University of Oslo

Norway

© Cecilia Rossetti, 2017

*Series of dissertations submitted to the
Faculty of Mathematics and Natural Sciences, University of Oslo
No. 1932*

ISSN 1501-7710

All rights reserved. No part of this publication may be
reproduced or transmitted, in any form or by any means, without permission.

Cover: Hanne Baadsgaard Utigard.
Print production: Reprosentralen, University of Oslo.

Ai miei nonni

Table of Content

Table of Content.....	IV
Acknowledgement.....	VI
List of papers.....	VII
List of abbreviations.....	VIII
Abstract	XI
1 Introduction	13
1.1 Proteomics as new tool in cancer management.....	13
1.2 Mass spectrometry-based proteomics.....	14
1.2.1 Ionization techniques and mass analyzers in proteomics.....	15
1.2.2 Targeted MS analysis of proteins by bottom-up strategy	17
1.3 Sample preparation in targeted MS proteomics	21
1.4 Molecularly imprinted polymers for sample clean-up	23
1.5 ProGRP as model biomarker	26
1.6 Analytical strategies for the quantification of ProGRP	27
2 Aim of the study.....	29
3 Results and Discussion.....	31
3.1 Application of MIPs to the ProGRP quantification workflow.....	31
3.2 Synthesis of MIPs.....	32
3.2.1 Reversible Addition Fragmentation Chain (RAFT) Polymerization	33
3.2.2 Precipitation Polymerization.....	34
3.2.3 Magnetic Polymers.....	35
3.3 Development of a MIP-SPE protocol.....	37
3.4 Study and application of different formats for MIP-SPE.....	46
3.4.1 Off-line SPE -1 mL cartridge (Paper I).....	46
3.4.2 Off-line SPE -300 µL tips (Paper II).....	49
3.4.3 Off-line SPE -Magnetic Beads (unpublished work)	52
3.4.4 Off-line SPE -384-well filter plate (Paper III)	54
3.4.5 On-line SPE –Integrated Selective Enrichment Target (ISET)-plate (unpublished work)	58
3.4.6 On-line SPE trap-column (paper IV)	61
3.5 The enrichment of NLLGLIEAK	66

3.5.1	Theoretical aspect of NLLGLIEAK retention by MIP	66
3.5.2	Retention contributions by peptide properties	67
3.5.3	The role of pH in peptide retention.	70
3.5.4	The clean-up effect of MIP extraction: removal of matrix interferences and benchmark with other analytical strategies for ProGRP	73
3.6	Future perspectives	77
4	Concluding remarks	79
	References	80
	Papers	91

Acknowledgement

The work presented in this thesis was performed at the Department of Pharmaceutical Chemistry, School of Pharmacy, University of Oslo, from September 2012 to August 2016.

All the research work involved in this thesis has been performed as part of the Innovative Training Networks (ITN)- project “Robust affinity materials for applications in proteomics and diagnostics - PEPMIP”, supported by the Seventh Research Framework Program of the European Commission (Grant agreement number: 264699).

First and foremost, my deepest and sincere gratitude goes to my supervisors Léon and Trine. Your support was way beyond of the academic supervision; it was a boost of inspiration, confidence and motivation, guiding my path up to here. Thanks for your trust and your care over the entire PhD period.

A great thank goes to Börje SELLERGRÉN too, the leader of the ITN-project and co-author of almost all of my papers. The sharing of your knowledge and brilliant ideas was impressive and I always felt my pieces of work improved upon your revisions.

I would also like to thank all my other co-authors: Maren Christin Stillesby Levernæs, Odd Gøran Ore, Kishore Kumar Jagadeesan, Magdalena Świtnicka-Plak, Abed Abdel Qader and Peter Cormack for your work, for the excellent discussions and the time spent together.

Many thanks to all my colleagues from the Department of Pharmaceutical Chemistry which have filled up my days with laughs, chatters, advices, open talks, encouraging words and cakes: Stig, Astrid, Finn, Inger, Marthe, Hanne, Lars Erik, Kristine, Linda, Siri H. and Siri V.E., it was a pure pleasure sharing the second floor of the Farmasøytisk Institutt with you. Thank you Chuixiu, you were a really good teammate in the ITN-project and in the department as well. A special thank goes to Silje, Knut, Maren and Cecilie, you were nice colleagues at the beginning, but after short time it turned out you were actually amazing friends.

To my “Oslo crew”, thank you for being my family in Oslo and my heart in Rome. Thanks to my friends from Rome for shortening the distances and to my Ciu for being always with me.

To my family, thank you for your restless encouragement and infinite love.

Rome, September 2017

Cecilia Rossetti

List of papers

This thesis is based on the following published papers:

- I. Rossetti, C., Abdel Qader, A., Halvorsen, T.G., Sellergren, B., Reubsaet, L.
Antibody-free biomarker determination: Exploring molecularly imprinted polymers for pro-gastrin releasing peptide.
Analytical Chemistry (2014), 86(24): 12291-12298
- II. Rossetti, C., Ore, O.G., Sellergren, B., Halvorsen, T.G., Reubsaet, L.
Exploring the peptide retention mechanism in molecularly imprinted polymers
Analytical and Bioanalytical Chemistry (2017), 409(24), 5631-5643
- III. Jagadeesan KK, Rossetti C, Abdel Qader A, Reubsaet L, Sellergren B, Laurell T, Ekström S.
Filter Plate-Based Screening of MIP SPE Materials for Capture of the Biomarker Pro-Gastrin-Releasing Peptide.
SLAS Discovery (2017), 1:2472555216689494.
- IV. Rossetti, C., Świtnicka-Plak M.A., Halvorsen, T.G., Cormack, P.A.G., Sellergren, B., Reubsaet, L.
Automated protein biomarker analysis: On-line extraction of clinical samples by Molecularly Imprinted Polymers
Scientific Reports (2017) 7: 44298
- V. Rossetti, C., Levernæs, M.C.S., Reubsaet, L., Halvorsen, T.G.
Evaluation of affinity-based serum clean-up in mass spectrometric analysis: Plastic vs monoclonal antibodies.
Journal of Chromatography A. (2016), 1471: 19-26.

List of abbreviations

ABC	Ammonium bicarbonate
ACN	Acetonitrile
AIBN	2,2'-azobisisobutyronitrile
BLAST	Basic Local Alignment Search Tool
BSA	Bovine serum albumin
CHCA	α -cyano-4-hydroxycinnamic acid matrix
CID	Collision induced dissociation
EAMA.HCl	N-(2-aminoethyl) methacrylamide hydrochloride
DVB	divinylbenzene
DMSO	Dimethyl sulfoxide
ED	Extensive disease
EDMA	Ethylene glycol dimethylacrylate
ELISA	Enzyme-linked immunosorbent assay
ESI	Electrospray Ionization
FA	Formic acid
FM	Functional monomer
GRP	Gastrin Releasing Peptide
IS	Internal standard
ISET	Integrated Selective Enrichment Target
LC	Liquid chromatography
LD	Limited disease
LOD	Limit of detection
LTQ	Linear trap quadrupole
MAA	Methacrylic acid

MALDI	Matrix-assisted laser desorption ionization
MeOH	Methanol
MeCN	Acetonitrile
MIPs	Molecularly imprinted polymers
MIP-SPE	Molecularly imprinted polymers solid phase extraction
MS	Mass spectrometry
MS/MS	Tandem mass spectrometry
m/z	Mass-to-charge ratio
NaOH	Sodium Hydroxide
NCBI	National Center for Biotechnology Information
NH ₃	Ammonia
NIPs	Non-imprinted polymers
Nle	Norleucine
NSE	Neuron-specific enolase
PP	Precipitation Polymerization
ProGRP	Pro-gastrin releasing peptide
QQQ	Triple quadrupole detector
RP	Reverse phase
RAFT	Reversible addition–fragmentation chain-transfer polymerization
RSD	Relative standard deviation
SCLC	Small cell lung cancer
SIM	Selected ion monitoring
SPE	Solid phase extraction
SRM	Selected reaction monitoring
S/N	Signal-to-noise ratio
TFU	N-3, 5-bis (trifluoromethyl)-phenyl-N' -4-vinylphenylurea

TOF	Time of flight detector
TR-IFMA	Time-resolved immunofluorometric assay
UniProtKB	UniProt Knowledgebase
Z-group	benzyloxycarbonyl group

Abstract

The objective of this thesis was the integration of Molecularly Imprinted Polymers (MIPs), selective for peptides, in targeted proteomic workflows. This aim has been realized by coupling the MIP extraction with the mass spectrometric (MS) determination of Pro-gastrin releasing peptide (ProGRP), a marker for Small Cell Lung Cancer (SCLC). The scope of this thesis was to study the MIP ability to selectively enrich the signature peptide of ProGRP (NLLGLIAK) and the further development of targeted MS-assays, by the MIP-extraction of NLLGLIEAK from serum samples.

In Paper I, RAFT polymers based on EAMA and DVB were packed in 1mL-cartridges for off-line extractions. The optimization of the extraction protocol has been achieved by the “fine-tune” screening of the wash-solvent composition, which could lead to a maximized differentiation of MIP and NIP retentions. The selectivity of the MIPs has been challenged by sample extraction of increasing complexity. The MIPs were able to extract the NLLGLIEAK peptide from a simple standard peptide solution, from digested ProGRP in protein mixtures and from spiked digested serum samples as well. The LOD estimated from the latter experiments was assessed to be around 640 pM, being higher than the ProGRP reference limit, by a factor of 80. Despite the unsuitability of the developed method to fulfill the sensitivity requirements of diagnostic assays for ProGRP, the application of MIPs in targeted extraction of NLLGLIEAK was verified for the first time in complex mixtures such as digested serum samples.

In Paper II the same EAMA-based RAFT polymers DVB were tested using smaller off-line format as the 300- μ L SPE-Tips. In this paper, spiked samples of digested BSA were extracted on the SPE-tips by sequential elution with increased concentration of acetonitrile. Thus elution profiles for 21 BSA peptides were acquired and further evaluated via multivariate analysis. A PLS regression model studied the correlation between the physical-chemical properties of the peptides and their elution from MIPs. The results highlighted the contribution to the retention model from the peptides negative charges and pI. Experiments performed at diverse pHs confirmed the contribution of the ionic-interactions occurring mainly in the MIPs binding sites.

In Paper III, the off-line extraction of NLLGLIEAK on a 384-well filter plate supported the evaluation of a new polymer library. These were RAFT polymers obtained from the use of two different functional monomers (EAMA and MAA) and two cross-linkers (EDMA and

DVB). All the MIPs were assembled in the filter plate wells for the simultaneous screening of several SPE-protocols, with the aim of elucidate the best-performing sorbents and the optimized condition of use, at the same time. EAMA and DVB-based polymers were shown to achieve the good extraction recovery and background removal, using the SPE conditions previously found in Paper I. Additionally, these polymers showed the effective peptide-background removal loading the digested sample in pure acetonitrile. Moreover, the suitability of the 384-well plate of being efficiently coupled with both LC-ESI/MS/MS and MALDI-TOF platforms has been proved.

In Paper IV polymers synthesized via precipitation polymerization were prepared including EAMA only and EAMA + TFU, using DVB as cross-linker. Both polymers were packed into trap column for further comparison in on-line settings. The MIPs based on EAMA only showed the longer retention time of the target peptide (about 1 min longer than the MIPs based on both functional monomers and 3 min longer than the corresponding NIP). Hence this polymer was further used for the development of an analytical method, which could provide ProGRP quantification by automated on-line extraction from serum samples. Promising results were acquired from the application of the developed method to the quantification of NLLGLIEAK in patient sample with clinically relevant concentrations of ProGRP. Main breakthroughs were achieved in the analytical pipeline, such as low sample consumption (50 μ L), and low extraction time (about 10 minutes). However the LOD was the main advance for MIP extraction, reaching 17 pM and exceeding the ProGRP reference concentration by a factor of 2. Thus this paper has underlined the potential of applying MIP extraction for biomarker analysis.

In Paper V the aforementioned on-line MIP trap columns, were directly compared with immuno-capture and protein- precipitation, for the evaluation of the clean-up effects. Ion suppression, limit of detection and identification of the co-extracted peptides allowed the understanding of extraction process in all the three techniques. The results of the experiments and peptide identifications awarded the MIP extraction a powerful tool for the depletion of abundant proteins, ion-suppressing interferences and for the enrichment of tryptic peptides.

1 Introduction

This thesis focuses on the research area of molecular diagnostics in the frame of clinical proteomics, the application of proteomics to the study and management of human diseases in the clinics. In particular, the thesis embraces the development of new technology for the detection and quantification of a diagnostic tumor biomarker, used as model protein for the realization and application of newly developed diagnostic assays in a clinical context.

Hence in this chapter a brief description of the proteomic background, of the techniques which are commonly used and recently developed will be given together with a short introduction on new applications of Molecularly Imprinted Polymers in separation sciences and a brief overview on the analytical strategies for quantification of the model biomarker pro-gastrin releasing peptide (ProGRP).

1.1 Proteomics as new tool in cancer management.

The definition of “proteome” was coined in 1995 by Wilkins *et al.*, meaning the protein complement expressed by a genome [1]. The study of the proteome, proteomics, was thus intended as the large-scale characterization of the entire protein complement of a cell or complex tissue, but it is now extended to the study of single proteins expression with their variants and modifications [2].

The interest in proteomic studies has massively grown since the 1990s due to the key information directly associated to the protein expression, responsible for the phenotype of an organism [3]. Despite the completion of the human genome sequencing, proteomics is often preferred over genomics for a more accurate description of disease state, since modification in gene expression might not results in functional alterations and might not reflect the actual protein profile [4]. In fact there are approximately 20000 defined human genes but the total number of human proteins is still a core proteomics question due to the products of alternative splicing, polymorphisms and post-translational modifications (PTMs) which may generate over 100 different proteins from a single gene [5]. Hence the study of the protein profile allows the collection of the main information, crucial for the understanding of many biological functions carried out by proteins.

The discovery and the detection of distinct proteins associated to a specific disease state enables the understanding of potential therapeutic targets and the definition of possible biomarkers, which allow the early-diagnosis, prognosis and monitoring of the pathology progression.

Determination of biomarkers can thus have a great impact in the management of pathologies such as cancer, where the preclinical detection, the early-diagnosis and the monitoring of drug response it is crucial for the positive outcome of the treatment [6].

It is not surprising that recent advances in biomarker discovery are mainly focused in clinical oncology [7-13] and new fields such as the secretomics, a branch of proteomics which studies the protein secretion from cells in serum, have arisen attracting growing interest as promising method to study the metastasis development in patients [14]. Moreover serum contains circulating proteins generated by cancer cells or produced by the body as a reaction to the tumor which could be used as biomarkers a very early stage of tumorigenesis [15, 16].

The attention on proteomics translation into the clinics has intensified and gives the clinical proteomics the opportunity to benefit of the most recent technology progress. A well-known example is the mass spectrometry technology, which has greatly improved in sensitivity and accuracy making the mass spectrometry-based proteomics the method of choice for the analysis of complex protein samples, such as serum, and the discovery and quantification of diagnostic tumor biomarkers [17-21].

1.2 Mass spectrometry-based proteomics

Mass spectrometry (MS) has rapidly grown as the key-technology of proteomics, being capable of qualitative and quantitative analysis of protein and peptides [22]. The development of MS-based proteomics has been accelerated by the technological advances of the mass spectrometers, which have gained tremendous resolution and sensitivity. Biomarker discovery and quantification have incredibly benefited from MS improvements, attracting increasing interest from growing multi-disciplinary studies [23-28].

The progress of soft-ionization techniques, such Matrix Assisted Laser Desorption (MALDI) and Electrospray Ionization (ESI) and focus on detector geometry, such as triple quadrupole (QqQ), ion trap, and Orbitrap[®] analyzers have permitted protein and peptide analysis to achieve high specificity, accuracy and sensitivity.

1.2.1 Ionization techniques and mass analyzers in proteomics

MALDI

The MALDI source provides protein and peptide ionization *via* sublimation from a crystalline matrix using laser pulses. This source is generally coupled with a Time of Flight (TOF) detector which separates the ions according their mass, but recently also other high-resolution detectors have been coupled with the MALDI source, such as the Orbitrap[®] [29]. Due to the generation of mainly singly charged ions $[M+H]^+$, the MALDI-TOF can be used for the analysis of intact proteins (top-down proteomics) [30] and for the identification of proteins by a peptide-mass fingerprint approach. This method is based on the proteolysis of the proteins and identification by match between the acquired signals and the masses of the corresponding generated peptide, listed in annotated databases [31]. The MALDI-TOF is a simple, rapid and accurate technique which is useful for the analysis of intact proteins and peptides, which have been already extracted from complex matrices. Further development of the technique, as the Surface-Enhanced Laser Desorption Ionization (SELDI), allows the ionization to occur directly from the sample surfaces, such as tissue or affinity arrays [32]. Unfortunately, surface ionization is highly vulnerable to ion suppression caused by the composition of the analyzed tissue, since competing endogenous species together with a poor matrix crystallization can decrease the signal intensity of the analyte, severely limiting the application of the technique to quantitative analysis [33].

ESI

The ionization in the ESI source occurs by the application of a potential to a flowing liquid, which creates an electrospray where the solvent is successively removed by heat and an orthogonal drying gas creating ion droplets which enter in the mass spectrometer. Because of the capability of ionizing analytes from a liquid phase, the ESI source is of particular advantage to be coupled with liquid chromatography (LC), which can separates the protein and peptides from complex matrices [34]. A drawback of using LC-MS for the analysis of biological samples with abundant interfering species is the suppression of the ionization of the analyte of interest, which is also affected by salts, detergents and buffers from the original sample and the mobile phase of the LC system [35]. For this reason the Reversed Phase (RP) chromatography is generally employed, as the RP solvents are compatible with the ESI. Further developments of the ESI source provided the reduction of flow rates for the coupling with nano-LC systems (nano-ESI) which could greatly increase the sensitivity of mass spectrometer. The ions which are generated in the ESI source are multiply charged $[M+nH]^{n+}$,

thus the detectors which are generally used with the ESI have a geometry able to separate and select the different ion produced, as the triple quadrupole and the ion traps including Orbitrap[®] but also hybridized geometries are in place such Q-trap, Q-TOF, LTQ-Ion trap/Orbitrap[®], with the aim of achieving high resolution, high mass accuracy and efficient ion fragmentation. The analysis of fragmented ions in a setting such LC-ESI/MSⁿ, in fact, is often used to obtain accurate throughput protein identification [36] and validated peptide quantification as described later in this section.

Triple Quadrupole (QqQ)

The triple quadrupole mass analyzer consists of three quadrupole in series where the first and the third quadrupole are able to separate and select the ions according the m/z of the ions by the application of both direct radio frequency (RF) and current (DC) offset voltage, while the second quadrupole, where only RF is applied, is used as collision-cell merely. Such configuration gives the triple quadrupole high sequence-based selectivity and great sensitivity; for this reason widely used for the absolute quantification of peptides [37]. The use of sequential quadrupole gives the opportunity to operate in Selected Reaction Monitoring (SRM), where in the first quadrupole the ions to be fragmented are selected and, after collision-induced dissociation (CID), fragments are separated in the third quadrupole. This operational mode allows highly specific peptide quantification, even from complex matrices, since all the ions which are not selected in the first and in the third quadrupole are discharged. The investigated m/z range is generally included between 300 and 1500 (with an upper limit of 2000), preferring the use of triple quadrupole for targeted MS analysis of peptides, where wide dynamic range and exceptional detection sensitivity are essential [38].

LTQ-Orbitrap[®]

The commercial configuration of the Orbitrap[®] analyzer has a linear ion trap front-end (LTQ), which allows the trapping and further transmission of ion “packages” into the Orbitrap[®] analyzer. Here ions are trapped with circular motion around the central electrode inside the trap, with additional harmonic axial oscillation, which allows the separation between ion species. The consequent image current is detected and successively digitalized, processed by Fourier transform into frequencies domain and converted in mass spectra [39]. This detection mode confers extremely high resolution, promoting the Orbitrap[®] analyzer application to intact protein analysis, peptide mapping of complex mixture and protein structural studies [40]. Latest releases of this technology were aimed to the increase in sensitivity and dynamic range, with special focus on the development of MSⁿ detection mode, using multiple SRM

acquisition in a single Orbitrap[®] spectrum and combining multiple fragmentation techniques such as CID and Higher-energy collisional dissociation (HCD). These innovations allow obtaining many different and well-resolved fragments from a single precursor ion. Hence the abundances of the fragmented ions can be added together for the quantification low abundant proteins in complex biological mixtures [41].

Despite the triple quadrupole instruments have been widely established for quantitative analysis and still represent the detection method of choice for absolute quantification of diagnostic low abundant protein, the newest versions of the Orbitrap[®] analyzer have the potential of combining accurate broad-screening approach with sensitive targeted analysis of the less abundant species, without the need of developing pre-acquisition methods for the determination of the peptide transitions to be included in the final instrument methods and with the possibility of post-acquisition data processing for additional target peptides inclusion.

1.2.2 Targeted MS analysis of proteins by bottom-up strategy

The targeted MS analysis of a marker or a group of markers is generally aimed to their individuation and quantification from biological samples. Biomarkers are often expressed in low concentration in complex matrices as plasma or serum, where the protein concentration ranges from mg/mL to pg/mL [42]. This indicates the triple quadrupole as the mass-spectrometer of choice for sensitive quantification purposes. However, quantification of intact proteins is not feasible on triple quadrupole instruments due to the limited m/z upper limit. As consequence of this, there is the need of reducing protein complexity to peptides.

For this reason in the bottom-up approach proteins are usually digested with trypsin, a serine protease able hydrolyze the peptide bonds *via* a catalysis mechanism, comprising nucleophilic attack, protonation, and deacylation of the protein acting as substrate of the enzyme, as schematically represented in Figure 1.1

Figure 1.1 A schematic illustration of general catalytic mechanism for serine proteases: (A) the protein binds to the recognition site of the serine protease and exposes the carbonyl of the amide bond to be hydrolyzed; (B) the histidine of the trypsin recognition site (His 57) attracts the proton from the hydroxyl group of the trypsin serine (Ser 195) which thus attacks the carbonyl of the peptide substrate; (C) the amide of the subtract peptide accepts a proton from His 57 and dissociates; (D) a water molecule from the digestion media attacks the acyl-enzyme complex, restoring the catalytic triad and dissociating the C-terminal of the peptide from the enzyme. Reproduced with permission from Yang et al. [43]. Copyright © 2015, Korean Society for Parasitology and Tropical Medicine.

The tryptic proteolysis is very reproducible since trypsin specifically cleaves the amidic bonds at the C-terminal of Lysine (K) and Arginine (R), not bound to Proline (P), as schematically illustrated in Figure 1.2

Figure 1.2 Schematic representation of the tryptic digestion: in green are highlighted the cleavage sites of the proteins where trypsin is able to hydrolyze the amidic bond at the carboxyl side of the lysine (K) and arginine (R). In red are highlighted the miss-cleavage sites due to the lysine and arginine bond to a C-terminal proline (P).

Peptides shorter than 5 amino acids are not expected to be detected in the mass spectrometer, thus they have been red-crossed. Reproduced with permission from <https://unipept.ugent.be> [44]. Copyright © 2014 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.

The use of trypsin as digestion enzyme is very convenient for the formation in the ESI source of doubly charged $[M+2H]^{2+}$ or triply charged $[M+3H]^{3+}$ peptides, which can easily fragment in the CID cell, mainly giving b- and y-ion type, represented in Figure 1.3.

Figure 1.3 Representation of peptide fragmentation: (a) three possible cleavage points of the peptide backbone: A, B and C when the charge is retained at the N-terminal fragment of the peptide (b), and X, Y and Z when the charge is retained by the C-terminal fragment (c). The numbering indicates which peptide bond is cleaved counting from the N- and C-terminus respectively. In CID fragmentation mainly b-ions (b) and y-ions (c) are generated. Reproduced with permission from Roepstorffer et al. [45]. Copyright © 1984 Wiley Heyden Ltd.

These ions are easily identifiable and of particular advantage for the assignment of the peptide structures [46]. Among the generated peptides, the bottom-up approach provides for the selection of a single or more peptides as signature peptides, meaning that their quantification uniquely corresponds, with defined stoichiometric, to the initial protein quantification. These peptides have to be specific and unique, meaning that they occur only in the proteins to be quantified. In addition they should not contain missed-cleavage or PTM sites and their signal in the MS detector should not overlap with signals coming from the auto-digestion of trypsin. The MS signal of signature peptides should also have good intensity and a constant fragmentation pattern which allows the identification by tandem mass spectrometry. Adequate retention on the separation column is also desirable in order to avoid the co-elution of the signature peptide with the sample matrix compounds, at the beginning of the chromatographic run.

The following set-up of the SRM experiment consist in the analysis of the peptides coming from the protein digestion, by selection in the first quadrupole of the precursor ions which will be fragmented in the second quadrupole. Fragments will be then selected in the third quadrupole for further detection, allowing the monitoring of the selected transition only. Usually 2-5 transitions are acquired simultaneously for the reliable quantification of a signature peptide, since multiplexed analyses are allowed in this configuration. Expected precursor and fragments are provided from *in-silico* digestion of the protein sequence from databases and can be matched with the observed signals for correct identification.

Figure 1.4 shows a schematic overview of the targeted protein analysis by shotgun proteomics experiments.

Figure 1.4 Overview of shotgun proteomics: 1) sample proteins are digested into peptides using trypsin. Resulting peptide mixtures are processed to capture a particular class of peptides indicated with * and then separated using a liquid chromatography (LC) system coupled to a mass spectrometer; 2) Peptides are subjected to tandem mass spectrometry (MS/MS) analysis in a triple quadrupole (QqQ) resulting in the acquisition of MS/MS spectra; 3) The correct assignment of MS/MS spectra to peptide sequences is the first step in proteomic data processing. Reproduced with permission from Nesvizhskii A.I. [47]. Copyright © 2010 Elsevier B.V.

The quantification of the peptides is generally performed by the use of a stable isotope labeled peptide used as internal standard, able to exactly mimic the peptide to be quantified. The use

of synthetic peptides with stable isotope labeled ^{13}C and ^{15}N has shown to be a successful approach, showing same, ionization efficiency, fragmentation pattern (with constant defined mass difference) and chromatographic co-elution [48].

The peptide concentration is assessed from the regression curve built as the ratio of the signal of the tryptic peptide on the heavy labeled peptide vs the peptide concentration.

Advantages of the clinical diagnosis by LC-MS/MS over traditional immunoaffinity-assays, concern the rapidity of the method development and the relatively low cost-per-assay, even considered high initial cost for the instruments acquisition [49]. In addition, high specificity and decrease in false positive rate are gained [50].

However the application of LC-MS/MS for diagnostic purposes is not as sensitive as the immunoassays yet. For the achievement of low detection limits also in complex biological samples such as plasma and serum, where high levels of interfering proteins, salts, and lipids can suppress the analyte ionization, sample preparation has an essential role.

Use of LC-MS/MS methods in the clinics will slowly grow if method sensitivity is appropriate and the sample preparation is automated providing none or just few handling steps.

1.3 Sample preparation in targeted MS proteomics

Since the dynamic range of protein concentration in plasma or serum exceeds 10 orders of magnitude [51, 42], the detection of low-abundant proteins is challenging in these matrices. Thus the removal of highly abundant proteins is required for the broadening of the analytical dynamic range and detection sensitivity of the MS. Hence a variety of sample preparation techniques have been introduced to enrich the proteins or peptides of interest from complex matrix samples [52], especially with the perspective of achieving adequate sensitivity for clinical quantification of protein biomarkers by tandem mass spectrometry as alternative to immunoassays for serum and plasma samples [53].

A simple and inexpensive preparation technique is protein precipitation, which is widely applied in plasma and serum samples for the depletion of high-abundant proteins such as serum albumin [54]. This technique is mainly considered a pre-treatment of the sample to be further processed, since it suffers from high unspecificity, which causes a variable protein composition. However the rapidity, cost-effectiveness and the easy optimization by the use of

a wide range of solvents, allowed the protein precipitation to have wide spread in the proteomic workflows, often coupled to additional separation steps [55].

Also Solid Phase Extraction (SPE) represents a rapid and inexpensive sample preparation technique and for this reason extensively applied in the proteomic workflows [56, 57]. Recent developments in the polymer chemistry used for SPE sorbents allowed supplying a large variety of materials, from the most common RP, anion- and cation- exchange particles to the novel mixed-mode polymeric [58] and nanostructured [59] sorbents. However the inadequate specificity of the produced materials still give the SPE a secondary role in the enrichment of low abundant proteins [51], limiting the use of SPE mainly for the removal of extract contaminants, such as buffers, salts and detergents, before the MS-detection [60].

Among many techniques, the use of antibodies, both for the depletion of the abundant protein and for the enrichment of low-expressed proteins, has been shown to be a successful tool for the quantification of several low-abundant proteins [61, 48]. Excellent specificity has been achieved by targeting proteins of interest using monoclonal antibodies and coupling this immuno-extraction step with the MS detection. The resulting assays are characterized by high sensitivity and specificity. This combination overcomes the criticisms often moved to the immunoassays of being susceptible of cross-reaction from endogenous or exogenous substances reflected to high false positive rate [62]. In addition the MS detection allows for isoforms differentiation of the studied biomarker and for overcoming of the Hook effect, a reduction in signal intensities after saturation [63]. However also in immuno-extraction MS analysis, the stability to extreme physical-chemical conditions, the availability and the costs of the antibodies are still issues to be solved, remaining the major drawbacks to be faced in the development of new sensitive, robust and cost-sustainable methods for the clinical routine [64].

Recently, growing interest on inexpensive and automated sample preparation platform for the MS analysis of biomolecules has risen from clinical requirements [65-67]. In this perspective the use of high quality antibodies notably increases the costs for the development of analytical methods in clinical routine and “antibody-free” methods are now emerging in the bioanalysis field [68-72].

1.4 Molecularly imprinted polymers for sample clean-up

Molecularly Imprinted Polymers (MIPs) are synthetic materials with affinity recognition sites, able to recognize specific molecules by a lock and key mechanism and, for this reason; they are often defined as plastic antibodies [73, 74]. This exceptional ability originates from their characteristic polymerization process, which provides the use of a template molecule together with functional monomers and a cross-linker molecule [75]. The template molecule is often exactly the same molecule which will be the target of the molecular recognition; however the use of a close analogue of the target molecule has also been implemented with the aim of using a template which could be soluble in the reaction media [76, 77]. The functional monomers are molecules characterized by functional groups able to establish chemical bonds of intermediate strength, such as hydrogen bonds and weak ionic bonds, with the template molecule since their interaction should be modulated according to their solvation media. In fact at the beginning of the polymerization process, the functional monomers and the template molecule are solubilized together in a solvent which promotes the formation of strong interactions in between them. Successively, the addition of the cross-linker allows the incorporation of the coordination complex, assembled between the functional monomers and the template, in a three-dimensional network with high degree of reticulation. After the completion of the cross-linked polymer structure, the removal of the template molecule is required for the creation of the polymer binding sites, which will thus have complementary shape and functionalities to the molecule to be recognized, as shown in Figure 1.5.

Figure 1.5 Schematic representation of the molecularly imprinting strategy: (a) Functional monomers, (b) a cross-linker, and (c) a template molecule are mixed together. (1) The functional monomers form a complex with the template molecule. (2) The functional monomers copolymerize with the cross-linker. (3) As polymerization proceeds, an insoluble, highly cross-linked polymeric network is formed around the template. (4) Removing the template liberates complementary binding sites that can re-accommodate the template in a highly selective manner. Reproduced with permission from K. Haupt [78]. Copyright © 2003, American Chemical Society.

In order to achieve a complete removal of the template, the polymers are washed by solvents able to disrupt all the interactions between template and functional monomers, without

permanent modification or degradation of the latter, since the binding sites functionalities should be able to re-bind the template or the target molecule with high affinity [79]. This step is highly crucial since the partial removal of the template could lead to a decrease of the polymer affinity in the further polymer use, due to steric effects which do not permit the entrance of the target molecule into the binding sites. Moreover the template left in the polymer network could also give a bleeding effect, being gradually released in the following applications of the polymers to extraction experiments [80].

Together with the synthesis of the MIPs a parallel polymerization of Non-Imprinted Polymers (NIPs) is usually carried out, by applying exactly the same synthetic protocol used for the production of the corresponding MIPs, but omitting the addition of the template molecule. In this way, polymers without structured binding sites are obtained, and they can be used for the evaluation of the imprinting process. In fact, the direct comparison of the binding properties between MIP and NIP reveals the efficiency of the imprinting process, responsible of creating affinity sites in the MIPs only by the means of the template. Thus binding differences are expected between MIPs and NIPs, and for an efficient imprinting process, the targeting of the studied molecule is theoretically expected only in the MIPs, while the NIPs are not expected to be able to fit and bind the target molecule. The measure of the imprinting effect is commonly estimated by the imprinting factor defined as the ratio of the retention factor of MIP to the retention factor of NIP [81]

However, the NIPs often show binding capability toward the target molecule, which may be ascribed to unspecific interactions, occurring despite the absence of template-shaped sites. This circumstance, which has been usually interpreted as lack of selectivity and efficiency of the imprinting process, has been lately re-considered as an advantage for the obtainment of MIPs characterized by significant imprinting effect [82].

Due the tailored affinity of the MIPs, following the imprinting process, their application to the separation science has rapidly developed as research area in the field of analytical chemistry [83-90]. In this perspective many polymerization approaches have been developed for the synthesis of a variety of materials and formats, such as RAFT-MIPs [91, 92], magnetic MIPs [93, 94], microspheres [95-99], membranes [100, 101], monoliths [102-104] and nanogels [105-107].

The RAFT polymerization uses a chain transfer agent (RAFT agent) comprising a thiocarbonyl group which ensures living radicals for the polymerization. This synthetic

approach represents a key tool for the design of well-defined polymers with controlled molecular weight and polydispersity [92].

Another synthetic strategy applied for the production of MIPs microspheres of controlled dimensions and porosity is precipitation polymerization [99]. This approach allows the obtainment of rather clean polymers without using stabilizers or surfactants [97].

Magnetic MIPs can be easily obtained via coprecipitation of Fe^{2+} and Fe^{3+} ions, included into the pores of the polymers, obtaining magnetic polymers with defined dimensions and binding structure.

Particularly suited for the application in the field of the sample preparation, MIPs have been widely employed as solid phase extraction (SPE) sorbents for the development of clean-up protocols providing the specific extraction of small molecules from food, environmental and biological matrices [108-117].

The successful application of MIPs in the separation field has to be ascribed to the opportunity of performing highly selective extractions and separations under extreme physical-chemical conditions. In fact, MIPs are sorbents characterized by pronounced robustness which allows the use of high temperatures, wide pH range and broad organic solvent compositions, with almost any limitation of the experimental conditions. Moreover, due to their production process, their synthesis is time and cost-effective, assuring high degree of selectivity even with the use of relatively inexpensive reagents and limited polymerization time. It has to be additionally considered that MIPs can be developed for a wide variety of target molecules, thus broadening their application field.

A recent application field of MIPs is the extraction of macromolecules such as peptides and proteins [118-125]. This field has been investigated later than the extraction of small molecules, due to the complexity in the imprinting process of large molecules which encounters many issues to be overcome such as template stability, solubility and scarcity, conformational matching of fully- or partial folded proteins, uncontrolled multiple interactions and mass transfer limitations. However spreading interest has risen from this field aimed to replace the use of natural receptors with MIPs which can address and overcome the main drawbacks of using expensive antibodies.

Progress in this field have confirmed a new application of MIP extraction in proteomic workflows [126-136] and promising perspectives are now opened for MIPs integration in

diagnostic assays for clinical management of severe diseases such as cancer [137], Alzheimer [138] and Parkinson disease [139].

1.5 ProGRP as model biomarker

Pro-Gastrin Releasing Peptide (ProGRP) is a sensitive and specific biomarker for the Small Cell Lung Carcinoma (SCLC), a very aggressive tumor with early and rapid development of the metastases, representing around the 20% of the bronchogenic carcinomas [140]. Due to this characteristics, most of the patients receive diagnosis of SCLC when the carcinoma is already in a late stage with extensive disease (ED) which results in a median survival of approximately one year [141]. Thus the diagnosis of SCLC, when the carcinoma is still in an early stage with limited disease (LD), become of vital importance for a successful outcome of the treatment.

The use of ProGRP as serum biomarker for the early diagnosis and the prognosis of SCLC has been studied within several studies focused on SCLC markers [142-147].

ProGRP is the precursor for the gut hormone gastrin releasing peptide (GRP), present in nerve fibers, brain and in fetal neuroendocrine cells [148] and biologically active in a range of tissues and in cancer cell lines, due to the multitude GRP forms involved in physiological functions such as a mitogenesis, morphogenesis, and pro-angiogenesis activities [149].

Despite the high levels of GRP in plasma from SCLC patients, the use of ProGRP as diagnostic marker is preferred to the GRP use due the instable nature of the latter in serum [150-152].

Applied solely, ProGRP has high diagnostic sensitivity for SCLC (around 60–70% in early stage limited disease and 75–90% in advanced stage of extensive disease cases) with a prognostic significance highly correlated with clinical staging during chemotherapy [153]. These evidences argue for robust quantification of ProGRP for both SCLC diagnosis and prognosis, since quantitative information on its abundance in serum can strongly impact SCLC management [154, 155].

Accurate quantitative information on ProGRP in serum are strongly challenged by the low concentration level (7.6 pM) which has been proposed as reference value for the assessment between healthy and diseased state [143].

Three isoforms of cloned human ProGRP occur in serum with common region referred to the ProGRP fragment (31–98) which has been measured for the investigation of the ProGRP expression in SCLC tumor tissues [156]. Amino acid sequences of all the isoforms are reported in Figure 1.6, where it has been highlighted in bold the sequence referred to the ProGRP fragment (31–98) and underlined is the amino acid sequence used for the quantification of ProGRP by MS-assays (see §1.6 and §3.1)

```
>NP_002082.2 gastrin-releasing peptide isoform 1 preproprotein [Homo sapiens]
MRGRELPLVLLALVLCLAPRGRAVPLPAGGGTVLTKMYPRGNHWAVGHLMGKKST
GESSSVSERGSLKQQLREYIRWEEAARNLLGLIEAKENRNHQPPQPKALGNQQP
SWDSEDSSNFKDVGSKGKVGRLSAPGSQREGRNPQLNQQ

>NP_001012530.1 gastrin-releasing peptide isoform 2 precursor [Homo sapiens]
MRGRELPLVLLALVLCLAPRGRAVPLPAGGGTVLTKMYPRGNHWAVGHLMGKKST
GESSSVSERGSLKQQLREYIRWEEAARNLLGLIEAKENRNHQPPQPKALGNQQP
SWDSEDSSNFKDVGSKGKGSQREGRNPQLNQQ

>NP_001012531.1 gastrin-releasing peptide isoform 3 preproprotein [Homo sapiens]
MRGRELPLVLLALVLCLAPRGRAVPLPAGGGTVLTKMYPRGNHWAVGHLMGKKST
GESSSVSERGSLKQQLREYIRWEEAARNLLGLIEAKENRNHQPPQPKALGNQQP
SWDSEDSSNFKDLVDSLLQVLNVKEGTPS
```

Figure 1.6 Amino acid sequences of the three ProGRP isoforms expressed in serum. Adapted from the National Centre for Biotechnology Information (NCBI) database [157].

1.6 Analytical strategies for the quantification of ProGRP

ProGRP quantification is currently carried out in the clinical practice by enzyme-linked immunosorbent assays (ELISA). Among them few are commercially available (ARCHITECT[®] from Abbott Diagnostics [158], CanAg[®] from Fujirebio Diagnostics and Elecsys[®] from Roche) and a time-resolved immunofluorometric assay (TR-IFMA) has been developed at Oslo University Hospital, (Radiumhospitalet, Norway) [159].

All these assays are characterized by high sensitivity reaching low concentrations of ProGRP (below 3 ng/L corresponding to 0.2 pM), and they are thus able to diagnose the SCLC at early stage (LD). For this reason they represent the “golden standard” for the accurate quantification of ProGRP.

Mass-spectrometry based ProGRP assays have also been investigated [160-165]. The aim of developing MS-assays was to search for quantification strategies for ProGRP which could

have high sensitivity and could overcome the limitations related to the use of enzymatic assays, occasionally suffering from cross-reactions and false positive responses.

All the aforementioned MS methods were based on the bottom-up approach, which means that the quantification of the total ProGRP in serum is carried out by the means of the signature peptide NLLGLIEAK, a unique proteotypic peptide detectable with high signal intensity for all the ProGRP isoforms (see Figure 1.6). Among the different sample preparation applied, such as protein precipitation before trapping on a restricted access media (RAM) [163] or in-well immunocapture [162], only the use of antibodies immobilized onto magnetic beads coupled to a triple quadrupole mass spectrometer (QqQ) [165] achieved high sensitivity. This method, in fact, is characterized by a low limit of detection (1 pM) which is below the reference value of 7.6 pM and thus which allows a robust and sensitive quantification of ProGRP in serum also in the early stage of the disease.

Despite the use of antibodies has been shown to be essential for the realization of analytical method with high sensitivity, other studies have focused on ProGRP extraction with the aim of replacing antibodies with synthetic receptors, such as MIPs and aptamers [137, 166]. Synthetic receptors, in fact represent a convenient alternative to the biological receptors, in terms of availability, costs and robustness, which makes MIPs attractive for the realization of diagnostic assays, in the frame of the clinical management.

The aforementioned studies were mainly focused on the creation of new enriching systems as “proof of concept” by the development of MIPs, able to capture the NLLGLIEAK peptide [137], and the development of DNA aptamers able to bind the ProGRP protein [166]. However, in these studies the application of the newly produced synthetic receptors to the real quantification of ProGRP in serum samples was not investigated.

2 Aim of the study

The aim of this thesis is the application of peptide-selective MIPs to the targeted proteomic workflows. The scope of the research presented here is to get insight in the integration of MIPs in the MS-assay for the determination of the biomarker ProGRP. The latter has been chosen as model marker for the following reasons:

- MS-assays have been already developed for the quantification of ProGRP proving the suitability of its signature peptide NLLGLIEAK of giving reliable quantification of ProGRP by bottom-up approach.
- Abundance of ProGRP in serum is very low, increasing the analytical challenge for the quantification from patient samples
- Time and cost-effective quantification of ProGRP could have relevant impact on SCLC management

Hence, the following research questions were answered within this work:

- How the MIPs can be applied to the workflow of ProGRP quantification.
- How the MIPs targeting NLLGLIEAK can be synthesized. (Paper I, Paper III, Paper IV)
- How a SPE protocol is developed using MIPs as sorbents. (Paper I, Paper III, Paper IV)
- Which SPE-formats can be used for the integration of MIPs in ProGRP analysis. (Paper I, II, III, IV)
- How the enrichment of NLLGLIEAK occurs within the MIPs. (Paper II and V)

3 Results and discussion

3.1 Application of MIPs to the ProGRP quantification workflow.

The strategy applied within this work provided the implementation of the MIPs in the bottom-up approach for the determination of ProGRP by LC-MS/MS.

The bottom-up workflow requires the digestion of ProGRP with trypsin, as previously described in section §1.2.2. Among the generated peptides a specific peptide, NLLGLIEAK, was previously identified as signature peptide for the further determination of ProGRP by tandem mass spectrometry [161]. Besides fulfilling all the requirements of the signature peptides, this peptide offers the advantage to occur in all ProGRP isoforms (see Figure 1.6).

Hence the idea behind this work was to develop MIPs which could specifically recognize and capture the signature peptide of ProGRP in a SPE step prior the mass spectrometric detection, as schematically represented in Figure 3.1.

Figure 3.1 Schematic representation of the bottom up approach for the determination of ProGRP using MIP-SPE.

Thus the signature peptide NLLGLIEAK is the target peptide to be “fished-out” within the binding sites of the MIPs among a variety of peptides produced in the digestion of the sample (serum) containing ProGRP.

The use of NLLGLIEAK as target peptide, beyond the direct extraction of ProGRP signature peptide, offers the advantage of producing polymers with a simplified imprinting strategy. In fact the peptide has the adequate amino acid length (9 residues) which allows the solubility in the media used for the syntheses and, in the meanwhile, allows the creation of multi-

functional binding sites without the need of taking in account the folding or the multiple intra-molecular interactions occurring in peptides with long amino acidic length (> 15 residues).

The efficiency in recognizing the target peptide NLLGLIEAK and the ability of releasing the peptide in a clean solution, suited for mass-spectrometric detection, were evaluated and fine-tuned by the use of different synthetic approaches, the development and optimization of SPE protocols and the incorporation of the produced MIPs in different formats.

3.2 Synthesis of MIPs

The approach chosen for the synthesis of MIPs able to retain the signature peptide NLLGLIEAK was the targeting of the carboxylic acid group on the glutamic acid (E) and peptide C-terminus lysine (K). Different functional monomers and cross-linker were used for producing MIP libraries which were consequently tested for the optimization of the SPE protocol.

A previous combinatorial approach on polymer synthesis, aimed to develop MIPs able to target the peptide NLLGLIEAK, highlighted the suitability of using N-(2-aminoethyl) methacrylamide hydrochloride (EAMA.HCl), N-3, 5-bis (trifluoromethyl)-phenyl-N' -4-vinylphenylurea (TFU) and methacrylic acid (MAA) as functional monomers (FMs), and ethylene glycol dimethylacrylate (EDMA) and divinylbenzene (DVB) as cross-linker [137]. Structures of the abovementioned FMs and cross-linkers are represented in Figure 3.2.

Figure 3.2 Chemical structures of the functional monomers and the crosslinking agents used for constructing the libraries of imprinted polymers for NLLGLIEAK, MAA: methacrylic acid; TFMAA: trifluoro methacrylic acid; 4-VPy: 4 vinylpyridine; HEMA: 2-hydroxyethyl methacrylate; DEAEMA: diethylaminoethyl methacrylate; EAMA: N-(2-aminoethyl) methacrylamide hydrochloride; TFU: N-3, 5-bis (trifluoromethyl)-phenyl-N'-4-

vinylphenylurea, EDMA: ethylene glycol dimethylacrylate; DVB: divinylbenzene. Reproduced with permission from Figure 2 of A.A. Qader et al. [137]. Copyright © 2014 Elsevier B.V.

Moreover the study pinpointed the need of using templates containing either N-, or C- side chain protected groups in order to promote the peptide solubility in the reaction media and to avoid the signal overlap between the template remained in the polymer after the synthesis and the peptide captured from the sample. Thus for the synthesis of the template, the signature peptide NLLGLIEAK was protected at the N-terminus with a benzyloxycarbonyl group (Z-group), which allowed to enhance the template solubility in the polymerization solvents; while the C-terminal lysine was replaced by the norleucine (Nle) group, which permitted to easier interact with the FMs, overcoming the intramolecular competition caused by the lysine side for the anionic sites of the FMs. The structure of the template is shown in Figure 3.3.

Figure 3.3 Structure of the template Z-NLLGLIEA(Nle)

Building on this knowledge, the polymers used for this work were synthesized using the aforementioned functional monomers, cross-linkers and template molecule. Various synthetic approaches were developed and the obtained MIPs, with the related NIPs, were tested.

3.2.1 Reversible Addition Fragmentation Chain (RAFT) Polymerization

Polymers synthesized by RAFT polymerization were prepared at the Department of Environmental Chemistry and Analytical Chemistry, Technical University of Dortmund, Germany.

The polymerization used RAFT-modified silica beads which were grafted for the obtainment of a homogeneous thin polymeric film around the beads, illustrated in Figure 3.4.

Figure 3.4 Synthesis of MIP for NLLGLIEAK via RAFT-modified mesoporous silica. Template: Z-NLLGLIEA(Nle). RAFT: RAFT-agent. ABDV: initiator. Reproduced with permission from Figure 1 of Paper I. Copyright © 2014 American Chemical Society

The RAFT polymers were produced using for the imprinting process EAMA as functional monomer, DVB as cross-linker and the template Z-NLLGLIEA(Nle).

A small library of RAFT polymer was also created using a variety of functional monomers, cross-linker and template quantities, as reported in Table 3-1.

Table 3-1 PMIP and PNIP polymer manufacturing parameters. Reproduced with permission from Table S1 of Paper III. Copyright © 2017, © SAGE Publications

	Template	Functional monomer	Cross - linker	Molar ratio	Ratio RAFT/ABDV	Solvent
PMIP-1	T2, 1.99 mg (1.82 μ mol)	MAA, 20.63 μ L (0.243 mmol)	EDMA, 229.37 μ L (1.216 mmol)	0.3/40/200	3	DMSO/ACN (20:80)
PMIP-2	T2, 19.87 mg (18.24 μ mol)	MAA, 20.63 μ L (0.243 mmol)	EDMA, 229.37 μ L (1.216 mmol)	3.0/40/200	3	DMSO/ACN (20:80)
PMIP-3	T2, 3.34 mg (3.06 μ mol)	EAMA, 67.22 μ L (0.408 mmol)	DVB, 290.78 μ L (2.041 mmol)	0.3/40/200	3	DMSO/ACN (20:80)
PMIP-4	T2, 33.35 mg (30.62 μ mol)	EAMA, 67.22 μ L (0.408 mmol)	DVB, 290.78 μ L (2.041 mmol)	3.0/40/200	3	DMSO/ACN (20:80)
PNIP-1	-	MAA, 20.63 μ L (0.243 mmol)	EDMA, 229.37 μ L (1.216 mmol)	-/40/200	3	DMSO/ACN (20:80)
PNIP-2	-	EAMA, 67.22 μ L (0.408 mmol)	DVB, 290.78 μ L (2.041 mmol)	-/40/200	3	DMSO/ACN (20:80)

PMIP/PNIP: RAFT Polymers MIP and NIP; T2: Template Z-NLLGLIEA(Nle); MAA Methacrylic acid; EAMA N-(2-aminoethyl) methacrylamide; DVB: divinyl benzene; EDMA: Ethylene glycol dimethylacrylate; DMSO: dimethyl sulfoxide; ACN: acetonitrile. Chemical structures of the FMs and cross-linkers are shown in Figure 3.2

The spherical composite beads obtained with this strategy were homogeneous and dimensions ranged around 30 μ m in diameter, which allowed the easy polymer packing in all the tested formats, using sedimentation under vacuum of the polymeric suspension in organic solvents.

3.2.2 Precipitation Polymerization

The polymers synthesized by precipitation polymerization were prepared at the Department of Pure and Applied Chemistry, University of Strathclyde, United Kingdom.

Two different imprinted polymers were designed by using two different functional monomers: the EAMA monomer and the TFU monomer (see Figure 3.2). The MIP A was designed in order to target the negative charge of the template by EAMA only; while in the MIP B the targeting occurs by both EAMA and TFU simultaneously, as shown in Figure 3.5.

Figure 3.5 Representation of the non-covalent molecular imprinting of Z-NLLGLIEA[Nle] for MIP A (A) and MIP B (B). The carboxylic acid groups in the glutamic acid (E) residue and C-terminus of Z-NLLGLIEA[Nle] are drawn explicitly for emphasis, since these functional groups are involved in the self-assembly of the Z-NLLGLIEA[Nle] with the functional monomers (FMs). The complexed synthetic receptors depict the hypothetical molecularly imprinted binding sites formed upon the free radical copolymerization of a molecular complex of Z-NLLGLIEA[Nle] and FM(s) with cross-linker (DVB-80). Reproduced with permission from Figure 1 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group

Since the dimensions of the obtained polymers were in the low micron-sized range (diameters $\leq 5 \mu\text{m}$), the particles were particularly well-suited for the packings in trap columns to be integrated in the LC-MS/MS system (Paper IV, see §3.4.6). The wet-packing into trap columns was performed under high pressure using the facilities of G&T Septech, Ski, Norway.

3.2.3 Magnetic Polymers

The co-precipitation of Fe^{2+} and Fe^{3+} ions allowed the obtainment of magnetic polymers with the same dimensions and binding structure as the polymers tested in Paper IV (see §3.4.6) with additional magnetic properties.

The magnetic polymers were also prepared at the Department of Pure and Applied Chemistry, University of Strathclyde, United Kingdom.

Two different polymers type (core-shell and non core-shell) were synthesized according two different strategies, described in detail by Świtnicka-Plak [167].

In Figure 3.6 a schematic representation of the two synthetic approaches is presented.

Figure 3.6 Schematic representation of the synthesis of magnetic MIPs core-shell (A) and non core-shell (B).

The core-shell particles (A) were obtained by a two-synthetic step protocol: the initial polymeric core was synthesized by typical precipitation polymerization using the cross-linker DVB and the monomer MAA. The further co-precipitation of Fe^{2+} and Fe^{3+} into the polymeric pores under basic conditions allowed the obtainment of the magnetic core. Thus a second synthetic step allowed the growth of the MIPs coating around the magnetic core.

The non core-shell particles (B) were obtained by a single synthetic step: the pre-formed macroreticular MIPs were further processed for the integration of the ions Fe^{2+} and Fe^{3+} into the pores obtaining directly the non core-shell magnetic MIP.

A small library was created also for magnetic polymers in order to pinpoint the synthetic strategy which could give better selective retention of the target peptide. The feed condition for each polymer tested are reported in Table 3-2

Table 3-2 Composition of core-shell and non-core shell magnetic MIPs and their corresponding NIPs.

Name	Functional monomer	Crosslinker	Template
MIP core-shell EAMA+TFU	MAA, EAMA.HCl, TFU	DVB-80	Z-NLLGLIEA[Nle]
NIP core-shell EAMA+TFU	MAA, EAMA.HCl, TFU	DVB-80	-
MIP core-shell EAMA	MAA, EAMA.HCl	DVB-80	Z-NLLGLIEA[Nle]
NIP core-shell EAMA	MAA, EAMA.HCl	DVB-80	-
MIP non-core-shell EAMA+TFU	EAMA.HCl, TFU	DVB-80	Z-NLLGLIEA[Nle]
NIP non-core-shell EAMA+TFU	EAMA.HCl, TFU	DVB-80	-
MIP non-core-shell EAMA	EAMA.HCl	DVB-80	Z-NLLGLIEA[Nle]
NIP non-core-shell EAMA	EAMA.HCl	DVB-80	-

MAA Methacrylic acid; EAMA N-(2-aminoethyl) methacrylamide; TFU: N-3, 5-bis (trifluoromethyl)-phenyl-N'-4-vinylphenylurea; DVB-80: divinyl benzene.

3.3 Development of a MIP-SPE protocol

For the development of a MIP-SPE protocol, able to extract the target peptide NLLGLIEAK from a complex matrix such as serum, the strategy applied was composed of different steps:

1. Optimization of the wash/elution condition with NLLGLIEA[K-¹³C₆¹⁵N₂]
2. Increase in sample complexity (from a single peptide standard solution to digested ProGRP isoforms and further to protein mixture, e.g. ProGRP with NSE)
3. Optimization of the sample pretreatment before the application of the MIP-SPE to serum samples.

The initial tests on all the polymers packed in all the formats were decided to be performed by using the NLLGLIEA[K-¹³C₆¹⁵N₂], the heavy-labeled form of the signature peptide ProGRP which is used as internal standard for the quantification of the peptide in the LC-MS/MS method. This choice has been determined by the need of initially testing the polymers with a molecule which could have exactly the same retention mode as the target peptide NLLGLIEAK within the polymer binding sites and which could simultaneously give a different MS signal. This circumstance is crucial in case the template used for the synthesis of MIP could give, after extreme pH or prolonged thermal stress, degradation products with similar structure or *m/z* values to the signature peptide and its MS fragmentation products. In fact the removal of the template molecule after the completion of the synthetic process is often incomplete and small amount of the template molecule could be gradually released from the polymer and overlap with the signature peptide signal [79, 168].

The initial tests with the heavy-labeled NLLGLIEAK form assured that the obtained response came from the amount of peptide loaded onto the cartridge for the test. With the further SPE-development, once the polymers were checked for the absence of template release, the heavy-labeled form of the signature peptide was used as internal standard and the test were performed with the digested samples.

The development of a SPE protocol for MIPs targeting peptides from complex samples aims to find the optimal conditions (loading, washing and elution composition and volumes) which make the peptide extraction selective (desirably specific), quantitative (with sufficient recovery) and reproducible.

The selectivity of the extraction is strongly dependent on the condition applied in the SPE protocol and, for MIP sorbents, can be primarily evaluated by the comparison with the NIP. In

fact, being the NIP the exact analogue of the MIP without binding sites, the retention of the target peptide is expected to be less specific. The target peptide is expected to be retained in minor extent without being differentiated from molecules with similar physical-chemical properties. However such retention differences are rarely verified because of the multiple interactions of the target molecule with the polymers, also external to the MIP binding site [82].

The application of a generic SPE protocol prior the additional optimization could not highlight the minimal differences between MIP and NIP polymers. Hence, we initially applied a “fine-tune” approach which had the aim to discover eventual MIP and NIP retention differences and to pinpoint the condition which could improve the selectivity by maximization of the retention differences between MIP and NIP.

The experiments consisted in gradually increasing the eluent strength after activation and sample load of the cartridges (at this stage the sample was still the standard solution of NLLGLIEA[K-¹³C₆¹⁵N₂]) and a final elution, as schematically illustrated in Figure 3.7. By the application of sequential washes it is possible to evaluate the cumulative peptide recovery from the cartridge which is expected to have different profiles for MIP and NIP, since the NIP is expected to elute the target peptide at lower acetonitrile concentrations.

Figure 3.7 Schematic illustration of the experiment leading to the “fine-tune” approach by sequential washes of the cartridges with increasing acetonitrile percentages (from 5 to 100% MeCN) for the final elution profile of the MIP and corresponding NIP.

An example of this approach applied to MIPs and NIPs packed in 1 mL-cartridges (Paper I) is given in Figure 3.8. In this experiment, the sequential washes were formerly performed by using an increase of 10% in organic content and successively was repeated by reducing the intervals to a 2.5% increase of organic content, in the range between 5 and 30% of acetonitrile, in order to create a zoom effect where the differences between the MIP and NIP could be better appreciated.

Figure 3.8 Cumulative total recovery of NLLGLIEA[K-¹³C₆¹⁵N₂] after loading 500 µL of 1nM solution in 50mM ABC buffer on MIP (black) and NIP (gray) cartridges followed by sequential wash step using aqueous solution (500 µL each) containing increasing percentage of acetonitrile (A) 10% intervals (5-100% MeCN) and (B) 2.5% intervals (5-30% MeCN). Reproduced with permission from Figure 2 of Paper I. Copyright © 2014 American Chemical Society.

From this experiment it was possible to discover a concentration range of acetonitrile which could give different peptide retention in MIP and NIP and which could be further used as wash composition in order to obtain maximized differences in the peptide recovery in the elution step, as shown in Figure 3.9.

Figure 3.9 Elution recoveries of NLLGLIEA[K-¹³C₆¹⁵N₂] after loading 500 µL of a 1nM solution in 50mM ABC buffer on MIP (black) and NIP (gray) followed by wash (5 mL) using solutions containing different MeCN percentages (N=3). Reproduced with permission from Figure 3 of Paper I. Copyright © 2014 American Chemical Society

Following the results of this experiment, the optimal concentration of acetonitrile in the wash step was set at 7.5%, which represented the best compromise between the MIP and NIP elution differences and the acceptable overall peptide recovery.

The “fine-tune” approach was applied as initial screening experiment for the polymers packed in 1 mL-cartridge (§3.4.1, Paper I), 300 μ L-tips (§3.4.2, Paper II), 384-well plate (§3.4.4, Paper III) and trap-column (§3.4.6, Paper IV). In all the tested formats this approach was a valuable tool for the discovering of the organic composition in the wash step which could result in high recovery and maximized selectivity, as shown also in Figure 3.10, where the experiment confirmed the use of 7.5% of acetonitrile to be added in the wash composition of the screened SPE protocols in Paper III.

Figure 3.10 Recovery (R%) of the analyte in the (A) wash and (B) elution fraction collected after SPE of 20 μ l of a 5 nM NLLGLIEAK sample in 50 mM ABC buffer on MIP (black square)/NIP (white circle) phases with washing buffer containing different percentage of ACN. Reproduced with permission from Figure S7 of Paper III. Copyright © 2017, © SAGE Publications

In the on-line format (Paper IV), the wash composition was strongly dependent from the initial organic composition of the chromatographic run, due to the on-line setup as illustrated in Figure 3.11.

Figure 3.11 Schematic representation of the mobile phase composition within the on-line setup: the loading buffer flushes the MIP trap-column until the valve switching for 10 minutes. At this time point the valve is switched and the solvent composition of the wash step (5% of MeCN) is modulated from the chromatographic pumps directly in the MIP trap-column. Such solvent composition is also the initial composition of the gradient starting after 10 minutes the valve switching. Adapted with permission from Figure 3 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

Hence, the screening approach was here mainly used for the appraisal of the MIP/NIP pair which could give larger differences of peptide retention, as shown in Figure 3.12.

Figure 3.12 Differences in retention times of NLLGLIEA[K₁₃C₆¹⁵N₂] (1 nM) on the MIPs (orange) and corresponding NIPs (black) for both polymer pairs (A and B). Reproduced with permission from Figure 4 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

From these experiments MIP A was chosen for integration in the on-line SPE method: using an isocratic run with 5% of acetonitrile, this polymer showed the highest peptide retention (longest retention time) and a significantly retention difference with the corresponding NIP.

Taking the screening experiment as the basis for a tailored SPE development, the elution composition can be easily optimized by the direct comparison of the different conditions to be tested in the MIP cartridge only, as shown in Figure 3.13 (see Paper I).

Figure 3.13 Elution efficiency in the MIP-SPE expressed as the recovery of target peptide NLLGLIEA[K-¹³C₆¹⁵N₂] (1nM solution in 50nM ABC buffer) in the elution fractions (500 µL) divided by the overall recovery in the SPE protocol (N=3). Reproduced with permission from Figure 4 of Paper I. Copyright © 2014 American Chemical Society.

In Paper I the eluent composition which gave the highest peptide recovery in the elution step was shown to be a mixture of acetonitrile, water and formic acid (80:17:3 respectively).

The further tests with the digested ProGRP isoforms allow the verification that the developed SPE protocol is able to capture the signature peptide also in samples where other peptides are present. As an example, in Paper I the MIPs packed in 1 mL-cartridge were preliminary tested with the NLLGLIEA[K-¹³C₆¹⁵N₂] standard solution for the development of a SPE-protocol which could enrich the target peptide NLLGLIEAK. Successively the sample complexity was increased ranging from a single peptide standard solution to the digested solution of the short-isoform of ProGRP, as shown in Figure 3.14.

Figure 3.14 Comparison of the recoveries of NLLGLIEA[K₁₃C₆¹⁵N₂] standard solution (darker color) and the target peptide (NLLGLIEAK) resulting from the digestion of short ProGRP (AA 31–98) (brighter color), using the optimized extraction protocol Reproduced with permission from Figure 5 of Paper I. Copyright © 2014 American Chemical Society.

Since the retention behavior of both MIP and NIP cartridges did not change upon the increased number of peptides, the SPE protocol was considered suited for the enrichment of the target peptide. Thus the MIP-extraction was further challenged by the loading of a digested protein mixture including a longer ProGRP isoform, the isoform 1 (see Figure 1.6), mixed with an excess of another protein biomarker for SCLC, the Neuron-Specific Enolase (NSE).

This experiment had the intention to highlight the retention difference between NLLGLIEAK and other tryptic peptides by the simultaneous detection of the signature peptide of ProGRP isoform 1 (LSAPGSQR), the signature peptide of NSE (ELPLYR) and the target peptide NLLGLIEAK. These peptides come from the tryptic digestion of two SCLC biomarkers which are overexpressed in patient serum, thus it is important that the MIPs are able to selectively enrich the target peptide in the eluate, removing the other two peptides during the washing step of the SPE protocol. The results of the experiment are shown in Figure 3.15.

Figure 3.15 Recoveries of NLLGLIEAK, LSAPGSQR, and ELPLYR (the signature peptides of ProGRP, ProGRP isoform 1 and NSE, respectively) in the SPE of a mixture of digested ProGRP isoform 1 (AA 1–125 + 8) and NSE (γ -enolase) (1:3) on MIP (black) and NIP (gray) cartridges. Reproduced with permission from Figure 7 of Paper I. Copyright © 2014 American Chemical Society.

This figure shows the extensive loss during the washing step of the peptides LSAPGSQR and ELPLYR, originating from the protein digestion of ProGRP isoform 1 and NSE (γ -enolase) respectively; while the occurrence of the target peptide is predominant in the elution step. This means that selective retention toward the target peptide occurs within the MIP particles using the optimized SPE protocol, which was thus applied to the extraction of NLLGLIEAK from a very complex sample matrix: a serum solution spiked with ProGRP (see §3.4.1).

Also the sample pretreatment can be adjusted by testing different experimental conditions in the MIP cartridge only. The pre-treatment of the sample has to be optimized and performed before the extraction of serum samples in order to avoid clogging of the cartridges with the high abundant albumin. In fact the sample complexity of the serum is notably increased compared to protein mixture digests and, together with the presence of many different peptides competing with NLLGLIEAK for the functional groups of the MIP binding sites, the limited capacity of the cartridge has to be taken into consideration. Protein precipitation with cold acetonitrile was a rapid and easy sample pre-treatment already used for the determination of the short isoform of ProGRP [156]. This technique allows for the precipitation of larger proteins, with higher folding attitude than ProGRP, which does not precipitate and can be separated from the precipitated proteins by the simple collection of the clean supernatant.

For this reason protein precipitation was performed before the tryptic digestion and the following extraction of the spiked or patient sera into the MIP off- and on-line cartridges (see Paper I, Paper IV and Paper V respectively).

An example of pretreatment optimization (from Paper IV) is reported in Figure 3.16.

Figure 3.16 Extraction optimization (A-D) by using 1 nM NLLGLIEA[K-¹³C₆¹⁵N₂]: (A) duration of the wash step (5 % MeCN) on MIP A column; (B) duration of the loading step (20 mM FA) on MIP A column; (C) capacity evaluation by extraction of different serum volumes; (D) injection volume evaluation by extraction of 50 µL of serum. Sample pretreatment optimization (E-F) by using 37 nM ProGRP isoform 1 spiked serum samples: (E) evaluation of trypsin amount and reduction and alkylation after protein precipitation (PP) on spiked serum; (F) optimization of the MeCN:serum ratio (v/v) in protein precipitation step. Reproduced with permission from Figure 6 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

In Paper IV the overall optimization of the on-line extraction and related sample pre-treatment adjustment was evaluated according the maximized signal intensity in the MS detector. Load and wash duration were performed using the only heavy-labeled peptide solution, being two steps of the SPE-protocol development, while the pretreatment optimization, in terms of serum and injection volumes to be used, was optimized by the spiking of the serum samples with the heavy-labeled peptide. The digestion was optimized according the enzyme/substrate ratio and the need of the reduction/alkylation steps, while protein precipitation was optimized depending on the acetonitrile volume to be used. These pretreatment steps have been optimized by the extraction of serum samples spiked with ProGRP isoform 1, in order to mimic the actual complexity of a clinical sample.

3.4 Study and application of different formats for MIP-SPE.

The incorporation of the MIPs in different, multiple formats represents one of the main advantage of such enrichment strategy. The versatility of the MIP particles to be packed in various arrangements allows the determination of the studied analyte for many diverse purposes, strictly depending from the investigated formats. The quantification of NLLGLIEAK, indeed, has not been achieved with the same degree of sensitivity and specificity among all the studied setups and the analytical high throughput of the applied platforms was closely related to the final purpose of the study; i.e. the quantification of low NLLGLIEAK concentration in serum or screening of polymer libraries or modeling of polymer retention mechanism.

The investigated formats can be grouped in two main categories: off-line and on-line formats according to the suitability of the extracted sample to be directly transferred into the LC-MS/MS system (on-line formats) or if further sample handling is required (off-line formats).

In this section the different formats used for the MIP-SPE experiments are presented together with the main results achieved using each format.

3.4.1 Off-line SPE -1 mL cartridge (Paper I)

The MIP-SPE cartridge with 1 mL volume was the first format to be studied for the extraction of the signature peptide NLLGLIEAK, as reported in Paper I.

The MIPs packed in this format were synthesized by RAFT polymerization from porous silica supports (see §3.2.1). The cartridge preparation was performed in-house and provided the sedimentation under vacuum of homogeneous slurry containing about 20 mg of polymers into 2 mL methanol. The cartridge capping was realized between two fritted polyethylene disks (20 µm pore size) as shown in Figure 3.17

Figure 3.17 Schematic representation of the MIP-SPE cartridges with 1mL volume.

This format allowed rapid and easy extraction of the target peptide NLLGLIEAK in matrices of different complexity (from a single peptide standard solution to serum samples) using a common vacuum manifold for SPE cartridges which permitted the dropwise collection of the eluate from the cartridges.

The experimental condition of the final SPE protocol optimized with this format and the LC-MS/MS system are detailed described in Paper I.

Among the results obtained during the study of MIP particles packed in 1mL-SPE cartridges (Paper I), significant evidence was collected on the selective retention of the MIP particles toward the target peptide NLLGLIEAK; using the optimized SPE protocol for the extraction of serum spiked with ProGRP isoform 1.

The use of ProGRP isoform 1 allowed to follow the signals for both the signature peptide coming from ProGRP, one related to the isoform 1 only (LSAPGSQR) and the other related to the target peptide (NLLGLIEAK) and allowed to confirm that the only NLLGLIEAK was recovered in the elution step as shown in Figure 3.18.

Figure 3.18 Serum sample extraction. Recovery of NLLGLIEAK and LSAPGSQR after SPE on MIP (black) and NIP (gray) of digested serum samples spiked with ProGRP isoform 1 (AA 1–125 + 8). Serum volumes: 1 mL (A), 500 µL (B), and 250 µL (C). Reproduced with permission from Figure 9 of Paper I. Copyright © 2014 American Chemical Society.

The figure shows the occurrence of the only target peptide in the MIPs elution, since the LSAPGSQR is lost during the washing step. An important aspect to be considered is also the difference in NLLGLIEAK retention between the MIP and the respective NIP, highlighted also in this experiment. The use of a fine-tuned extraction protocol in fact allows for the enrichment of the target peptide mainly in the MIP elution also extracting serum samples fortified with ProGRP.

The actual extraction of NLLGLIEAK from serum samples (Figure 3.18), represented the main novelty in MIP-SPE application to the extraction of tryptic peptides since was the first

time that MIPs were selective for tryptic peptides in serum samples. At the same time the figure also highlights here the increasing recovery of NLLGLIEAK when the volume of the spiked serum sample to be extracted decreases. Such observation has been explained by the limited MIP capacity which has been also a crucial constraint in the application of the MIP extraction in the on-line format also (Paper IV).

From the work presented in Paper I some considerations can be anticipated on the packing of RAFT-MIP particles in 1mL SPE cartridges. Such off-line format allowed the determination of NLLGLIEAK in serum samples, which is an essential result itself, but the application of this extraction format to the analysis of patient samples with clinical relevant concentration of ProGRP, is limited from the LOD of the method which is about 80 times higher than the reference limit of ProGRP. This circumstance is probably caused by the uncomplete recovery from the cartridge and by the further sample handling after the SPE extraction prior the chromatographic analysis, missing in the on-line setups. In addition the relatively large sample and eluent volume to be used (compared to other formats successively discussed) together with the relatively large amount of polymer to be packed in each cartridge represent a drawback of this format. The latter aspect strongly limits the number of parallel extractions, which makes this format unsuited for the high throughput screening of polymer libraries and SPE operating conditions, as it has been achieved instead with other formats such as 384-well filter plate. On the other hand these circumstances required the re-use of the same cartridges for the repetition of the extraction experiments, demonstrating the opportunity to easy regenerate these sorbents after the SPE step, which further decreases the extraction costs compared with the immuno-based techniques.

3.4.2 Off-line SPE -300 μ L tips (Paper II)

In order to reduce the sorbent amount required in the off-line 1 mL cartridge a smaller format was investigated using 300 μ L pipette tips. About 800 μ g of the same RAFT polymers based on EAMA monomer and DVB, as previously used in the 1 mL cartridges (see §3.2.1), were packed into the Bevel Point™ pipette (1–300 μ L, VWR) on an etched polyethylene (PE) disk support, placed at the bottom of the tip as shown in Figure 3.19.

Figure 3.19 Schematic representation of the MIP-SPE tips with 300 μ L volume.

Due to the low polymer consumption for the packing of the tips, the packing of several SPE-tips was allowed with the same polymer synthetic batch. This gave the opportunity to perform parallel extractions simultaneously, which was particularly advantageous in increasing the confidence of the peptide identification and relative quantification through the peptide screening in the Orbitrap mass spectrometer. This format was thus used for the study of the retention mechanism in both MIP and NIP sorbents, defining the identity and abundance of the peptides in each elution fraction collected from the tips. Using a simple protein model, such as serum albumin, the cartridges were used in order to find a relation between different peptides' physical-chemical properties and their retention in the polymers (see §3.5.2), with the final aim of increasing the knowledge on the interaction occurring between sorbent and different peptides, during the SPE, as described in paper II.

Despite other authors investigated MIPs packed in 200 μ L- format using C8-membrane disks as polymer supports at the bottom of the tips [169, 170], the need of studying the MIP and NIP retention mechanism solely, without the retention contribution of the C8 membrane, has driven to the choice of using polyethylene disk supports (as used in Paper I), punched at the bottom of the tips (see Figure 3.19).

The use of the Orbitrap mass spectrometer allowed the identification and signal acquisition of the BSA peptides simultaneously and thus allowed the analysis of the peptides co-eluting with the NLLGLIEAK from the MIP when the applied eluent was varying in composition

(sequential elutions with increasing acetonitrile concentrations as previously described in §0). The elution profile of the identified peptides is shown in Figure 3.20.

Figure 3.20 Cumulative recovery of the serum albumin peptides from MIP cartridge plotted versus the acetonitrile percentage (MeCN %) applied for each sequential elution step. Reproduced with permission from Figure 1 of Paper II. © Springer-Verlag GmbH Germany 2017

Among the identified and recovered peptides from the MIP cartridge, the target peptide NLLGLIEAK is one of the most retained peptides, indicating different and strong interactions occurring between the polymers and NLLGLIEAK. The elution profiling of the extracted peptides was equally performed on the NIP-tips in order to build retention models by partial least square regression, which could explain similarities and differences in polymers retention, as discussed in paper II (see §3.5.2).

The main advantage of using 300 μ L-cartridges was the low sample, eluent and sorbent amount required for each single extraction. The parallel extractions could be performed in the same analytical section without the need of regenerate and re-use the same tips, reducing the overall analytical time required for the whole study and showing the suitability of this format for SPE-screening purposes. However the use of smaller volumes and polymer amount affect the reproducibility of the tips-packing, the extraction recovery and the cartridges overload compared to the 1mL-cartridges, thus the application of such format to quantitative ProGRP determination from serum samples is not feasible as for the 1 mL-cartridges or for the on-line SPE formats.

3.4.3 Off-line SPE -Magnetic Beads (unpublished work)

Magnetic MIPs have been synthesized and provided from Strathclyde University, (see §3.2.3) and tested within this project. The handling of the magnetic format was directly harmonized with the antibody-coated magnetic beads extraction, previously employed for the quantification of ProGRP in serum samples [165]. The opportunity to simply use a magnet to localize the MIP particles containing the targeted peptide NLLGLIEAK (Figure 3.21) allows the rapid discharge of the unbound peptides, resulting in an overall rapid and simplified NLLGLIEAK extraction. Time-consuming or difficult packing procedures requiring specific equipment are hence avoided by the use of such format.

Figure 3.21 Schematic representation of the magnetic MIP extraction.

The extraction protocol applied to the magnetic MIPs was a direct adaptation of the optimized SPE protocol realized with the MIP particles packed into 1 mL cartridges.

The particles were suspended (about 50 mg) in 500 μ L of acetonitrile and successively pipetted into 1.5 mL Eppendorf vials. The acetonitrile was discharged and the magnetic MIPs were conditioned with 250 μ L of ammonium bicarbonate buffer 50 mM before the loading of the digested ProGRP standard solution. The beads and the sample were incubated for 30 minutes in a sample mixer providing rotation and shake of the vials in order to enable the interaction of the target peptide within the MIP binding sites. The extensive wash step was realized by three additions of 250 μ L of the aqueous solution containing 7.5% acetonitrile; while the elution was performed by the addition of 500 μ L of the organic solution containing 80% acetonitrile and 5% of formic acid. In order to gain better understanding of the extraction process, all the fractions were collected, dried, reconstituted with 0.1% formic acid and analyzed into the chromatographic system coupled with the mass spectrometer. The LC-

MS/MS analysis was performed with the same LC method and the same MS settings used with the 1 mL-SPE cartridge format and as reported in Paper I.

The experiments which were carried out were aimed to compare four different magnetic MIP particles: core shell, non-core shell, EAMA-based and EAMA + TFU-based particles. The aim of the experiments was to show which of the different particles type could give higher efficiency in selectively retain the target peptide NLLGLIEAK by the removal of other peptides. For this reason ProGRP isoform 1 was digested and extracted onto all the magnetic MIP particles and the recovery of both NLLGLIEAK and LSAPGSQR was calculated in each fraction as shown in Figure 3.22.

Figure 3.22 Recoveries of the extraction of 10 nM ProGRP isoform 1 by magnetic MIP.

The non-core shell magnetic MIP based on EAMA solely gave the higher elution recovery of NLLGLIEAK and, at the same time, the complete removal of the other peptide LSAPGSQR during the load and wash steps. This suggests that polymers based on the EAMA monomer are able to efficiently retain the target peptide in the binding sites. Polymers based on TFU and EAMA showed also NLLGLIEAK retention but in this case the NIP polymers have better elution recoveries, meaning that the interaction of the target peptide is not completed directly in the binding sites. Moreover the core-shell particles retained the peptide LSAPGSQR, with a recovery about 20% in the elution step.

Magnetic MIP particles were thus easily applied for the screening of a small polymer library, highlighting the polymers with higher affinity and specificity for the target peptide NLLGLIEAK. The extraction comprises an incubation step which increases the sample preparation time if compared with the other off-line format as the 1mL-SPE cartridges and the 384-well filter plate. The amount of the polymer required for the extraction strongly depends

on their magnetism and on the synthesis yield in the Fe^{2+} and Fe^{3+} incorporation into the polymers. Before the extraction, the particles were washed in acetonitrile for the removal of the polymers which were not magnetic enough to be pulled down by the magnet. When the polymers have pronounced magnetic properties, the amount to be used is relatively small, allowing parallel extractions with the same polymer batch. This feature and the easy-handling of the overall extraction make this format more suited for screening purposes than for the quantification of NLLGLIEAK in serum matrices for diagnostic purpose.

3.4.4 Off-line SPE -384-well filter plate (Paper III)

The high-throughput screening of polymers libraries requires a setup of an extraction technique which could easily and rapidly extract a variety of different sorbents and eluents, simultaneously.

Moreover the opportunity to analyze the collected fractions with different mass spectrometry techniques is one of the main goals in such screening approach since deeper understanding of the polymers performances is achieved evaluating the target peptide recovery together with the capability of the polymers to deplete matrices of increasing complexity from interfering peptides.

In this scenario the 384-well extraction plate plays a fundamental role as SPE-format being capable of many simultaneous extractions (up to 384) and capable of being off-line interfaced with different analytical platforms such as LC-MS/MS and MALDI-TOF analysis, as described in Paper III.

The extraction occurs directly in the filter plate, loading the slurred polymers into a MultiScreen HTS 384-well filter plates from Millipore made of styrene acrylonitrile with polyvinylidene fluoride membrane/polyester supports. The application of vacuum for the SPE was realized by a Millipore MultiScreen HTS Vacuum Manifold coupled to a vacuum pump. The eluates were collected into Thermo Scientific Nunc plates made of polystyrene, as shown in Figure 3.23.

In addition the dispense of multiple solutions in the different wells was realized by a laboratory automation workstation; in order to enable fully-automated sample preparation which could increase the reproducibility and rapidity of the extraction.

Figure 3.23 Schematic representation of the 384-well filter plates and the workflow of the SPE step in the microwell. (A) 384-well filter plate. (B) SPE sample preparation, where the sample is transferred to the microwell loaded with SPE material (1), followed by a wash step to remove undesired components (2), and the captured analytes are then displaced by the elution step (3). Reproduced with permission from Figure 1 of Paper III. Copyright © 2017, © SAGE Publications.

The 384-well format was preliminary tested by performing the simultaneous screening of five SPE protocols with identical load and elution phases (50 mM ABC and 80% ACN with 3% FA) and only differing for the composition of wash solutions (5, 10, 30, 50 and 95 % ACN). The MIP and related NIP selected for the experiment were RAFT-polymers prepared as describer in Table 3-1 (see §3.2.1). All the SPE fractions were collected and analyzed on the LC-MS/MS system (Figure 3.24), previously used for the detection of NLLGLIEAK also during the study of 1 mL-cartridges format (Paper I). This approach allowed the direct benchmarking of the recoveries obtained using the 384-well format and the studied 1 mL-SPE cartridges.

Figure 3.24 Comparison of recovery percentage (R%) in each extracted fraction after loading (L) 20 μ l of a 5 nM NLLGLIEAK peptide in 50 mM ABC buffer on MIP/NIP phases followed by 80 μ l washes (W) using solutions containing different percentage of ACN and eluting (E) with 80% ACN and 3% FA. Reproduced with permission from Figure S6 of Paper III. Copyright © 2017, © SAGE Publications.

The figure shows good agreement with the recovery trends previously obtained in the study of 1 mL-cartridge (see Paper I). The SPE protocol which uses a wash buffer containing 5% of acetonitrile (ACN) gives the highest recovery of NLLGLIEAK from both MIP and NIP polymers and differences between the polymers are not emphasized. On the other hand using higher concentrations of acetonitrile in the wash buffers (from 10% to 95% in ACN) allows the differentiation of the NLLGLIEAK recoveries from the MIP and the NIP, emphasizing the MIP retention but reducing at the same time the peptide elution recovery in both MIP and NIP elution. Hence, in order to highlight the selective retention of NLLGLIEAK, the strength of the wash buffer should be 7.5% ACN representing a compromise between the NLLGLIAK recovery and the maximized retention differences between MIP and NIP polymers.

The accordance of these results with the results obtained in a similar experimental setup using the 1 mL-cartridge format (Paper I) means that the difference in SPE formats does not affect the experimental outcome of the polymer investigation, which is thus reliable and only depends on the polymers properties and the SPE protocols applied.

The 384-well plate was hence used as screening format to investigate a polymer library and different SPE protocols, all in a single analytical session, for the simultaneous evaluation of NLLGLIEAK recovery and background removal. The experiment performed for this purpose was tested on a matrix of reduced complexity such as β -casein digest spiked with NLLGLIEAK, which was extracted on a polymer library including 6 different polymers (see Table 3-1) with 4 different SPE protocols according the Table 3-3.

Table 3-3 Different SPE Optimization Conditions Used for the Semiquantitative Method for Materials PMIP-1–4 to PNIP-1–2. Reproduced with permission from Table I of Paper III. Copyright © 2017, © SAGE Publications

SPE Condition	Load Buffer	Wash Buffer	Elution Buffer
L1W1E1	ABC + 0.5% FA	7.5% ACN + 0.5% FA	80% ACN + 3% NH ₃
L2W2E2	ABC + 0.8% NaOH	7.5% ACN + 0.8% NaOH	80% ACN + 3% FA
L3W3E2	ABC	7.5% ACN	80% ACN + 3% FA
L4W4E3	100% ACN	100% ACN + 0.1% FA	50% MeOH + 5% FA

L: load solution; W: wash solution; E: elution; ABC: ammonium bicarbonate buffer; FA: formic acid; NaOH: sodium hydroxide; ACN: acetonitrile; NH₃ ammonia; MeOH: methanol

In order to evaluate the background removal, the mass spectrometric analysis was performed off-line after the extraction on a MALDI LTQ Orbitrap XL (Thermo Fisher Scientific) mass spectrometer.

The intensity of the target peptide NLLGLIEAK and the sum of all other peptides detected in the extracts coming from the different polymers with the different SPE protocols (Table 3-3) are plotted in Figure 3.25

Figure 3.25 Intensity of the analyte peak (NLLGLIEAK) and sum of the background peaks (i.e., sum of the intensity of the peptide peaks corresponding to the β -casein digest), corresponding to each SPE material in four different conditions using MALDI-MS analysis: condition 1, L1W1E1; condition 2, L2W2E2; condition 3, L3W3E2; and condition 4, L4W4E3. The box shows the MALDI-MS intensities generated by the replicates of the corresponding polymer, and the solid black line inside the box represents the median. Black dots above and below the boxes represent the outliers. Reproduced with permission from Figure 5 of Paper III. Copyright © 2017, © SAGE Publications.

The collected data showed a substantial decrease in background signals when the protocols L3W3E2 and L4W4E3 providing load solution 3, wash solution 3, elution 2 and load solution 4, wash solution 4, elution 3, respectively (see Table 3-3) were applied. Although the

NLLGLIEAK intensity is lower than the intensities measured with the protocols L1W1E1 and L2W2E2, the protocols L3W3WE2 and L4W4E3 allowed the selection of two candidate sorbents (MIP-4 and related NIP-2) which showed selective retention of the target peptide in these conditions.

Hence, this experiment confirmed the feasibility of using the SPE-protocol L3W3WE2 on EAMA-based MIP and NIP, as previously optimized in Paper I. Moreover, the experiment highlighted the opportunity of using a completely new extraction procedure such as L4W4E3 which could drastically remove the signal interferences from other matrix peptides, enriching the target peptide NLLGLIEAK. In addition, the coupling of the 384-well format with MALDI-MS analysis allowed the rapid screening of the polymer library by avoiding the extended LC-MS analysis time.

The 384-well plate thus demonstrates to be a convenient SPE format which can be easily interfaced with different MS setups creating an efficient experimental platform for the high-throughput screening of SPE protocols and sorbents. The chance of automatizing the sample extraction by using a Laboratory Automation Workstation further minimized the sample preparation time together with the risk of sample handling errors, giving a convenient and robust analytical platform to be employed for screening purposes.

3.4.5 On-line SPE –Integrated Selective Enrichment Target (ISET)-plate (unpublished work)

In the frame of searching for SPE-platforms, which can be directly integrated in the mass analyzers for rapid, automated and high-throughput screening of polymer libraries, the ISET plate was investigated as SPE-format for on-line MALDI-TOF analysis of NLLGLIEAK.

The ISET plate is a silicon wafer, 53 x 41 mm in size, etched by Deep Reactive Ion Etching (DRIE) technique in order to produce 96 miniaturized wells (30 x 30 μm) where is possible to pack sorbent materials and to perform 96 parallel SPE experiments (left part of Figure 3.26) [171-173]. The plate has the dimension and geometry suited for the fitting in an automated sample handling workstation and in the target holder of a MALDI loading-plate.

Since no sample transfer/treatment is needed before the ionization in the mass analyzer, the ISET plate format can be considered an on-line format.

The SPE process occurs directly on the wafer by the application of vacuum in a 384-pitch manifold and the eluate is collected by the rotation upside down of the plate, which allows the collected drop to dry with the crystallization of the α -cyano-4-hydroxycinnamic acid (CHCA),

added in the elution phase for the ionization in the MALDI source, as schematically represented in Figure 3.26.

Figure 3.26 Schematic representation of the MIP-SPE experiment on the ISET-plate. Adapted with permission from Figure 1 and Figure 2 of Jagadeesan et al. [173]. © 2015 Elsevier B.V.

Diverse experiments were performed with this format with the aim of testing several SPE protocols and sorbent polymers. As example of the data obtained with the ISET-MALDI-TOF one of the experiments is detailed as follow: three of the polymer library (2 MIPs and related NIP, see paragraph §3.2.1) were RAFT polymers based on EAMA monomer and DVB cross-linker and six different protocols were applied simultaneously, according Table 3-4.

Table 3-4 Experimental plan for the screening of the materials MIP-3–4 and NIP-2 using 6 different wash conditions starting from the same loading and elution buffers.

Load (10 μ L)	Wash 1 (2x2.5 μ L)	Wash 2 (2x2.5 μ L)	Wash 3 (2x2.5 μ L)	Wash 4 (2x2.5 μ L)	Wash 5 (2x2.5 μ L)	Wash 6 (2x2.5 μ L)	Elution (2 μ L)
50 mM Ammonium bicarbonate	30 % MeOH	30% MeOH, 3% NH ₃	30% MeOH, 0.1% TFA	20 % MeOH	20% MeOH, 3% NH ₃	20% MeOH, 0.1% TFA	80% MeCN, 3% TFA, 10 mg CHCA

MeOH: methanol; NH₃ ammonia; TFA: trifluoroacetic acid; MeCN: acetonitrile; CHCA: α -cyano-4-hydroxycinnamic acid matrix.

The polymers were washed and suspended in MeOH before the packing into each ISET well by the *sedimentation* of 2 μ L of the polymer slurry, according the setup described by Jagadeesan et al.[173]. After MeOH removal by vacuum flow-through, 10 μ L of the tryptic digest mixture (500 nM Yeast Alcohol dehydrogenase 1 (YADH-1) and 500 nM ProGRP isoform 1) were loaded onto the polymers. The SPE protocols were subsequently applied and the elution drops were collected as described above, lowering the vacuum with the aim to create a confined spot of the analyte around the well outlet-hole, for a better crystallization of the CHCA matrix. After plate rotation and spot complete dryness the plate was inserted into the MALDI plate holder and full scan MALDI –TOF spectra were acquired. As an example of the spectra acquired the first 3 SPE protocols on MIP 3 and NIP 2 (see Table 3-1) are reported in Figure 3.27.

Figure 3.27 MALDI-TOF spectra of the eluates on the ISET-plate of the EAMA-based MIP (MIP 3) and related NIP (NIP 2) of the Table 3-1, applying the first the SPE protocol different described in Table 3-4.

From the signals acquired in the MALDI-TOF spectra the most predominant are the m/z ratios 948.48 and 2313.15, corresponding to the peptides EALDFFAR and ATDGGAHGVINVSVEAAIEASTR respectively. These peptides belongs to the YADH-1 digestion, while the other signal visible at m/z 1618.84 is probably a peptide coming from the auto-digestion of the trypsin, since it has been revealed also in the MALDI-TOF spectra of the ProGRP and YADH-1 digestion before the extraction and additionally, does not belong to the tryptic peptides set obtained for both protein in the *in-silico* digest.

The signal of NLLGLIEAK (m/z 970.60) is seen in the background of many of the acquired spectra, but it was not predominant in any spectra and its signal did not show any significant increase or decrease in connection with the protocol applied.

From the experiments performed on the ISET plate, none of the conditions tested allowed the selection of a MIP/NIP pair or SPE protocol which could selectively retain the target peptide (NLLGLIEAK) or substantially deplete the analyzed peptide from the interfering background. A reason for this circumstance could be found in the limited capacity of these polymers, which requires higher polymer quantities in order to achieve selective and efficient extractions. Another reason could be found in the MALDI-TOF detection mechanism where the ions intensity strongly depends on the ions attitude to fly in the TOF detector. Further information regarding the ions abundancy could be thus obtained by using another detection technique such as ESI-MS. In this context the 384-well plate format was a more convenient format to be applied for fast high-throughput screening of RAFT MIP-libraries, since the amount of polymers in each well could be 10 times higher than the amount allowed in the wells of the ISET-plate and, additionally, the collected eluates could be analyzed by ESI-QqQ and MALDI-TOF at the same time.

3.4.6 On-line SPE trap-column (paper IV)

In order to set up an automated biomarker quantification requiring low sample volume and minimal sample handling, the SPE cartridge was directly integrated in the LC-MS systems, by using a trap column before the analytical column, as shown in Figure 3.28.

Figure 3.28 Schematic representation of the on-line SPE trap-cartridge integrated in the LC-MS/MS system: at the beginning the serum peptides are loaded into the trap column along the red line and excess goes to the waste, while LC pumps equilibrate the analytical column (black line). Successively the valve is switched and the trap column is connected (via the dashed black lines) to the LC pumps and the analytical column coupled to the ESI-MS/MS for data acquisition.

MIPs and NIPs synthesized via precipitation polymerization (see §3.2.2) were packed into trap columns ($1.4 \times 5\text{mm}$) between $1\text{ }\mu\text{m}$ stainless steel frits at G&T Septech site (Ski, Norway). The wet packing of the polymers was performed by suspending around 10 mg of polymer in 1200 μL of acetonitrile. 200 μL of the slurry were subsequently loaded into the cartridge and flushed using a flowrate of 500 $\mu\text{L}/\text{min}$ of 70%acetonitrile, as described in Paper IV.

The cartridges were first checked for selectivity comparing MIP and NIP cartridges and observing the retention time of the target peptide NLLGLIEAK and the retention time of a peptide which should not be retained as LSAPGSQR (proteotypic peptide of the ProGRP isoform 1 only). Since the study was focused on the peptide separation occurring into the MIP and NIP trap column only, the digested ProGRP isoform 1 was loaded onto the MIP and NIP columns directly coupled with the ESI interface of the triple quadrupole without the analytical column. The SRM transitions corresponding to NLLGLIEAK and LSAPGSQR [165] were acquired from the moment of the injection to the end of the gradient. The results of this experiment are shown in Figure 3.29.

Figure 3.29 MS/MS Chromatograms of 10 nM digested ProGRP isoform 1 obtained by using MIP B (orange) and NIP B (black) coupled directly to the MS detector without analytical column. Reproduced with permission from Figure 2 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

From the figure, differences between MIP and NIP retention can be seen. The peptide LSAPGSQR is poorly retained in both cartridges giving a slight retention difference (0.25 min), while NLLGLIEAK is longer retained in the MIP (1.27 minutes longer than the NIP). In addition the NLLGLIEAK elution time above the 19 minutes, was indicative of the suitability of the MIP column to be further used as a trap column followed by the analytical column.

A wide optimization of the sample preparation, sample volume, loading buffer composition, load and wash duration successively allowed the analysis of low concentration of NLLGLIEAK from spiked serum samples (Paper IV).

The linearity of the method was verified over a range of ProGRP concentration from 180 pM to 109 nM and by looking at the S/N of the chromatogram corresponding to the lowest concentration, the method LOD was assessed around 17 pM. This was the lowest LOD achieved with MIP selective for NLLGLIEAK, especially comparing this result with the LOD achieved by using the 1 mL-cartridge format (Paper I).

Thus patient sera were extracted and analyzed as shown in Figure 3.30.

Figure 3.30 Analysis of patient serum samples: chromatograms of NLLGLIEAK (orange) and the Internal Standard (IS) NLLGLIEA[K- $^{13}\text{C}_6^{15}\text{N}_2$] (black) (left side) and corresponding ion spectra for selected reaction monitored (fragments y6 and y7) for NLLGLIEAK determination (right side). Reproduced with permission from Figure 7 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

The ProGRP amounts obtained from this analysis were benchmarked with the ProGRP amounts previously obtained analyzing the same samples using two reference methods: the immunocapture – liquid chromatography-mass-spectrometric method (immuno-LC-MS) and the time-resolved immuno fluorometric assay (TR-IFMA) [174], as shown in Table 3-5.

Table 3-5 Benchmarking of ProGRP concentrations in patient samples measured by the three analytical methods (Reproduced with permission from Table 1 of Paper IV). Copyright © 2017, Rights Managed by Nature Publishing Group.

	MISPE-LC-MS	immuno-LC-MS[174]	TR-IFMA[174]
Patient 39	2402 pM	922 pM	2425 pM
Patient 43	1029 pM	918 pM	1899 pM

From the table is possible to assume that analyzing samples with high ProGRP amount (such as Patient_39 serum) by the MIP-SPE-LC-MS method the obtained results are close to the amount found by TR-IFMA, which is the golden standard of the analytical methods for the total ProGRP quantification and is currently used in the clinics for diagnostic purposes.

Another consideration raised from the results reported in Table 3-5 is that, in case of extended disease, clinically relevant ProGRP concentrations are well above the LOD achieved with this method. Despite these promising results, the developed method is not able to discriminate healthy donors close to the reference limit of 7.6 pM.

Although this cannot be achieved at the present moment, this format represents a significant breakthrough in creating a new alternative for total ProGRP quantification which uses synthetic receptors (such as MIPs) instead of recombinant antibodies.

In addition, remarkable advances in ProGRP quantification are intrinsic into the on-line MIP SPE format since this format enabled direct integration of the enrichment step with the LC-

MS system, resulting in the first automated extraction method for ProGRP quantification in patient samples with low sample consumption (only 50 μ L were required for the analysis).

The on-line SPE trap-cartridge was thus not intended to be used for polymer screening purposes, but the development of this format aimed to comply the analytical requirements from the clinics in creating a time- and cost- effective analytical strategy with minimized sample handling and sample-volume consumption.

Since this format was shown to be the most promising setup for clinical serum analysis, the extraction by on-line MIP-SPE was further benchmarked in terms of specificity, sample clean-up efficiency and sensitivity in Paper V (see §3.5.4) with two sample pre-treatment techniques previously applied in the LC-MS analysis of ProGRP: the immuno-capture on magnetic beads and protein precipitation [165, 161].

For the evaluation of the methods sensitivity, 6 lots of serum were spiked with ProGRP (short isoform) at two concentration levels, 2 and 20 nM, and further processed using the three sample preparation strategies. Results are summarized in Table 3-6.

Table 3-6 Spiked serum analysis by using immunocapture, protein precipitation and MIP extraction as sample pre-treatments. Reproduced with permission from Table 1 of Paper V. Copyright © 2016 Elsevier B.V.

	Serum volume (μ L)	Concentration (nM)	S/N ^a	Intensity ^a	Area ^a	RSD ^b (%)	LOD ^c (pM)
Immunocapture	1000	2	4711	20325	523991	7	1
	50	2	442	628	10178	16	14
	1000	20	31918	340428	8230091	8	2
	50	20	5798	12345	300639	11	10
Protein Precipitation	1000	2	38	9	211	57	160
	50	2	63	34	397	34	96
	1000	20	252 ^d	85 ^d	1170 ^d	n.d	238
	50	20	389	128	1576	70	154
MIP	50	2	534	336	6669	7	11
	50	20	8431	2953	54342	11	7

n.d: Not determined; ^aAverage on the 6 spiked lots of serum samples; ^bRelative to the area; ^cBased on S/N = 3; ^dNumber of sample successfully analyzed: 1.

When the sample volume to be extracted 50 μ L MIP extraction performances were shown to be close to the performances of immunocapture, in terms of signal intensity and reproducibility (RDS $\leq$ 11 %). This was the first time that MIP for peptides achieved high affinity, close to the antibodies performances.

Limit of detections, calculated from the S/N values, showed to be in accordance with the values previously reported [161, 165, 132], considering the lower ProGRP concentration (2 nM).

The use of small sample volumes to achieve low detection limits is a convenient property of the extraction techniques to be employed in the clinics. However, the low volume in the MIP extraction (50 μ L) represents the upper capacity limit due to cartridge overload, while the immunocapture beads are able to extract larger sample volumes (1000 μ L) for the reaching of very low detection limits.

The extraction of such large volume into the on-line MIP is not possible and sensitivity cannot be improved by the extraction of larger serum volume as shown in Figure 3.16.

Despite the limitation in achieving LOD below the reference limit of ProGRP (8 pM), the advantage of the on-line MIP format is the rapid and automated (minimal sample handling is required) extraction which has shown to be sensitive and reproducible, also by re-using the same cartridge for several extractions.

3.5 The enrichment of NLLGLIEAK

3.5.1 Theoretical aspect of NLLGLIEAK retention by MIP

Among the polymers tested, the MIP and NIP based on DVB and EAMA.HCl (cross-linker and functional monomer respectively) showed to have high affinity for the target peptide NLLGLIEAK.

By looking at the chemical structures of the polymer components and the target peptide (Figure 3.31 and Figure 3.32), it is possible to pinpoint the groups which interact in the experimental condition tested.

Figure 3.31 Chemical structures of the DVB (left side) and the EAMA.HCl (right side) used for the MIP and NIP synthesis.

Figure 3.32 Chemical structures of the target peptide NLLGLIEAK.

It can be assumed that ionic and hydrophobic forces, taking place at the same time, are the responsible of the peptide retention in both MIP and NIP polymers. However such mixed mode-retention mechanism is differently completed in the MIP and the NIP polymers, causing the general differences in peptide retention and recoveries.

3.5.2 Retention contributions by peptide properties

MIP retention mechanism was deeply investigated in Paper II by looking at the correlation between the physical-chemical properties of the extracted peptides and their retention in the MIP and NIP sorbents.

This knowledge was acquired by using multivariate analysis for the design of a correlation model, by the means of Partial Least Square (PLS) regression, which could interpolate the peptide elution from the MIP and the NIP with the physical-chemical properties of the peptides.

Thus the aim was to identify which of the physical-chemical peptide properties (independent variables or descriptor) contributed to the retention of the peptide in the MIP or in the NIP cartridge (dependent variable or response).

The retention of the peptide in the MIP and NIP were assessed by SPE experiments where the MIP and NIP particles were packed into 300 μ L pipette tips and the elution of the peptides was modulated by gradual increasing of the acetonitrile content in the eluent phase (see §3.4.2). Thus the percentage of acetonitrile necessary to achieve 50% of the total peptide elution in MIP and NIP cartridges was set as model response.

The PLS regression model was obtained by Unscrambler® program using three principal components (PCs) and applying random cross validation and the Martens uncertainty test in order to obtain a validated method and uncertainty limits on the regression coefficients associated to each descriptor chosen for the model (for details see Paper II).

The physical-chemical properties of the peptide chosen as model descriptors were: number of amino acids, number of negative charges, number of positive charges, number of aromatic residues, molecular weight, gravity index, isoelectric point and aliphatic index. These variables were considered according to the preliminary hypotheses on the peptide groups which could interact with the polymer components (see §3.5.1). The accessible molecular surface area as peptide descriptor was also evaluated but it was not included due to the information overlap with the information given from the peptide molecular weights [175]. Moreover the set of descriptors chosen for this model were in accordance with the variables of peptide retention models previously developed for RP-LC, where the accessible molecular surface area was not considered in the principal component analysis [176].

The model was based on the linear combination of the initial variables and the resulting regression coefficients were used to identify the original descriptors that contribute most to the retention, according to their absolute values and to the uncertainty range associated to each descriptor, as shown in Figure 3.33.

Figure 3.33 Regression coefficient of the MIP model (A) and NIP model (B) for each descriptor: number of amino acids (#AA), number of negative charges (#Ne), number of positive charges (#Po), number of aromatic residues (#Ar), molecular weight (Mw), gravity index (Gra), isoelectric point (pI), aliphatic index (Al). Reproduced with permission from Figure 5 of Paper II. © Springer-Verlag GmbH Germany 2017.

The descriptors which gave significant contribution to both the MIP retention model (A) and the NIP model (B) were the negative charge (#Ne), the isoelectric point (pI) and the aliphatic index (AI) of the peptides. However in the NIP model also the numbers of aromatic residues (#Ar) gives a significant contribution and, at the meantime, the absolute value of the negative charge is slightly inferior to the value displayed in the MIP model.

It is then reasonable to hypothesize an improved selectivity toward peptides with acidic residues in the MIP cartridge due to the interaction of the negative charges on the peptides and the functional monomer EAMA.HCl, which is positively charged at pH below 10. Simultaneously peptides with aliphatic side chains such as alanine, isoleucine and leucine interact with the apolar part of the polymer. However such interactions occurs also in the NIP polymer, even though the ionic interaction seems to influence in minor extent the peptide retention, but an additional contribution of the peptide retention is given by the aromatic group of the polymer skeleton of the NIP interacting with the of the peptide, mainly made up from the cross-linker of the polymer reaction (DVB).

Differences in retention models could be explained in the structural organization of the functional monomer EAMA.HCl within the polymers. The polymerization of the MIP provides the addition of the template molecule at the beginning of the synthesis. Thus the template arranges and organizes the directions of the functional monomer EAMA.HCl before the addition of the cross-linker DVB, which is responsible of the polymeric reticulation growth. In the NIP polymer instead, the absence of the template causes a random incorporation of EAMA.HCl in the polymeric structure. A reason why the negative charges contribute more in the MIP retention model could be the molecular recognition mainly occurring within the binding sites where the functional monomers are properly directed. Vice-versa, in the NIP polymer, the contribution from the negative charges becomes less effective, probably due to the random distribution and orientation of EAMA.HCl. In this case the interaction with the polymer structure is increased, probably promoted by an ordered reticulation. In fact, the absence of the binding sites within the NIP could lead to a polymeric skeleton without distortions.

The isoelectric point of the retained peptides plays a crucial role in the peptide retention in both MIP and NIP, thus the effect of the pH on the extraction process is a variable to be considered and studied with the aim of maximizing the SPE efficiency and acquiring further insights on polymers retention.

3.5.3 The role of pH in peptide retention.

The pH contribution has been extensively studied within Paper II and partially investigated in the SPE optimization in Paper IV.

Both studies considered the change in charge distribution on the target peptide NLLGLIEAK and on functional monomer caused by the pH: by looking at the pK_a of the basic terminal of EAMA.HCl (see Figure 3.34) and the acidic residues (glutamic acid - Figure 3.35 - and the lysine C-terminal - Figure 3.36) of NLLGLIEAK it is thus possible to estimate the pH range (between 2 and 9) where the interaction between these species will be promoted.

In Paper II an experiment was performed in order evaluate the pH effect on the loading of NLLGLIEAK and on the wash step of the SPE. The choice of the pH of these steps was driven by the combination of pH values where the functional monomer EAMA.HCl and the acidic chains of NLLGLIEAK could change their charge state.

Figure 3.34 Microspecies distribution vs pH of the functional monomer EAMA.HCl occurring in both MIP and NIP polymers. Adapted with permission from Chemicalize.org [177].

Figure 3.35 Microspecies distribution vs pH of the glutamic acid (E) in the target peptide NLLGLIEAK. Adapted with permission from Chemicalize.org [177].

Figure 3.36 Microspecies distribution vs pH of the lysine (K) in the target peptide NLLGLIEAK. Adapted with permission from Chemicalize.org [177].

Four different pHs (2.2, 7.1, 9.5 and 12.0) were then tested and the recovery of each SPE step was calculated and is shown in Figure 3.37.

Figure 3.37 Influence of the loading pH on the NLLGLIEA[K- $^{13}\text{C}_6$ $^{15}\text{N}_2$] recovery in all the collected SPE fractions (flow through, wash and elution). Reproduced with permission from Figure 7 of Paper II. © Springer-Verlag GmbH Germany 2017.

By matching the pK_a information with the recovery results, it could be inferred that at pH 2.2 the interaction between polymers (both MIP and NIP) and targeted peptide is based on the functional monomer EAMA.HCl, positively charged, and the peptide C-terminal carboxylic acid, negatively charged. At this pH the glutamic acid of the target peptide slightly starts to be negatively charged, thus the interaction between this group and the polymer is weak and additional retention has to be ascribed to the hydrophobic interactions between polymer structure, given from DVB, and aliphatic peptide chains. This circumstance can also explain the partial the elution recovery from both cartridges, which follows a wash step where the target peptide is partly lost.

Another consideration on the MIP recovery ($\sim 20\%$) can be done by comparison with the NIP recovery ($\sim 80\%$). The difference in NLLGLIEAK retention could be ascribed to the increased NIP tendency to retain peptides with aromatic and aliphatic groups over the negative charges, as previously shown in the comparison between MIP and NIP retention

models (see Figure 3.33). Thus the supplementary hydrophobic interactions mainly occurring in the NIP cartridge could be responsible of the higher recovery; while the MIP cartridge, retaining peptides essentially by ionic interaction, misses the most part of NLLGLIEAK in the wash step.

In the experiment performed at pH 12.0, the MIP and NIP cartridges show similar behavior. The ionic interactions are massively reduced as the EAMA.HCl is not charged and most of the target peptide is thus lost in the sample load and wash of both cartridges. Also in this case the increased NIP recovery could be attributed to stronger hydrophobic interactions.

When the pH is 7.1 and 9.5 both glutamic acid and the C-terminal carboxylic acid of the peptide are negatively charged. Thus a strengthening of their interactions with the EAMA.HCl, positively charged, is displayed in both MIP and NIP cartridges. In this instance almost the totality of the peptide is recovered in the elution step without losses in the load and wash steps.

Similar results were found in the study on loading pH in Paper IV (packing the MIPs in the on-line trap cartridge) during the SPE optimization, as shown in Figure 3.38

Figure 3.38 Effect of loading pH on retention times and peak areas of NLLGLIEA[K-¹³C₆¹⁵N₂] (5 nM) extracted on both MIPs. Reproduced with permission from Figure 3 of Paper IV. Copyright © 2017, Rights Managed by Nature Publishing Group.

Since this study was performed on the on-line MIP cartridges, the retention within the polymers was quantitatively assessed by the retention time. The higher was the loading pH, the longer the peptide was retained within the cartridges, revealing a strengthening of the ionic interactions between the positive charge of EAMA monomer and the negative charges of the glutamic acid residue and the lysine C-terminal of the peptide.

Loading the peptide at pH 3.0 allowed the peptide retention mainly by the carboxylic group of the lysine C-terminal.

However, in this study the drop in signal intensities was substantial compared to the increase in retention time. Since loading solution with pH above 7 led to incomplete peptide ionization in the MS detector, the solution with pH 3.0 was used for the sample loading in the further on-line SPE development.

3.5.4 The clean-up effect of MIP extraction: removal of matrix interferences and benchmark with other analytical strategies for ProGRP

In Paper V a study on the clean-up efficiency of the MIP extraction was performed by qualitative and quantitative approach, comparing the extract from the online-MIP SPE with the extracts obtained by immunocapture and protein precipitation, two sample preparation methods previously applied in the analysis of ProGRP [165, 161].

The study aimed to compare the performances of these three sample preparation methods in terms of ion suppression and specificity of the enrichment.

The ion suppression assessment was a qualitative study aimed to check for ion signal drop or enhancement of the target peptide NLLGLIEAK in the tandem mass analyzer. It was realized by the signal acquisition over the chromatographic run of the NLLGLIEAK solution, of the digestion buffer and of the sera extracted with the three methods, and the simultaneous post-column infusion of a standard solution of NLLGLIEA[K- $^{13}\text{C}_6^{15}\text{N}_2$]. This setup facilitated the direct comparison of the results obtained with the three techniques. In fact, a quantitative evaluation would have been required a more complicated extrapolation of the different methods, since the MIP-cartridge was an on-line sample preparation, while immunocapture and protein precipitation were off-line techniques. Results of the experiment are shown in Figure 3.39.

Figure 3.39 Chromatograms of LC-MS method with post-column infusion experiments for qualitative assessment of matrix effect in samples extracted by immunocapture (A), protein precipitation (B) and MIP (C) by using the NLLGLIEA[K- $^{13}\text{C}_6^{15}\text{N}_2$] 5nM, the 6 extracted serum lots and ABC 50 mM. Reproduced with permission from Figure 2 of Paper V. Copyright © 2016 Elsevier B.V.

Since the NLLGLIEA[K- $^{13}\text{C}_6^{15}\text{N}_2$] solution is introduced post-column into the mass detector at a constant rate, a constant ion current should ideally be observed over the entire chromatogram if no suppression/enhancement is given by interferences in the serum extracts [178].

From the performed experiments, it is possible to notice how the amount of ion suppression is dependent on the sample preparation applied. The immuno-capture (A) showed no ion suppression or enhancement since the serum extracts have constant ion current as the ammonium bicarbonate buffer or the standard peptide elution; while the protein precipitation (B) gave extracts rich in interfering species, being the sera ion current enhanced in many parts of the chromatograms and significantly below to the ion currents of the buffer and the standard solution in the elution range of NLLGLIEAK.

The on-line MIP-SPE gave a minor ion suppression effect in the retention time of NLLGLIEAK since the extracted sera intensities were marginally below the buffer and the standard peptide baseline. However interfering species were also extracted in the MIP cartridge, giving an extra peak before the elution of NLLGLIEAK.

Thus, a further study was performed to identify the interfering peptides, which were co-extracted during the sample preparation using immunocapture, protein precipitation and online MIP-SPE. The experiment required the injection of the sera extracts to the LC-LTQ-

Orbitrap mass analyzer in order to gain the necessary resolution for the peptide identification, thus the on-line MIP SPE extracts were formerly collected as heart-cut fraction of the analytical run, collected in the elution range of NLLGLIEAK (from 34 to 37 min), and then injected in the LC-LTQ-Orbitrap mass analyzer.

The peptide identification was performed by the processing of the raw MS-files with Proteome Discoverer 1.4 (Thermo Fisher) and the subsequent protein identification was based on the presence in the extracts of unique peptides. In Figure 3.40 the Venn diagrams of the number of identified peptides (A) and proteins (B) in all the extracts coming from the three tested techniques are shown.

Figure 3.40 Venn diagrams of identified proteins (A) and all peptides (B) co-extracted with NLLGLIEAK after immunocapture (red), protein precipitation (blue) and on-line MIP extraction (green) (Reproduced with permission from Figure 3 of Paper V). Copyright © 2016 Elsevier B.V.

Only 16 peptides were commonly co-extracted by all three techniques. Surprisingly, the immunocapture extracts displayed a high number of peptides (708) and only 161 peptides were found in protein precipitation extracts.

The MIP-SPE gave the extracts with the lowest number of identified peptides (116). Not surprisingly, almost half of them (31+16) were shared with protein precipitation extracts, easily understandable since a step of protein precipitation is used also before the on-line MIP extraction for the depletion of serum albumin.

Similarly, the highest number of identified proteins was in the immunocapture extracts (61) followed by the protein precipitation extracts (41). Again MIP extracts showed the lowest number of identified proteins. Among them, only four proteins were shared among the sample pre-treatment methods: serum albumin, apolipoprotein A-I, apolipoprotein A-II and alpha-1-antitrypsin.

The protein identification was validated using Scaffold 4.5.3 (Proteome Software Inc.) which allowed the relative protein quantification based on the spectral counts. In Figure 3.41 the quantification of the four proteins common in all the extracts are shown.

Figure 3.41 Quantity of the common proteins (based on spectral counts) left in the sample after the three sample preparation method (Reproduced with permission from Figure 4 of Paper V). Copyright © 2016 Elsevier B.V.

As expected, in the immunocapture extracts low quantities of the four common proteins (normalized total spectra < 1000) were found. In the protein precipitation extracts, the serum albumin was highly expressed (7000 spectral counts) and the quantity of apolipoprotein A-I reached the 2000 spectral counts.

In the MIP extracts a high quantity of serum albumin was found (11000 spectral count), despite the preliminary serum albumin precipitation step before the extraction.

For the explanation of the obtained results and further characterization of the clean-up effect, the abundancy of the identified proteins in plasma was considered by using Peptide Atlas (build 2015-09 Non-Glyco) (see Table S7 in the Supporting Information of Paper V).

Most of the identified proteins in the extracts from online MIP-SPE and immunocapture are low-abundant proteins, mainly present in plasma in the range of ng/mL; while the majority of the proteins identified in the extracts of protein precipitation are in the range of $\mu\text{g/mL}$.

The four proteins common to all extraction techniques are high abundant proteins in the range of $\mu\text{g/mL}$.

In light of this, it is possible to explain the high number of identified peptides and protein in the extract of the immunocapture. In fact Fonslow et al. [179] previously described the improved identification of low-abundant peptides and proteins by the depletion of the most

abundant proteins. This circumstance is displayed here in the immunocapture extracts where the identification of lower-abundance proteins and peptides which naturally occur in serum matrices in elevated number is increased. This hypothesis well agrees also with the absence of ion suppression or enhancement of the experiment previously shown in Figure 3.39, and with the low quantity of abundant protein displayed in Figure 3.41.

On the other hand, the number of identified peptides and high abundant protein in the protein precipitation extract was not surprising, being protein precipitation rather unspecific and being affected by ion suppression and enhancement from many species co-extracted together.

The MIP on-line SPE allowed the clean-up of many interfering species. The identification of low abundant proteins was the consequence of the depletion of many abundant proteins. The clean-up effect of the MIP extraction in this circumstance has to also be linked to the on-line setup which allowed to collect a heart-cut of a limited elution range (from 34 to 37 minutes) and to discharge all the species eluting before and after.

In this elution range, the enrichment of peptides coming from serum albumin (Figure 3.41) was unintended but could explain the increase in ion current registered at 34 minutes during the experiment checking for ion suppression/enhancement (Figure 3.39).

It is thus plausible that serum albumin peptides interact with the hydrophobic structure of the polymer and the charges of the functional monomer, being released close to the retention time of NLLGLIEAK.

3.6 Future perspectives

The findings described in this thesis have showed the real application of MIPs in proteomic settings, by the enrichment and the quantification of cancer biomarker from patient samples. However before the developed approach can be effectively integrated of the in clinical settings, the extraction reproducibility and analysis sensitivity have to improve.

In first instance, using of new reagents and protocols could ensure higher particle reproducibility in the MIP synthesis, especially concerning sizes and porosity. The use of different cross-linker and more specific functional monomers could ultimately lead to reduced unspecific interactions with interfering peptides. Moreover, the increase of MIP synthesis reaction yield is desirable to allow parallel testing of the materials, fundamental for the extraction optimization outcome.

Adding of multiple targets in the reaction media could be achieved by using new imprinting strategies. This would result in the enrichment of multiple peptides coming either from the same protein biomarker (as the simultaneous enrichment of NLLGLIEAK and LSAPGSQR for the determination of ProGRP) or from different protein biomarker with combined clinical value for the same disease (such as ProGRP and the NSE).

Concerning the improvement of the analytical methods, the coupling of MIP with modern nanoLC-MS/MS could tremendously increase the method sensitivity, reaching LOD lower than 7.6 pM, the ProGRP reference value.

Despite the on-line MIP enrichment has decreased the handling and extraction time of the MS-assays for the quantification of ProGRP by immune-capture (from 60 to 15 minutes) much can be still done in terms of automation and analysis time. The efficiency of the albumin removal by acetonitrile protein precipitation could be improved by a preceding chromatography dimension, such as size exclusion or ion exchange chromatography. These techniques should ensure the effective removal of the albumin, leaving the sample in a buffer solution with a pH suitable for the further protein digestion. In addition, the proteolytic step could be performed into an on-line system providing the immobilization of Trypsin into an enzyme reactor [180], resulting in a fully-automated ProGRP analysis.

4 Concluding remarks

This thesis has disclosed the application of MIPs to the targeted LC-MS analysis of the biomarker ProGRP, relevant for the SCLC diagnosis.

Among the tested polymers, MIPs produced using EAMA.HCl, as functional monomer, and DVB, as cross-linker, shown superior ability to selectively recognize, capture and release the signature peptide of ProGRP, NLLGLIEAK, for the further MS determination.

The diverse synthetic protocols applied led to the differentiation of the physical-chemical properties of the MIP particles, determining their feasibility to be integrated in different SPE formats. Precipitation polymerization gave homogeneous microspheres particularly suited for the packing into on-line SPE columns, while RAFT-polymers were easily integrated in-house into off-line formats, such as 1 mL-cartridges, 300 μ L-tips, 384-well and ISET plates.

The ISET plate was revealed to be an inefficient format for the simultaneous screening and optimization of SPE protocols, but the 384-well filter plate enabled high throughput screening of MIP libraries and SPE conditions at the same time, by using both LC-MS/MS and MALDI-TOF analysis.

The use of on-line trap column for automated MIP-SPE gave major breakthroughs in the MIPs application to the quantification of ProGRP. The developed method reached a limit of detection of 17 pM being able to accurately quantify the ProGRP concentrations occurring in patients sera. In addition the automated on-line extraction improved critical aspects of the established methods providing LC-MS quantification of ProGRP, by reduction of the sample handling, sample volumes (only 50 μ L required) and extraction time (15 minutes).

Considering the aforementioned method, the suitability of employing MIPs, able to selectively extract tryptic peptides, for further targeted protein MS analysis, has been demonstrated in this thesis by the quantification of the marker ProGRP. Hence the prospect of implementing synthetic receptors in biomarker analysis and other proteomic applications is now opened.

References

1. Wilkins MR, Pasquali C, Appel RD, Ou K, Golaz O, Sanchez JC et al. From proteins to proteomes: large scale protein identification by two-dimensional electrophoresis and amino acid analysis. *Bio/technology* (Nature Publishing Company). 1996;14:61-5.
2. Baak JPA, Janssen EAM, Soreide K, Heikkilä R. Genomics and proteomics - The way forward. *Ann Oncol*. 2005;16:ii30-ii44.
3. Lin JL, Bonnicksen MH, Nogeh EU, Raftery MJ, Thomas PS. Proteomics in detection and monitoring of asthma and smoking-related lung diseases. *Expert Rev Proteomics*. 2010;7:361-72.
4. Indovina P, Marcelli E, Pentimalli F, Tanganelli P, Tarro G, Giordano A. Mass spectrometry-based proteomics: The road to lung cancer biomarker discovery. *Mass Spectrom Rev*. 2013;32:129-42.
5. Ponomarenko EA, Poverennaya EV, Ilgisonis EV, Pyatnitskiy MA, Kopylov AT, Zgoda VG et al. The Size of the Human Proteome: The Width and Depth. *Int J Anal Chem*. 2016;2016:7436849, 6 pages.
6. Marko-Varga G, Ogiwara A, Nishimura T, Kawamura T, Fujii K, Kawakami T et al. Personalized Medicine and Proteomics: Lessons from Non-Small Cell Lung Cancer. *J Proteome Res*. 2007;6:2925-35.
7. Palchetti I. Affinity biosensors for tumor-marker analysis. *Bioanalysis*. 2014;6:3417-35.
8. Banach P, Suchy W, Dereziński P, Matysiak J, Kokot ZJ, Nowak-Markwitz E. Mass spectrometry as a tool for biomarkers searching in gynecological oncology. *Biomed Pharmacother*. 2017;92:836-42.
9. Muthu M, Vimala A, Mendoza OH, Gopal J. Tracing the voyage of SELDI-TOF MS in cancer biomarker discovery and its current depreciation trend - need for resurrection? *Trends Anal Chem*. 2016;76:95-101.
10. Meral O, Uysal H. Comparative proteomic analysis of fibrosarcoma and skin fibroblast cell lines. *Tumor Biol*. 2015;36:561-7.
11. Zhang RR, Schroeder AB, Grudzinski JJ, Rosenthal EL, Warram JM, Pinchuk AN et al. Beyond the margins: Real-time detection of cancer using targeted fluorophores. *Nat Rev Clin Oncol*. 2017;14:347-64.
12. Bernicker EH, Miller RA, Cagle PT. Biomarkers for selection of therapy for adenocarcinoma of the lung. *J Oncol Pharm Pract*. 2017;13:221-7.
13. Perez-Gracia JL, Sanmamed MF, Bosch A, Patiño-García A, Schalper KA, Segura V et al. Strategies to design clinical studies to identify predictive biomarkers in cancer research. *Cancer Treat Rev*. 2017;53:79-97.
14. Abildgaard SKO, Vorum H. Proteomics of uveal melanoma: A minireview. *J Oncol*. 2013.
15. Sung HJ, Cho JY. Biomarkers for the lung cancer diagnosis and their advances in proteomics. *BMB reports*. 2008;41:615-25.
16. Lehtio J, De Petris L. Lung cancer proteomics, clinical and technological considerations. *J Proteomics*. 2010;73:1851-63.
17. Beretta L. Proteomics from the clinical perspective: many hopes and much debate. *Nat Meth*. 2007;4:785-6.

18. Alfaro JA, Ignatchenko A, Ignatchenko V, Sinha A, Boutros PC, Kislinger T. Detecting protein variants by mass spectrometry: A comprehensive study in cancer cell-lines. *Genome Med.* 2017;9.
19. Gao Z, Luo G, Ni B. Progress in mass spectrometry-based proteomic research of tumor hypoxia (Review). *Oncol Rep.* 2017;38:676-84.
20. Schubert OT, Röst HL, Collins BC, Rosenberger G, Aebersold R. Quantitative proteomics: Challenges and opportunities in basic and applied research. *Nat Protoc.* 2017;12:1289-94.
21. Conrad DH, Goyette J, Thomas PS. Proteomics as a Method for Early Detection of Cancer: A Review of Proteomics, Exhaled Breath Condensate, and Lung Cancer Screening. *J Gen Intern Med* 2008;23:78-84.
22. Palmblad M, Tiss A, Cramer R. Mass spectrometry in clinical proteomics - From the present to the future. *Proteomics Clin Appl.* 2009;3:6-17.
23. Fu S, Liu X, Luo M, Xie K, Nice EC, Zhang H et al. Proteogenomic studies on cancer drug resistance: towards biomarker discovery and target identification. *Expert Rev Proteomics.* 2017;14:351-62.
24. Ma H, Chen G, Guo M. Mass spectrometry based translational proteomics for biomarker discovery and application in colorectal cancer. *Proteomics Clin Appl.* 2016;10:503-15.
25. Timms JF, Hale OJ, Cramer R. Advances in mass spectrometry-based cancer research and analysis: from cancer proteomics to clinical diagnostics. *Expert Rev Proteomics.* 2016;13:593-607.
26. Velghe S, Capiou S, Stove CP. Opening the toolbox of alternative sampling strategies in clinical routine: A key-role for (LC-)MS/MS. *Trends Anal Chem* 2016;84:61-73.
27. Vyse S, Desmond H, Huang PH. Advances in mass spectrometry based strategies to study receptor tyrosine kinases. *IUCrJ.* 2017;4:119-30.
28. Wang H, Shi T, Qian WJ, Liu T, Kagan J, Srivastava S et al. The clinical impact of recent advances in LC-MS for cancer biomarker discovery and verification. *Expert Rev Proteomics.* 2016;13:99-114.
29. Chen B, Lietz CB, Li L. In situ characterization of proteins using laserspray ionization on a high-performance MALDI-LTQ-orbitrap mass spectrometer. *J Am Soc Mass Spectrom.* 2014;25:2177-80.
30. Yates JR, Ruse CI, Nakorchevsky A. Proteomics by mass spectrometry: approaches, advances, and applications. *Annual review of biomedical engineering.* 2009;11:49-79.
31. Aebersold R, Mann M. Mass spectrometry-based proteomics. *Nature.* 2003;422:198-207.
32. Tang N, Tornatore P, Weinberger SR. Current developments in SELDI affinity technology. *Mass Spectrom Rev.* 2004;23:34-44.
33. Tomlinson L, Fuchser J, Fütterer A, Baumert M, Hassall DG, West A et al. Using a single, high mass resolution mass spectrometry platform to investigate ion suppression effects observed during tissue imaging. *Rapid Commun Mass Spectrom.* 2014;28:995-1003.
34. Fenn JB, Mann M, Meng CK, Wong SF, Whitehouse CM. Electrospray ionization for mass spectrometry of large biomolecules. *Science.* 1989;246:64-71.
35. Aebersold R, Goodlett DR. Mass spectrometry in proteomics. *Chemical reviews.* 2001;101:269-95.

36. Lim H, Eng J, Yates JR, Tollaksen SL, Giometti CS, Holden JF et al. Identification of 2D-gel proteins: A comparison of MALDI/TOF peptide mass mapping to μ LC-ESI tandem mass spectrometry. *J Am Soc Mass Spectrom.* 2003;14:957-70.
37. Rauh M. LC–MS/MS for protein and peptide quantification in clinical chemistry. *J Chromatogr B: Anal Technol Biomed Life Sci.* 2012;883–884:59-67.
38. Grebe SKG, Singh RJ. Clinical peptide and protein quantification by mass spectrometry (MS). *Trends Anal Chem.* 2016;84:131-43.
39. Zubarev RA, Makarov A. Orbitrap Mass Spectrometry. *Anal Chem.* 2013;85:5288-96.
40. Perry RH, Cooks RG, Noll RJ. Orbitrap mass spectrometry: instrumentation, ion motion and applications. *Mass Spectrom Rev.* 2008;27:661-99.
41. Muqaku B, Slany A, Bileck A, Kreutz D, Gerner C. Quantification of cytokines secreted by primary human cells using multiple reaction monitoring: evaluation of analytical parameters. *Anal Bioanal Chem.* 2015;407:6525-36.
42. Schiess R, Wollscheid B, Aebersold R. Targeted proteomic strategy for clinical biomarker discovery. *Mol Oncol.* 2009;3:33-44.
43. Yang Y, Wen Yj, Cai YN, Vallée I, Boireau P, Liu MY et al. Serine Proteases of Parasitic Helminths. *Korean J Parasitol.* 2015;53:1-11.
44. Mesuere B, Debyser G, Aerts M, Devreese B, Vandamme P, Dawyndt P. The Unipept metaproteomics analysis pipeline. *Proteomics.* 2015;15:1437-42.
45. Roepstorff P, Fohlman J. Proposal for a common nomenclature for sequence ions in mass spectra of peptides. *Biomed Mass Spectrom.* 1984;11:601.
46. Dupré M, Cantel S, Martinez J, Enjalbal C. Occurrence of C-Terminal Residue Exclusion in Peptide Fragmentation by ESI and MALDI Tandem Mass Spectrometry. *J Am Soc Mass Spectrom.* 2012;23:330-46.
47. Nesvizhskii AI. A survey of computational methods and error rate estimation procedures for peptide and protein identification in shotgun proteomics. *J Proteomics.* 2010;73:2092-123.
48. Pan S, Aebersold R, Chen R, Rush J, Goodlett DR, McIntosh MW et al. Mass Spectrometry Based Targeted Protein Quantification: Methods and Applications. *J Proteome Res.* 2008;8:787-97.
49. Shushan B. A review of clinical diagnostic applications of liquid chromatography–tandem mass spectrometry. *Mass Spectrom Rev.* 2010;29:930-44.
50. Vidova V, Spacil Z. A review on mass spectrometry-based quantitative proteomics: Targeted and data independent acquisition. *Anal Chim Acta.* 2017;964:7-23.
51. Anderson NL, Anderson NG. The human plasma proteome: history, character, and diagnostic prospects. *Molecular & cellular proteomics : MCP.* 2002;1:845-67.
52. Stastna M, Van Eyk JE. Secreted proteins as a fundamental source for biomarker discovery. *Proteomics.* 2012;12:722-35.
53. Hoofnagle AN, Wener MH. The fundamental flaws of immunoassays and potential solutions using tandem mass spectrometry. *J Immunol Methods.* 2009;347:3-11.
54. Mahboob S, Mohamedali A, Ahn SB, Schulz-Knappe P, Nice E, Baker MS. Is isolation of comprehensive human plasma peptidomes an achievable quest? *J Proteomics.* 2015;127:300-9.

55. Jiang L, He L, Fountoulakis M. Comparison of protein precipitation methods for sample preparation prior to proteomic analysis. *J Chromatogr A*. 2004;1023:317-20.
56. Binai NA, Marino F, Soendergaard P, Bache N, Mohammed S, Heck AJR. Rapid analyses of proteomes and interactomes using an integrated solid-phase extraction-liquid chromatography-MS/ms system. *J Proteome Res*. 2015;14:977-85.
57. Walker V, Mills GA. Solid-phase extraction in clinical biochemistry. *Ann Clin Biochem*. 2002;39:464-77.
58. Fontanals N, Marcé RM, Borrull F, Cormack PAG. Mixed-mode ion-exchange polymeric sorbents: dual-phase materials that improve selectivity and capacity. *Trends Anal Chem*. 2010;29:765-79.
59. Herrero-Latorre C, Barciela-García J, García-Martín S, Peña-Creciente RM, Otárola-Jiménez J. Magnetic solid-phase extraction using carbon nanotubes as sorbents: A review. *Anal Chim Acta*. 2015;892:10-26.
60. Huck CW, Bakry R, Bonn GK. Sample preparation techniques for mass spectrometry in proteomics using recently developed highly selective materials. *Curr Proteomics*. 2005;2:269-85.
61. Becker JO, Hoofnagle AN. Replacing immunoassays with tryptic digestion-peptide immunoaffinity enrichment and LC-MS/MS. *Bioanalysis*. 2012;4:281-90.
62. Chen T, Hedman L, Mattila PS, Jartti L, Jartti T, Ruuskanen O et al. Biotin IgM antibodies in human blood: A previously unknown factor eliciting false results in biotinylation-based immunoassays. *PLoS ONE*. 2012;7.
63. Kift RL, Messenger MP, Wind TC, Hepburn S, Wilson M, Thompson D et al. A comparison of the analytical performance of five commercially available assays for neutrophil gelatinase-associated lipocalin using urine. *Ann Clin Biochem*. 2013;50:236-44.
64. Boström T, Takanen JO, Hober S. Antibodies as means for selective mass spectrometry. *J Chromatogr B: Anal Technol Biomed Life Sci*. 2016;1021:3-13.
65. Rogeberg M, Malerod H, Roberg-Larsen H, Aass C, Wilson SR. On-line solid phase extraction-liquid chromatography, with emphasis on modern bioanalysis and miniaturized systems. *J Pharm Biomed Anal*. 2014;87:120-9.
66. Moein MM, Said R, Abdel-Rehim M. Microextraction by packed sorbent. *Bioanalysis*. 2015;7:2155-61.
67. Massolini G, Calleri E. Immobilized trypsin systems coupled on-line to separation methods: Recent developments and analytical applications. *J Sep Sci*. 2005;28:7-21.
68. Alpha-Bazin B, Quéméneur E. Antibody-Free Detection of Phosphoserine/Threonine Containing Peptides by Homogeneous Time-Resolved Fluorescence. *Anal Chem*. 2012;84:9963-70.
69. Ding X, Yang K-L. Antibody-free Detection of Human Chorionic Gonadotropin by Use of Liquid Crystals. *Anal Chem*. 2013;85:10710-6.
70. Wilffert D, Reis CR, Hermans J, Govorukhina N, Tomar T, de Jong S et al. Antibody-Free LC-MS/MS Quantification of rhTRAIL in Human and Mouse Serum. *Anal Chem*. 2013;85:10754-60.
71. Wu H-J, Li Y, Fan J, Deng Z, Hu Z, Liu X et al. Antibody-Free Detection of Mycobacterium tuberculosis Antigen Using Customized Nanotraps. *Anal Chem*. 2014;86:1988-96.

72. Shi T, Sun X, Gao Y, Fillmore TL, Schepmoes AA, Zhao R et al. Targeted Quantification of Low ng/mL Level Proteins in Human Serum without Immunoaffinity Depletion. *J Proteome Res.* 2013;12:3353-61.
73. Sellergren B. Molecularly imprinted polymers: Shaping enzyme inhibitors. *Nat Chem.* 2010;2:7-8.
74. Haupt K. Biomaterials: Plastic antibodies. *Nat Mater.* 2010;9:612-4.
75. Chen L, Wang X, Lu W, Wu X, Li J. Molecular imprinting: Perspectives and applications. *Chem Soc Rev.* 2016;45:2137-211.
76. Manesiotis P, Hall AJ, Courtois J, Irgum K, Sellergren B. An Artificial Riboflavin Receptor Prepared by a Template Analogue Imprinting Strategy. *Angew Chem, Int Ed.* 2005;44:3902-6.
77. Manesiotis P, Kashani S, McLoughlin P. Molecularly imprinted polymers for the extraction of imiquimod from biological samples using a template analogue strategy. *Anal Methods.* 2013;5:3122-8.
78. Haupt K. Peer Reviewed: Molecularly Imprinted Polymers: The Next Generation. *Anal Chem.* 2003;75:376 A-83 A.
79. Ellwanger A, Berggren C, Bayouth S, Crecenzi C, Karlsson L, Owens PK et al. Evaluation of methods aimed at complete removal of template from molecularly imprinted polymers. *Analyst* 2001;126:784-92.
80. Rampey AM, Umpleby Ii RJ, Rushton GT, Iseman JC, Shah RN, Shimizu KD. Characterization of the Imprint Effect and the Influence of Imprinting Conditions on Affinity, Capacity, and Heterogeneity in Molecularly Imprinted Polymers Using the Freundlich Isotherm-Affinity Distribution Analysis. *Anal Chem* 2004;76:1123-33.
81. Nantasenamat C, Isarankura-Na-Ayudhya C, Naenna T, Prachayasittikul V. Quantitative structure-imprinting factor relationship of molecularly imprinted polymers. *Biosens Bioelectron.* 2007;22:3309-17.
82. Baggiani C, Giovannoli C, Anfossi L, Passini C, Baravalle P, Giraudi G. A Connection between the Binding Properties of Imprinted and Nonimprinted Polymers: A Change of Perspective in Molecular Imprinting. *J Am Chem Soc.* 2012;134:1513-8.
83. Beltran A, Borrull F, Marcé RM, Cormack PAG. Molecularly-imprinted polymers: useful sorbents for selective extractions. *TrAC, Trends Anal Chem.* 2010;29:1363-75.
84. Greibrokk T. Molecular Imprinting in Separation Science. *J Sep Sci.* 2016;39:815-7.
85. Jandera P. Stationary and mobile phases in hydrophilic interaction chromatography: A review. *Anal Chim Acta.* 2011;692:1-25.
86. Scientific Assembly on Microbiology T, and Pulmonary Infections. Diagnostic Standards and Classification of Tuberculosis in Adults and Children. *Am J Respir Crit Care Med.* 2000;161:1376.
87. Płotka-Wasyłka J, Szczepańska N, de la Guardia M, Namieśnik J. Modern trends in solid phase extraction: New sorbent media. *Trends Anal Chem.* 2016;77:23-43.
88. Scognamiglio V, Antonacci A, Lambrea MD, Litescu SC, Rea G. Synthetic biology and biomimetic chemistry as converging technologies fostering a new generation of smart biosensors. *Biosens Bioelectron.* 2015;74:1076-86.
89. Ye L, A. G. Cormack P, Mosbach K. Molecularly imprinted monodisperse microspheres for competitive radioassay. *Anal Commun.* 1999;36:35-8.

90. Siegel D. Applications of reversible covalent chemistry in analytical sample preparation. *Analyst*. 2012;137:5457-82.
91. Halhalli MR, Aureliano CSA, Schillinger E, Sulitzky C, Titirici MM, Sellergren B. An improved grafting technique for producing imprinted thin film composite beads. *Polym Chem*. 2012;3:1033-42.
92. de Brouwer H, Tsavalas JG, Schork FJ. Living Radical Polymerization in Miniemulsion Using Reversible Addition–Fragmentation Chain Transfer. *Macromolecules*. 2000;33:9239-46.
93. Li XS, Zhu GT, Luo YB, Yuan BF, Feng YQ. Synthesis and applications of functionalized magnetic materials in sample preparation. *Trends Anal Chem*. 2013;45:233-47.
94. Riveros G D, Cordova K, Michiels C, Verachttert H, Derdelinckx G. Polydopamine imprinted magnetic nanoparticles as a method to purify and detect class II hydrophobins from heterogeneous mixtures. *Talanta*. 2016;160:761-7.
95. Beltran A, Marcé RM, Cormack PAG, Borrull F. Synthesis by precipitation polymerisation of molecularly imprinted polymer microspheres for the selective extraction of carbamazepine and oxcarbazepine from human urine. *J Chromatogr A*. 2009;1216:2248-53.
96. Song R, Hu X, Guan P, Li J, Du C, Qian L et al. Surface modification of imprinted polymer microspheres with ultrathin hydrophilic shells to improve selective recognition of glutathione in aqueous media. *Mater Sci Eng C*. 2016;60:1-6.
97. Wang J, Cormack PAG, Sherrington DC, Khoshdel E. Monodisperse, Molecularly Imprinted Polymer Microspheres Prepared by Precipitation Polymerization for Affinity Separation Applications. *Angew Chem, Int Ed*. 2003;42:5336-8.
98. Yoshimatsu K, Reimhult K, Krozer A, Mosbach K, Sode K, Ye L. Uniform molecularly imprinted microspheres and nanoparticles prepared by precipitation polymerization: The control of particle size suitable for different analytical applications. *Anal Chim Acta*. 2007;584:112-21.
99. Sambe H, Hoshina K, Moaddel R, Wainer IW, Haginaka J. Uniformly-sized, molecularly imprinted polymers for nicotine by precipitation polymerization. *J Chromatogr A*. 2006;1134:88-94.
100. Zhu W, Jiang G, Xu L, Li B, Cai Q, Jiang H et al. Facile and controllable one-step fabrication of molecularly imprinted polymer membrane by magnetic field directed self-assembly for electrochemical sensing of glutathione. *Anal Chim Acta*. 2015;886:37-47.
101. Sergeyeva T, Yarynka D, Piletska E, Lynnik R, Zaporozhets O, Brovko O et al. Fluorescent sensor systems based on nanostructured polymeric membranes for selective recognition of Aflatoxin B1. *Talanta*. 2017;175:101-7.
102. Oxelbark J, Legido-Quigley C, Aureliano CSA, Titirici M-M, Schillinger E, Sellergren B et al. Chromatographic comparison of bupivacaine imprinted polymers prepared in crushed monolith, microsphere, silica-based composite and capillary monolith formats. *J Chromatogr A*. 2007;1160:215-26.
103. Lin Z, Lin Y, Sun X, Yang H, Zhang L, Chen G. One-pot preparation of a molecularly imprinted hybrid monolithic capillary column for selective recognition and capture of lysozyme. *J Chromatogr A*. 2013;1284:8-16.
104. Zheng C, Huang YP, Liu ZS. Synthesis and theoretical study of molecularly imprinted monoliths for HPLC. *Anal Bioanal Chem*. 2013;405:2147-61.
105. Daoud Attieh M, Zhao Y, Elkak A, Falcimaigne-Cordin A, Haupt K. Enzyme-Initiated Free-Radical Polymerization of Molecularly Imprinted Polymer Nanogels on a Solid Phase with an Immobilized Radical Source. *Angew Chem Int Ed*. 2017;56:3339-43.

106. Zhang Z, Liu J. Improving molecularly imprinted nanogels by pH modulation. *RSC Adv.* 2015;5:91018-25.
107. Biffis A, Dvorakova G, Falcimaigne-Cordin A. Physical forms of MIPs. *Top Curr Chem.* 2012;325:29-82.
108. Abdel-Rehim M. Current advances in microextraction by packed sorbent (MEPS) for bioanalysis applications. *LC·GC Eur.* 2009;22.
109. Baggiani C, Anfossi L, Giovannoli C. Solid phase extraction of food contaminants using molecular imprinted polymers. *Anal Chim Acta.* 2007;591:29-39.
110. Baggiani C, Giovannoli C, Anfossi L. Man-made synthetic receptors for capture and analysis of ochratoxin A. *Toxins.* 2015;7:4083-98.
111. Beltran A, Borrull F, Cormack PAG, Marcé RM. Molecularly imprinted polymer with high-fidelity binding sites for the selective extraction of barbiturates from human urine. *J Chromatogr A.* 2011;1218:4612-8.
112. Caro E, Marcé RM, Borrull F, Cormack PAG, Sherrington DC. Application of molecularly imprinted polymers to solid-phase extraction of compounds from environmental and biological samples. *TrAC, Trends Anal Chem.* 2006;25:143-54.
113. Hashim SNNS, Schwarz LJ, Boysen RI, Yang Y, Danylec B, Hearn MTW. Rapid solid-phase extraction and analysis of resveratrol and other polyphenols in red wine. *J Chromatogr A.* 2013;1313:284-90.
114. Yu Z, Su Q, Tang Y, Xu Z. Preparation and evaluation of aconitine imprinted microspheres and its application to body fluid samples. *J Appl Polym Sci.* 2012.
115. Ansari S, Karimi M. Novel developments and trends of analytical methods for drug analysis in biological and environmental samples by molecularly imprinted polymers. *Trends Anal Chem.* 2017;89:146-62.
116. Speltini A, Scalabrini A, Maraschi F, Sturini M, Profumo A. Newest applications of molecularly imprinted polymers for extraction of contaminants from environmental and food matrices: A review. *Anal Chim Acta.* 2017;974:1-26.
117. Gilart N, Borrull F, Fontanals N, Marcé RM. Selective materials for solid-phase extraction in environmental analysis. *Trends Environ Anal Chem.* 2014;1:e8-e18.
118. Molinelli A, Janotta M, Mizaikoff B. Molecularly imprinted polymers for biomolecular recognition. *Methods Mol Biol.* 2005;300:243-54.
119. Bossi AM, Sharma PS, Montana L, Zoccatelli G, Laub O, Levi R. Fingerprint-imprinted polymer: Rational selection of peptide epitope templates for the determination of proteins by molecularly imprinted polymers. *Anal Chem.* 2012;84:4036-41.
120. Helling S, Shinde S, Brosseron F, Schnabel A, Müller T, Meyer HE et al. Ultratrace enrichment of tyrosine phosphorylated peptides on an imprinted polymer. *Anal Chem.* 2011;83:1862-5.
121. Koeck R, Bakry R, Tessadri R, Bonn GK. Monolithic poly(N-vinylcarbazole-co-1,4-divinylbenzene) capillary columns for the separation of biomolecules. *Analyst.* 2013;138:5089-98.
122. Li Q, Shen F, Zhang X, Hu Y, Zhang Q, Xu L et al. One-pot synthesis of phenylphosphonic acid imprinted polymers for tyrosine phosphopeptides recognition in aqueous phase. *Anal Chim Acta.* 2013;795:82-7.

123. Wang C, Howell M, Raulji P, Davis Y, Mohapatra S. Preparation and characterization of molecularly imprinted polymeric nanoparticles for atrial natriuretic peptide (ANP). *Adv Funct Mater.* 2011;21:4423-9.
124. Xu L, Hu Y, Shen F, Li Q, Ren X. Specific recognition of tyrosine-phosphorylated peptides by epitope imprinting of phenylphosphonic acid. *J Chromatogr A.* 2013;1293:85-91.
125. Turiel E, Martín-Esteban A. Molecularly imprinted polymers for sample preparation: A review. *Anal Chim Acta.* 2010;668:87-99.
126. Zaidi SA. Molecular imprinting polymers and their composites: A promising material for diverse applications. *Biomater Sci.* 2017;5:388-402.
127. Yang X, Dong X, Zhang K, Yang F, Guo Z. A molecularly imprinted polymer as an antibody mimic with affinity for lysine acetylated peptides. *J Mater Chem B.* 2016;4:920-8.
128. Liu J, Deng Q, Tao D, Yang K, Zhang L, Liang Z et al. Preparation of protein imprinted materials by hierarchical imprinting techniques and application in selective depletion of albumin from human serum. *Sci Rep.* 2014;4.
129. Jagadeesan KK, Rossetti C, Abdel Qader A, Reubsaet L, Sellergren B, Laurell T et al. Filter Plate-Based Screening of MIP SPE Materials for Capture of the Biomarker Pro-Gastrin-Releasing Peptide. *SLAS Discov.* 2017;2472555216689494.
130. Rossetti C, Abdel Qader A, Halvorsen TG, Sellergren B, Reubsaet L. Antibody-free biomarker determination: Exploring molecularly imprinted polymers for pro-gastrin releasing peptide. *Anal Chem.* 2014;86:12291-8.
131. Rossetti C, Levernæs MCS, Reubsaet L, Halvorsen TG. Evaluation of affinity-based serum clean-up in mass spectrometric analysis: Plastic vs monoclonal antibodies. *J Chromatogr A.* 2016;1471:19-26.
132. Rossetti C, Switnicka-Plak MA, Grønhaug Halvorsen T, Cormack PAG, Sellergren B, Reubsaet L. Automated protein biomarker analysis: On-line extraction of clinical samples by Molecularly Imprinted Polymers. *Sci Rep.* 2017;7.
133. Rossetti C, Ore OG, Sellergren B, Halvorsen TG, Reubsaet L. Exploring the peptide retention mechanism in molecularly imprinted polymers. *Anal Bioanal Chem.* 2017;409:5631-43.
134. Bertolla M, Cenci L, Anesi A, Ambrosi E, Tagliaro F, Vanzetti L et al. Solvent-Responsive Molecularly Imprinted Nanogels for Targeted Protein Analysis in MALDI-TOF Mass Spectrometry. *ACS Appl Mater Interfaces.* 2017;9:6908-15.
135. Cenci L, Anesi A, Busato M, Guella G, Bossi AM. Molecularly imprinted polymers coupled to matrix assisted laser desorption ionization mass spectrometry for femtomoles detection of cardiac troponin i peptides. *J Mol Recognit.* 2016;29:41-50.
136. Cenci L, Bertolla M, Anesi A, Ambrosi E, Guella G, Bossi AM. Micro- versus nano-sized molecularly imprinted polymers in MALDI-TOF mass spectrometry analysis of peptides. *Anal Bioanal Chem.* 2017;1-9.
137. Qader AA, Urraca J, Torsetnes SB, Tonnesen F, Reubsaet L, Sellergren B. Peptide imprinted receptors for the determination of the small cell lung cancer associated biomarker progastrin releasing peptide. *J Chromatogr A.* 2014;1370:56-62.
138. Urraca JL, Aureliano CSA, Schillinger E, Esselmann H, Wiltfang J, Sellergren B. Polymeric complements to the Alzheimer's disease biomarker β -amyloid isoforms A β 1-40 and a β 1-42 for blood serum analysis under denaturing conditions. *J Am Chem Soc.* 2011;133:9220-3.

139. Naklua W, Mahesh K, Chen YZ, Chen S, Roongnapa S. Molecularly imprinted polymer microprobes for manipulating neurological function by regulating temperature-dependent molecular interactions. *Process Biochem* 2016;51:142-57.
140. Simon G, Ginsberg RJ, Ruckdeschel JC. Small-cell lung cancer. *Chest surgery clinics of North America*. 2001;11:165-88, ix.
141. Spira A, Ettinger DS. Multidisciplinary management of lung cancer. *N Engl J Med*. 2004;350:379-92.
142. Niho S, Nishiwaki Y, Goto K, Ohmatsu H, Matsumoto T, Hojo F et al. Significance of serum pro-gastrin-releasing peptide as a predictor of relapse of small cell lung cancer: comparative evaluation with neuron-specific enolase and carcinoembryonic antigen. *Lung Cancer*. 2000;27:159-67.
143. Molina R, Filella X, Augé JM. ProGRP: a new biomarker for small cell lung cancer. *Clin Biochem*. 2004;37:505-11.
144. Molina R, Augé JM, Bosch X, Escudero JM, Viñolas N, Marrades R et al. Usefulness of Serum Tumor Markers, Including Progastrin-Releasing Peptide, in Patients with Lung Cancer: Correlation with Histology. *Tumor Biol*. 2009;30:121-9.
145. Wang J, Gao J, He J. Diagnostic value of ProGRP and NSE for Small Cell Lung Cancer: A meta-analysis. *Chin J Lung Cancer* 2010;13:1094-100.
146. Yang HJ, Gu Y, Chen C, Xu C, Bao YX. Diagnostic value of pro-gastrin-releasing peptide for small cell lung cancer: A meta-analysis. *Clin Chem Lab Med*. 2011;49:1039-46.
147. Kim HR, Oh IJ, Shin MG, Park JS, Choi HJ, Ban HJ et al. Plasma proGRP concentration is sensitive and specific for discriminating small cell lung cancer from nonmalignant conditions or non-small cell lung cancer. *J Korean Med Sci*. 2011;26:625-30.
148. Taneja T, Sharma S. Markers of small cell lung cancer. *World J Surg Oncol*. 2004;2:10.
149. Ischia J, Patel O, Shulkes A, Baldwin GS. Gastrin-releasing peptide: different forms, different functions. *BioFactors (Oxford, England)*. 2009;35:69-75.
150. Pujol J, Quantin X, Jacot W, Boher J, Grenier J, Lamy P. Neuroendocrine and cytokeratin serum markers as prognostic determinants of small cell lung cancer. *Lung Cancer*. 2003;39:131 - 8.
151. Holst JJ, Hansen LB, Schwartz TW, Hansen M, Borch E. Nature and Release of Products of the GRP Precursor Other than GRP. *Ann N Y Acad Sci*. 1988;547:443-4.
152. Holst JJ, Hansen M, Bork E, Schwartz TW. Elevated plasma concentrations of C-flanking gastrin-releasing peptide in small-cell lung cancer. *J Clin Oncol*. 1989;7:1831-8.
153. Maruno K, Yamaguchi K, Abe K, Suzuki M, Saijo N, Mishima Y et al. Immunoreactive gastrin-releasing peptide as a specific tumor marker in patients with small cell lung carcinoma. *Cancer Res*. 1989;49:629-32.
154. Shibayama T, Ueoka H, Nishii K, Kiura K, Tabata M, Miyatake K et al. Complementary roles of pro-gastrin-releasing peptide (ProGRP) and neuron specific enolase (NSE) in diagnosis and prognosis of small-cell lung cancer (SCLC). *Lung Cancer*. 2001;32:61-9.
155. Planchard D, Le Péchoux C. Small cell lung cancer: new clinical recommendations and current status of biomarker assessment. *Eur J Cancer*. 2011;47, Supplement 3:S272-S83.

156. Uchida K, Kojima A, Morokawa N, Tanabe O, Anzai C, Kawakami M et al. Expression of progastrin-releasing peptide and gastrin-releasing peptide receptor mRNA transcripts in tumor cells of patients with small cell lung cancer. *J Cancer Res Clin Oncol*. 2002;128:633 - 40.
157. National Center for Biotechnology Information (NCBI) [database on the Internet]. Available from: www.ncbi.nlm.nih.gov. Accessed: 08/13/2017
158. Yoshimura T, Fujita K, Kinukawa H, Matsuoka Y, Patil RD, Beligere GS et al. Development and analytical performance evaluation of an automated chemiluminescent immunoassay for pro-gastrin releasing peptide (ProGRP). *Clin Chem Lab Med*. 2009;47:1557-63.
159. Nordlund MS, Stieber P, Brustugun OT, Warren DJ, Paus E. Characteristics and clinical validity of two immunoassays for ProGRP. *Tumor Biol*. 2012:1-9.
160. Winther B, Moi P, Nordlund MS, Lunder N, Paus E, Reubsaet JLE. Absolute ProGRP quantification in a clinical relevant concentration range using LC-MS/MS and a comprehensive internal standard. *J Chromatogr B Anal Technol Biomed Life Sci*. 2009;877:1359-65.
161. Winther B, Moi P, Paus E, Reubsaet JLE. Targeted determination of the early stage SCLC specific biomarker pro-gastrin-releasing peptide (ProGRP) at clinical concentration levels in human serum using LC-MS. *J Sep Sci*. 2007;30:2638-46.
162. Winther B, Nordlund M, Paus E, Reubsaet L, Halvorsen TG. Immuno-capture as ultimate sample cleanup in LC-MS/MS determination of the early stage biomarker ProGRP. *J Sep Sci*. 2009;32:2937-43.
163. Winther B, Reubsaet JL. Determination of the small cell lung cancer associated biomarker pro-gastrin-releasing peptide (ProGRP) using LC-MS. *J Sep Sci*. 2007;30:234-40.
164. Torsetnes SB, Levernæs MS, Broughton MN, Paus E, Halvorsen TG, Reubsaet L. Multiplexing Determination of Small Cell Lung Cancer Biomarkers and Their Isovariants in Serum by Immunocapture LC-MS/MS. *Anal Chem*. 2014;86:6983-92.
165. Torsetnes SB, Nordlund MS, Paus E, Halvorsen TG, Reubsaet L. Digging deeper into the field of the small cell lung cancer tumor marker progrp: A method for differentiation of its isoforms. *J Proteome Res*. 2013;12:412-20.
166. Mie M, Kai T, Le T, Cass AEG, Kobatake E. Selection of DNA aptamers with affinity for pro-gastrin-releasing peptide (proGRP), a tumor marker for small cell lung cancer. *Appl Biochem Biotechnol*. 2013;169:250-5.
167. Świtnicka-Plak MA. Molecularly Imprinted Polymers for Applications in Proteomics and Diagnostics [Unpublished Doctoral Thesis]. Glasgow, UK: Strathclyde University; 2017.
168. Tamayo FG, Turiel E, Martín-Esteban A. Molecularly imprinted polymers for solid-phase extraction and solid-phase microextraction: Recent developments and future trends. *J Chromatogr A*. 2007;1152:32-40.
169. Chen J, Shinde S, Koch MH, Eisenacher M, Galozzi S, Lerari T et al. Low-bias phosphopeptide enrichment from scarce samples using plastic antibodies. *Sci Rep* 2015;5.
170. Chen J, Shinde S, Subedi P, Wierzbicka C, Sellergren B, Helling S et al. Validation of molecularly imprinted polymers for side chain selective phosphopeptide enrichment. *Sci Rep*. 2016;1471:45-50.
171. Ekström S, Wallman L, Malm J, Becker C, Lilja H, Laurell T et al. Integrated selective enrichment target - A microtechnology platform for matrix-assisted laser desorption/ionization-mass spectrometry applied on protein biomarkers in prostate diseases. *Electrophoresis*. 2004;25:3769-77.

172. Adler B, Boström T, Ekström S, Hober S, Laurell T. Miniaturized and automated high-throughput verification of proteins in the ISET platform with MALDI MS. *Anal Chem.* 2012;84:8663-9.
173. Jagadeesan KK, Wierzbicka C, Laurell T, Sellergren B, Shinde S, Ekstrom S. Multiplexed MALDI-MS arrays for screening of MIP solid phase extraction materials. *J Chromatogr B Anal Technol Biomed Life Sci.* 2016;1021:213-20.
174. Torsetnes SB, Broughton MN, Paus E, Halvorsen TG, Reubsaet L. Determining ProGRP and isoforms in lung and thyroid cancer patient samples: comparing an MS method with a routine clinical immunoassay. *Anal Bioanal Chem.* 2014;406:2733.
175. Ali SA, Imtaiyaz Hassan M, Islam A, Ahmad F. A review of methods available to estimate solvent-accessible surface areas of soluble proteins in the folded and unfolded states. *Curr Protein Pept Sci.* 2014;15:456-76.
176. Houbart V, Rozet E, Matagne A, Crommen J, Servais AC, Fillet M. Influence of sample and mobile phase composition on peptide retention behaviour and sensitivity in reversed-phase liquid chromatography/mass spectrometry. *J Chromatogr A.* 2013;1314:199-207.
177. Csizmadia JS, Szegezdi, J. Chemicalize.com. 2004-2007. <https://chemical/#/calculation>. Accessed 23/07/2017 2015.
178. Annesley TM. Ion Suppression in Mass Spectrometry. *Clin Chem.* 2003;49:1041-4.
179. Fonslow BR, Stein BD, Webb KJ, Xu T, Choi J, Park SK et al. Digestion and depletion of abundant proteins improves proteomic coverage. *Nat Methods.* 2013;10:54-6.
180. Hustoft HK, Brandtzaeg OK, Rogeberg M, Misaghian D, Torsetnes SB, Greibrokk T et al. Integrated enzyme reactor and high resolving chromatography in “sub-chip” dimensions for sensitive protein mass spectrometry. *Sci Rep.* 2013;3:3511

Papers