Materials and junctions for a novel oxide solar cell

Heine Nygard Riise

January 5, 2018

Thesis submitted for the degree of Philosophiæ Doctor

© **Heine Nygard Riise, 2018**

*Series of dissertations submitted to the
Faculty of Mathematics and Natural Sciences, University of Oslo
No. 1970*

ISSN 1501-7710

All rights reserved. No part of this publication may be
reproduced or transmitted, in any form or by any means, without permission.

Cover: Hanne Baadsgaard Utigard.
Print production: Reprosentralen, University of Oslo.

Abstract

This thesis explores various processing and materials aspects of an oxide solar cell. A tandem structure consisting of a Silicon (Si) bottom cell, and a Cuprous Oxide (Cu_2O)/Zinc Oxide (ZnO) top cell is suggested, and several materials challenges relevant for the design is addressed. Using Flash Lamp Annealing, shallow p-type emitters are produced in Si by indiffusion of Boron (B) from a surface source. The B diffusion is shown to be enhanced by a transient of Si interstitials originating from the surface coating. The n^{++} -side of a Si tunneling junction is realized by sputter depositing highly Phosphorus (P) doped Si thin films on quartz. The P activation and thin film conductivity are highest after prolonged, high temperature annealing, and thin film roughness is significantly reduced after a Reactive Ion Etch treatment of the quartz substrates. A rectifying $\text{Cu}_2\text{O}/\text{Si}$ heterojunction is demonstrated, and most of its depletion layer is located in Si showing that the acceptor concentration in the sputtered Cu_2O is significantly higher than $1.1 \times 10^{17} \text{cm}^{-3}$. Epitaxial growth of Cu_2O is realized on single crystal ZnO , and XRD measurements reveal that the Cu_2O grows in two separate [111]-oriented domains which are rotated 180° relative to each other. Further, a thin, detrimental layer of CuO is evidenced by TEM at the interface between the sputtered Cu_2O and the ZnO single crystal. Homoepitaxial sputter growth of ZnO is investigated in some detail, and the growth is found to depend on sputter target power density, substrate polarity, and growth ambient. Specifically, c-axis growth is promoted when growing on the Zn-face of ZnO , while slower, in-plane growth is promoted during O-face growth and during growth in a Nitrogen ambient. Treating sputter grown Cu_2O thin films by Rapid Thermal Annealing is demonstrated by XRD, PL and Hall effect measurements to be highly beneficial for the thin film structural quality. Finally, two band gap defects in Cu_2O are revealed using Temperature Dependent Hall effect measurements, and the defect ionization energy values are found to be dependent on sample strain.

Acknowledgments

There are naturally many people who have contributed to the realization of this thesis. My main supervisor, Edouard Monakhov, has given me the opportunity to work with the interesting and important topic of solar cells. He has been a true support through the entire work with the thesis, and always knows the right path for getting the most out of my results. My co-supervisor, Bengt Gunnar Svensson, has invariably shared his experience and vast knowledge on semiconductors when I have been short on answers. He always takes time out of his busy schedule to give advice and guidance.

I would also like to thank Kristin Bergum, Per Lindberg, Jiantuo Gan, and Ramón Schifano for enjoyable collaborations leading to article papers with me as a co-author. Certainly, without their contribution, this thesis would not be possible. I had the pleasure of supervising the Master's thesis of Vegard Skiftstad Olsen and the Bachelor's thesis of Lars Kristian Henriksen, and I am grateful to both of them for their important contribution to this dissertation.

A big thanks to all my colleagues who make the lunches, cabin trips, skiing trips, social gatherings, and ping pong matches such pleasant breaks from the PhD work. In particular, I would like to mention Mads, Vegard, Sigbjørn, and Nishant who have made sure that my progression in ping pong during the PhD has far surpassed my academic progression. Thanks to Hussein for all the lovely conversations and for always taking an interest in my work.

I am very grateful to have so many amazing friends who have supported and inspired me during these 4 years, and I thank each and every one of them for making life outside of work wonderful.

My family deserves a special thanks for always being there for me. They have given me the confidence and security needed to complete this degree, and I am incredibly lucky to have such a loving, generous, and warm family.

Noone in the entire world meets me with the same joy and enthusiasm as Giggs, and any difficulty vanishes when he greets me. Trude, the most important person in my life, is the reason I have been able to complete this work. You give me purpose. I love you so much

Tusen takk!

List of included papers

Paper I Formation of shallow boron emitters in crystalline silicon using flash lamp annealing: Role of excess silicon interstitials

H. N. Riise, T. Schumann, A. Azarov, R. Hübner, W. Skorupa,
B. G. Svensson and E. Monakhov
Appl. Phys Lett. **107** (2015) 022105

My contribution: Coordinating experiments, analyzing results, and writing manuscript

Paper II Structural properties of Cu₂O epitaxial films grown on c-axis single crystal ZnO by magnetron sputtering

J. Gan, S. Gorantla, H. N. Riise, Ø. S. Fjellvåg, S. Diplas,
O. M. Løvvik, B. G. Svensson, E. Monakhov and A. E. Gunnæs
Appl. Phys Lett. **108** (2016) 152110

My contribution: Coordinating XRD phi-scans, analyzing phi-scan results, rewriting and resubmitting manuscript after reviewer comments

Paper III Electronic Properties of Au/Cu₂O/n-type Si Heterojunctions for Energy Conversion

P. F. Lindberg, H. N. Riise, K. Bergum, B. G. Svensson
and E. Monakhov
Conference record of the Photovoltaic Specialists Conference 2016 (2016) 2807

My contribution: XRD measurements, analyzing XRD measurements, discussing results, and proof reading

Paper IV Local homoepitaxy of zinc oxide thin films by magnetron sputtering

H. N. Riise, V. S. Olsen, A. Azarov, A. Galeckas, T. N. Sky,
B. G. Svensson and E. Monakhov
Thin Solid Films **601** (2016) 18-21

My contribution: Supervising experiments, analyzing results, and writing manuscript

Paper V Comparison of the structural properties of Zn-face and O-face single crystal homoepitaxial ZnO epilayers grown by RF-magnetron sputtering

R. Schifano, H. N. Riise, J. Z. Domagala, A. Yu. Azarov,
R. Ratjczak, E. Monakhov, V. Venkatachalapathy, L. Vines,
K. S. Chan, J. Wong-Leung and B. G. Svensson
J. Appl. Phys. **121** (2017) 015304

My contribution: XRD measurements, discussing results, and proof reading

Paper VI Thin film Cu₂O for solar cell applications

K. Bergum, H. N. Riise, S. Gorantla, E. Monakhov
and B. G. Svensson
Conference record of the Photovoltaic Specialists Conference 2016 (2016)
2770

My contribution: TDH measurements, analyzing TDH results, writing section on TDH, discussing results, and proof reading

Paper VII Improving carrier transport in Cu₂O thin films by rapid thermal annealing

K. Bergum, H. N. Riise, S. Gorantla, P. F. Lindberg,
I. J. T. Jensen, A. E. Gunnæs, A. Galeckas, S. Diplas,
B. G. Svensson and E. Monakhov

Submitted to Journal of Physics: Condensed Matter

My contribution: Analyzing PL results, writing PL section, discussing results, and proof reading

Paper VIII Strain induced defect ionization energy variation in Cuprous Oxide

H. N. Riise, K. Bergum, T. N. Sky, B. G. Svensson
and E. Monakhov

In manuscript

My contribution: Characterizing samples by TDH and XRD, analyzing results, and writing manuscript

Contents

1	Introduction	1
2	A tandem oxide solar cell	3
2.1	Bottom Cell	4
2.1.1	Shallow p-type Si emitters	5
2.1.2	Tunneling contacts	8
2.2	Top Cell	9
2.2.1	Cu ₂ O/Si heterojunction	11
2.2.2	Cu ₂ O/ZnO heterojunction	11
2.2.3	Epitaxy of ZnO	12
2.2.4	High quality sputter deposited Cu ₂ O	13
2.2.5	Defects in Cu ₂ O	15
3	Experimental methods	17
3.1	Magnetron sputtering	17
3.1.1	Ion bombardment and plasma characteristics	18
3.1.2	Nucleation	19
3.1.3	Thin film growth	21
3.2	X-ray Diffraction	22
3.2.1	Modes of operation	24
3.2.2	Reciprocal Space Mapping	26
3.3	Hall effect measurements	27
3.3.1	False polarity	28
3.3.2	Temperature dependent Hall effect measurements	29
3.4	Atomic Force Microscopy	32
3.5	Heat treatments	33
3.5.1	Flash Lamp Annealing	33
3.5.2	Rapid Thermal Annealing	34

3.5.3	Furnace Annealing	34
3.6	Photoluminescence spectroscopy	35
3.7	Secondary Ion Mass Spectrometry	36
3.8	Rutherford Backscattering Spectrometry	37
4	Summary of Results	39
4.1	Shallow B emitters in Si	39
4.2	Highly P doped Si for tunneling junctions	41
4.3	Oxide heterojunctions	44
4.4	Homoepitaxial growth of ZnO by RF-magnetron sputtering . .	47
4.5	Cu ₂ O sputter grown thin films for enhanced solar cell perfor- mance	53
5	Conclusions and Future Work	61

Chapter 1

Introduction

With the increasing demand for energy in the world and stricter restrictions imposed on CO₂ emissions, the need for clean renewable energy is greater than ever. Photovoltaics (PV) has the potential to meet the projected world energy demand [1], and has indeed stepped up to the task in recent years with an annual market growth of 40 % between 2010 and 2016 [2]. However, if the solar revolution is to persist, new technologies pushing the PV cell conversion efficiencies up and driving the cost down must be developed. At the moment, the Silicon (Si) solar cell is dominating the PV market [2] and will continue to do so in the near future, and novel concepts arguably need to combine with the traditional Si PV cell to have commercial viability. A natural combination is a tandem cell where the Si solar cell acts as the bottom cell utilizing low energy photons, while the top cell exploits the high energy photons. The structure hence uses more of the available solar spectrum potentially championing the conversion efficiency of the standard Si solar cell.

The oxide semiconductors Zinc Oxide (ZnO) and Cuprous Oxide (Cu₂O) have promising properties for a top cell in tandem with a Si bottom cell. They both have wide band gaps (E_g) making them transparent to light which can be efficiently utilized by the Si solar cell. In fact, Cu₂O has an E_g close to ideal for a top cell material combined with a Si bottom cell [3]. Furthermore, both ZnO and Cu₂O are abundant materials [4] which are cheap to manufacture [5], satisfying both the requirement of clean renewable energy and cost efficient fabrication. This thesis explores several aspects of a tandem architecture consisting of a Si bottom cell and a Cu₂O/ZnO top cell.

A new and promising method of preparing the emitter in Si through indiffusion of Boron (B) from a surface source by Flash Lamp Annealing (FLA) is

described. The method produces emitters shallower than 140 nm, and the diffusion of B is greatly enhanced compared to its equilibrium diffusion due to the injection of a large number of Si interstitials from the B-rich surface coating.

To realize a tandem structure, a good Ohmic contact between the two cells must be established, and the n-side of a Si tunnel contact is explored. Low resistance thin films of highly Phosphorus (P) doped Si is realized by sputtering and various annealing treatments. It is also found that treating the substrates (quartz) with Reactive Ion Etch (RIE) before deposition considerably reduces the surface roughness of the thin films without affecting their electrical properties.

Heteroepitaxy of Cu_2O on ZnO is explored, revealing a thin interfacial layer of Cupric Oxide (CuO) between bulk mono-crystalline ZnO and sputtered Cu_2O ; the layer relieves strain in the structure. Further, the Cu_2O thin film grows in two separate [111]-oriented domains which are rotated 180° with respect to each other.

The electrical characteristics of the heterojunction between Cu_2O and Si (with a gold (Au) top electrode) is studied and seven orders of magnitude of rectification is achieved between forward and reverse biasing. The Au/ Cu_2O /Si system which preferably should behave as a normal pn structure, instead acts as a single sided p^+n junction where the Cu_2O thin film has a significantly higher fixed charge than what is evidenced from Hall effect measurements.

ZnO homoepitaxy by conventional magnetron sputtering is successfully demonstrated and shown to depend on target power, processing atmosphere and substrate polarity.

The improvement of Cu_2O through post-growth Rapid Thermal Annealing (RTA) is also reported. A defect study of the RTA treated thin films reveals two distinct acceptor levels in the E_g of Cu_2O and their ionization energies are found to depend on thin film strain.

The thesis is organized as follows: Chapter 2 gives an overview of relevant concepts and literature. Chapter 3 introduces the experimental methods utilized in the work and Chapter 4 summarizes the scientific findings of the thesis. Following some conclusions and suggestions of future work in Chapter 5, the scientific publications are presented.

Chapter 2

A tandem oxide solar cell

The overarching purpose of this work is to explore and develop materials and techniques relevant for accomplishing a tandem oxide PV cell. Numerous PV concepts exist in literature and in industry, but many of these are associated with intrinsic problems. New, promising and emerging PV technologies such as dye-sensitized [6] and perovskite [7] solar cells can boast conversion efficiencies above 10 and 20 % [8], respectively, but suffer from degradation over time [9, 10]. Further, more established technologies such as CdTe [11], CIGS [12] and GaAs/InP alloys [13] solar cells have high conversion efficiencies [8], but are either expensive to produce or use materials which are toxic or scarce (or both) [4, 14, 15]. Oxide PV cells on the other hand are chemically stable [5], can be manufactured inexpensively [5], and the materials explored in this thesis (ZnO and Cu₂O) are both abundant and non-toxic [4, 16, 17]. Solar cells based on Cu₂O have achieved conversion efficiencies of around 8 % [18] and have a theoretical efficiency limit around 20 % [19]. Because of its direct E_g of 2.17 eV, intrinsic p-type conductivity and high absorption, Cu₂O is a good candidate as an absorber layer in a tandem architecture with a Si bottom cell and an oxide top cell [20]. A potential tandem architecture is displayed in Fig. 2.1 where a common crystalline Si (c-Si) bottom cell is combined with a Cu₂O/ZnO top cell. Cu₂O acts as an absorber layer for photons with a higher energy than the E_g of Si, ZnO functions as the n-terminal of the top cell providing efficient rectification and carrier separation, while the bottom Si cell collects and converts low energy photons. There are several critical design features of the structure which need to be investigated and understood and this thesis explores a new method of preparing the p-Si emitter, fabrication of the n⁺⁺-Si tunnel layer, epitaxial growth of the ZnO layer, enhancement of the i-Cu₂O absorber layer,

Figure 2.1: Band structure of a tandem architecture with a Si bottom cell and a ZnO/Cu₂O top cell.

and the structural and electrical characteristics of the Cu₂O/Si and Cu₂O/ZnO heterojunctions.

2.1 Bottom Cell

In Fig. 2.1, the proposed bottom cell is a modified, standard c-Si solar cell, optimized for conversion of low energy photons. Si is an indirect semiconductor with an E_g of 1.11 eV at 300 K [21], and has an outstanding minority carrier diffusion length [22], superior passivating oxide or nitride [23], high carrier mobility [24, 25], and can efficiently be doped both p-type and n-type. Si solar cells have dominated the PV industry for decades [2], and the maturity of fabrication technology and price reduction of Si wafers have outweighed the disadvantages associated with power conversion in Si solar cells (e.g. non-ideal E_g , poor absorption coefficient, high energy consumption in production) and is hence the solar cell material of choice for most PV manufacturers. Although the Si solar cell is a very mature technology, there are still areas which are not sufficiently understood or which can be improved. For instance are light-induced degradation (LID), kerfless wafering and emitter blue response active areas of research [26–29].

Figure 2.2: The efficiency of a standard Si solar cell as a function of emitter depth and doping concentration. Two maxima at high doping/short emitter and moderate doping/long emitter can be seen.

2.1.1 Shallow p-type Si emitters

Si solar cells suffer from having an indirect E_g forcing the Si thickness to be on the order of 100s of μm to collect sufficient sunlight. As minority carriers are photogenerated throughout the volume of the cell, the minority carrier diffusion length, L , needs to be equal to or longer than the cell thickness. A long L is hence an important requirement when preparing high efficiency solar cells. L is highly dependent on the doping concentration of the material [22] leading to the common design criteria of having a wide, lowly doped base where most photogeneration occurs and a shallow, highly doped emitter for carrier collection. With a highly doped emitter, the contact resistance between the emitter and the front electrode is kept low, thus improving the series resistance of the cell. In addition, a high doping concentration in the emitter will improve the open circuit voltage (V_{oc}) since the Fermi level position (E_f) in the emitter moves towards the conduction/valence band edge (E_c/E_v). As blue photons are absorbed close to the surface of the Si, a shallow emitter will improve the blue response of a solar cell since more of the blue photons can be absorbed in the lowly doped base, where the carrier collection efficiency is higher. The efficiency of a stan-

Figure 2.3: Shallow emitters realized by in-diffusion from a surface source of a boron spin on diffusant through FLA and RTA (inset). The emitters fabricated by FLA have a high B concentration and are below 200 nm in depth.

dard solar cell as a function of the emitter depth and doping concentration was modelled using the Silvaco TCAD software [30], and the results are displayed in Fig. 2.2. Two maxima for the efficiency can be seen. One maximum occurs at moderate doping (mid 10^{19}cm^{-3}) and emitter depths of around $1\text{ }\mu\text{m}$. For this maximum, the diffusion length of the minority carriers is sufficient for them to reach the pn-junction while the V_{oc} is relatively high and the contact resistance is low. A second and higher maximum can be seen at a doping $>10^{20}\text{cm}^{-3}$ and emitters shallower than $\sim 200\text{ nm}$. In this case, because of the very shallow emitter, the minority carrier diffusion length is still sufficient to reach the junction, while V_{oc} is high and the contact resistance is very low.

Different strategies have been employed to improve the blue response of the cell. A common strategy in industry for fabricating emitters is through diffusion from a gas source in a tube furnace [31,32], but this requires prolonged heat treatments which deepens the emitter and reduces the blue response. Several rapid heat treatment schemes such as RTA [29, 33, 34], Excimer Laser Annealing (ELA) [35, 36] and FLA [28, 37] have successfully been employed to realize very shallow emitters with high doping concentrations. Perhaps the most efficient of these is ELA where a high intensity laser melts a very thin layer (~ 150

Figure 2.4: The two designs of a tandem solar cell, (a) four terminal configuration and, (b) two terminal configuration.

nm [38]) close to the surface greatly enhancing the diffusion of dopants producing a box like diffusion profile with very high dopant concentrations. However, this technique requires expensive low energy ion implantation and suffers from low throughput since the laser only heats the wafer locally. A higher throughput strategy for fabricating shallow emitters is using RTA to heat up wafers and in-diffusing dopants from a surface source [29, 33, 34]. This technology has the advantage of being able to treat several wafer simultaneously in a matter of seconds, but as seen in the inset of Fig. 2.3, the extension of the emitters are slightly too large, while the maximum doping concentration is lower than the ones leading to the highest maximum of Fig. 2.2. FLA combines both high throughput (due to exposure of a whole wafer in one flash), high doping, and shallow profiles. FLA can heat a wafer close to the melting point in a matter of ms, enhancing dopant diffusion and promoting a high incorporation of dopants, but since the annealing duration is short, the diffusion is still limited to below 200 nm as seen in Fig. 2.3. FLA is hence a promising alternative for enhancing the blue response of Si solar cells by creating very shallow and highly doped emitters.

Figure 2.5: A schematic tunnel junction. The E_v and E_c of the two sides align with each other allowing electrons and holes to tunnel through the depletion region to the other side.

2.1.2 Tunneling contacts

Fabricating a tandem solar cell requires electrical contacts to the top cell and bottom cell. Ideally, these two cells are contacted individually and the load on each cell is controlled separately thus maximizing the power output of both cells in a so-called four terminal configuration as shown in Fig. 2.4 (a). A four terminal device, however, is complex to fabricate, and the alternative two terminal configuration (Fig. 2.4 (b)) is a first natural choice when realizing tandem solar cells. In this configuration, the two cells are connected in series. The voltages of the two cells are additive, while the current between the two cells needs to be matched in order to avoid carrier loss at their contact point. A tunnel junction is a possible way for achieving such a series connection. In the case of Fig. 2.1, the tunnel junction is between an n⁺⁺ layer and p⁺⁺ layer of Si. The E_c and E_v of the n⁺⁺ and p⁺⁺ layer will align and an electron (or hole) can move from the n⁺⁺ side to the p⁺⁺ side (or vice versa) without changing its energy (cf. Fig. 2.5). A forward bias over the junction would even provide a driving force for charge carriers to pass from one side to the other since they may reduce their energy by tunneling. The tunneling charge carrier, however, will need to sur-

pass a barrier determined by the pn junction's depletion region width [39]. The depletion region width, W , is given by

$$W = \left[\frac{2\epsilon k_B T}{q^2} \ln \frac{N_a N_d}{n_i^2} \left(\frac{1}{N_a} + \frac{1}{N_d} \right) \right] \quad (2.1)$$

where ϵ is the permittivity of the material, k_B is Boltzmanns constant, T is the absolute temperature, q is the elementary charge, N_a is the acceptor concentration on the p-side, N_d is the donor concentration on the n-side and n_i is the intrinsic carrier density of the material. Hence, W is dependent on the doping concentration on both sides of the junction, and by doping both sides heavily, the narrowing of W reduces the tunneling barrier and effectively increases the tunneling current over the junction. To achieve a good tunneling contact, the doping needs to be high, but the junction must also be abrupt. An abrupt, highly doped junction is possible through depositing heavily doped thin film poly-Si by e.g. magnetron sputtering. Conventional magnetron sputtering has previously yielded n-type, Si thin films with P doping concentrations of $6.5 \times 10^{17} \text{cm}^{-3}$ [40], but higher values have been achieved by using pulsed DC sputtering [41]. Obtaining high mobility, crystalline thin films usually requires a post-deposition crystallization step after sputter deposition, and because of the high crystallization activation energy of amorphous Si (3.2 eV [42]), elevated annealing temperatures are beneficial [40, 43].

2.2 Top Cell

The top cell in the tandem structure of Fig. 2.1, requires excellent optical, electrical and structural properties. Several materials aspects need to be addressed for realizing an efficient oxide top cell. For sufficient light to pass to the Si bottom cell, the sub- E_g transparency of the top cell materials must be high; the presence of electrically active defects in either top cell material affects the carrier transport properties and may significantly limit the short circuit current of the top cell; crystal imperfections may lead to carrier trapping, poor transparency or reduced rectification. Further, because of the intrinsic p-type conductivity of Cu_2O , homojunctions of Cu_2O are challenging to obtain, and a so-called electron-selective contact (ESC) is necessary to achieve rectification, i.e. realizing a tandem solar cell utilizing Cu_2O requires the use of heterojunctions. Unlike homojunctions, the two sides of such a heterojunction usually have different E_g s, electron affinities (χ) and lattice constants, and to fabricate

Figure 2.6: Band structure of a heterojunction between n-Si and i-Cu₂O/p-Cu₂O.

a good heterojunction, care must be taken to find materials where these properties fit the purpose. In general, a poor lattice constant match between the two sides will lead to a high concentration of electrically active defects at the junction, since atoms with dangling bonds can give rise to energy levels in the E_g [44, 45], and strain in either material may lead to dislocations which trap charge carriers [46, 47].

Other properties important for a good heterojunction is the E_g s, doping and χ which all affect the magnitude of the contact potential (which in turn determines the magnitude of the V_{oc} of a solar cell). In addition, the E_g s of the two sides dictate which wavelength of light is absorbed by the cell. Since the light intensity of different wavelengths varies over the solar spectrum, the E_g s effectively determine the photogenerated current across the junction (which in turn governs the short circuit current of the solar cell). Hence, the choice of materials of a heterojunction is decisive for the performance of the junction. Fulfilling all the material requirements for an optimal heterojunction, however, is rarely possible, and normally the material choice of a heterojunction is a compromise between the material properties listed above (and several others such as bulk properties, toxicity, abundance, availability at the fabrication lab etc.).

2.2.1 Cu₂O/Si heterojunction

An alternative to the tandem design of Fig. 2.1 is replacing the ZnO n-side of the heterojunction with n-type Si (n-Si) as seen in Fig. 2.6. The benefits of this configuration is the ease of fabrication with only two materials in the tandem cell, the improved carrier transport between the top and bottom cell, and better work function match. By employing Si as the n-side in the top cell, however, challenges arise in allowing enough low wavelength light to the bottom c-Si cell, but these can partially be solved by keeping the Si of the top cell sufficiently thin. Since Si has an indirect E_g , a thin layer will transmit a significant amount of the light.

By using p-type Si (where both sides of the junction are p-type), the Cu₂O/Si heterojunction has previously been shown to be rectifying [48,49], and this was explained by a current provided by interface states [49]. Further, the heterojunction capacitance-voltage (CV) characteristics were modelled satisfactorily by a metal-semiconductor junction. Cu₂O/n-Si heterojunction rectification (albeit low) has also been demonstrated [50], but also in this case, the interface was defect-rich due to the large lattice mismatch causing a high concentration of dangling bonds. In fact, an XRD and TEM study of the Cu₂O/Si interface showed that a thin layer of amorphous Silicon Dioxide (SiO₂) existed between Si and Cu₂O mediating the growth of Cu₂O on Si by relieving strain in the structure [51]. The thin interfacial layer found in Ref. 51 could explain the high concentration of defects which is found in Refs. 48–50 for the Cu₂O/Si heterojunction.

2.2.2 Cu₂O/ZnO heterojunction

The disadvantage of using Si as the n-side of the top cell of the tandem structure of Fig. 2.1 (i.e. its absorbance of low energy photons) can be avoided by using ZnO which has a much larger E_g . Manufacturing a purely oxide based top cell is also beneficial for the reasons already mentioned in the introduction of this chapter. As with Si, there are challenges with the Cu₂O/ZnO junction. For instance, ZnO has a hexagonal lattice while Cu₂O crystallizes in a cubic structure. Although this yields incommensurate unit cells, the Cu₂O (111) plane has a periodic lattice coincidence with the (0002) lattice of ZnO. The mismatch between the (111) Cu₂O and (0002) ZnO lattice planes, however, is 7.6 %, making direct epitaxy of Cu₂O on ZnO challenging. Previously, an interfacial layer of Cu has been observed between Cu₂O and ZnO [52], presumably due to the large lattice

mismatch between Cu_2O and ZnO . After sufficient strain relief was provided by the intermediate metallic layer, ZnO resumed its (0002) textured growth and the system displayed an epitaxial relationship of $(111)\text{Cu}_2\text{O} \parallel (0002)\text{ZnO}$. Cu or CuO interfacial layers significantly reduce the V_{oc} [53] emphasizing the importance of interface control during the heterojunction preparation. On the other hand, if an interfacial layer is avoided, the large lattice mismatch between Cu_2O and ZnO will most likely give rise to interfacial defect states acting as recombination centers, and it has been theorized whether this is the cause of the poor IV characteristics of $\text{Cu}_2\text{O}/\text{ZnO}$ heterojunctions and solar cells [54–56].

Rectification by the $\text{Cu}_2\text{O}/\text{ZnO}$ heterojunction has been demonstrated on several occasions [54–58], and a solar cell with a conversion efficiency of around 4 % has been realized [59]. The solar cell displayed a V_{oc} of 0.69 V demonstrating the feasibility of preparing a defect reduced and stoichiometric $\text{Cu}_2\text{O}/\text{ZnO}$ heterojunction.

2.2.3 Epitaxy of ZnO

ZnO is commonly utilized as an ESC in combination with Cu_2O due to its intrinsic n-type character [60], direct E_g , earth-abundancy [4], non-toxicity [16], high carrier mobility [61], and ease of fabrication. As evidenced in the previous section, both the defect properties of Cu_2O and the structural integrity of the $\text{Cu}_2\text{O}/\text{ZnO}$ interface is of vital importance for good rectification, and controlling and understanding the growth and defect properties of the materials is hence crucial to realizing an efficient oxide solar cell. Epitaxial growth of oxide thin films simplifies the interpretation of material properties and can give further insight to the limiting factors of the solar cell conversion efficiencies, potentially enhancing thin film solar cell performance.

Epitaxial sputter deposition of ZnO requires careful control over a range of sputtering parameters. Kim et al. showed that an increased target power during deposition degraded the structural characteristics of a heteroepitaxial, sputter grown ZnO thin film on sapphire, while it improved the photoluminescence properties [62]. A higher deposition temperature was seen to have an advantageous effect on both the structural and optical characteristics. Other authors have also highlighted the importance of deposition temperature when preparing heteroepitaxial ZnO thin films [63, 64]. Both temperature and sputtering power affect the adatom surface mobility (cf. Sec. 3.1), and a high surface mobility promotes an unstrained epitaxy leading to high quality thin films. As in

heteroepitaxy, the temperature and sputtering power have a great influence on homoepitaxial sputter grown thin films [65].

Similarly to the sputtering power, the processing pressure also affects the adatom surface mobility (cf. Sec. 3.1) and consequently the thin film properties [66]. Further, in the case of heteroepitaxy, growing epitaxial ZnO films on foreign substrates inevitably leads to interfacial strain, and achieving high quality heteroepitaxy requires alleviation of the intrinsic lattice mismatch between the substrate and the thin film. If the epilayer is grown directly on the substrate, this can be obtained through Domain Matching Epitaxy (DME) [66–68], but buffer layers have also been successfully employed to produce excellent ZnO epilayers [68–70].

The superior quality of hetero- and homoepitaxial thin films compared to polycrystalline ones enables advanced characterization of the epilayers and the improved properties of the thin films can reveal elusive information on defect properties [71], carrier scattering mechanisms [66,72], carrier generation [73] and recombination mechanisms [74].

2.2.4 High quality sputter deposited Cu_2O

Preparing the top cell Cu_2O absorber layer of Fig. 2.1 can be a challenging task, since Cu_2O is highly sensitive to its preparation and post deposition processing conditions. For instance, at low oxygen partial pressure (p_{O_2}) and high temperature, Cu will tend to form; at high p_{O_2} and low temperature CuO is the stable phase of Cu_xO (cf. Fig. 2.7). At ambient temperature and pressure, CuO is the stable phase. In fact, Cu_2O is only stable at moderate p_{O_2} and temperatures, requiring careful control over deposition and post-deposition parameters. Further, the electrical properties of Cu_2O , are sensitive to whether the material is O-rich or Cu-rich, putting additional constraints on the processing parameters.

Despite being a low-cost and large-area technique, sputtering is a deposition method with close control of the relevant parameters for thin film Cu_2O growth. The plasma power can be tuned to vary the sputtering rate and energy deposited in the growing thin film; the partial pressure of oxygen can be changed to tune the phase and orientation of Cu_xO , and even control whether the film is Cu-rich or O-rich [76–78]; the substrate temperature controls the atom mobility and hence the crystal quality of the film [78]. Gan et al. investigated the effect of changing plasma power on the structural, optical and electrical properties of Cu_xO thin films, finding that the highest deposition power of 190 W

Figure 2.7: The phase diagram of the Cu-O system as a function of temperature and oxygen partial pressure. After Ref. 75.

produced superior thin films [79]. Depositions with different oxygen partial pressures in the sputtering chamber revealed that up to an O_2 flow ratio of 9 %, the amount of Cu_2O in the thin films increased. An O_2 flow of above 14 %, on the other hand, decreased the Cu_2O and increased the CuO content of the thin films [79]. This sensitivity of Cu_2O towards p_{O_2} is exemplified by Li et al. where an oxygen ratio change from 2.9 % to 3.1 % led to an order of magnitude increase in carrier density [76].

Post-deposition heat treatment is an effective method for improving the crystal quality and electrical characteristics of Cu_2O . Annealing Cu_2O thin films leads to an increase in surface grain size, crystallinity, and hole mobility [80–83]. Most of these reports, however, only consider the effect of varying annealing temperature, and do not report on the thin film quality (and phase) dependency on p_{O_2} . For instance, post-deposition in elevated p_{O_2} [82] and in air [84] leads to a change of phase from Cu_2O to CuO with a detrimental effect on the mobility of the samples.

Figure 2.8: The electrical conductivity of Cu_2O as a function of chemical N concentration as reported by Benz et al. [85]. The inset shows a fit of Eq. 2.2 to the acceptor ionization energies found in the study.

2.2.5 Defects in Cu_2O

The presence of defects in a material can be both beneficial and adverse to device performance. On the one hand, carrier generating defects with states situated close to the band edges lead to improved conductivity. On the other hand, defects deep in the E_g can trap carriers leading to high recombination rates (and low carrier lifetime), reduced carrier concentration and low mobility.

Cu_2O has a rich defect fauna and acceptor and donor levels have been reported at 0.08-1.08 eV above E_v [85–96]. There seems to exist a general consensus that the Cu vacancy (v_{Cu}) is the dominant acceptor giving rise to the intrinsic p-type conduction in Cu_2O [97–100], but experimentally the exact position of the defect level is disputed [88–90, 92, 101], although most reports

place its level around 0.25 eV above E_v . The defect is also predicted to have two different configurations giving rise to an additional defect level in the E_g [97–99, 102, 103]. Further, shallower levels have been ascribed to extrinsic defects [85, 101, 104–106].

The large spread in reported energy level values for the major acceptor has been explained by a range of trap states close to E_v with their concentrations and energy positions sensitive to the deposition and post-deposition treatment [93]. However, the hypothesis has not been verified by other authors and is not widely adopted in the field. An alternative explanation of the acceptor level variation has recently been put forward by Benz et al. [85]. They report on N doped Cu_2O and find that the acceptor ionization energy, E_a , depends on the chemical concentration of N, $[\text{N}]$, as

$$E_a([\text{N}]) = E_{a,0} - \alpha'[\text{N}]^{1/3} \quad (2.2)$$

where $E_{a,0}$ is the ionization energy at high dilution and α' is an empirical parameter. The model explains the reduction in ionization energy as an increasing charge interaction between charge carriers and dopant ions when the distance between the dopants decreases [107, 108]. A good agreement is obtained when fitting Eq. 2.2 to the experimental data (cf. Fig. 2.8), and Eq. 2.2 can account for the variation in conductivity and E_a with $[\text{N}]$.

Chapter 3

Experimental methods

The work described in this thesis is mainly experimental, and hence, quite a few experimental techniques have been utilized. Magnetron sputtering was used for deposition in almost all the reports of the thesis, X-ray Diffraction was the characterization technique of choice for extracting structural information, and Hall effect measurements were utilized to extract electrical information. These are described in some detail in the following. Apart from these three main experimental techniques, were also Atomic Force Microscopy (AFM), different heat treatments, Photoluminescence (PL) spectroscopy, Secondary Ion Mass Spectrometry (SIMS) and Rutherford Backscattering Spectrometry (RBS) exploited to a large degree to reach the results of this thesis, and a brief overview of these techniques are presented.

3.1 Magnetron sputtering

Sputtering relies on the ejection of material from a target by accelerated ions, and is a widely used technique for depositing thin films. A plasma of positive ions (normally Ar^+) is accelerated towards the negatively biased target (cathode), and the positive ions strike the target surface ejecting target material (ions, atoms, molecules). The energy of Ar^+ -ions hitting the cathode is determined by the voltage (V) applied to the cathode, while the amount of ejected material is dependent on the discharge current (I). In most sputtering systems, these two parameters are jointly controlled by the discharge power ($P = VI$). The ejected target species have momentum directed away from the target, travel through the plasma, and are deposited on the substrate (anode). On the way through the chamber, the target species experience collisions with the processing gas and

Figure 3.1: Different scenarios which can occur when an ion impinges on a solid material. a) On the left, an ion with an intermediate energy creates a sputtering event. b) In the middle, a low energy ion is reflected off the surface picking up a neutralizing electron and releasing a secondary electron from the material in the process. c) On the right, a high energy ion is implanted into the material damaging the lattice.

lose part of their momentum, and their energy when arriving at the substrate is hence correlated to both the discharge voltage and the processing pressure in the chamber [109–114]. The target species, mainly in the form of atoms and diatoms [115], arriving at the substrate, spend part of their energy adhering to the substrate as adatoms while their excess energy is manifested as adatom mobility. A high adatom mobility is beneficial for growing a dense thin film since the adatoms then have a higher probability of finding energetic minima on the substrate surface [116].

3.1.1 Ion bombardment and plasma characteristics

When a negative voltage is established at the cathode, positive ions from the plasma are accelerated towards the target. If the ions strike the surface of the target with an energy between 30-1000 eV, several large angle collisions occur just below the surface eventually leading to a collision with a surface atom which is then ejected from the target with a velocity component normal to the target surface, cf. Fig 3.1a); impinging ions with too low energies reflect off or adsorb

to the target surface, Fig. 3.1b); while a too high energy leads to implantation, Fig. 3.1c) [115]. The impact of the ion collision also releases secondary electrons from the target; these are accelerated away from the substrate and ionize additional ions in the plasma, and hence the plasma is self-sustained as long as sputtering occurs. If the target is isolating, however, electrons are not replenished to the surface of the target, fewer secondary electrons are emitted and plasma atoms are not ionized, in turn extinguishing the plasma. Thus, to sustain the plasma in the case of isolating substrates, the plasma is excited by an RF signal. The ions in the plasma have a too large inertia to follow the excitation, but the electrons, having a low mass, will be oscillated at the RF frequency between the anode and cathode ionizing atoms in the process and thus sustaining the plasma. Both the cathode and the anode will be negatively charged by this process, but by giving the anode a large area (typically the entire chamber functions as the anode) there will be a voltage drop over the plasma accelerating the plasma ions towards the cathode.

In a typical plasma, charged particles may make up only 0.001 % of the total plasma particles [115], and increasing this concentration is beneficial to the sputtering process. A high ion concentration increases the energetic ion flux to the target giving a higher sputtering rate. Further, by increasing the ion concentration the gas pressure inside the chamber may be reduced, leading to fewer collisions between sputtered atoms and gas atoms and thus increasing the impinging energy of the target species at the substrate. A common method for increasing the ion concentration in a plasma is by use of permanent magnets below the cathode in a sputtering mode termed magnetron sputtering. Magnetic field lines induce a helical motion of the electrons close to the cathode increasing their path length yielding more collisions between gas atoms and electrons, hence leading to a higher ionization degree in the plasma.

3.1.2 Nucleation

A growing thin film goes through several different processes during sputter deposition. Initially, when the target species arrive at the clean substrate, the atoms may adsorb to or reflect off the surface. An atom adsorbing to the surface (adatom) feels attraction to the surface by van der Waals forces [117]. This attraction is relatively weak (0.01-0.1 eV) [117] allowing the adatom to migrate on the surface and even desorb. If the adatom does not desorb, however, it will eventually change its binding from the weak van der Waals bond to a strong

Figure 3.2: The three growth modes described in the text. a) Layer by layer growth, b) island growth, and c) layer by layer + island growth.

chemical bond with a binding energy of 1-10 eV [118] in a process termed chemisorption. Because of the high binding energy, the adatom will at this point be incorporated into the growing film and the probability of desorption of the chemisorbed atom is low (unless the substrate temperature is very high).

After the initial impingement and adsorption, the deposited atoms migrate on the surface and bind to other atoms to create clusters. If the cluster is larger than a critical size it is stable and continues to incorporate impinging adatoms. If the cluster is smaller than the critical size, however, it is unstable and will spontaneously decompose. The critical size of the cluster is determined through a competition between its surface free energy, γ , (energy cost in creating a surface) and the energy gain associated with the creation of a stable nucleus, ΔG_v . The total change in free energy, ΔG_{tot} , is determined by

$$\Delta G_{tot} = 4\pi r^2 \gamma - \frac{4}{3}\pi r^3 \Delta G_v \quad (3.1)$$

where r is the size of the nucleus. When $\frac{\partial \Delta G_{tot}}{\partial r} = 0$, the nucleus reaches its critical size r^* and continues to grow. The ΔG_{tot} value when $\frac{\partial \Delta G_{tot}}{\partial r} = 0$ (ΔG_{tot}^*) determines the growth mode of the thin film. If ΔG_{tot}^* is less than zero, there is no barrier for nucleation and the film grows layer by layer (Frank-van der Merwe growth). Conversely, if ΔG_{tot}^* is positive, there is energy cost associated with increasing the area between the substrate and the nucleus, and the incoming adatoms rather seek to increase the nucleus to air area hence dewetting the surface. This leads to island growth (Volmer-Weber growth). A third growth mode termed Stranski-Krastanov may occur if ΔG_{tot}^* changes during growth (e.g. by change in film stress). Initially, the film grows layer by layer, but if ΔG_{tot}^* is increasing, the film will after a while start to develop island growth. All three growth modes are visualized in Fig. 3.2. Note that these models assume thermodynamic equilibrium, but in a real growth scenario there

Figure 3.3: Structural zone model as proposed by Thornton [116].

will be several limiting kinetic factors, e.g. the embedding of adatoms by incoming target species before they chemisorb to a surface or cluster, lack of energy to dissociate diatoms arriving at the surface, or presence of foreign species on the surface.

3.1.3 Thin film growth

For Frank-van der Merwe growth, the crystal growth after the initial nucleation proceeds by adding additional layers to the crystal. In the case of Volmer-Weber growth (and Stranski-Krastanov after island growth has been established), the growth proceeds by the enlargement of existing islands. When the islands touch, the thin film covers the surface and further growth depends on the surface mobility (and bulk mobility) of adatoms (and bulk atoms). A structure zone model describing the morphology of the thin film as a function of the process pressure and the deposition temperature has been detailed in several reports [116, 119–121]. Thornton divides the growth into four different zones (cf. Fig. 3.3) [116]. In zone 1, at high pressures and low temperatures, adatoms have a low surface mobility, are not able to migrate on the surface, and their fi-

nal position is determined by their impinging location resulting in a voided and amorphous-like structure. In zone T, at low pressures and temperatures (or intermediate temperatures), the adatoms have a high enough mobility to migrate on the grain (island) but not between grains. Voids are filled and the thin film develops fibrous grains which do not necessarily extend through the whole film. Further increasing the temperature (zone 2) gives the adatoms enough mobility to migrate between grains. The thin film restructures during growth leading to large columnar grains of the same orientation extending from the substrate to the surface. At very high substrate temperatures (zone 3), both the surface diffusion and bulk diffusion is high enough for significant re-structurative grain growth resulting in large grains which do not necessarily extend through the whole thin film or have a preferential orientation.

3.2 X-ray Diffraction

Insight in the crystal quality and structure of a material is of crucial importance for designing and synthesizing materials for applications, and X-Ray Diffraction (XRD) is a versatile and powerful tool in this context. X-rays incident on a material interact with the matrix atoms in different ways. The x-rays may ionize an atom (photoelectric effect); they may inelastically scatter off the atoms transferring part of their energy to the electrons of the atom (Compton scattering); or they may elastically scatter off the atoms by exciting the electron cloud to oscillate at the same frequency as the incoming photons, subsequently inducing the electrons to emit photons with the same energy as the incoming x-rays (Thomson scattering). In XRD, the latter scattering mechanism is exploited.

It is useful to consider the Thomson scattering mechanism by regarding an incoming x-ray as a wave with a wave vector $\mathbf{K}_0$. The wave is elastically scattered by atoms in the material, and the outgoing wave has a wave vector $\mathbf{K}$. The vector difference between these two wave vectors is the scattering vector $\mathbf{Q} = \mathbf{K} - \mathbf{K}_0$, as seen in Fig. 3.4. Only a fraction of the incoming wave interacts with each atom, and this scattered wave fraction may interfere constructively or destructively with other scattered wave fractions. If the material is crystalline, atoms are arranged in crystal planes and in the case of a cubic lattice, the criterion for constructive interference of the scattered waves is given by the Laue equations

Figure 3.4: An illustration of the scattering vector $\mathbf{Q}$ defined as the vector difference between the incoming wave vector $\mathbf{K}_0$ and the outgoing, scattered wave vector $\mathbf{K}$.

$$\begin{aligned}
 a\mathbf{Q}\mathbf{a}_1 &= 2\pi h \\
 a\mathbf{Q}\mathbf{a}_2 &= 2\pi k \\
 a\mathbf{Q}\mathbf{a}_3 &= 2\pi l
 \end{aligned} \tag{3.2}$$

where a is the lattice constant of the cubic lattice, $\mathbf{a}_1$, $\mathbf{a}_2$, $\mathbf{a}_3$ are the unit vectors of the cubic unit cell and h , k and l are the Miller indices of the reflecting crystal planes. The absolute value of the sum of the three contributions to $\mathbf{Q}$ gives the magnitude of the scattering vector:

$$\frac{|\mathbf{Q}|}{2\pi} = \frac{\sqrt{h^2 + k^2 + l^2}}{a} \tag{3.3}$$

The absolute value of $\mathbf{Q}$ is also equal to $\frac{4\pi}{\lambda} \sin \theta$ (cf. Fig. 3.4) and the equation simplifies to

$$2 \frac{a}{\sqrt{h^2 + k^2 + l^2}} \sin \theta = \lambda \tag{3.4}$$

Figure 3.5: An illustration of a $\theta/2\theta$ scan. The x-ray source and the detector are locked together keeping the incoming and outgoing angle the same. In-plane rotation is described by ϕ

$d_{hkl} = \frac{a}{\sqrt{h^2+k^2+l^2}}$ is the distance between two adjacent planes of Miller index (hkl), reducing Eq. 3.4 to Bragg's equation

$$2d_{hkl} \sin \theta_B = \lambda \quad (3.5)$$

with the subscript on θ_B signifying that the scattering angle is the Bragg angle where the outgoing wave has maximum intensity. The Bragg equation describes the relation between the wavelength of the probing x-rays, the distance between lattice planes and the angle of the incoming radiation. It states that the outgoing waves interfere constructively if the difference in pathlength for two waves scattering off separate crystal planes is an integer multiple of their wavelength.

3.2.1 Modes of operation

Several different modes of operation are used in XRD. A common way to identify the investigated material, the phase, the strain and the crystallinity is by

using the $\theta/2\theta$ scan. In this mode, the incoming beam angle and the outgoing angle are kept the same relative to the sample surface, and the incoming beam (and the detector recording the outgoing beam) is scanned from a low starting angle to a high end angle, as seen in Fig. 3.5. Referring to Eq. 3.5, scanning across angles is identical to scanning over lattice spacings in the sample, and since most materials have unique lattice dimensions, crystal reflections found in $\theta/2\theta$ scans act as a fingerprint pattern for a specific material and crystal phase. Because of the geometry of the measurement, however, a $\theta/2\theta$ scan can only detect lattice planes which are perpendicular to the scattering vector $\mathbf{Q}$, i.e. lattice planes parallel with the sample surface. This is a useful trait of the scan since it reveals whether the material has a preferential orientation (texturization). Further, by analyzing the peaks of the spectrum, the crystallinity and strain of a sample may be extracted. A peak displaced from its relaxed, unstrained position indicates strain in the sample. The intensity of a given reflection is dependent on the number of lattice planes which contribute to the reflection, and a high intensity indicates a highly crystalline sample (comparing samples, however, requires knowledge on the thickness of the samples since a thick sample yields a more intense reflection than a thin one although their crystallinity may be identical). A more robust method for determining crystallinity is by looking at the full width at half maximum (FWHM) of the reflection. A wide peak indicates a large spread in the lattice spacing stemming from dislocations, microstrain, grain boundaries or small crystallite sizes, i.e. the crystallinity of the material.

Dislocations in a material may also be detected by a separate mode of operation termed rocking curve measurements or ω scans. In this mode, the detector is kept stationary at a Bragg reflection while the incoming beam is scanned across the Bragg angle. This tilts the scattering vector and the set up allows detection of lattice planes which are not completely perpendicular to the sample surface. Dislocations lead to variations in the lattice spacing (which lead to a widening of the $\theta/2\theta$ peaks), but also to variations in the orientation of the lattice planes, and a high number of dislocations yields a large spread in lattice plane orientation leading to a widening of the rocking curve peak.

A given crystal plane has a certain symmetry, and if this symmetry is rotational, the in-plane rotation of the sample (illustrated in Fig. 3.5 as ϕ , which rotates the sample plane around $\mathbf{Q}$) determines whether the crystal plane can be detected. Consider a cubic unit cell as seen in Fig. 3.6, where the $\{111\}$ plane has four different equivalent planes. Obtaining a Bragg reflection from either of these planes requires careful alignment of the scattering vector (through chang-

Figure 3.6: The four equivalent $\{111\}$ planes in a simple cubic unit cell.

ing the detector and source angles) and the rotational angle, ϕ . A ϕ scan fixes the source and detector to a specific Bragg reflection (e.g. the (111) reflection in a cubic system) and rotates the sample about its center. The intensity of the reflection will reach a maximum when each of the rotationally equivalent planes align to the beam (in Fig. 3.6, four maxima will be recorded by rotating the sample 360°), revealing the rotational symmetry of the investigated plane.

3.2.2 Reciprocal Space Mapping

A useful representation of the lattice planes in a crystal is by considering them in reciprocal space. Lattice planes reduce to points in reciprocal space. Fig. 3.7 shows the reciprocal space of a cubic lattice, with how a rocking curve (ω scan), detector (2θ scan), 2θ - ω , and $\theta/2\theta$ scan traces the reciprocal space. A $\theta/2\theta$ scan traces a straight line from the origin, and a peak in this scan is hence only a slice of a reciprocal point along the h -direction. Such a peak will reveal information on strain, dislocations and limited grain size in the $[100]$ direction of the crystal, but does not reveal this information in any of the other directions. A reciprocal

Figure 3.7: Part of the reciprocal space of a simple cubic system seen in the plane spanned by the $[100]$ and $[010]$ direction. The traces in reciprocal space of different XRD scans (ω , 2θ , $2\theta-\omega$, and $\theta/2\theta$ scans) are represented schematically.

space map maps an entire peak in reciprocal space by a series of rocking curve, detector, or $2\theta-\omega$ scans over a reciprocal point. A reciprocal space map may hence reveal strain, dislocations and limited grain sizes in any of the directions of the reciprocal plane shown in Fig. 3.7 (or indeed any other directions in reciprocal space).

3.3 Hall effect measurements

Measuring the conductivity and carrier concentration (and deducing mobility) in a material is possible through Hall effect measurements. A moving charge carrier subjected to a transverse magnetic field is deflected perpendicularly to both the magnetic field and its instantaneous velocity. Hence, by passing current through a sample and applying a magnetic field, a large number of charge carriers are deflected, charge is accumulated and an electric field builds up perpendicular to the current flow. This field counteracts the force on the charge carriers from the magnetic field, and when equilibrium has been established, the electric field, E_y , is equal to

$$E_y = v_x B_z \quad (3.6)$$

where v_x and B_z is the average velocity of the charge carriers and the applied magnetic field, respectively. The average velocity of the charge carriers can be written $v_x = \frac{J_x}{qn(p)}$, where J_x is the current density, q the charge of the carrier and $n(p)$ is the concentration of electrons (holes). Combining these two equations yields

$$E_y = \frac{J_x}{qn(p)} B_z = R_H J_x B_z. \quad (3.7)$$

$R_H \equiv \frac{1}{qn(p)}$ is the Hall coefficient, and since J_x and B_z are known, R_H can be determined through measuring the built up electric field. R_H contains information of both the concentration of charge carriers and their polarity.

Four point measurements give the conductivity, σ , of the material and with knowledge of both the carrier concentration and the conductivity, the mobility, μ , of the carriers can be deduced through

$$\mu = \frac{\sigma}{qn(p)}. \quad (3.8)$$

3.3.1 False polarity

Accurate determination of E_y requires the carrier mobility to be sufficiently high. A low mobility reduces v_x (through the relation $v_x = \mu E_x$; in this case the electric field is along the direction of travel of the charge carriers and not to be confused with the magnetically induced field, E_y) and through Eq. 3.6 also the transverse electric field, E_y , making it challenging to extract a meaningful carrier concentration. In Fig. 3.8, this challenge is illustrated. The transverse voltages of two symmetric Cu_2O samples with photolithography defined contacts are tracked as the samples are subjected to a perpendicular magnetic field cycled between -10 kG and +10 kG. The temperature is kept constant. For the sample represented by the red line, the mobility is sufficiently high, and the transverse voltage follows the magnetic field as expected from Eq. 3.6. The sample represented by the black line, however, has a low mobility and its transverse voltage is noisy and does not follow the magnetic excitation. A carrier concentration extracted from this sample will not represent the actual concentration of the sample, but will rather be an arbitrary number determined by the noise level of the transverse voltage. Similarly, the polarity of the majority charge

Figure 3.8: Transverse voltage of two Cu_2O samples (black and red lines) subjected to a perpendicular magnetic field (blue line). The transverse voltage of the sample represented by the red line follows the magnetic field, while the transverse voltage of the sample represented by the black line does not. In the latter case, determination of the carrier concentration and carrier polarity is not possible.

carriers in the sample is determined by the sign of E_y , and if this is an arbitrary number (which can be both positive or negative), measurements of low mobility materials may show false polarities. Hence, reports based on Hall effect measurements of low mobility n-type or p-type materials [122–125] (typically below $1 \text{ cm}^2/\text{Vs}$) should be treated with skepticism.

3.3.2 Temperature dependent Hall effect measurements

The carrier scattering mechanisms and the energy position of defect levels in the E_g of a semiconductor can be obtained by recording the carrier concentration and mobility as a function of temperature. The mobility of a material is limited by several different carrier scattering mechanisms, and each one has a specific temperature dependency [126]. Hence, by simulating the temperature dependency of the mobility, the carrier scattering mechanisms are attainable.

The temperature dependency of the carrier concentration in a non-degenerate semiconductor may be dominated by excitations across the E_g or by the ionization of defects with energy levels in the E_g [39]. In the case of defect ionization,

a carrier occupying a defect level in the E_g may be excited into the conduction or valence band. With more energy available in the material, more carriers will be excited and thus with increasing temperature, the concentration of excited carriers increases. This thermally induced increase in carrier concentration has an Arrhenius type temperature dependency, with the ionization energy of the defect level as the activation energy of the reaction. This relation can be deduced by considering the neutrality condition in a semiconductor in the case of a p-type semiconductor (the same equations hold for an n-type semiconductor) [127]:

$$p + p_a = N_a - N_d \quad (3.9)$$

where p_a is the concentration of holes bound to an acceptor, N_a is the total concentration of acceptors and N_d is the concentration of compensating donors. Combining this equation with the relations

$$p = N_v e^{-\frac{E_f - E_v}{k_B T}} \quad (3.10)$$

and

$$p_a = \frac{N_a}{1 + \beta e^{\frac{E_f - E_a}{k_B T}}} \quad (3.11)$$

yields the following expression

$$p^2 + p(N_d + N'_v) - (N_a - N_d)N'_v = 0. \quad (3.12)$$

In the equations above, N_v is the effective density of states in the valence band, E_a is the acceptor energy level position, β is a factor describing the degeneracy of the acceptor level and N'_v is defined as

$$N'_v = \beta N_v e^{-\frac{E_a - E_v}{k_B T}}. \quad (3.13)$$

Solving Eq. 3.12 for p gives the temperature dependency of the holes in the semiconductor, and by fitting the equation to experimental data, N_a , N_d , and the energy position of the acceptor level in the E_g , $E_a - E_v$, can be extracted. Accurate determination of N_a and N_d , however, requires the acceptor level to reach full ionization and this normally requires elevated temperatures. If full ionization can not be achieved, only the energy position of the acceptor level, $E_a - E_v$, and the ratio between the compensating donor and the acceptor, $\frac{N_d}{N_a}$ are

attainable.

An alternative approach for simulating the temperature dependency of the carrier density is to regard the defects as carrier traps. A trap has a certain probability of emitting a charge carrier and of capturing a charge carrier. These charge-altering processes can be described by the rate equation of the trap, and in steady-state conditions, the trap occupancy is constant and all charge-altering processes are in balance. For a single charge, acceptor-like trap [128]

$$e_{N_a \rightarrow v}[1 - f_{N_a}(E)] - e_{N_a \rightarrow c}f_{N_a}(E) - \bar{p}_{v \rightarrow N_a}f_{N_a}(E) + \bar{n}_{c \rightarrow N_a}[1 - f_{N_a}(E)] = 0 \quad (3.14)$$

describes the steady-state conditions of the ionized state of the trap, where $e_{N_a \rightarrow v}$ is the emission rate of holes to the valence band, $e_{N_a \rightarrow c}$ is the emission rate of electrons to the conduction band, $\bar{p}_{v \rightarrow N_a}$ is the capture rate of holes from the valence band, $\bar{n}_{c \rightarrow N_a}$ is the capture rate of electrons from the conduction band, and $f_{N_a}(E)$ is the distribution function of the ionized trap. Assuming a p-type material and a trap level close to the valence band, the terms involving electron transfer can be neglected. In that case, $f_{N_a}(E)$ is approximated to

$$f_{N_a}(E) = \frac{e_{N_a \rightarrow v} + \bar{n}_{c \rightarrow N_a}}{e_{N_a \rightarrow v} + e_{N_a \rightarrow c} + \bar{p}_{v \rightarrow N_a} + \bar{n}_{c \rightarrow N_a}} \approx \frac{e_{N_a \rightarrow v}}{e_{N_a \rightarrow v} + \bar{p}_{v \rightarrow N_a}} \quad (3.15)$$

The capture rate of holes is given by $\bar{p}_{v \rightarrow N_a} = v_p \sigma_{v \rightarrow N_a} p$ (v_p is the average thermal velocity of holes, $\sigma_{v \rightarrow N_a}$ is the capture cross section of the trap, and p is the free hole concentration in the material), and the emission rate of holes is given by $e_{N_a \rightarrow v} = g_a v_p \sigma_{v \rightarrow N_a} N_v e^{-(E_a - E_v)/kT}$ (g_a is the degeneracy of the acceptor-like trap). Combining these relations with Eq. 3.15 yields

$$f_{N_a}(E) = \frac{g_a N_v e^{-(E_a - E_v)/k_B T}}{g_a N_v e^{-(E_a - E_v)/k_B T} + p} \quad (3.16)$$

Similarly, for a donor-like trap close to the E_v in a p-type material

$$-e_{N_d \rightarrow v}f_{N_d}(E) + e_{N_d \rightarrow c}[1 - f_{N_d}(E)] + \bar{p}_{v \rightarrow N_d}[1 - f_{N_d}(E)] - \bar{n}_{c \rightarrow N_d}f_{N_d}(E) = 0 \quad (3.17)$$

and

$$f_{N_d}(E) = \frac{e_{N_d \rightarrow c} + \bar{p}_{v \rightarrow N_d}}{e_{N_d \rightarrow v} + e_{N_d \rightarrow c} + \bar{p}_{v \rightarrow N_d} + \bar{n}_{c \rightarrow N_d}} \approx \frac{p}{g_d N_v e^{-(E_d - E_v)/kT} + p}. \quad (3.18)$$

Here, g_d is the degeneracy of the donor-like trap and $E_d - E_v$ is the trap ioniza-

tion energy relative to E_v . The concentration of ionized acceptor-like, N_a^- , and donor-like traps, N_d^+ , is given by

$$N_a^- = N_a \times f_{N_a}(E)$$

$$N_d^+ = N_d \times f_{N_d}(E).$$

Inserting these terms into the neutrality equation yields the following relation for the temperature dependency of the hole concentration in a p-type material:

$$p = \sum_{i=1}^r N_{ai} \frac{g_{ai} N_v e^{-(E_{ai}-E_v)/k_B T}}{g_{ai} N_v e^{-(E_{ai}-E_v)/k_B T} + p} - \sum_{j=1}^s N_{dj} \frac{p}{g_{dj} N_v e^{-(E_{dj}-E_v)/k_B T} + p} \quad (3.19)$$

Where r and s are the number of acceptor-like traps and donor-like traps present in the material. Eq. 3.19 is a polynomial in p of $(r+s+1)$ th degree, and similarly as Eq. 3.12, a fitting of Eq. 3.19 to experimental points will yield N_a , N_d , E_a-E_v and E_d-E_v . Again, accurate determination of N_a and N_d requires full ionization of the traps usually implying measurements at elevated temperatures.

3.4 Atomic Force Microscopy

The surface morphology of samples can reveal important information about the growth mode of thin films [129], and Atomic Force Microscopy (AFM) is a widely used technique for imaging the surface morphology. The technique utilizes a cantilever with a sharp tip which is scanned across the surface of a sample. As the tip of the cantilever is scanned across the sample, it tracks the surface and the movement of the cantilever is recorded creating an image of the sample surface. The cantilever movement is commonly detected by reflecting a laser beam off the cantilever onto a photodetector.

During a scan, the tip may either be in direct contact with the surface, oscillated above the surface, or oscillated closer to the surface making the tip touch the surface in the lower part of the oscillation. For the second and latter case (termed non-contact mode and tapping mode respectively), the oscillation frequency and amplitude will be modulated by the van der Waals forces the tip experiences in the lower part of the oscillation, and this modulation can be translated to a height profile of the sample surface.

Figure 3.9: Xe flash lamp emission and Si absorption coefficient [130, 131].

3.5 Heat treatments

Three different heat treatments have been utilized in this work. The purpose of annealing is for instance dopant activation, lattice restoration/crystallization, impurity diffusion, and defect annihilation, and each of these require different heat treatments for ideal processing. For instance, impurity diffusion can be a rather slow process compared to dopant activation and promoting the latter over the former requires a fast process. The following describes the three processes used in this work along with an overview of the benefits of each technique.

3.5.1 Flash Lamp Annealing

FLA is a very rapid heat treatment where a bank of capacitors discharges a large amount of energy into Xe flash lamps [37, 132–134]. The capacitors are discharged in a matter of milliseconds inducing the flash lamps to emit a light pulse with a high energy density peaking in intensity around 500 nm [135]. Fig. 3.9 shows the spectrum of a Xe flash lamp along with the wavelength dependent

absorption coefficient of Si [130, 131]. Since the Xe flash lamp emits photons in a wavelength range where Si absorbs strongly, FLA of Si wafers occurs through radiative heating and yields very rapid heating rates (50-100°C/ms [136]).

The fast heating limits defect diffusion even though the surface temperature of the wafer can approach the melting temperature of Si [28, 136], but it promotes dopant activation [137] and annealing of implantation induced lattice damage [138, 139].

3.5.2 Rapid Thermal Annealing

While FLA commonly gives direct radiative heating of a Si wafer, the RTA system used in this work instead relies on radiatively heating a SiC susceptor which in turn heats up the samples. The SiC susceptor is heated by halogen lamps, and the samples placed inside the susceptor are rapidly heated at a rate of $\sim 50^\circ\text{C/s}$ due to an excellent thermal contact between the susceptor and the sample. The cool down of the wafer occurs at a similar rate as the heating, allowing processes to be equilibrated at a high temperature and subsequently quenched, e.g. reaching a high equilibrium intrinsic point defect concentration at an elevated temperature and then quenching the samples to retain the high defect concentration at a low temperature [140]. The fast processing also allows kinetically fast processes to reach equilibrium while at the same time limiting slow processes, e.g. efficient activation of dopants in a material while at the same time limiting their diffusion [29].

3.5.3 Furnace Annealing

In conventional Furnace Annealing (FA), resistive heating elements heat a chamber volume where a sample is situated. The thermal contact between the heating elements and the samples is indirect (sample heating mainly occurs through convection) and less efficient than in RTA leading to slower heating rates. As the heating is resistive, however, the sample may be kept at an elevated temperature for a longer duration than in RTA where the filaments of the halogen lamps might burn out. Slow cooling rates prohibit quenching of samples inside the chamber, but by removing the samples from the chamber they may be quenched in air or other ambients (this poses challenges if the process or sample is sensitive to the ambient).

Figure 3.10: PL spectra of homoepitaxial sputter grown ZnO thin films taken at room temperature. Three prominent peaks are seen: NBE emission and two defect related peaks. The legend indicates the power density of the deposition.

3.6 Photoluminescence spectroscopy

Optical characteristics of a semiconductor reveals important information about its crystal quality, defect structure, carrier dynamics, and band structure. Photoluminescence (PL) spectroscopy is a well known technique for investigating such properties. It utilizes a laser which excites charge carriers in a material. These excited carriers will eventually relax into their original energy state by various relaxation mechanisms. In radiative relaxation, an excited carrier relaxes by emitting a photon, and this photon has a characteristic energy determined by the relaxation process. By detecting the emitted photons, details about the

emission can be surmised. The excited charge carriers, however, do not necessarily relax through a radiative pathway, but may find other relaxation mechanisms. A prominent non-radiative mechanism is the emission of a phonon to relax a charge carrier from the band edge to a mid- E_g defect level and subsequent full relaxation by the emission of another phonon. The more defects a material contains, the higher is the probability of an excited carrier following this non-radiative mechanism, and the emission of photons is suppressed. Hence, a luminous material indicates a high crystal quality with fewer intrinsic and extrinsic defects. In a high quality material, the dominant emission comes from near band edge (NBE) emission where mechanisms such as band-to-band, exciton, defect-bound exciton and phonon-assisted recombination lead to the emission of photons.

The relaxation of a carrier through a mid- E_g defect level, may also occur through the emission of a low-energy photon, and in that case, it is possible to determine defect level properties. Fig. 3.10 shows emission spectra of sputter grown homoepitaxial ZnO thin films revealing both NBE emission at around 370 nm (3.35 eV) and two broad defect emissions at around 410 nm (3 eV) and 550 nm (2.25 eV). The high intensity NBE emission indicates a material of good crystal quality, while the two lower energy peaks evidence the presence of (at least) two mid- E_g defect levels.

3.7 Secondary Ion Mass Spectrometry

Secondary Ion Mass Spectrometry (SIMS) is a technique for determining the chemical concentration of different impurities in a material. An ion beam is directed towards a sample, and as the ion beam strikes the sample surface, sample sputtering occurs. A fraction of the sputtered particles will be ionized, and these ions are then extracted and focused by ion lenses, filtered by velocity and mass through electrostatic and magnetic analyzers, and the ion beam (in which all ions have the same mass over charge ratio) is directed onto a detector which records the ion current. Quantification of an impurity signal is done by calibrating the recorded signal towards that of a reference sample of the same material with a known concentration of the investigated impurity. Since the impurity signal may be tracked in time, the impurity distribution as a function of depth is also obtainable by measuring the depth of the crater left by the ion beam and translating sputtering time to depth. SIMS has a very high sensitivity and a large

dynamic range, enabling measurements of impurity concentrations in the ppb range.

3.8 Rutherford Backscattering Spectrometry

Combining the possibility of gleaning stoichiometry as well as crystal quality, Rutherford Backscattering Spectrometry (RBS) is a powerful characterization tool. A sample is bombarded by energetic ions (commonly He^{2+}), and a fraction of those ions strike the surface and collide with nuclei of target atoms, and the incoming ions are backscattered. The energy of the backscattered ion is dependent on the angle of scattering, the mass and energy of the incoming ion and the mass of the matrix (target) atom, and by measuring the energy of the backscattered ion, the identity of the matrix atoms may be extracted. Further, different elements scatter the ions differently, depending on the element's scattering cross section. If this is known, the relative and absolute concentration of different elements in the material can be determined by considering the difference in backscattered ion signal originating from different elements.

For determining the concentration of elements in a material, a high backscattering yield is beneficial, and to this end, the ions are ideally impinging on the sample at an angle maximizing the backscattering yield. In channeling RBS (RBS/C), however, the ion beam is directed along a dominant crystal direction, and the He^{2+} -ions may pass through the channel between the atomic planes. If the atomic channel and the alignment of the ion beam is perfect, very limited backscattering will occur. The backscattering yield in RBS/C is an indication of the crystal perfection of the material since a large amount of displaced atoms in the crystal channel will increase the number of backscattered ions. RBS/C is hence a useful method for determining the crystal quality of a material.

Chapter 4

Summary of Results

The focus of this work has been to investigate different materials challenges related to the tandem oxide solar cell of Fig. 2.1. Aspects of both the bottom cell and the top cell has been addressed. The different topics covered, may roughly be divided into three: Dopant diffusion and activation in Si, ZnO homoepitaxial growth, and defect studies in Cu_2O . In the following, the main findings from these three topics is presented.

4.1 Shallow B emitters in Si

Short wavelength photons incident on a Si solar cell is absorbed very close to the surface. As an example, 400 nm wavelength photons have a penetration depth of 108 nm [130]. This places constraints on solar cells aiming to exploit these photons since emitters in Si solar cells typically have high doping concentrations to increase V_{oc} [141] and to reduce the series resistance to the metal front contact; the high doping promotes high recombination rates, limiting the diffusion length of optically excited minority charge carriers. In this sense, it is important that the emitter depth is shallow allowing diffusion of minority carriers to the junction where they are collected. Hence, an ideal emitter is as shallow as possible with as high dopant concentration as possible.

In Paper I realization of p-type emitters shallower than 140 nm and with B doping concentrations higher than $9 \times 10^{19} \text{cm}^{-3}$ is demonstrated. The emitters were produced by spin coating a Si wafer by a commercial B spin-on diffusant (Filmtronics B155 SOD) and subsequent FLA for 10 and 20 ms at energy densities between 83 J/cm^2 and 105 J/cm^2 . The short, high-temperature treatment

Figure 4.1: Concentration of indiffused B as a function of depth for Si samples spin coated with B diffusant and subsequently heat treated by FLA. The inset displays data of similar Si samples treated by RTA for 40 s. From Paper I.

mediates the diffusion of B from the spin-on diffusant into the Si wafer leading to shallow emitters with a low sheet resistance ($70\text{-}260\ \Omega/\square$), ideal for solar cell applications. The depth profiles of the emitter's B concentrations are displayed in Fig. 4.1. Interestingly, comparing the depth of the B profiles with the thermodynamic equilibrium diffusion length of B in Si at the estimated wafer temperature and heat duration ($\sim 1050\text{-}1100^\circ\text{C}$ and 20 ms) reveal a large discrepancy. The equilibrium diffusion length of B in Si at 1100°C for 20 ms is around 1 nm, but the experimental profiles extend between 50 and 140 nm.

But, by simulating the heat treatment, using Silvaco's SSupreme4 process simulator [30], with $1\text{-}2 \times 10^{18}\ \text{cm}^{-3}$ excess Si interstitials at the surface of the wafer, however, the experimental profile depths are recreated, indicating that the diffusion of B in the FLA treated samples is mediated and enhanced by a transient of interstitials similar to what is observed in heat treated, B implanted Si [142]. Additional evidence of transient enhanced diffusion (TED) is provided in Paper I by successful simulation of a decrease in profile extension at higher annealing temperatures (seen in the experimental profiles of Fig. 4.1). The decrease is a consequence of an increased equilibrium concentration of Si vacancies acting as direct competitors to B for the trapping of Si interstitials. As the va-

cancy concentration goes up, the interstitial concentration decreases and TED has less impact on the B diffusion, effectively reducing the profile depth (the formation energy of vacancies is ~ 1.3 eV lower than that of interstitials [30]). In Paper I, two causes of injection of excess interstitials are put forward: (i) the formation of Silicon Boride precipitates at the interface between the SOD and the Si wafer [143], and (ii) formation of SiO_2 at the interface between the SOD and the Si wafer [144].

In conclusion, Paper I reports the realization of shallow, highly B-doped emitters in Si by FLA. Further, the B diffusion is promoted by TED where an excess of Si interstitials injected from the surface of the wafer mediates and increases the diffusion of B.

4.2 Highly P doped Si for tunneling junctions

Manufacturing a tandem structure as seen in Fig. 2.1 requires an Ohmic contact between the bottom cell and the top cell. One of the possible strategies for such a connection is manufacturing a tunneling junction where a highly doped p^{++} layer is in contact with an n^{++} layer of the same material. The high doping will align the E_v in the p^{++} layer to the E_c in the n^{++} layer with a narrow depletion region separating the two terminals. The probability of tunneling across a barrier (in this case the depletion region) decreases exponentially with the width of the barrier [39]. Hence, if the two sides of the pn-junction are highly doped, the width of the depletion region will be small [39], the probability of tunneling increases, and a tunneling current across the junction establishes an Ohmic behavior.

Sputter deposition of highly P doped Si was performed to obtain a polycrystalline, low resistive n^{++} layer. The deposition was done at room temperature (RT) or 200°C from a mono-crystalline Si target with a P concentration of $\sim 5 \times 10^{19} \text{ cm}^{-3}$ on fused silica substrates at a deposition power of 200 W with a constant flow of 50 SCCM Ar yielding a processing pressure of 0.93 Pa. After deposition, selected samples were subjected to RTA at 1100°C for 3 min or annealed in a tube furnace at 1100°C for 30 min. The film thicknesses were between 270 nm and 300 nm after heat treatment.

In Fig. 4.2, the effect of RTA and furnace annealing on the electron concentration of the sputter deposited samples is shown. Furnace annealing yields a significantly higher carrier density compared to RTA (a factor 2-3 higher) and by comparing with SIMS data, the activation of P increases from ~ 10 -11 % in

Figure 4.2: Carrier density of the sputter deposited and heat treated Si.

the RTA treated samples to ~19-27 % in the furnace annealed samples. The deposition temperature does not significantly impact the electron concentration. The higher activation in the furnace annealed samples indicates slow kinetics in the activation of P in poly-Si, as these samples were kept at 1100°C for a longer duration.

A high carrier density reflects a high concentration of ionized impurities which normally limits the mobility. The mobility, however, is highest in the furnace annealed samples (Fig. 4.3), indicating that the mobility is not limited by the ionized impurities but rather by extended crystal defects such as dislocations, grain boundaries and amorphous regions [66]. Hence, the increase in mobility with furnace annealing attests to an improved crystal quality in the furnace annealed thin films compared to the RTA treated ones. Further, the deposition temperature influences the electron mobility in the thin films; the samples deposited at 200°C display higher mobilities than the ones deposited at room temperature. Nevertheless, the annealing procedure seems to be the most important determining factor for the mobility.

XRD measurements reveal weak but defined Si (111) and (220) reflections in the sample sputter deposited at room temperature and RTA treated at 1100°C testifying to a poly-crystalline thin film. Considering that this thin film has the lowest mobility in the study, this indicates that all the thin films have a

Figure 4.3: Hall mobility of the sputter deposited and heat treated Si.

poly-crystalline nature.

A good tunnel junction should be as abrupt as possible, but as evidenced by AFM, the deposited samples have high values of root mean square (RMS) roughness (between 5 and 13 nm). A junction fabricated from a rough thin film will experience non-uniform current distribution leading to undesirable heating and possible shunting. To prevent this, the quartz substrates were treated by a 200 W, 5 min RIE treatment prior to deposition. The thin films deposited on RIE treated substrates all show RMS roughnesses below 2 nm regardless of deposition temperature or post-deposition annealing procedure. Furthermore, the electrical properties of the thin films are not affected by the RIE treatment; both the mobilities and the carrier densities of the RIE treated samples are the same as the untreated ones (within experimental accuracy). Hence, RIE treatment of the substrates prior to deposition is beneficial for reducing the roughness of the thin films, while at the same time retaining the electrical properties.

By sputter depositing highly doped Si on RIE treated quartz substrates and heat treating the samples at 1100°C by RTA and tube furnace, respectively, low resistivity, poly-crystalline and flat thin films have been produced. The thin films have high electrical activation of P and mobilities around 10 cm²/Vs making them ideal as the n^{++} layer in a tunneling contact. The substrates used

Figure 4.4: HAADF HRSTEM images of a reactively grown Cu_2O thin film grown on single crystal ZnO . An epitaxial relationship of $(111)\text{Cu}_2\text{O} \parallel (0001)\text{ZnO}$ is found, with a thin, ~ 5 nm CuO interfacial layer between ZnO and Cu_2O . This is supported by Fast-Fourier Transform diffraction patterns (side panel).

in this study are quartz, but the fabrication of a solar cell requires a Si wafer as the substrate, and the results here do not necessarily reflect the properties of a highly P-doped Si thin film on a Si wafer. The study, however, evidences the close control of film properties which is possible by various preparation schemes.

4.3 Oxide heterojunctions

A key component of an oxide solar cell is its pn junction. The electrical and structural characteristics of such a junction is of paramount importance for realizing efficient solar cells. A $\text{Cu}_2\text{O}/\text{ZnO}$ heterojunction is ideal as a top cell in a tandem structure due to the large E_g s of both materials allowing transmission of long wavelength light to the bottom cell. Reported conversion efficiencies of $\text{Cu}_2\text{O}/\text{ZnO}$ solar cell systems, however, suffer from low V_{oc} s and Fill factors (FF) [59, 145–148] indicating an efficiency loss at the interface between the Cu_2O and the wider E_g ZnO . Understanding and improving the $\text{Cu}_2\text{O}/\text{ZnO}$ junction would hence assist in increasing cell efficiency.

The interface between a [0001]-oriented ZnO single crystal and sputter grown Cu₂O film is investigated in Paper II. Both reactively sputtered and ceramically sputtered Cu₂O was deposited on O-polar and Zn-polar ZnO crystals, and XRD measurements reveal predominantly [111]-oriented growth of Cu₂O. The only exception is ceramically grown Cu₂O on O-polar ZnO where parts of the film grow along the [110] direction. In-plane (331) ϕ scans of a [111]-oriented, reactively sputtered Cu₂O thin film on Zn-polar ZnO show that Cu₂O grows epitaxially on the substrate, with 6 well defined (331) peaks in the diffractogram (evidencing rotational coherence of the Cu₂O unit cells through the entire film). The {331} planes, however, have a three-fold symmetry rather than a six-fold suggesting that the thin film grows in two different domains which are rotated 180° (around the [111]-axis) with respect to each other. The result is supported by an in-depth TEM analysis of a similar thin film [149] and the same phenomenon has been reported for other oxide based heterostructures [150]. High Angle Annular Dark Field High Resolution Scanning Transmission Electron Microscopy (HAADF HRSTEM) confirms the epitaxial nature of the Cu₂O thin films, but also proves the existence of a thin, ~5 nm interfacial CuO layer (Fig. 4.4). Because of the large lattice mismatch between Cu₂O and ZnO, CuO growth is promoted to relieve the strain, but since the stoichiometry of the deposition dictates Cu₂O formation, Cu₂O forms after the strain is reduced below a certain level [149], explaining the presence of the thin CuO interface layer. The interfacial CuO is detrimental to a ZnO/Cu₂O-based solar cell through poorer band alignment, higher number of defects at the interface, and E_f pinning, and can partially explain the poor conversion efficiencies reported for ZnO/Cu₂O heterojunctions [59, 145–148].

Summarizing, heteroepitaxial growth of thin film Cu₂O on single crystal ZnO is evidenced by XRD and TEM in Paper II. The thin films grow in two separate domains which are rotated 180° with respect to each other. Further, a thin interfacial layer of CuO is revealed, and this layer is detrimental to a solar cell based on the system.

Similarly to the Cu₂O/ZnO system, a Cu₂O/Si heterojunction may also provide rectification with the benefit of reducing the number of materials if the heterojunction is combined with a Si bottom cell, and hence simplifying thin film growth and band alignment. Reports in literature on Cu₂O/Si heterojunctions detail low rectification [48–50, 151], and to make the heterojunction relevant for solar cell applications, the degree of rectification needs to be increased.

In Paper III, Cu_2O thin films were sputter deposited on n-type (100) Si (n-Si) substrates and the electronic properties of the heterostructure are investigated. Current-voltage (IV) measurements show 7 orders of magnitude rectification on a diode architecture of n-Si, Cu_2O deposited at 400°C , and evaporated Au contacts, significantly more than what has been reported in literature, and indicating a good interface with no undesirable interfacial SiO_2 . A similar system with room temperature deposited Cu_2O only has 3 orders of magnitude rectification, and this thin film also displays poorer crystal quality, lower conductivity, and higher defect concentrations compared to the thin film deposited at 400°C . In addition, the thin film deposited at room temperature contains undesirable CuO inclusions. From Hall effect measurements, the thin film deposited at 400°C has a hole mobility of $17 \text{ cm}^2/\text{Vs}$ and a net hole concentration of $3 \times 10^{15} \text{ cm}^{-3}$. Calculations on an equivalent pn structure (n-Si/ Cu_2O /Au), with a Cu_2O carrier concentration of $3 \times 10^{15} \text{ cm}^{-3}$, however, yields a capacitance around two orders of magnitude lower than that extracted from CV measurements (1 MHz probe frequency). In fact, CV evidences a fixed charge concentration at the junction of $1.1 \times 10^{17} \text{ cm}^{-3}$, equal to the carrier concentration of the Si substrate, indicating that the depletion region is mainly inside Si even though Cu_2O has a nominally lower carrier concentration at room temperature. On the other hand, calculations of a single sided p^+n structure, with the depletion region mainly inside Si and an n-side doping concentration equal to that of the Si substrate yields a capacitance of the same order of magnitude as the experimental one. Hence, the Cu_2O thin film does not behave as a moderately doped semiconductor, but displays instead a significantly higher fixed charge than Si, leading to a p^+n structure with its depletion region mainly inside Si.

Paper III shows that Cu_2O deposited at 400°C on n-Si has beneficial characteristics for use in a heterojunction solar cell. A relatively high mobility ($17 \text{ cm}^2/\text{Vs}$) and 7 orders of magnitude rectification prove that an n-si/ Cu_2O /Au architecture is suitable for energy conversion. The system does not act as a pn junction with depletion in Cu_2O , but rather as a p^+n junction with the depletion region mainly in Si.

4.4 Homoepitaxial growth of ZnO by RF-magnetron sputtering

Realizing an oxide based solar cell requires careful control and understanding of the fabrication processes. Depositing ZnO thin films is an integral part of the fabrication process of the oxide solar cell of Fig. 2.1, and by depositing homoepitaxial ZnO thin films, insight in the deposition process and thin film properties can be obtained. Further, mastering homoepitaxial growth of ZnO is an important step on the path to shift from GaN based to ZnO based optical devices (e.g. blue LEDs).

Homoepitaxial growth of ZnO has been demonstrated on several occasions, but most of these reports involve the use of elaborate techniques such as Molecular Beam Epitaxy (MBE), Metal-Organic Chemical Vapor Deposition (MOCVD) or Pulsed Laser Deposition (PLD) [71, 73, 152–155] which are to a large extent limited to research applications. Sputtering on the other hand is an established technique for large-area depositions and is widely used in the industry. Hence, realizing homoepitaxy through conventional sputtering [65, 72] could simplify the shift from GaN to ZnO based optical devices. Further, homoepitaxial growth eliminates strain fields and grain boundaries during growth, and is a simpler material system to analyze than strained, polycrystalline thin films. Sputter grown homoepitaxial thin films may thus give a more fundamental understanding of the sputtering process.

In Paper IV, the homoepitaxial growth of ZnO by RF magnetron sputtering on O-polar hydrothermally (HT) grown ZnO substrates is demonstrated. Six thin films deposited with different plasma power densities were investigated, and RBS/C, XRD and PL spectroscopy all testify to homoepitaxial growth for the thin films deposited at low power densities. The channeling yield from RBS/C is around 2 %, a value rivaling bulk ZnO crystals [156, 157]. All the analyzing techniques evidence a deterioration in crystal quality at higher deposition power densities, most readily visualized by the $\theta/2\theta$ data of Fig. 4.5 where the low power density samples fully overlap with the substrate peak, while at higher power densities a strained thin film is seen as a shoulder peak on the main substrate peak.

AFM measurements show that the growth mode of the thin films is not Frank-van der Merwe growth, but rather 3D growth; the surface is dominated by small grains typical for this type of growth. In Paper IV, homoepitaxy was hence not conclusively confirmed and the growth was labelled as "local ho-

Figure 4.5: $\theta/2\theta$ measurements of the (0002) reflection of homoepitaxially sputter grown ZnO thin films. At low power densities, the thin film reflection overlaps with the substrate peak indicating perfect coherence. At higher power densities, a strained thin film is evidenced.

moepitaxy" suggesting that the thin film does not exhibit a coherent crystal in the lateral dimension. However, further analysis of the sample deposited at 0.22 W/cm² power density by High-resolution Transmission Electron Microscopy (HRTEM) reveals that the thin film is indeed laterally coherent (Fig. 4.6). Although the thin film is homoepitaxial both in the c-direction and in-plane, the 3D growth mode as revealed by AFM is still valid, and the thin films hence grow as islands which coalesce perfectly.

Paper IV hence demonstrates homoepitaxial growth of ZnO by sputtering, but also the importance of controlling the sputtering power density during deposition. At low power densities, defect free, homoepitaxial thin film is obtained, while at high power densities the thin film is strained and defect rich. Instead of growing in a 2D Frank-van der Merwe growth mode, the thin films grow in a 3D island growth mode.

Frank-van der Merwe growth is beneficial for optoelectronic devices since a flat surface yields abrupt junctions and good templates for growing additional layers. To realize this type of growth, a sample was sputter deposited in an N₂ atmosphere (gas flow mix of 48 SCCM Ar, 1 SCCM O₂ and 5 SCCM N₂),

Figure 4.6: HRTEM image of the thin film deposited at 0.22 W/cm^2 power density evidencing perfect epitaxy.

resulting in near-2D thin film growth. Atomic surface steps are seen on the faces of large hexagonal domains in the AFM image of the thin film seen in Fig. 4.7. The thin film still retains the excellent crystal quality of the films grown without N_2 evidenced by its XRD rocking curve FWHM of 35 arcsecs, a value which is comparable to single crystal ZnO, MBE and MOCVD grown homoepitaxial thin films [153, 158, 159]. TEM analysis (Fig. 4.8) also verify the high structural quality and homoepitaxial nature of the thin film, although a nm-thick defect-rich interface layer is revealed. The TEM analysis also reveals a possible cause for the switch from 3D to near-2D growth mode: The film grown with N_2 is significantly thinner than the ones deposited without N_2 , although they have the same deposition time (cf. Figs. 4.6 and 4.8). The reduced thickness is corroborated by SIMS measurements. Further, the film grown with N_2 on ZnO is also significantly thinner than a film deposited with the same parameters on a (100) Si substrate (76 nm vs 391 nm), ruling out poor sputtering efficacy of N_2 -ions as a possible cause for the reduction in deposition rate.

The growth rate in the c-direction is hence considerably reduced when growing homoepitaxially in a partial N_2 atmosphere, suggesting that N_2 inhibits

Figure 4.7: AFM image of a thin film grown in an N_2 atmosphere. Atomic steps are seen on the faces of large hexagonal domains evidencing a near-2D growth mode.

Figure 4.8: TEM image of a thin film grown in N_2 atmosphere. The thin film exhibits epitaxial growth, but has a nm-thick defect-rich layer at the substrate interface.

nucleation, forcing adatoms to migrate longer distances before chemisorbing, effectively increasing the adatom mobility and the desorption rate. Similar effects have been reported for (i) polycrystalline sputter growth of ZnO, where N suppresses the nucleation of grains by increasing the nucleation energy barrier [160, 161]; (ii) Si oxidation where the growth rate of SiO₂ was significantly reduced by an increase in the area density of surface N either due to "neutralization of oxide growth sites" or due to N acting as a diffusion barrier for O [162]; and (iii) Metal Organic Vapor Phase Epitaxy grown ZnSe where N reduced the growth rate because N adsorbed to the surface inhibiting reaction between the Se-terminated surface and Zn-containing precursors [163]. The increase in adatom mobility and desorption rate from N inhibition of nucleation sites, favors in-plane growth over c-direction growth and hence lowers the growth rate. A higher ratio of in-plane over c-direction growth promotes the steps and terraces associated with Frank-van der Merwe growth, resulting in an atomically flat surface when ZnO is sputter grown in a partial N₂ atmosphere.

In conclusion, near-2D sputter growth of ZnO is demonstrated by introducing N₂ in the sputtering chamber during deposition. The crystal quality is excellent, but the film thickness is significantly reduced indicating that N₂ inhibits nucleation, which increases in-plane surface diffusion of adatoms and reduces the deposition rate.

Deposition power density and processing atmosphere hence influence the homoepitaxial growth of ZnO, and in paper V the difference in thin film properties between homoepitaxial deposition of ZnO on Zn-polar and O-polar HT grown bulk ZnO crystal is investigated. ZnO was sputter deposited simultaneously on the O-polar surface (O-face) and the Zn-polar surface (Zn-face) using a power density of 1.11 W/cm² at 400°C. As seen in the $\theta/2\theta$ diffractograms of Fig. 4.9, the thin film deposited on the O-face (sample B) is elongated 0.7 % in the c-direction, while the Zn-face thin film (sample A) has perfect coherence to the substrate. The superior crystal quality of sample A is corroborated by transverse ω scans, with a FWHM of the ZnO (0002) peak of 70 arcsec, compared to a 1400 arcsec FWHM for sample B. Sample B hence has a defective epilayer with a high dislocation density and this conclusion is supported by RBS/C, RSM and HRTEM analysis.

HRTEM also reveals that sample B is ~400 nm thinner than sample A, although they were deposited simultaneously. The difference in thickness is consistent with previous reports of epitaxial growth on Zn-face and O-face [164]. Owing to Zn incorporation at step edges for the O-polar surface and Zn in-

Figure 4.9: $\theta/2\theta$ measurements of two homoepitaxial ZnO thin films deposited on Zn-face (sample A) and O-face (sample B) bulk ZnO single crystals. Sample A shows an excellent coherence to the substrate, while sample B is strained in the c-direction.

corporation directly on the surface for the Zn-polar surface, the growth rate is much faster in the c-direction for the Zn-face compared to the O-face (where in-plane growth is promoted) [164]. It is suggested in Paper V that the slower growth rate of sample B leads to longer exposures to ion bombardment and re-sputtering. Consequently, excess Zn atoms are incorporated at bombardment induced nucleation sites giving a defective growth and thinner film.

AFM images show that the thin films grow in a 3D growth mode, but HRTEM images verify that the thin film is coherent both in the c-direction and in-plane, and the thin films grow as islands which merge perfectly without any detectable grain boundaries (cf. the above discussion regarding Paper IV).

In summary, Paper V reveals that the homoepitaxial growth of ZnO is highly dependent on the polarity of the substrate surface. Deposition on the O-face of the ZnO substrate leads to a strained layer with a high dislocation density, while deposition on the Zn-face yields a high quality thin film with excellent coherence to the substrate. The difference between the two polarities is suggested to arise from the lower growth rate on O-face leading to more ion bombardment during deposition and hence a defective growth.

4.5 Cu₂O sputter grown thin films for enhanced solar cell performance

A solar cell requires a p-type layer, and in that respect, Cu₂O (which is intrinsically p-type) is a highly relevant material for oxide cells. The highest conversion efficiencies of Cu₂O-based solar cells have been achieved with thermally oxidized Cu sheets [165]. For ease of fabrication, however, thin film solar cells would be preferable over oxidized sheet solar cells. To close the gap in conversion efficiency between these two, preparation of high quality Cu₂O thin films is paramount.

Controlling the crystal phase and crystal quality of copper oxide is possible by changing the oxygen partial pressure, p_{O_2} , during sputter deposition, and this is explored in Paper VI. Cu_xO was RF sputtered at a power density of 1.11 W/cm² at 400°C from a Cu target. The p_{O_2} in the chamber during deposition was varied between 2.6×10^{-5} and 3.8×10^{-2} Pa. At $p_{O_2} < 1.9 \times 10^{-2}$ Pa, the films have a phase mix of Cu₂O and Cu, as evidenced by $\theta/2\theta$ scans; a $p_{O_2} \geq 2.2 \times 10^{-2}$ Pa yields films consisting of Cu₂O and CuO. Between these p_{O_2} values, two films of phase pure Cu₂O are obtained. In the paper, these two thin films are labelled sample no. 5 and sample no. 6 (deposited at $p_{O_2} = 1.9 \times 10^{-2}$ and 2.1×10^{-2} Pa, respectively). Although both samples were phase pure Cu₂O, their crystal orientations differ and sample no. 6 has a more pronounced (200) reflection than sample no. 5.

The electrical properties of these two thin films are also different. Sample no. 5, which is deposited in Cu-rich conditions, has a higher carrier concentration and mobility than sample no. 6, which is deposited in O-rich conditions. The decrease in carrier concentration when going from Cu-rich to O-rich conditions is surprising, since acceptor-like defects such as v_{Cu} and O_i are more likely to form at O-rich conditions, whereas donor-like defects (v_O and Cu_i) are less likely to form. The crystal orientation of the thin films may play a role here. A shift of crystal orientation from (111) to (200) from sample no. 5 to no. 6 could lead to more charge carrier traps at the grain boundaries, reducing the free carrier concentration. Elevated fixed charge concentrations at the grain boundaries increase the barrier for charge carriers passing the boundary which, in turn, decreases the carrier mobility (a shift which is indeed seen).

A temperature dependent Hall effect measurement (TDH) of sample no. 6 reveals two E_g levels with ionization energies of 0.16 eV and 0.23 eV relative to the E_v (cf. Fig. 4.10). These values are close to the ionization energy of the v_{Cu}

Figure 4.10: Carrier density as a function of the reciprocal temperature of a Cu_2O sample sputter deposited at 400°C . Two states with ionization energies of 0.16 eV and 0.23 eV are resolved.

acceptor reported from experimental work [88–90, 92, 101] and first-principles studies [97–100]. Further, the presence of two levels could be related to the two configurations of v_{Cu} , i.e. the normal configuration, v_{Cu} , and the split configuration, $v_{\text{Cu}(s)}$, which both have similar formation energies but different ionization energies [97–99, 102, 103].

Summarizing, Paper VI details the preparation of Cu_2O by RF sputtering. Two phase pure Cu_2O thin films are produced in a narrow p_{O_2} range, but they differ in their crystal orientation, carrier concentration, and mobility. These three properties are likely interlinked. Two deep levels in the E_g are revealed from TDH data and it is speculated whether these could arise from the two configurations of v_{Cu} .

Achieving high carrier mobility in as-deposited Cu_2O thin films is feasible (cf. Paper VI and Refs. 76, 95, 166), but most reported as-deposited Cu_2O thin film mobilities are below $10 \text{ cm}^2/\text{Vs}$ [80, 82, 83, 167–172]. A common way of improving the electrical, optical and structural characteristics of semiconductors is through heat treatment, since the excess energy provided to the lattice annihilates point and extended defects, improves the crystallinity, and reduces

Figure 4.11: Room temperature PL spectra of sputter deposited and RTA treated samples. A dominant NBE is seen for all the RTA treated samples.

the number of scattering centers.

In Paper VII, reactively RF sputtered Cu_2O thin films are RTA treated at 600°C, 700°C, 800°C, and 900°C for 3 min in a p_{O_2} of 10 Pa, and subsequently, their structural, optical, and electrical properties are probed by XRD, Scanning Electron Microscopy (SEM), UV-VIS spectroscopy, PL spectroscopy and Hall effect measurements. Upon RTA treatment, the lateral crystal grain size of the thin films (as evidenced by SEM) increases significantly, and assuming a growth driven by excess energy stored in the grain boundaries, an activation energy of 0.8 ± 0.1 eV is extracted for the grain boundary motion. It is speculated whether this activation energy is correlated with the formation energy of v_{Cu} (reported to be 0.28-1.34 eV [97–100,103]) pointing to grain growth controlled by vacancy mediated copper (Cu) atom diffusion.

The increase in grain size (and increase in XRD (111) intensity) indicates an improved crystal quality, and this is corroborated by the PL spectra seen

in Fig. 4.11. After RTA treatment, the NBE emission dominates the spectra indicating a low concentration of non-radiative carrier recombination pathways and a high crystallinity. A broad deep level peak centered at 1.5 eV is apparent in the samples annealed at 600°C, 700°C, and 800°C, while it is not present in the sample annealed at 900°C. The annealing behavior of this peak appears to be correlated with the sample mobilities. In the RTA treated samples where the deep level peak is prevalent (600°C, 700°C, and 800°C), the mobility is around 20-30 cm²/Vs, but in the 900°C sample, the deep level peak vanishes and the mobility increases to 54 cm²/Vs.

The identity of the deep level PL peak is not ascertained in the paper, but its annealing behavior can offer some clues. The disappearance of the peak at 900°C is unexpected for an intrinsic defect under equilibrium conditions, since higher annealing temperatures promotes higher intrinsic defect concentrations (not lower as observed in the 900°C) pointing to an extrinsic origin. It is, however, not possible to exclude an intrinsic origin, since clustering of intrinsic defects, leading to electrical deactivation, could occur at elevated temperatures. Further, the disappearance of a donor-like defect should lead to a hole concentration increase, but between 800°C and 900°C, the hole concentration remains constant. Hence, it is probable that the deep level PL peak centered around 1.5 eV is related to an extrinsic, acceptor-like defect.

Finally, following the temperature evolution of the main peak in the NBE emission (the peak originates from emission of the orthoexciton coupled with a Γ_{12}^- -phonon) for the sample annealed at 800°C, the temperature dependency of the E_g was extracted. A Varshni fit to the experimental points yielded the following temperature dependence for E_g :

$$E_g(T) = 2.172[\text{eV}] - \frac{4.7 \times 10^{-4}[\text{eV/K}] \times T^2}{T + 161[\text{K}]} \quad (4.1)$$

The first term in the equation is E_g at 0 K and is in excellent agreement with previous reports [173, 174]. Indeed, the Varshni parameter values of Eq. 4.1 are similar to the ones reported by Snoke et al. [173] for Cu₂O.

In conclusion, the enhancement of structural, optical and electrical properties of sputter deposited Cu₂O thin films by RTA treatment is described in Paper VII. An increase in the grain size and XRD (111) intensity of the films after RTA is accompanied by a significant increase in the NBE emission evidenced by PL spectroscopy, pointing to an improved crystallinity. The deep level PL emission of the RTA treated films seems to be related to the hole mobility, since

Figure 4.12: Temperature dependency of the carrier concentration of Cu_2O samples annealed at 600°C at different p_{O_2} . The inset shows the variation in ionization energy for the two band gap states as a function of strain in the sample.

the disappearance of the deep level emission coincides with a doubling of the mobility. The deep level PL peak is suggested to be related to an extrinsic, acceptor-like defect. Finally, the temperature dependency of E_g is extracted and found to be in excellent agreement with previous reports.

The major acceptor responsible for hole conduction in Cu_2O is predicted by first-principles studies to be v_{Cu} with an ionization energy between 0.18-0.28 eV relative to the E_v [97–100]. Experimentally the defect has been reported with an ionization energy between 0.22 eV and 0.55 eV [88–90, 92, 101]. This spread suggests a ionization energy dependency on preparation conditions, and in Paper VIII, this topic is explored.

Sputter deposited thin films of Cu_2O were RTA treated at 600°C , 700°C , 800°C and 900°C (same preparation procedure as in Paper VII). These thin films were subsequently characterized by TDH between 120 K and 550 K at 10

kG. Two separate defect levels are found to contribute to the conduction of the samples. In the following and for simplicity, the two defect levels are assumed to be acceptor-like, although no unambiguous evidence exists for this assumption. A shallow acceptor, with ionization energies of 0.26-0.37 eV, dominates at low temperatures, and a deep acceptor, with ionization energies of 0.47-0.52 eV, dominates at elevated temperatures. Note that these values are not directly comparable to literature values since they are extracted assuming an uncompensated material. The ionization energies vary between samples, conforming to the large spread found in literature. Previously, the ionization energy of the major acceptor in N-doped Cu_2O thin films was seen to decrease with increasing N-concentration [85], and the dependency was explained by a reduction in the potential energy of holes residing on acceptors at increasing acceptor concentrations [107, 108]. The ionization energy variation observed in Paper VIII, however, does not follow this trend. In fact, the ionization energy of the deep defect increases when the acceptor concentration increases (the acceptor concentration is extracted from TDH), opposite to the behavior reported in Refs. 85, 107, 108.

The RTA treated samples were processed at different temperatures for only 3 min, and they may not have reached steady-state conditions during the heat treatment. In order to study the ionization energy variation under stable conditions, 4 samples RTA treated at 900°C for 3 min were annealed at 600°C in varying O_2 pressures for 1 h promoting steady-state conditions. One shallow acceptor with ionization energy 0.37-0.41 eV and one deep acceptor with ionization energy 0.61-0.69 eV are extracted from TDH measurements (cf. Fig. 4.12). Like the RTA only samples, the ionization energies increase with higher acceptor concentration, but as seen in the inset of Fig. 4.12, the ionization energy of both the deep and the shallow defect has a dependency on sample strain (extracted from XRD diffractograms). A defect ionization energy dependency on strain is well-established for several semiconductors both experimentally and theoretically [175–182]. It is discussed in Paper VIII whether this effect also may explain the results of Benz et al. [85], since an increasing N concentration affects the sample strain.

Paper VIII hence offers a potential explanation for the large spread in ionization energy values quoted for the main acceptor in Cu_2O . Eight Cu_2O samples with different preparation conditions were characterized by TDH, and in all the samples, two acceptors were found to contribute to the hole conduction. The ionization energies of these acceptors change with preparation conditions,

and by comparing XRD and TDH measurements of four samples in steady-state conditions, a correlation between sample strain and ionization energy is demonstrated.

Chapter 5

Conclusions and Future Work

This thesis explores different processing and materials challenges for realizing a tandem oxide PV cell. The bottom cell of this tandem structure is proposed to be a modified, standard Si cell (cf. Fig. 2.1), and Paper I presents a novel way of preparing a shallow p-type emitter by FLA. A good Ohmic contact between the bottom Si cell and the top oxide cell is important for an efficient tandem cell, and a process for obtaining the n-side of this junction is developed (Sec. 4.2). In Papers II and III, two different heterojunctions relevant for the oxide top cell is explored. Although Cu_2O grows epitaxially on ZnO , the $\text{Cu}_2\text{O}/\text{ZnO}$ heterojunction interface contains a nm-thick layer of CuO , detrimental to the rectifying performance of such a junction (Paper II). Further, seven orders of rectification is achieved for a $\text{Cu}_2\text{O}/\text{Si}$ heterojunction, proving its relevance for an oxide-Si solar cell (Paper III). The homoepitaxy of ZnO , a simplified process appropriate for gaining a deeper understanding of the sputtering process and growth mechanisms of oxides, is found to depend on power density (Paper IV), substrate polarity (Paper V), and processing atmosphere (Sec. 4.4). The Cu_2O absorber layer of the top cell in the proposed tandem structure (Fig. 2.1), requires good crystallinity, high transmittance below E_g and high mobility. Paper VI and Paper VII detail the enhancement of these properties through optimization of the sputter process (Paper VI) and through RTA treatment (Paper VII). Finally, Paper VIII looks at the variation in ionization energy of the major acceptor in Cu_2O as a function of strain.

Although a great variety of aspects of the tandem cell has been covered in the thesis, there are certain additional elements which need to be addressed. For instance, thin film Cu_2O solar cells are consistently outperformed by solar cells based on oxidized Cu sheets, possibly because of lower carrier densities

and higher mobilities in the oxidized sheet cells. Improving thin film Cu_2O through prolonged high-temperature treatments or by selective doping schemes could be a viable path towards closing the efficiency gap between thin film and oxidized sheet solar cells.

Paper VIII provides evidence that the ionization energy of the major acceptor level in Cu_2O is dependent on strain, but the surmise is based on only four different samples. A more well-designed study including a larger number of samples with a wider range of sample strains would be useful for confirming the conclusions of Paper VIII.

The homoepitaxial sputter deposition of ZnO was proved to be dependent on the presence of N_2 in the chamber during processing (Sec. 4.4), yielding atomically flat thin films with N-doping. The deposition rate, however, was significantly reduced, and developing a process with an acceptable deposition rate which also produces atomically flat thin films would be a worthwhile effort. Specifically, this study should investigate the effect of other elements which could modify the growth of ZnO , such as Li, Al, Ga, and F.

Finally, the studies of this thesis centers around the realization of an oxide-Si tandem solar cell, and the obvious way forward is to produce a functioning PV cell founded on the insights of this thesis. Perhaps most importantly, the CuO interfacial layer between ZnO and Cu_2O is detrimental to the conversion efficiency of the cell, and a modified cell structure where ZnO is replaced with an electron selective contact with better interfacial properties towards Cu_2O could significantly improve the performance of the top cell. For instance, different alloys of ZnO combined with Cu_2O has been predicted and demonstrated to give better band alignment and rectification than ZnO [18, 183].

It is the sincere hope of the author that the findings and suggestions of this thesis will bring about the realization of an environmentally friendly, affordable, stable, and efficient tandem solar cell based on oxide semiconductors.

References

- [1] World Energy Council. World Energy Resources 2013. Online, 2013.
- [2] Fraunhofer ISE. Photovoltaic Report. Online, 2017.
- [3] M. H. Futscher and B. Ehrler. *ACS Energy Lett.*, 1:863, 2016.
- [4] S. R. Taylor. *Geochim. Cosmochim. Acta*, 28:1273, 1964.
- [5] S. Rühle, A. Y. Anderson, H.-N. Barad, B. Kupfer, Y. Bouhadana, E. Rosh-Hodesh, and A. Zaban. *J. Phys. Chem. Lett.*, 3:3755, 2012.
- [6] M. Grätzel. *J. Photochem. Photobiol., C*, 4:145, 2003.
- [7] W. S. Yang, B.-W. Park, E. H. Jung, N. J. Jeon, Y. C. Kim, D. U. Lee, S. S. Shin, J. Seo, E. K. Kim, J. H. Noh, and S. I. Seok. *Science*, 356:1376, 2017.
- [8] National Renewable Energy Laboratory. Best Research-Cell Efficiencies. Online, 2017.
- [9] B. Li, L. Wang, B. Kang, P. Wang, and Y. Qiu. *Sol. Energy Mater. Sol. Cells*, 90:549, 2006.
- [10] M. I. Asghar, J. Zhang, H. Wang, and P. D. Lund. *Renewable Sustainable Energy Rev.*, 77:131, 2017.
- [11] First Solar. First Solar Press Release. Online, 2016.
- [12] P. Jackson, R. Wuertz, D. Hariskos, E. Lotter, W. Witte, and M. Powalla. *Phys. Status Solidi RRL*, 10:583, 2016.
- [13] Fraunhofer ISE. Fraunhofer ISE Press Release. Online, 2014.

- [14] J. Godt, F. Scheidig, C. Grosse-Siestrup, V. Esche, P. Brandenburg, A. Reich, and D. A. Groneberg. *J. Occup. Med. Toxicol.*, 1:22, 2006.
- [15] M. Woodhouse and A. Goodrich. A Manufacturing Cost Analysis Relevant to Single- and Dual-Junction Photovoltaic Cells Fabricated with III-Vs and III-Vs Grown on Czochralski Silicon. Online, 2013.
- [16] G. J. Fosmire. *Am. J. Clin. Nutr.*, 51:225, 1990.
- [17] L. M. Gaetke and C. K. Chow. *Toxicology*, 189, 2003.
- [18] T. Minami, Y. Nishi, and T. Miyata. *Appl. Phys. Express*, 9:052301, 2016.
- [19] L. C. Olsen, F. W. Addis, and W. Miller. *Solar Cells*, 7:247, 1982.
- [20] A. De Vos. *J. Phys. D: Appl. Phys.*, 13:839, 1980.
- [21] C. Kittel. *Introduction to Solid State Physics*. John Wiley & Sons, 8th edition edition, 2005.
- [22] M. S. Tyagi and R. van Overstraeten. *Solid-State Electron.*, 26:577, 1983.
- [23] A. G. Aberle. *Prog. Photovoltaics Res. Appl.*, 8:473, 2000.
- [24] P. Norton, T. Braggins, and H. Levinstein. *Phys. Rev. B*, 8:5632, 1973.
- [25] G. Ottaviani, L. Reggiani, C. Canali, F. Nava, and A. Alberigi-Quaranta. *Phys. Rev. B*, 12:3318, 1975.
- [26] J. Lindroos and H. Savin. *Sol. Energy Mater. Sol. Cells*, 147:115, 2016.
- [27] A. Goodrich, P. Hacke, Q. Wang, B. Sopori, R. Margolis, T. L. James, and M. Woodhouse. *Sol. Energy Mater. Sol. Cells*, 114:110, 2013.
- [28] H. B. Normann, L. Vines, V. Privitera, W. Skorupa, T. Schumann, B. G. Svensson, and E. V. Monakhov. *Appl. Phys. Lett.*, 102:132108, 2013.
- [29] H. B. Normann, B. G. Svensson, and E. Monakhov. *phys. stat. sol. (b)*, 9:2138, 2012.
- [30] Silvaco, Inc. *Athena User's Manual*, 2014.
- [31] Y. Komatsu, V. D. Mihailetschi, L. J. Geerligs, B. van Dijk, J. B. Rem, and M. Harris. *Sol. Energ. Mat. Sol. C.*, 93:750–752, 2009.

- [32] M. A. Kessler, T. Ohrdes, B. Wolpensinger, and N. P. Harder. *Semicond. Sci. Technol.*, 25:055001, 2010.
- [33] S. Peters, C. Ballif, D. Borchert, R. Schindler, W. Warta, and G. Willeke. *Semicond. Sci. Technol.*, 17:677, 2002.
- [34] B. Hartiti, R. Schindler, A. Slaoui, B. Wagner, J. C. Muller, I. Reis, A. Eyer, and P. Siffert. *Prog. Photovoltaics*, 2:129, 1994.
- [35] E. V. Monakhov, B. G. Svensson, M. K. Linnarsson, A. La Magna, C. Spinella, C. Bongiorno, V. Privitera, G. Fortunato, and L. Mariucci. *Appl. Phys. Lett.*, 86:151902, 2005.
- [36] P. Baeri, S. U. Campisano, G. Foti, and E. Rimini. *J. Appl. Phys.*, 50:788–797, 1979.
- [37] T. Gebel, M. Voelskow, W. Skorupa, G. Mannino, V. Privitera, F. Priolo, E. Napolitani, and A. Carnera. *Nucl. Instr. Meth. Phys. Res. B*, 186:287, 2002.
- [38] E. Monakhov, B. G. Svensson, M. K. Linnarsson, A. La Magna, V. Privitera, G. Fortunato, and L. Mariucci. *Mater. Sci. Eng., B*, 114-115:114, 2004.
- [39] B. G. Streetman and S. J. Banerjee. *Solid State Electronic Devices*. Pearson Prentice Hall, 6th edition edition, 2006.
- [40] W. Wang, J. Huang, W. Xu, J. Huang, Y. Zeng, and W. Song. *J. Mater. Sci.: Mater. Electron.*, 24:2122, 2013.
- [41] F. Fenske and B. Gorka. *J. Appl. Phys.*, 105:074506, 2009.
- [42] I.-W. Wu, A. Chiang, M. Fuse, L. Öveçoglu, and T. Y. Huang. *J. Appl. Phys.*, 65:4036, 1989.
- [43] S.-I. Jun, P. D. Rack, T. E. McKnight, A. V. Melechko, and M. L. Simpson. *Appl. Phys. Lett.*, 89:022104, 2006.
- [44] E. H. Poindexter, G. J. Gerardi, M.-E. Rueckel, and P. J. Caplan. *J. Appl. Phys.*, 56:2844, 1984.
- [45] P. Broqvist, A. Alkauskas, and A. Pasquarello. *Phys. Rev. B*, 78:075203, 2008.

- [46] D. Macdonald and A. Cuevas. *Appl. Phys. Lett.*, 74:1710, 1999.
- [47] J. S. Speck and S. J. Rosner. *Physica B*, 273-274:24, 1999.
- [48] R. K. Gupta, K. Ghosh, and P. K. Kahol. *Physica E*, 41:876, 2009.
- [49] T. Serin, S. Gürakar, N. Serin, N. Yildirim, and F. Özyurt Kus. *J. Phys. D: Appl. Phys.*, 42:225108, 2009.
- [50] R. A. Ismail. *J. Semicond. Tech. Sci.*, 1:51, 2009.
- [51] J. A. Switzer, R. Liu, E. W. Bohannon, and F. Ernst. *J. Phys. Chem. B*, 106:12369, 2002.
- [52] B. M. Fariza, J. Sasano, T. Shinagawa, H. Nakano, S. Watase, and M. Izaki. *J. Electrochem. Soc.*, 158:D621, 2011.
- [53] S. S. Wilson, J. P. Bosco, Y. Tolstova, D. O. Scanlon, G. W. Watson, and H. A. Atwater. *Energy Environ. Sci.*, 7:3606, 2014.
- [54] S. Ishizuka, K. Suzuki, Y. Okamoto, M. Yanagita, T. Sakurai, K. Akimoto, N. Fujiwara, H. Kobayashi, K. Matsubara, and S. Niki. *phys. stat. sol. (c)*, 1:1067, 2004.
- [55] S. S. Jeong, A. Mittiga, A. Masci, and S. Passerini. *Electrochim. Acta*, 53:2226, 2008.
- [56] D. K. Zhang, Y. C. Liu, Y. L. Liu, and H. Yang. *Physica B*, 351:178, 2004.
- [57] S.-M. Chou, M.-H. Hon, I.-C. Leu, and Y.-H. Lee. *J. Electrochem. Soc.*, 155:H923, 2008.
- [58] J. Katayama, K. Ito, M. Matsuoka, and J. Tamaki. *J. Appl. Electrochem.*, 34:687, 2004.
- [59] T. Minami, Y. Nishi, T. Miyata, and J. i. Nomoto. *Appl. Phys. Express*, 4:062301, 2011.
- [60] C. G. van de Walle. *Phys. Rev. Lett.*, 85:1012, 2000.
- [61] Ü. Özgür, Y. I. Alivov, C. Liu, A. Teke, M. A. Reshchikov, S. Dogan, V. Avrutin, S. J. Cho, and H. Morkoç. *J. Appl. Phys.*, 98:041301, 2005.

- [62] K.-K. Kim, J.-H. Song, H.-J. Jung, and W.-K. Choi. *J. Appl. Phys.*, 87:3573, 2000.
- [63] H. Xu, K. Ohtani, M. Yamao, and H. Ohno. *Appl. Phys. Lett.*, 89:071918, 2006.
- [64] Y. Igasaki and H. Saito. *J. Appl. Phys.*, 69:2190, 1991.
- [65] I.-S. Kim, S.-H. Jeong, and B.-T. Lee. *Semicond. Sci. Technol.*, 22:683, 2007.
- [66] K. Ellmer and G. Vollweiler. *Thin Solid Films*, 496:104, 2006.
- [67] J. Narayan and B. C. Larson. *J. Appl. Phys.*, 93:278, 2003.
- [68] C.-Y. J. Lu, K. H. Ploog, and M. M. C. Chou. *J. Cryst. Growth*, 378:172, 2013.
- [69] N. Itagaki, K. Kuwahara, K. Matsushima, D. Yamashita, H. Seo, K. Koga, and M. Shiratani. *Opt. Eng.*, 53:087109, 2014.
- [70] K. Kuwahara, N. Itagaki, K. Nakahara, D. Yamashita, G. Uchida, K. Kamataki, K. Koga, and M. Shiratani. *Thin Solid Films*, 520:4674, 2012.
- [71] D. C. Look, D. C. Reynolds, C. W. Litton, R. L. Jones, D. B. Eason, and G. Cantwell. *Appl. Phys. Lett.*, 81:1830, 2002.
- [72] A. Bikowski and K. Ellmer. *J. Appl. Phys.*, 114:063709, 2013.
- [73] H. Kato, M. Sano, K. Miyamoto, and T. Yao. *Jpn. J. Appl. Phys., Part 2*, 42:L1002, 2003.
- [74] K. Furusawa, H. Nakasawa, Y. Ishikawa, and S. F. Chichibu. *Jpn. J. Appl. Phys., Part 2*, 53:100301, 2014.
- [75] F. Biccari. *Defects and Doping in Cu₂O*. PhD thesis, Universita di Roma, 2009.
- [76] B. S. Li, K. Akimoto, and A. Shen. *J. Cryst. Growth*, 311:1102, 2009.
- [77] K. Lim, J. Park, D.-G. Kim, J.-K. Kim, J.-W. Kang, and Y.-C. Kang. *Appl. Surf. Sci.*, 258:9054, 2012.
- [78] J. Deuermeier, J. Gassmann, J. Brötz, and A. Klein. *J. Appl. Phys.*, 109:113704, 2011.

- [79] J. Gan, V. Venkatachalapathy, B. G. Svensson, and E. Monakhov. *Thin Solid Films*, 594:250, 2015.
- [80] V. Figueiredo, E. Elangovan, R. Barros, J. V. Pinto, T. Busani, R. Martins, and E. Fortunato. *J. Disp. Technol.*, 8:41, 2012.
- [81] S. Noda, H. Shima, and H. Akinaga. *J. Phys. Conf. Ser.*, 433:012027, 2013.
- [82] J. H. Hsieh, P. W. Kuo, K. C. Peng, S. J. Liu, J. D. Hsueh, and S. C. Chang. *Thin Solid Films*, 516:5449, 2008.
- [83] F. M. Li, R. Waddingham, W. I. Milne, A. J. Flewitt, S. Speakman, J. Dutton, S. Wakeham, and M. Thwaites. *Thin Solid Films*, 520:1278, 2011.
- [84] E. M. Alkoy and P. J. Kelly. *Vacuum*, 79:221, 2005.
- [85] J. Benz, K. P. Hering, B. Kramm, A. Polity, P. J. Klar, S. C. Siah, and T. Buonassisi. *phys. stat. sol. (b)*, 254:1600421, 2017.
- [86] A. E. Rakshani, Y. Makdisi, and X. Mathew. *Thin Solid Films*, 288:69, 1996.
- [87] A. E. Rakshani. *J. Appl. Phys.*, 69:2365, 1991.
- [88] G. P. Pollack and Dan Trivich. *J. Appl. Phys.*, 46:163, 1975.
- [89] G. K. Paul, Y. Nawa, H. Sato, T. Sakurai, and K. Akimoto. *Appl. Phys. Lett.*, 88:141901, 2006.
- [90] N. Kikuchi, K. Tonooka, and E. Kusano. *Vacuum*, 80:756, 2006.
- [91] R. Garuthara and W. Siripala. *J. Lumin.*, 121:173, 2006.
- [92] M. Zouaghi. *phys. stat. sol. (a)*, 11:219, 1972.
- [93] L. Papadimitriou, C. A. Dimitriadis, and L. Dozsa. *Solid-State Electron.*, 31:1477, 1988.
- [94] L. Papadimitriou. *Solid State Commun.*, 71:181, 1989.
- [95] Y. S. Lee, M. T. Winkler, S. C. Siah, R. Brandt, and T. Buonassisi. *Appl. Phys. Lett.*, 98:192115, 2011.

- [96] Y. S. Lee, J. Heo, M. T. Winkler, S. C. Siah, S. B. Kim, R. G. Gordon, and T. Buonassisi. *J. Mater. Chem. A*, 1:15416, 2013.
- [97] A. Soon, X.-Y. Cui, B. Delley, S.-H. Wei, and C. Stampfl. *Phys. Rev. B*, 79:035205, 2009.
- [98] M. Nolan and S. D. Elliott. *Phys. Chem. Chem. Phys.*, 8:5350, 2006.
- [99] D. O. Scanlon, B. J. Morgan, and G. W. Watson. *Phys. Rev. Lett.*, 103:096405, 2009.
- [100] H. Raebiger, S. Lany, and A. Zunger. *Phys. Rev. B*, 76:045209, 2007.
- [101] S. Ishizuka, S. Kato, T. Maruyama, and K. Akimoto. *Jpn. J. Appl. Phys., Part 1*, 40:2765, 2001.
- [102] A. F. Wright and J. S. Nelson. *J. Appl. Phys.*, 92:5849, 2002.
- [103] L. Y. Isseroff and E. A. Carter. *Chem. Mater.*, 25:253, 2013.
- [104] S. Ishizuka, S. Kato, Y. Okamoto, and K. Akimoto. *Appl. Phys. Lett.*, 80:950, 2002.
- [105] K. P. Hering, C. Kandzia, J. Benz, B. G. Kramm, M. Eickhoff, and P. J. Klar. *J. Appl. Phys.*, 120:185705, 2016.
- [106] S. Ishizuka, S. Kato, Y. Okamoto, T. Sakurai, K. Akimoto, N. Fujiwara, and H. Kobayashi. *Appl. Surf. Sci.*, 216:94, 2003.
- [107] P. J. Price. *Phys. Rev.*, 124:713, 1961.
- [108] J. J. Hall. *Phys. Rev.*, 128:68, 1962.
- [109] K. Ellmer. *J. Phys. D: Appl. Phys.*, 33:R17, 2000.
- [110] J. L. Andújar, F. J. Pino, M. C. Polo, A. Pinyol, C. Corbella, and E. Bertran. *Diamond Relat. Mater.*, 11:1005, 2002.
- [111] M. A. Arranz, J. P. Andrés, J. A. De Toro, S. E. Paje, M. A. López de la Torre, and J. M. Riveiro. *J. Magn. Magn. Mater.*, 242:952, 2002.
- [112] K.-Y. Chan and B.-S. Teo. *Microelectron. J.*, 37:1064, 2006.
- [113] K.-Y. Chan and B.-S. Teo. *Microelectron. J.*, 38:60, 2007.

- [114] D.-K. Hwang, K.-H. Bang, M.-C. Jeong, and J.-M. Myoung. *J. Cryst. Growth*, 254:449, 2003.
- [115] S. A. Campbell. *Fabrication Engineering at the Micro- and Nanoscale*. Oxford University Press, 4th edition, 2013.
- [116] J. A. Thornton. *J. Vac. Sci. and Technol.*, 11:666, 1974.
- [117] H. Lüth. *Solid Surfaces, Interfaces and Thin Films*, chapter Adsorption on Solid Surfaces. Springer, 5th edition edition, 2010.
- [118] M. Ohring. *Materials Science of Thin Films*, chapter Substrate Surfaces and Thin-Film Nucleation. Academic Press, 2002.
- [119] B. A. Movchan and A. V. Demchishin. *Phys. Met. Metall.*, 28:83, 1969.
- [120] R. Messier, A. P. Giri, and R. A. Roy. *J. Vac. Sci. Technol. A*, 2:500, 1984.
- [121] H. T. G. Hentzell, C. R. M. Grovenor, and D. A. Smith. *J. Vac. Sci. Technol. A*, 2:218, 1984.
- [122] K.-K. Kim, H.-S. Kim, D.-K. Hwang, J.-H. Lim, and S.-J. Park. *Appl. Phys. Lett.*, 83:63, 2003.
- [123] M. Joseph, H. Tabata, and T. Kawai. *Jpn. J. Appl. Phys.*, 38:L1205, 1999.
- [124] T. Li-dan, W. Bing, and Z. Yue. *J. Alloys Compd.*, 509:384, 2011.
- [125] L. Balakrishnan, S. Gowrishankar, P. Premchander, and N. Gopalakrishnan. *J. Alloys Compd.*, 512:235, 2012.
- [126] R. Schifano, E. V. Monakhov, L. Vines, B. G. Svensson, W. Mtangi, and F. D. Auret. *J. Appl. Phys.*, 106:043706, 2009.
- [127] P. Blood and J. W. Orton. *The Electrical Characterization of Semiconductors: Majority Carriers and Electron States*. Academic Press, 1992.
- [128] J. G. Simmons and G. W. Taylor. *Phys. Rev. B*, 4:502, 1971.
- [129] G. Capellini, L. Di Gaspare, F. Evangelisti, and E. Palange. *Appl. Phys. Lett.*, 70, 1997.
- [130] M. A. Green. *Sol. Energy Mater. Sol. Cells*, 92:1305, 2008.

- [131] M. Smith, R. A. McMahon, M. Voelskow, and W. Skorupa. *J. Appl. Phys.*, 96:4843, 2004.
- [132] H. A. Bomke, H. L. Berkowitz, M. Harmatz, S. Kronenberg, and R. Lux. *Appl. Phys. Lett.*, 33:955, 1978.
- [133] R. L. Cohen, J. S. Williams, L. C. Feldman, and K. W. West. *Appl. Phys. Lett.*, 33:751, 1978.
- [134] W. Skorupa, R. A. Yankov, W. Anwand, M. Voelskow, T. Gebel, D. F. Downey, and E. A. Arevalo. *Mater. Sci. Eng. B*, 114-115:358, 2004.
- [135] W. Skorupa, T. Gebel, R. A. Yankov, S. Paul, W. Lerch, D. F. Downey, and E. A. Arevalo. *J. Electrochem. Soc.*, 152:G436, 2005.
- [136] H. N. Riise, T. Schumann, A. Azarov, R. Hübner, W. Skorupa, B. G. Svensson, and E. Monakhov. *Appl. Phys. Lett.*, 107:022105, 2015.
- [137] T. Ito, T. Iinuma, A. Murakoshi, H. Akutsu, K. Suguro, T. Arikado, K. Okumura, M. Yoshioka, T. Owada, Y. Imaoka, H. Murayama, and T. Kusuda. *Jpn. J. Appl. Phys., Part 1*, 41:2394, 2002.
- [138] J. T. Lue. *Appl. Phys. Lett.*, 36:73, 1980.
- [139] R. Klabes, J. Matthxi, M. Voelskow, G. A. Kachurin, E. V. Nidaev, and H. Bartsch. *phys. stat. sol. (a)*, 66:261, 1981.
- [140] H. M. Ayedh, R. Nipoti, A. Hallén, and B. G. Svensson. *J. Appl. Phys.*, 122:025701, 2017.
- [141] J. Nelson. *The Physics of Solar Cells*. Imperial College Press, 2003.
- [142] P. A. Stolk, H.-J. Gossmann, D. J. Eaglesham, D. C. Jacobson, C. S. Rafferty, G. H. Gilmer, M. Jaraiz, J. M. Poate, H. S. Luftman, and T. E. Haynes. *J. Appl. Phys.*, 81:6031, 1997.
- [143] N. E. B. Covern, M. J. J. Theunissen, F. Roozeboom, and J. G. M. van Berkum. *Appl. Phys. Lett.*, 75:181, 1999.
- [144] S. M. Hu. *J. Appl. Phys.*, 45:1567, 1974.
- [145] T. Minami, T. Miyata, K. Ihara, Y. Minamino, and S. Tsukada. *Thin Solid Films*, 494:47, 2006.

- [146] H. Tanaka, T. Shimakawa, T. Miyata, H. Sato, and T. Minami. *Appl. Surf. Sci.*, 244:568, 2005.
- [147] J. Herion, E. A. Niekisch, and G. Scharl. *Sol. Energy Mater.*, 46:163, 1980.
- [148] A. Mittiga, E. Salza, F. Sarto, M. Tucci, and R. Vasanthi. *Appl. Phys. Lett.*, 88:163502, 2006.
- [149] A. E. Gunnæs, S. Gorantla, O. M. Løvvik, J. Gan, P. A. Carvalho, B. G. Svensson, E. V. Monakhov, K. Bergum, I. T. Jensen, and S. Diplas. *J. Phys. Chem. C*, 120:23552, 2016.
- [150] L. Qiao, H. Y. Xiao, W. J. Weber, and M. D. Biegalski. *Appl. Phys. Lett.*, 104:221602, 2014.
- [151] N. Gupta, R. Singh, F. Wu, J. Narayan, C. McMillen, G. F. Alapatt, K. F. Poole, S.-J. Hwu, D. Sulejmanovic, and M. Young. *J. Mater. Res.*, 28:1740, 2013.
- [152] I. Bisotto, C. Granier, S. Brochen, A. Ribeaud, P. Ferret, G. Chicot, J. Rothman, J. Pernot, and G. Feuillet. *Appl. Phys. Express*, 3:095802, 2010.
- [153] S. Heinze, A. Krtschil, J. Bläsing, T. Hempel, P. Veit, A. Dadgar, J. Christen, and A. Krost. *J. Cryst. Growth*, 308:170, 2007.
- [154] D. J. Rogers, F. Hosseini Teherani, A. Largeau, G. Demazeau, C. Moisson, D. Turover, J. Nause, G. Garry, R. Kling, T. Gruber, A. Waag, F. Jomard, P. Galtier, A. Lusson, T. Monteiro, M. J. Soares, A. Neves, M. C. Carmo, M. Peres, G. Lerondel, and C. Hubert. *Appl. Phys. A*, 88:49, 2007.
- [155] R. Triboulet and J. Perriere. *Prog. Cryst. Growth Charact. Mater.*, 47:65, 2003.
- [156] A. Yu. Azarov, A. Hallen, X. L. Du, P. Rauwel, A. Yu. Kuznetsov, and B. G. Svensson. *J. Appl. Phys.*, 115:073512, 2014.
- [157] E. Rita, E. Alves, U. Wahl, J. G. Correia, T. Monteiro, M. J. Soares, A. Neves, and M. Peres. *Nucl. Instrum. Meth. B*, 242:580, 2006.

- [158] M. W. Cho, C. Harada, H. Suzuki, T. Minegishi, T. Yao, H. Ko, K. Maeda, and I. Nikura. *Superlattices Microstruct.*, 38:349, 2005.
- [159] M. Wei, R. C. Boutwell, G. A. Garrett, K. Goodman, P. Rotella, M. Wraback, and W. V. Schoenfeld. *J. Alloys Compd.*, 552:127, 2013.
- [160] I. Suhariadi, M. Shiratani, and N. Itagaki. *Mater. Res. Express*, 1:036403, 2014.
- [161] I. Suhariadi, K. Oshikawa, K. Kuwahara, K. Matsushima, D. Yamashita, G. Uchida, K. Koga, M. Shiratani, and N. Itagaki. *Jpn. J. Appl. Phys.*, 52:11NB03, 2013.
- [162] I. J. R. Baumvol, T. D. M. Salgado, F. C. Stedile, C. Radtke, and C. Krug. *J. Appl. Phys.*, 83, 1998.
- [163] B. Hahn, H. Preis, M. Schindler, T. Reisinger, and W. Gebhardt. *J. Cryst. Growth*, 179:415, 1997.
- [164] H. Kato, M. Sano, K. Miyamoto, and T. Yao. *J. Cryst. Growth*, 265:375, 2004.
- [165] T. Minami. *J. Semicond.*, 37:014002, 2016.
- [166] K. Akimoto, S. Ishizuka, M. Yanagita, Y. Nawa, G. K. Paul, and T. Sakurai. *Sol. Energy*, 80:715, 2006.
- [167] Y. S. Jung, H. W. Choi, and K. H. Kim. *Jpn. J. Appl. Phys.*, 53:11RA10, 2014.
- [168] W.-C. Chen, P.-C. Hsu, C.-W. Chien, K.-M. Chang, C.-J. Hsu, C.-H. Chang, W.-K. Lee, W.-F. Chou, H.-H. Hsieh, and C.-C. Wu. *J. Phys. D: Appl. Phys.*, 47:365101, 2014.
- [169] H.-C. Lu, C.-L. Chu, C.-Y. Lai, and Y.-H. Wang. *Thin Solid Films*, 517:4408, 2009.
- [170] P. Lv, W. Zheng, L. Lin, F. Peng, Z. Huang, and F. Lai. *Physica B*, 406:1253, 2011.
- [171] A. S. Reddy, P. S. Reddy, S. Uthann, G. V. Rao, and A. Klein. *phys. stat. sol. (a)*, 203:844, 2006.

- [172] W.-Y. Yang, W.-G. Kim, and S.-W. Rhee. *Thin Solid Films*, 517:967, 2008.
- [173] D. W. Snoke, A. J. Shields, and M. Cardona. *Phys. Rev. B*, 45:11693, 1992.
- [174] B. K. Meyer, A. Polity, D. Reppin, M. Becker, P. Hering, P. J. Klar, Th. Sander, C. Reindl, J. Benz, M. Eickhoff, C. Heiliger, M. Heinemann, J. Bläsing, A. Krost, S. Shokovets, C. Muller, and C. Ronning. *phys. stat. sol. (b)*, 249:1487, 2012.
- [175] S. Nicolaysen, M. G. Ganchenkova, and R. M. Nieminen. *Solid State Phenom.*, 108-109:433, 2005.
- [176] K. Sueoka, P. Spiewak, and J. Vanhellemont. *ECS Trans.*, 11:375, 2007.
- [177] A. Rockett, D. D. Johnson, S. V. Khare, and B. R. Tuttle. *Phys. Rev. B*, 68:233208, 2003.
- [178] Y. Fujimoto and S. Saito. *Phys. Rev. B*, 93:045402, 2016.
- [179] A. G. Kazanskii, P. L. Richards, and E. E. Haller. *Solid State Commun*, 24:603, 1977.
- [180] A. V. Germanenko, G. M. Minkov, and O. E. Rut. *phys. stat. sol. (b)*, 171:159, 1992.
- [181] G. A. Samara and C. E. Barnes. *Phys. Rev. B*, 73:155206, 2006.
- [182] M. Mamor, M. Elzain, K. Bouziane, and S. H. Al Harthi. *Phys. Rev. B*, 77:035213, 2008.
- [183] R. E. Brandt, M. Young, H. H. Park, A. Dameron, D. Chua, Y. S. Lee, G. Teeter, R. G. Gordon, and T. Buonassisi. *Appl. Phys. Lett.*, 105:263901, 2014.

PAPER I

Formation of shallow boron emitters in crystalline silicon using flash lamp annealing: Role of excess silicon interstitials

H. N. Riise, T. Schumann, A. Azarov, R. Hübner, W. Skorupa,
B. G. Svensson and E. Monakhov

Appl. Phys Lett. 107 (2015) 022105

Formation of shallow boron emitters in crystalline silicon using flash lamp annealing: Role of excess silicon interstitials

Heine Nygard Riise,^{1,a)} Thomas Schumann,² Alexander Azarov,¹ Renè Hübner,² Wolfgang Skorupa,² Bengt G. Svensson,¹ and Edouard Monakhov¹

¹Department of Physics/Centre for Materials Science and Nanotechnology, University of Oslo, P. O. Box 1048 Blindern, N-0316 Oslo, Norway

²Institute of Ion Beam Physics and Materials Research, Helmholtz-Zentrum Dresden-Rossendorf, P. O. Box 510119, 01314 Dresden, Germany

(Received 8 May 2015; accepted 30 June 2015; published online 13 July 2015)

Shallow, Boron (B)-doped p^+ emitters have been realized using spin-on deposition and Flash Lamp Annealing (FLA) to diffuse B into monocrystalline float zone Silicon (Si). The emitters extend between 50 and 140 nm in depth below the surface, have peak concentrations between $9 \times 10^{19} \text{ cm}^{-3}$ and $3 \times 10^{20} \text{ cm}^{-3}$, and exhibit sheet resistances between 70 and 3000 $\Omega/\square$. An exceptionally large increase in B diffusion occurs for FLA energy densities exceeding $\sim 93 \text{ J/cm}^2$ irrespective of 10 or 20 ms pulse duration. The effect is attributed to enhanced diffusion of B caused by Si interstitial injection following a thermally activated reaction between the spin-on diffusant film and the silicon wafer. © 2015 AIP Publishing LLC.

[<http://dx.doi.org/10.1063/1.4926661>]

Formation of p-type emitters in n-type crystalline Silicon (c-Si) solar cells is possible by several different schemes, e.g., implantation,^{1,2} diffusion from a gas source,^{3,4} and diffusion from a surface source.^{5,6} All these schemes require high temperature treatments to drive in and electrically activate the dopants^{1,3,5} to reduce the series resistance of the cell. However, if the duration of the treatments is long, the diffusion length will be significant, and a highly doped emitter may extend several μm into the c-Si. This reduces the blue response of the cell since high energy photons are absorbed close to the surface followed by a fast recombination of the generated electron-hole pairs.

Flash Lamp Annealing (FLA) is a technique in which Si can be heated to temperatures above its melting point within a few milliseconds.⁷⁻⁹ Thus, FLA enables both a reduction in the thermal budget of solar cell processing and improvement of the blue response. FLA has already been shown to be suitable for annealing of implantation-induced damage^{9,10} and for activation of implanted dopants.¹¹ Recently, FLA was also proved to be effective in forming shallow Phosphorous (P) emitters in Si by diffusion from a spin-coated P surface source.¹² In the case of solar cells, this also requires the implementation of alternative schemes of contacting, e.g., electroplating and use of advanced silver pastes,^{13,14} since the ordinary screen printing technique can provoke shunting of shallow emitters.

In this study, it is demonstrated that shallow Boron (B) emitters can be formed in c-Si by spin coating and subsequent in-diffusion using FLA.

A 300 μm Float Zone (FZ) c-Si wafer (n-type with resistivity of $\rho \approx 2000 \Omega \text{ cm}$) was rinsed using a standard RCA clean leaving the wafer surface hydrophilic and ensuring good adhesion of the spin-on diffusant (SOD). 2 ml of a polyboron SOD (Filmtronics B155 SOD) was then applied to the substrate and spun at 6000 rpm for 30 s yielding a $\sim 190 \text{ nm}$

thick film with a B concentration of $\sim 9 \times 10^{21} \text{ cm}^{-3}$, as determined by Rutherford Backscattering Spectrometry (RBS). The deposited film was then baked at 200 °C for 20 min and subsequently laser cut into samples of $2 \times 2 \text{ cm}^2$ in size before FLA processing.

Four capacitors with capability to be charged up to a voltage of 4.4 kV were discharged within 10 or 20 ms into a bank of Xenon lamps positioned above the sample.¹⁵ This produces a short light flash which emits in a wavelength range where Si absorbs strongly, and the Si sample can be heated to temperatures well above its melting temperature within a few milliseconds. The annealing was undertaken in N_2 -atmosphere and the relevant FLA processing parameters for the different samples are summarized in Table I. An energy density above $\sim 120 \text{ J/cm}^2$ leads to sample melting, signifying that $\sim 120 \text{ J/cm}^2$ corresponds to approximately 1414 °C.

After FLA, and prior to characterization, the SOD film was removed by chemical etching. The SOD film was very stable after FLA and could not be etched by HF alone.

TABLE I. FLA parameters and characteristics of the processed samples. The emitter depth is defined as where the B concentration drops below $1 \times 10^{17} \text{ cm}^{-3}$.

Sample #	Pulse duration (ms)	Capacitor voltage (kV)	Energy density (J/cm^2)	Boron peak concentration (cm^{-3})	Emitter depth (nm)
1	10	3.3	83	9×10^{19}	50
2	10	3.4	88	2×10^{20}	70
3	10	3.5	93	2×10^{20}	80
4	10	3.6	100	3×10^{20}	140
5	10	3.7	105	2×10^{20}	120
6	20	3.3	83	2×10^{20}	60
7	20	3.4	88	2×10^{20}	65
8	20	3.5	93	3×10^{20}	130
9	20	3.6	100	2×10^{20}	140
10	20	3.7	105	2×10^{20}	125
11	20	4.4	147	1×10^{20}	>30000

^{a)}Electronic mail: h.n.riise@fys.uio.no

Hence, the film was oxidized in $\text{HNO}_3\text{:H}_2\text{SO}_4$ (1:1) before the HF treatment. The procedure was repeated several times (10–20) before the sample surface became hydrophobic after the final HF treatment indicating complete removal of the SOD film.

Secondary Ion Mass Spectrometry (SIMS) measurements to detect ^{11}B -ions were performed using a Cameca IMS 7f microanalyzer with 10 keV O_2^+ -ions as the primary beam. The depth of the sputtered crater was measured by a Dektak 8 stylus profilometer and used to convert sputtering time to depth (assuming a uniform and time-independent erosion rate). A B-implanted reference sample was used to translate the measured ^{11}B signal to B concentration. The sheet resistance of the samples was measured at room temperature by a four point probe Jandel KM3-AR setup. Transmission Electron Microscopy (TEM) analysis was performed on sample # 8 using an image-corrected FEI Titan 80–300 microscope.

Fig. 1 presents B profiles of all samples in a logarithmic depth scale with the melting of sample # 11 giving rise to an extension of the B profile to more than 30 μm . The inset displays B profiles from samples produced by spin-on deposition and Rapid Thermal Annealing (RTA) for 40 s. In the samples subjected to high FLA densities, a B concentration above the solubility limit appears in the vicinity of the surface. However, the SIMS data from the first 10 nm have limited validity since steady-state conditions for the measurements are not fully established and no definite conclusion on the possible existence of Si-B precipitates can be made. For the samples flashed for 10 ms (# 1–5, filled symbols), sample # 1 has a low integrated B concentration in terms of emitter requirements, whilst samples # 2–5 show more suitable profiles with emitter depths between 70 and 140 nm (cf. Table I). For these depths, the photon wavelength penetrating the emitter is above 420 nm, and most of the available sunlight will be absorbed in the base; this estimate is based on the absorption coefficient values given by Green.¹⁶ The peak concentrations are between $9 \times 10^{19} \text{ cm}^{-3}$ and $3 \times 10^{20} \text{ cm}^{-3}$ which exceeds the solid solubility limit of B in Si ($2 \times 10^{20} \text{ cm}^{-3}$ at 1100 °C (Ref. 17)).

FIG. 1. Concentration of B as a function of depth for all samples. The inset displays data of samples treated by RTA for 40 s.

A similar conclusion can also be made from the data of the samples exposed to 20 ms FLA pulses (# 6–10, open symbols). The 20 ms profiles in Fig. 1 have an emitter depth between 60 and 140 nm with a peak concentration ranging from $2 \times 10^{20} \text{ cm}^{-3}$ to $3 \times 10^{20} \text{ cm}^{-3}$, values similar to those of samples # 2–5.

Fig. 1 reveals two distinct sets of profiles; at energy densities below 93 J/cm^2 (10 ms duration) and 88 J/cm^2 (20 ms), a gradual increase in the peak concentration and emitter depth occurs (see, e.g., Table I). However, a further modest increase in the energy density leads to a considerable increase in both extension and peak concentration of the profiles with the emergence of a relatively flat, high B concentration plateau region. An increase above 93 J/cm^2 (20 ms) and 100 J/cm^2 (10 ms) does not significantly increase neither the emitter depth nor the peak concentration even though the resulting temperature increases by approximately 150 °C, in accordance with previous calibration.^{15,18} In fact, the profile extension decreases (~ 20 nm) at 105 J/cm^2 relative to 100 J/cm^2 , Fig. 1. Examining Fig. 1, it is also evident that the extension, peak concentration, and integrated B concentration of the deep profiles (# 4–5 and # 8–10) are almost independent of the pulse duration.

The corresponding sheet resistance values reveal high electrical activation of the incorporated B atoms as shown in Fig. 2. The filled, black squares and the filled, red circles represent the experimental sheet resistance values for samples # 1–5 and samples # 6–10, respectively. The calculated values (open symbols) were obtained by using the experimental SIMS-profiles (accounting for the isotopic abundance of ^{11}B) and Klaassen's mobility model¹⁹ assuming full activation of all the incorporated B dopants. The samples # 2–5 and # 8–10 display values in the range of 70–260 $\Omega/\square$, which is appropriate for high efficiency solar cells. The calculated data follow the experimental values and point to a high activation ratio of B, although with some deviations presumably caused by inaccuracy of the mobility model.

The shape of the profiles of samples # 4–5 and # 8–10 in Fig. 1 resembles that in low energy B-implanted Si wafers subjected to Excimer Laser Annealing (ELA) and melting of the surface region.^{20,21} The peak temperatures employed in our work are, however, well below that required for melting of Si (except for sample # 11, cf. Fig. 1). In fact, spin-on deposition and RTA for 40 s at 1050 °C and 1100 °C give rise to a similar abrupt increase in the profile extension as FLA at 93 J/cm^2 (20 ms) and 100 J/cm^2 (10 ms) (cf. the inset of Fig. 1), which indicates a threshold temperature between 1050 °C and 1100 °C for this abrupt increase. Partial melting of the samples as a cause of the increase in profile extension is hence ruled out. Further, it can be noted that RTA produces deeper profiles than FLA since the duration is much longer, and ordinary diffusion plays a larger role.

At the annealing temperatures and pulse durations used in this work, the equilibrium diffusion length of B in c-Si is only between 10 and 14 Å,²² i.e., one to two orders of magnitude smaller than those in Fig. 1, clearly indicating nonequilibrium diffusion conditions reminiscent of so-called Transient Enhanced Diffusion (TED).²³ This is in direct contrast to that found in Ref. 12 for diffusion of P during FLA where no TED was observed nor any shrinkage of the profile

FIG. 2. Sheet resistance of all samples with calculated data deduced from the SIMS profiles using Klaassen's mobility model.¹⁹ The calculations account for the natural abundance of ^{10}B and ^{11}B .

depth after high density FLA. Further, the temperatures used in Ref. 12 for similar extensions of the P profiles as those of the B profiles in Fig. 1 were about 200–300 °C higher. B diffusion in Si is primarily governed by an interstitialcy mechanism,²⁴ $B_S + I \rightleftharpoons BI$, where B_S represents the immobile (substitutional) configuration, I is the Si self-interstitial, and BI is the mobile (interstitial) configuration of B. Hence, an excess concentration of I's leads to enhanced diffusion of B and can account for the nonequilibrium diffusion seen in Fig. 1. Further, an I can also recombine with a Si vacancy, V , through the reaction, $I + V \rightarrow \emptyset$, i.e., V and B_S compete as traps for I .

The SSUPREM4 process simulator, within Silvaco's Athena framework,²⁵ has been employed to simulate B-diffusion profiles assuming an excess of I's at the Si surface. A c-Si surface layer with a thickness of 190 nm, B-concentration of $9 \times 10^{21} \text{ cm}^{-3}$, and a certain concentration of excess I's was assumed as the diffusion source in the

simulations. Fig. 3(a) shows simulated profiles for a 10 ms FLA pulse with peak $T = 1060^\circ\text{C}$ using different excess initial I concentrations in the source, $C_{I,s}$. The FLA pulse is simulated to emulate the shape of the experimental FLA pulse given in Ref. 26. A drastic increase in the emitter depth is seen by comparing results without excess I's (black squares) and with excess I's (colored symbols), corroborating that the big leap in the experimental profiles for FLA densities at 93 J/cm^2 (20 ms) and 100 J/cm^2 (10 ms), Fig. 1, is governed by a sudden (transient) excess of I's at the surface. Also shown in Fig. 3(a) is a comparison between 5, 10, 20, and 60 ms pulses while keeping $C_{I,s}$ constant at $2 \times 10^{18} \text{ cm}^{-3}$ and $T_{\text{peak}} = 1060^\circ\text{C}$. The resulting profiles overlap closely, which is consistent with the SIMS data in Fig. 1 for the samples flash lamp annealed with energy densities of 100 J/cm^2 and 105 J/cm^2 , and pulse durations of 10 and 20 ms. This evidences that the temperature evolution in the samples is dominated by the heat dissipation after the flash rather than by the heating phase of the FLA treatment; the former has a characteristic rate of 400°C/s , while the latter is much faster with a rate of $50\text{--}100^\circ\text{C/ms}$.¹⁸

The decrease in emitter width for the highest (non-melting) FLA density used (105 J/cm^2) is surprising, see Fig. 1 and Table I, and it suggests that the B diffusion is retarded at high temperatures. Indeed, this suggestion is supported by the simulation results in Fig. 3(b) showing how the profile width gradually shrinks when the temperature exceeds 1080°C (10 ms pulse and $C_{I,s} = 2 \times 10^{18} \text{ cm}^{-3}$). The shrinkage arises from a lower concentration of excess I's available to mediate the B diffusion at high temperatures because of a strongly increasing concentration of V's (Fig. 3(c)) leading to a higher recombination rate of the I's ($I + V \rightarrow \emptyset$). In other words, at high temperature, the V's becomes a serious competitor to B's for trapping of the highly mobile I's and less B is transformed into the mobile BI configuration. Here, it should be underlined that the formation energy of self-interstitials is substantially higher than that of the vacancies

FIG. 3. Simulated boron and defect concentrations as a function of depth. (a) B profiles. Constant $T = 1060^\circ\text{C}$ with varying $C_{I,s}$. (b) B profiles. Constant $C_{I,s} = 2 \times 10^{18} \text{ cm}^{-3}$ and $t = 10 \text{ ms}$ with varying T . (c) I (solid lines) and V (dotted lines) profiles. Constant $C_{I,s} = 2 \times 10^{18} \text{ cm}^{-3}$ and $t = 10 \text{ ms}$ with varying T .

FIG. 4. High resolution TEM micrograph of the surface region of sample # 8. No crystal defects are observed.

(2.36 versus 1.08 eV)²⁵ and the equilibrium concentration of I's remains negligible to the excess one even at temperatures approaching the melting point.

As discussed above, a temperature above $\sim 1050^\circ\text{C}$ is required for the enhanced B diffusion to occur; the process is thus thermally activated and provides evidence of TED. Data from RBS analysis give a composition of $\sim 25\%$ B, 55% C, and 20% O of the SOD film. Accordingly, at least two possible mechanisms can be put forward for injection of excess I's: (i) for a B-to-Si ratio above ~ 0.01 at the SOD/Si interface and temperatures below $\sim 1270^\circ\text{C}$, a mixture of Si, SiB_3 , and SiB_6 co-exists at the Si surface.^{27,28} The formation of such silicon boride precipitates, which is likely under the FLA conditions used, is accompanied by a large amount of released/injected I's. (ii) Because of the high oxygen content in the SOD films, formation of SiO_2 is anticipated at SOD/Si interface leading to injection of I's, i.e., so-called oxidation-enhanced-diffusion (OED).²⁹ Further investigations need to be pursued in order to unveil the relative importance of these two processes.

In Fig. 4, a TEM image of the surface region of sample # 8 is shown. Neither the surface region nor the junction region (not included) exhibits structural defects, demonstrating that the FLA treatment does not induce a high defect concentration. The roughness ($\leq 10\text{ nm}$) observed at the top of the image is due to the post-FLA etching treatment and may partially limit the SIMS depth-profiling resolution ($\sim 10\text{ nm}$). Further, no secondary phases (such as SiB_3 or SiB_6) are observed in the bulk of Si (deeper than $5\text{--}10\text{ nm}$). The lack of TEM evidence for precipitates does, however, not preclude their presence *during* FLA as the precipitates may have been etched away by the chemical treatment prior to TEM characterization.

In conclusion, by depositing a polyboron SOD on a Si wafer and heat treating the system with FLA for 10 or 20 ms, high concentration shallow p^+ emitters have been realized. The emitters are highly electrically activated with B peak concentrations between $9 \times 10^{19}\text{ cm}^{-3}$ and $3 \times 10^{20}\text{ cm}^{-3}$

and depths between 50 and 140 nm. TEM analysis reveals no structural defects induced by the FLA treatment. A drastic broadening of the B profiles occurs above an energy density of 88 J/cm^2 , attributed to TED mediated by Si self-interstitials as supported by process simulations. The interstitials originate most likely from a thermally activated reaction between the SOD film and the Si wafer surface.

This work was performed within "The Norwegian Research Centre for Solar Cell Technology" (Project No. 460976), a Centre for Environment-friendly Energy Research cosponsored by the Norwegian Research Council and research and industry partners in Norway.

¹B. J. Pawlak, T. Janssens, S. Singh, I. Kuzma-Filipek, J. Robbelein, N. E. Posthuma, J. Poortmans, F. Cristiano, and E. M. Bazizi, *Prog. Photovoltaics* **20**, 106 (2011).

²N. Bateman, P. Sullivan, C. Reichel, J. Benick, and M. Hermle, *Energy Procedia* **8**, 509–514 (2011).

³Y. Komatsu, V. Mihailetschi, L. Geerligs, B. van Dijk, J. Rem, and M. Harris, *Sol. Energy Mater. Sol. Cells* **93**, 750 (2009).

⁴M. A. Kessler, T. Ohrdes, B. Wolpensinger, and N. P. Harder, *Semicond. Sci. Technol.* **25**, 055001 (2010).

⁵F. Recart, I. Freire, L. Perez, R. Lago-Aurrekoetxea, J. Jimeno, and G. Bueno, *Sol. Energy Mater. Sol. Cells* **91**, 897 (2007).

⁶R. R. King and R. M. Swanson, *IEEE Trans. Electron Devices* **38**, 1399 (1991).

⁷H. A. Bomke, H. L. Berkowitz, M. Harmatz, S. Kronenberg, and R. Lux, *Appl. Phys. Lett.* **33**, 955 (1978).

⁸R. L. Cohen, J. S. Williams, L. C. Feldman, and K. W. West, *Appl. Phys. Lett.* **33**, 751 (1978).

⁹J. T. Lue, *Appl. Phys. Lett.* **36**, 73 (1980).

¹⁰R. Klages, J. Matthxi, M. Voelskow, G. A. Kachurin, E. V. Nidaev, and H. Bartsch, *Phys. Status Solidi A* **66**, 261 (1981).

¹¹T. Ito, T. Iinuma, A. Murakoshi, H. Akutsu, K. Suguro, T. Arikado, K. Okumura, M. Yoshioka, T. Owada, Y. Imaoka, H. Murayama, and T. Kusuda, *Jpn. J. Appl. Phys., Part 1* **41**, 2394 (2002).

¹²H. B. Normann, L. Vines, V. Privitera, W. Skorupa, T. Schumann, B. G. Svensson, and E. V. Monakhov, *Appl. Phys. Lett.* **102**, 132108 (2013).

¹³S. W. Glunz, *Adv. Optoelectron.* **2007**, 97370 (2007).

¹⁴Z. G. Li, L. Liang, A. S. Ionkin, B. M. Fish, M. E. Lewittes, L. K. Cheng, and K. R. Mikeska, *J. Appl. Phys.* **110**, 074304 (2011).

¹⁵T. Gebel, M. Voelskow, W. Skorupa, G. Mannino, V. Privitera, F. Priolo, E. Napolitani, and A. Carnera, *Nucl. Instrum. Methods Phys. Res., Sect. B* **186**, 287 (2002).

¹⁶M. A. Green, *Sol. Energy Mater. Sol. Cells* **92**, 1305 (2008).

¹⁷C. Zaring, A. Pisch, J. Cardenas, P. Gas, and B. G. Svensson, *J. Appl. Phys.* **80**, 2742 (1996).

¹⁸T. Schumann, private communication (2015).

¹⁹D. B. M. Klaassen, *Solid-State Electron.* **35**, 953 (1992).

²⁰P. Baeri, S. U. Campisano, G. Foti, and E. Rimini, *J. Appl. Phys.* **50**, 788 (1979).

²¹E. V. Monakhov, B. G. Svensson, M. K. Linnarsson, A. L. Magna, C. Spinella, C. Bongiorno, V. Privitera, G. Fortunato, and L. Mariucci, *Appl. Phys. Lett.* **86**, 151902 (2005).

²²P. M. Fahey, P. B. Griffin, and J. D. Plummer, *Rev. Mod. Phys.* **61**, 289 (1989).

²³P. A. Stolk, H.-J. Gossmann, D. J. Eaglesham, D. C. Jacobson, C. S. Rafferty, G. H. Gilmer, M. Jaraiz, J. M. Poate, H. S. Luftman, and T. E. Haynes, *J. Appl. Phys.* **81**, 6031 (1997).

²⁴W. Windl, M. M. Bunea, R. Stumpf, S. T. Dunham, and M. P. Masquelier, *Phys. Rev. Lett.* **83**, 4345 (1999).

²⁵*Athena User's Manual*, Silvaco, Inc., 2014.

²⁶W. Skorupa, T. Gebel, R. A. Yankov, S. Paul, W. Lerch, D. F. Downey, and E. A. Arevalo, *J. Electrochem. Soc.* **152**, G436 (2005).

²⁷R. W. Olesinski and G. J. Abbaschian, *Bull. Alloy Phase Diagrams* **5**, 478 (1984).

²⁸T. L. Aselage, *J. Mater. Res.* **13**, 1786 (1998).

²⁹S. M. Hu, *J. Appl. Phys.* **45**, 1567 (1974).

PAPER II

Structural properties of Cu₂O epitaxial films grown
on c-axis single crystal ZnO by magnetron sputtering

J. Gan, S. Gorantla, H. N. Riise, Ø. S. Fjellvåg, S. Diplas, O. M. Løvvik,
B. G. Svensson, E. Monakhov and A. E. Gunnæs

Appl. Phys Lett. 108 (2016) 152110

Structural properties of Cu₂O epitaxial films grown on c-axis single crystal ZnO by magnetron sputtering

J. Gan,¹ S. Gorantla,¹ H. N. Riise,^{1,a)} Ø. S. Fjellvåg,¹ S. Diplas,² O. M. Løvvik,^{1,2}
 B. G. Svensson,¹ E. V. Monakhov,¹ and A. E. Gunnæs¹

¹*Department of Physics/Center for Materials Science and Nanotechnology, University of Oslo, P.O. Box 1048, Blindern, N-0316 Oslo, Norway*

²*SINTEF Materials and Chemistry, P.O. Box 124, Blindern, Forskningsveien 1, N-0314 Oslo, Norway*

(Received 7 March 2016; accepted 16 March 2016; published online 15 April 2016)

Epitaxial Cu₂O films grown by reactive and ceramic radio frequency magnetron sputtering on single crystalline ZnO (0001) substrates are investigated. The films are grown on both O- and Zn-polar surface of the ZnO substrates. The Cu₂O films exhibit a columnar growth manner apart from a ~5 nm thick CuO interfacial layer. In comparison to the reactively sputtered Cu₂O, the ceramic-sputtered films are less strained and appear to contain nanovoids. Irrespective of polarity, the Cu₂O grown by reactive sputtering is observed to have (111)Cu₂O|| (0001)ZnO epitaxial relationship, but in the case of ceramic sputtering the films are found to show additional (110)Cu₂O reflections when grown on O-polar surface. The observed CuO interfacial layer can be detrimental for the performance of Cu₂O/ZnO heterojunction solar cells reported in the literature. © 2016 AIP Publishing LLC.
[\[http://dx.doi.org/10.1063/1.4945985\]](http://dx.doi.org/10.1063/1.4945985)

Cu₂O (copper(I) oxide, cuprous oxide) is a p-type semiconductor material with a direct band gap ($E_g^{Cu_2O} \approx 2.1$ eV) and a high absorption coefficient.^{1,2} Cu₂O thin films grown by reactive radio frequency (rf) magnetron sputtering can exhibit a high hole mobility of ~60 cm²/V s at room temperature (RT) with a carrier density of ~10¹⁵ cm⁻³.³ Besides, Cu₂O is chemically stable, non-toxic and earth-abundant.⁴ This makes Cu₂O a particularly suitable candidate for thin film solar cells, where high conversion efficiency is required while manufacturing in large-scale at low costs. Oxide based thin film solar cells with Cu₂O as the absorber layer show a theoretical efficiency around 20% (Ref. 5) while currently reported experimental values remain in the range of 2%–6%.^{6,7} For further understanding and improvement, both the thin film properties (transport, optical, and structural) and interface quality should be investigated.

Fariza *et al.*⁸ have reported on studies of a heterojunction (HJ) between polycrystalline ZnO and Cu₂O. It was prepared by low-temperature electrodeposition where Cu₂O is deposited on a Au/Si(100) substrate, followed by deposition of ZnO. The X-ray Diffraction (XRD) measurement results have shown preferential orientations for Cu₂O and ZnO of being (111) and (0001), respectively. The HJ shows a higher rectification in the current-voltage (I-V) measurement when the ZnO film was deposited at a high cathode current density, where Cu was believed to be formed at the HJ interface due to reduction in Cu₂O. Chou *et al.*⁹ compared the HJs of magnetron sputtered Al-doped ZnO films on polycrystalline Cu₂O underlayers with orientations of (111) and (100) prepared by potentiostatic electrodeposition. They demonstrated that the HJ based on Cu₂O(111) without substrate heating had the highest solar conversion efficiency, ~0.07%.⁹ Li *et al.*¹⁰ have shown that the Cu₂O(111) orientation can be realized by low temperature (<300 °C) oxidation of Cu(111)

epi-layer grown on single crystal ZnO(0001) using a radio-frequency plasma assisted molecular beam epitaxy (rf-MBE) system. In addition, preferential orientations of polycrystalline Cu₂O films deposited on fused silica can also be tuned, via the magnetron target power, between (111) and (100) during reactive sputtering.¹¹

In order to elucidate the atomic and electronic structure of the Cu₂O/ZnO HJ, samples with well-defined, sharp, and non-inclined interfaces are highly desirable. This enables studies with atomic (or sub-atomic) spatial resolution and may unveil the reason for the poor performance of Cu₂O-based HJ solar cells relative to that expected theoretically. In the present work, Cu₂O films have been magnetron sputtered on O- and Zn-polar c-axis ZnO single crystal substrates by reactive sputtering and by sputtering from a ceramic Cu₂O target (ceramic-sputtered). The crystal structure and strain of the films are studied by XRD and the strain reflected in the Cu₂O lattice constants is compared between the different samples. Further, the crystal structure is also studied by high-resolution scanning transmission electron microscopy (HRSTEM) and especially, a few nm thick interfacial layer of CuO is clearly revealed in all the samples. Such a layer is anticipated to be highly detrimental to the opto-electronic performance of the Cu₂O/ZnO HJ.

Cu₂O thin films were deposited on c-axis oriented ZnO single crystal wafers purchased from Tokyo Denpa Co., Ltd., employing a direct current/radio frequency (DC/RF) Magnetron Sputter system (Semicore Triaxis). ZnO substrates (double-side polished, Zn/O polar) were cut into pieces of 5 × 5 mm² and treated in consecutive RT ultra-sonic baths using acetone, isopropanol, and deionized water, 10 min each. Subsequently, the substrates were dried with nitrogen flow and loaded into the deposition chamber. The substrate temperature T_s was kept at 400 °C during deposition regardless of sputtering method used (reactive sputtering and sputtering from ceramic Cu₂O target). Other key process parameters are

^{a)}Electronic mail: h.n.riise@fys.uio.no

TABLE I. Selected processing parameters and values used for the two sputtering methods used for deposition.

Method	Target (-)	$Q(\text{Ar})^a$ (sccm)	$Q(\text{O}_2)^b$ (sccm)	P_P^c (Pa)	P_T^d (W)	R^e (nm min ⁻¹)
Reactive	Cu	20.0	3.6	0.95	250	~60
Ceramic	Cu ₂ O	15.8	0	0.73	50	~2.7

^a $Q(\text{Ar})$ is argon mass flow.

^b $Q(\text{O}_2)$ is oxygen mass flow.

^c P_P is plasma pressure.

^d P_T is target power.

^e R is growth rate.

summarized in Table I. The base pressure was kept below 4.0×10^{-4} Pa at $T_S = 400^\circ\text{C}$, and the sample stage was rotated at a constant speed of 12 rpm during the deposition in order to attain a good film uniformity. In this context, it is important to mention that sputtering with closed shutter to the

substrate was performed for ~5 and ~30 min for reactive and ceramic methods, respectively, prior to the actual film deposition (so-called pre-sputtering), and no influence of the deposition time on the resulting film stoichiometry has been found, i.e., steady-state conditions prevail. The films were afterwards characterized by: (1) XRD (Bruker AXS D8 Discover, Cu $K\alpha$ X-rays) analysis to determine the crystal structures (including the crystal orientation and strain) in normal θ - 2θ scanning mode and to determine the epitaxial relationship through in-plane ϕ -scans (PanAlytical Empyrean diffractometer with a 4-bounce Ge(220) Barthels monochromator as primary optics, a 0.27° parallel collimator with 0.04 rad soller slits as secondary optics and a proportional Xe-detector), (2) high resolution scanning transmission electron microscopy (HRSTEM) imaging performed in a FEI Titan G2 60–300 with DCOR C_s probe corrector operated at 300 kV. The thin-film cross-section specimens are prepared by tripod wedge mechanical polishing method,¹² followed by ion milling for 1 h in a Fischione 1010

FIG. 1. 2θ -X-ray diffraction (XRD) patterns for the Cu₂O films grown on ZnO with different polarities, reactive sputtering (a)–(c) and ceramic sputtering (d)–(f). The peaks labelled with stars indicate artefact reflections from the sample holder.

TABLE II. Summary of the lattice constant a , 2θ position and their intensities I_{peak} , and full width half maximum (FWHM) of Cu_2O films with crystal orientations of (111) and (110) sputtered on both Zn- and O- polar ZnO substrates.

Method	Polarity (-)	(hkl) (-)	a (Å)	$2\theta_{peak}$ (deg)	I_{peak} (arb. units)	FWHM (deg)
Reactive	O-polar	111	4.318 ± 0.004	36.008	58 076	0.094
				76.349	1078	0.288
	Zn-polar	111	4.301 ± 0.004	36.163	48 768	0.107
				76.730	1025	0.259
Ceramic	O-polar	110	4.283 ± 0.004	29.473	482	0.175
				61.161	986	0.352
		111		36.297	672	0.142
				77.069	12	0.312
	Zn-polar	111		36.396	30 503	0.092
				77.288	536	0.244

with 5 keV ion energy and 5 mA beam current. High angle annular dark field (HAADF) Z-contrast HRSTEM imaging were performed with a probe convergence angle of 22 mrad, collection angles of 58–200 mrad, and a probe current of ~ 80 pA, resulting in a spatial resolution of 0.08 nm to investigate the cross-section of the $\text{Cu}_2\text{O}/\text{ZnO}$ structures.

X-ray diffraction (XRD) patterns (Figs. 1(a)–1(c)) show that the reactively sputtered films have a strong $\text{Cu}_2\text{O}\{111\}$ reflection regardless of substrate terminations, while the ceramic-sputtered ones exhibit an additional $\text{Cu}_2\text{O}\{110\}$ reflection (Figs. 1(d)–1(f)) when they are grown on an O-polar substrate. The (111) surface has the most suitable lattice coherence at the interface with ZnO (0001). The (111) plane is, therefore, expected to be the most probable one under given conditions. Previous studies have shown that Cu_2O may grow preferentially in the [110] direction on [0001]-oriented ZnO substrates, since Domain Matching Epitaxy (DME) relieves the lattice mismatch strain.¹³ The lower growth rate of the ceramic sputtering may promote this growth as it gives the sputtered species more time to relax.¹⁴ However, in this study, we focus on the (111) Cu_2O preferential growth, and an extensive investigation on the origin of {110} reflections is outside the scope of this work.

The shift of the peak positions from the dashed lines (from powder diffraction file (PDF)) in all diffractograms (Figs. 1(a)–1(f)) indicate that the Cu_2O films are strained, with a larger strain in the reactively sputtered films. To further compare strain in the films, the lattice parameter a has been extracted from the XRD patterns assuming a hydrostatic strain, and the results are summarized in Table II. Compared with the value a from powder diffraction ($a = 4.2685$ Å), a increases about 1.16% and about 0.76% for the reactively sputtered films when grown on O- and Zn-polar substrates, respectively. On the other hand, a increases only by about 0.34% and 0.08% for the ceramic-sputtered films when grown on O- and Zn-polar substrates, respectively. Thus, the reactively sputtered films have a larger strain than the ceramic-sputtered ones, irrespective of the substrate polarity. Especially, the reactively sputtered film grown on O-terminated substrate has the highest strain ϵ among all.

FIG. 2. In-plane ϕ -scans of the (331)-reflection of a Cu_2O reactively sputtered film and the (11 $\bar{2}$ 4)-reflection of the Zn-face ZnO substrate.

In-plane ϕ -scans of the (331)- and (11 $\bar{2}$ 4)-reflections of a Cu_2O reactively sputtered film and the Zn-polar substrate, respectively, are shown in Fig. 2. The diffractogram reveals complete coherence of the film crystal structure with respect to the substrate. One can notice, however, that the ϕ -scan shows a 6-fold rotational symmetry for the Cu_2O film, while the [111]-axis is a 3-fold rotational symmetry axis. Detailed TEM studies have shown that this apparent contradiction is due to epitaxial twinning, i.e., the film grows in two separate domains with the crystal structures rotated 180° around the [111]-axis with respect to each other.¹⁵ In addition, similar epitaxial twinning has been reported for other oxide-based epitaxial heterostructures.¹⁶

The HAADF-STEM images in Figs. 3(a) and 3(b) show cross-section views of $\text{Cu}_2\text{O}/\text{ZnO}$ junctions, where the Cu_2O films were prepared on O-polar ZnO by reactive and ceramic sputtering, respectively. The thickness of the film is estimated to be ~ 1 μm . A sharp and well-defined junction interface occurs between the substrates and the films, irrespective of the growth method used (see Table I). The images also reveal columnar growth. However, in the case of ceramic sputtering, the Cu_2O film is less dense and contains nano-sized voids seen as gray speckles, indicated by the arrows in Fig. 3(b). Similar results were also found for films grown on

FIG. 3. HAADF-STEM cross-sectional images of Cu_2O films grown by reactive sputtering (a) and ceramic sputtering (b) on O-polar ZnO single crystal.

FIG. 4. HAADF HRSTEM images (a) showing cross-sectional view of the interface of the Cu_2O film grown on Zn-polar ZnO single crystal by reactive sputtering and (b) by ceramic sputtering. The FFTs of the numbered boxed regions 1-3 in the HRSTEM image are shown on the right. The phase of the interfacial layer between the ZnO and Cu_2O has been identified as CuO by analyzing the FFTs from different layers across the cross-section. The darker patch like areas in the ZnO layer in both images (a) and (b) are due to electron beam damage induced artefacts. The FFT diffractograms were analyzed using ELDISCA electron diffraction patterns analyzing software.¹⁷

the Zn-polar substrates. The formation of the nanovoids in ceramic-sputtered films correlates well with the strain unveiled by Fig. 1, considering that the nanovoids can be a source for relieving the strain.

Further, the ZnO/ Cu_2O interface in cross-section was investigated by HAADF-STEM cross-section imaging. Fig. 4 shows a comparison for Zn-polar substrates for reactively and ceramic-sputtered films. In both cases, an interfacial CuO layer is present between ZnO and Cu_2O (Figs. 4(a) and 4(b)). For reactive sputtering, this interfacial layer is continuous along the ZnO substrate with a thickness of roughly 5 nm (Fig. 4(a)), whereas for ceramic sputtering, the nature of the interfacial layer is discontinuous and occurs as separate islands along the ZnO substrate (Fig. 4(b)). Fast Fourier Transform (FFT) diffractograms from these HRSTEM images (also shown in Fig. 4) are consistent with a monoclinic CuO (copper (II) oxide, cupric oxide) phase for the interfacial layer. The presence of such a phase at the Cu_2O /ZnO hetero-junction interface is mostly detrimental to the performance of a solar cell,^{18,19} CuO has a narrower band gap ($E_g^{\text{CuO}} \approx 1.2 \text{ eV}$) than Cu_2O , and the desirable energy band alignment at the Cu_2O /ZnO HJ to promote the transfer of optically generated minority carriers over

the interface is hampered. Moreover, also pinning of the Fermi-level position in the Cu_2O /CuO/ZnO structure can be anticipated because of interfacial defect states,¹⁹ and the presence of the CuO layer needs indeed to be eliminated for optimum solar cell performance.

It should also be mentioned that the $\sim 5 \text{ nm}$ interfacial CuO phase is not observed in the XRD patterns due to the small thickness in comparison to the bulk Cu_2O . The formation of the interfacial layer is expected to be related to the strain at the epitaxial interface with ZnO. The ZnO/ Cu_2O interface has a lower mismatch than the ZnO/CuO interface and it has a better atomistic coherence. It is expected that the interfacial CuO relieves the misfit strain between ZnO and Cu_2O lattices (7.6%).⁸ This can explain the relatively low strain values quoted in Table II.

In summary, Cu_2O thin films have been grown on single crystal ZnO polar ZnO substrates by both reactive and ceramic rf sputtering. High resolution STEM imaging shows sharp, well-defined epitaxial heterojunction interfaces of the Cu_2O films towards the ZnO substrates for all the samples. The Cu_2O films exhibit a columnar growth manner. However, a $\sim 5 \text{ nm}$ thick interfacial layer, identified as CuO, is found in all the samples. The layer is continuous along ZnO interface in the case of reactive sputtering whereas it appears as islands for the ceramic sputtering. The reactively sputtered Cu_2O films are dense and more strained than the ceramic-sputtered ones which contain speckle-like nanovoids. Irrespective of polarity, Cu_2O grown by reactive sputtering is observed to have $(111)\text{Cu}_2\text{O}||(\text{0001})\text{ZnO}$ epitaxial relationship with the substrate. However, in the case of ceramic sputtering the Cu_2O films are found to show an additional $(110)\text{Cu}_2\text{O}||(\text{0001})\text{ZnO}$ relationship when grown on the O-polar surface. Finally, the CuO interfacial layer is detrimental to the performance of the Cu_2O /ZnO-based solar cells.

This work was conducted under the research project ES483391 “Development of a Hetero-Junction Oxide-Based Solar Cell Device (HeteroSolar),” financially supported by the Research Council of Norway (RCN) through the RENERGI program. We acknowledge use of the Norwegian Center for X-ray diffraction and scattering.

¹C. L. A. Ricardo, M. D’Incau, M. Leoni, C. Malerba, A. Mittiga, and P. Scardi, *Thin Solid Films* **520**, 280 (2011).

²C. Malerba, F. Biccari, C. L. A. Ricardo, M. D’Incau, P. Scardi, and A. Mittiga, *Sol. Energy Mater. Sol. Cells* **95**, 2848 (2011).

³S. Ishizuka, T. Maruyama, and K. Akimoto, *Jpn. J. Appl. Phys., Part 2* **39**, L786 (2000).

⁴S. Ruhle, A. Y. Anderson, H.-N. Barad, B. Kupfer, Y. Bouhadana, E. Rosh-Hodesh, and A. Zaban, *J. Phys. Chem. Lett.* **3**, 3755 (2012).

⁵L. C. Olsen, F. W. Addis, and W. Miller, *Sol. Cells* **7**, 247 (1982).

⁶A. Mittiga, E. Salza, F. Sarto, M. Tucci, and R. Vasanthi, *Appl. Phys. Lett.* **88**, 163502 (2006).

⁷T. Minami, Y. Nishi, and T. Miyata, *Appl. Phys. Express* **8**, 022301 (2015).

⁸B. M. Fariza, J. Sasano, T. Shinagawa, H. Nakano, S. Watase, and M. Izakic, *J. Electrochem. Soc.* **158**, D621 (2011).

⁹S.-M. Chou, M.-H. Hon, I.-C. Leu, and Y.-H. Lee, *J. Electrochem. Soc.* **155**, H923 (2008).

¹⁰J.-Q. Li, Z.-X. Mei, D.-Q. Ye, Y.-N. Hou, Y.-P. Liu, A. Kuznetsov, and X.-L. Du, *Chin. Phys. B* **21**, 076401 (2012).

¹¹J. Gan, V. Venkatachalapathy, B. G. Svensson, and E. V. Monakhov, *Thin Solid Films* **594**, 250 (2015).

- ¹²P. M. Voyleys, J. L. Crazul, and D. A. Muller, *Ultramicroscopy* **96**, 251 (2003).
- ¹³S. Jeong and E. S. Aydil, *J. Cryst. Growth* **311**, 4188 (2009).
- ¹⁴Y. Wang, J. Ghanbaja, F. Soldera, P. Boulet, D. Horwat, F. Mucklich, and J. F. Pierson, *Acta Mater.* **76**, 207 (2014).
- ¹⁵A. E. Gunnæs, S. Gorantla, O. M. Løvvik, J. Gan, P. A. Carvalho, B. G. Svensson, E. V. Monakhov, K. Bergum, I. T. Jensen, and S. Diplas, “Epitaxial strain induced growth of CuO on ZnO/Cu₂O interfaces” (to be published).
- ¹⁶L. Qiao, H. Y. Xiao, W. J. Weber, and M. D. Biegalski, *Appl. Phys. Lett.* **104**, 221602 (2014).
- ¹⁷J. Thomas and T. Gemming, in 14th European Microscopy Conference (2008), Vol. 1.
- ¹⁸Y. Ievskaya, R. L. Z. Hoyer, A. Sadhanala, K. P. Musselman, and J. L. MacManus-Driscoll, *Sol. Energy Mater. Sol. Cells* **135**, 43 (2015).
- ¹⁹S. S. Wilson, Y. Tolstova, and H. A. Atwater, in *IEEE 39th IEEE Photovoltaic Specialists Conference (PVSC)*, 2013, p. 2410.

PAPER III

Electronic Properties of Au/Cu₂O/n-type Si Heterojunctions for Energy Conversion

P. F. Lindberg, H. N. Riise, K. Bergum, B. G. Svensson and E. Monakhov

Conference record of the Photovoltaic Specialists Conference 2016 (2016)

2807

PAPER IV

Local homoepitaxy of zinc oxide thin films by
magnetron sputtering

H. N. Riise, V. S. Olsen, A. Azarov, A. Galeckas, T. N. Sky,
B. G. Svensson and E. Monakhov

Thin Solid Films 601 (2016) 18-21

PAPER V

Comparison of the structural properties of Zn-face
and O-face single crystal homoepitaxial ZnO epilayers
grown by RF-magnetron sputtering

R. Schifano, H. N. Riise, J. Z. Domagala, A. Yu. Azarov, R. Ratjczak,
E. Monakhov, V. Venkatachalapathy, L. Vines, K. S. Chan, J. Wong-Leung
and B. G. Svensson

J. Appl. Phys. 121 (2017) 015304

Comparison of the structural properties of Zn-face and O-face single crystal homoepitaxial ZnO epilayers grown by RF-magnetron sputtering

R. Schifano,^{1,2,a)} H. N. Riise,¹ J. Z. Domagala,² A. Yu. Azarov,¹ R. Ratajczak,³
 E. V. Monakhov,¹ V. Venkatachalapathy,¹ L. Vines,¹ K. S. Chan,⁴ J. Wong-Leung,⁴
 and B. G. Svensson¹

¹Department of Physics/Center for Material Science and Nanotechnology, University of Oslo, P.O. Box 1048, Blindern, N-0316 Oslo, Norway

²Institute of Physics, Polish Academy of Sciences, Al. Lotników 32/46, 02-668 Warsaw, Poland

³National Centre for Nuclear Research, A. Soltana 7, 05-400 Otwock-Swierk, Poland

⁴Department of Electronic Materials Engineering, Research School of Physics and Engineering and Centre for Advanced Microscopy, The Australian National University, Canberra, Australian Capital Territory 2601, Australia

(Received 16 September 2016; accepted 14 December 2016; published online 4 January 2017)

Homoepitaxial ZnO growth is demonstrated from conventional RF-sputtering at 400 °C on both Zn and O polar faces of hydrothermally grown ZnO substrates. A minimum yield for the Rutherford backscattering and channeling spectrum, χ_{min} , equal to $\sim 3\%$ and $\sim 12\%$ and a full width at half maximum of the 00.2 diffraction peak rocking curve of (70 ± 10) arc sec and (1400 ± 100) arc sec have been found for samples grown on the Zn and O face, respectively. The structural characteristics of the film deposited on the Zn face are comparable with those of epilayers grown by more complex techniques like molecular beam epitaxy. In contrast, the film simultaneously deposited on the O-face exhibits an inferior crystalline structure $\sim 0.7\%$ strained in the c -direction and a higher atomic number contrast compared with the substrate, as revealed by high angle annular dark field imaging measurements. These differences between the Zn- and O-face films are discussed in detail and associated with the different growth mechanisms prevailing on the two surfaces. *Published by AIP Publishing.* [<http://dx.doi.org/10.1063/1.4973342>]

I. INTRODUCTION

ZnO is a promising material for a wide variety of device applications ranging from optoelectronics to piezoelectricity and spintronics.^{1–4} In this respect, the growth of films with device-worthy structural, optical, and electrical properties becomes crucial, and homoepitaxy represents a fascinating choice. In recent years, due to the commercial availability of high quality ZnO single crystal substrates, several studies on ZnO homoepitaxy have been published. However, up till now, among all the techniques investigated, the main focus has been on films deposited by plasma-assisted molecular beam epitaxy (PA-MBE),^{5–7} metalorganic vapor-phase epitaxy (MOVPE),^{8–10} chemical vapor deposition (CVD),¹¹ pulsed-laser deposition (PLD),^{12,13} and atomic layer deposition (ALD);¹⁴ for a review, see, for example, Ref. 15 and references therein. On the other hand, magnetron sputtering has been extensively investigated for obtaining polycrystalline transparent conductive oxide (TCO) films based on ZnO,¹⁶ while less work has been devoted to sputtering based ZnO homoepitaxy.^{17–20}

As an example, films with ~ 40 arc sec 00.2 rocking curve full width at half maximum (FWHM) have recently been obtained by Radio Frequency (RF) sputtering on pre-baked Zn face of hydrothermally grown (HT) ZnO wafers at a substrate temperature ≤ 500 °C.¹⁸ Another study indicated that substrate temperatures of ~ 800 °C are necessary to

obtain similar rocking curve FWHMs on films with comparable thickness.¹⁹ Further, contradicting results on the surface polarity role have been reported suggesting a higher crystal quality, in terms of 00.2 rocking curve FWHMs, for depositions on the Zn-face,¹⁹ the O-face,²⁰ or almost no polarity dependence.¹⁷ Beside the structural characteristics of the films, their stoichiometry and structural defects are also key properties from a technological point of view; however, so far, little attention has been paid to these aspects.

In this study, it is shown that homoepitaxial single crystal stoichiometric ZnO films can be grown by RF-sputtering on the Zn face of HT ZnO wafers at 400 °C, using previously optimized deposition parameters for glass substrates.²¹ Structural, crystallographic, and compositional analysis of the grown layers provide evidence of different optimum deposition conditions between O- and Zn-face, consistent with a polarity dependence of the growth mechanisms.

II. EXPERIMENTAL DETAILS

A commercially available 1×1 cm Tokyo Denpa HT wafer double sided polished and with a nominal resistivity equal to ~ 75 Ω cm was divided into two 1×0.5 cm pieces used for Zn and O face deposition and labeled hereafter as samples A and B, respectively. These two samples are part of a study based on a batch of 14 samples in total.²² Afterwards, acetone, ethanol, and deionized water cleaning was performed for 5 min each sequentially, prior to loading them simultaneously into a Semicore Tri-axis Multi Source Sputtering

^{a)}Electronic mail: schifano@ifpan.edu.pl

System balanced magnetron sputtering deposition system. As ZnO source, a 99.99% pure ZnO ceramic target mounted on a RF-powered 3 in. cathode was used, and the target to substrates distance was set equal to ~ 11 cm. The ZnO substrates were placed on a quartz support corresponding to a sample floating potential condition. The sample chamber was evacuated to a base pressure of $\sim 6 \times 10^{-7}$ Torr. After reaching the desired deposition substrate temperature of 400°C , 99.999% pure Ar was introduced to a pressure of ~ 17 mTorr. The film deposition was performed by keeping the ZnO cathode power at 50 W and the rotation of the sample stage at 12 rpm. A pre-sputtering time of 10 min for cleaning the target was performed, and subsequently, the shutter was opened. The deposition lasted 5 h corresponding to an expected film thickness of (560 ± 30) nm on glass substrates according to a previous work.²¹ The cathode voltage during deposition was constant at a level of (177 ± 1) V.

The sputtered thin films were analyzed by Rutherford backscattering spectrometry in channeling (*RBS/C*) and random mode (*RBS/R*) with 3.085 MeV $^4\text{He}^{++}$ ions incident along the $[00.1]$ direction and a Si surface barrier based detector positioned at 165° relative to the incident beam direction. The energy of the incident $^4\text{He}^{++}$ ions was selected in order to exploit the O resonance^{23,24} and accurately verify the stoichiometry of the films. A 1×1 mm² beam size was used, the detector resolution was 15 keV and no bias was applied to the samples. The stoichiometry of the grown layers was determined by comparing the deposited layers *RBS/R* spectra with those of a single crystal ZnO wafer, anticipated to be stoichiometric. In addition, from the *RBS/C* and *RBS/R* measurements, the minimum yield, $\chi_{\min}$ was extracted as well. Finally, the *RBS* spectra channel width was converted to Zn depth using the stopping power given by the SRIM code²⁵ and assuming the ZnO atomic density equal to $8.3 \times 10^{22} \text{ cm}^{-3}$.

The structural quality of the samples was investigated with a Bruker AXS D8 Discover X-ray diffractometer (*XRD*) and a High Resolution Philips X'Pert Diffractometer (*HXRD*) by using the $\text{CuK}\alpha_1$ line selected by a 2 and 4 bounce Ge(022) asymmetric monochromator placed on the primary beam side, respectively. The $2\Theta - \omega$ scans shown were acquired with a position sensitive detector (LynxEye) utilized in the 1D mode (virtual receiving slit size = $75 \mu\text{m}$), while for the transverse ω -scan, a three bounce Ge(220) analyzer in the diffracted path was used. Further, in double axis geometry, the Philips X'Pert diffractometer utilized a $1/4^\circ$ receiving slit placed in front of the detector to record reciprocal space maps (*RSM*). Line profiles were fitted with a Voigt function. The full width at half maximum (FWHM_V) of the Voigt functions given in Sec. III has been corrected for the instrumental broadening according to the procedure outlined in Ref. 26.

Transmission electron microscopy (*TEM*), high resolution transmission electron microscopy (*HR-TEM*), and scanning transmission electron microscopy (*STEM*) were carried out on a JEOL 2100F instrument equipped with a field emission gun and operated at a 200 kV acceleration voltage. Cross-sectional *TEM* samples were prepared by mechanically polishing the films into wedge samples having a $\sim 5^\circ$

angle using an Allied tripod polisher, followed by ~ 2 h of Ar ion beam milling at low temperature (-168°C) using a Gatan 691 Precision Ion Polishing System (*PIPS*) operated at 3.5 keV.

Finally, the samples and substrates surface morphology was investigated by Atomic force microscopy (*AFM*) measurements performed with a Veeco D3100 microscope running in tapping mode. The root mean square (*RMS*) surface roughness was deduced by averaging four $2.00 \times 2.00 \mu\text{m}$ *AFM* amplitude images taken at different positions of the samples surfaces.

III. EXPERIMENTAL RESULTS

A comparison of *RBS/R* spectra of samples A and B and of a single crystal ZnO wafer acquired in random geometry is shown in Fig. 1(a). The results confirm that samples A and B are stoichiometric within the experimental accuracy (± 1 at. %). The stoichiometry of the epilayers was also confirmed by simulated curves to the experimental spectra using the SIMNRA code²⁷ (not shown) even though, this is only indicative because of the uncertainty of the non-Rutherford

FIG. 1. (a) Comparison between the *RBS/R* spectra for samples A, B (scatter points) and a single crystal ZnO wafer (solid line). (b) *RBS/C* spectra for samples A and B and the *RBS/R* spectra of sample A. In both figures (a) and (b), the positions of the surface peaks of Zn and O are denoted by arrows.

TABLE I. $\chi_{\min}$, $FWHM_V$ of the 00.2 rocking curves fitted with a Voigt function, lattice parameters, lateral correlation length, $L_{\parallel}$, and angular tilt misorientation, α_{tilt} , for samples A and B. In the case of $L_{\parallel}$ and α_{tilt} the values in parentheses are the ones obtained by the single 00.2 transverse ω -scan profile analysis described in Ref. 37.

Sample	$\chi_{\min}$	c (Å)	a (Å)	$FWHM_V$ (arc sec)	$L_{\parallel}$ (μm)	α_{tilt} (arc sec)
A	~ 3	5.2074 ± 0.0001	3.2506 ± 0.0006	70 ± 10	~ 2.5 (3 ± 1)	90 ± 10 (70 ± 10)
B	~ 12	5.243 ± 0.001	3.255 ± 0.007	1400 ± 100	0.12 ± 0.03 (0.11 ± 0.04)	1300 ± 100 (1300 ± 100)

stopping power cross section. According to secondary ion mass spectrometry results, the H content is estimated to be $\sim 10^{20} \text{ cm}^{-3}$ in the films with other unintentionally introduced impurities like Mg, Cl, Al, and Si occurring in the $\sim 10^{17}$ – 10^{19} cm^{-3} range.²⁸ The RBS/C results for the A and B samples are shown in Fig. 1(b), together with the RBS/R of sample A. The extracted $\chi_{\min}$ equals $\sim 3\%$ and $\sim 12\%$ for samples A and B, respectively, as summarized in Table I. The former value is similar to that ($\sim 2\%$ – 3%) typically recorded for single crystal HT ZnO wafers purchased from the same vendor.²⁹ Hence, the RBS/C measurements are suggesting a film crystalline quality of sample A comparable to that of the substrate, while for sample B, the higher $\chi_{\min}$ and larger dechanneling vs Zn depth indicate a more defective epilayer. In addition, Fig. 1(b) reveals no bulk to film interface change in the slope of the RBS/C spectra for sample A, but for sample B, it occurs at a Zn depth of ~ 400 nm. Here, also the small peak in the yield may suggest a defective film-substrate interface. This indicates that the film deposited on the O-face is ~ 160 nm thinner than expected using glass substrates. This difference will be discussed in detail in Sec. IV. In Fig. 2, $2\theta - \omega$ scans of the 00.2 reflection are shown, and for sample A, the film related peak overlaps closely with the substrate one implying equal lattice constants in the c -direction. In contrast, for B, a distinct film peak is observed $\sim 0.25^\circ$ below the substrate signal, thus indicating a unit cell elongated in the c -direction. In Fig. 3(a), results from transverse ω -scans corresponding to the 00.2, 00.4, and 00.6 peak positions are shown for sample A. A $FWHM_V$ of the Voigt function describing the 00.2 transverse ω -scan, after eliminating the instrumental broadening, is extracted and found equal

FIG. 2. 00.2 reflection $2\theta - \omega$ scans for samples A and B normalized to the main/substrate peak intensity.

to (70 ± 10) arc sec. This is to be compared with a starting Zn- as well as O-face $FWHM_V$ within (20 ± 10) arc sec as measured on a substrate of the same batch and in agreement with what was previously reported by the vendor.³⁰ The value found for sample A here is similar to that previously obtained by RF-sputtering on substrates kept at $\sim 800^\circ\text{C}$ and comparable to the values recently reported for films obtained by MOVPE, PLD, and PA-MBE, typically in the ~ 20 – 40 arc sec range.^{10,19,31} The peak widths in the transverse ω -scans are much broader for sample B, as can be seen in Fig. 3(b), and indicating a poor crystal quality of the grown epilayer. This is consistent with the RBS/C results. In addition, a close look on

FIG. 3. 00.2, 00.4, and 00.6 transverse ω -scans for samples A and B in (a) and (b), respectively. In both cases, the curves are displaced along the intensity axis for clarity, and the Voigt functions used to model the experimental data are indicated by solid lines (two Voigt functions centered in $\Delta\omega$ equal to 0 have been used to fit the 00.2 peak in the case of sample B). Note that the large maximum and dynamical intensity difference between samples A and B is related not only to the superior crystal quality of the former, but also to the presence of an overlapping substrate contribution.

the 00.2 data in Fig. 3(b) actually reveals the existence of two contributions: a broad diffuse component and a sharper one with a $FWHM_V$ of (1400 ± 100) arc sec and (150 ± 40) arc sec, respectively. Furthermore, at the higher orders of reflection, the sharp component vanishes. The presence of two components in the 00.2 transverse ω -scan can be related to: (i) a substrate surface related streak overlapping with the film signal,³² (ii) an unconventional mosaic structure of the film with the single crystallites coherently scattering the X-rays because of a long range order due to the substrate film interfacial interactions.³³ In the latter case, the specular component is attenuating at high reflection orders due to the residual disorder present, whereas in the former case, it disappears due to the increasing angular distance between the substrate/film peak positions. Both interpretations are consistent with the results obtained, and further measurements are necessary to distinguish between the two physical mechanisms. Here, it is also worth pointing out that rocking curves showing similar characteristics have also been reported for ZnO films grown by PA-MBE on *c*-sapphire substrate.³⁴ In this case, interfacial degradation due to the large lattice mismatch to the substrate was discussed as a possible reason for the double peak feature. However, in our case, the absence of a double peak for the high order reflections excludes the occurrence of a two region structure along the growth direction, as expected, since no lattice mismatch is present. In the following, the broad diffuse component $FWHM_V$ is taken as a figure of merit of the crystallographic quality of sample B and used to extract relevant film characteristics.

For transverse ω -scans corresponding to symmetric reflections, the averaged lateral correlation length, $L_{||}$, is independent on the scattering vector, $\mathbf{Q}$. On the other hand, the angular tilt misorientation, α_{tilt} , causes a broadening (in arcs) in the reciprocal space and is therefore proportional to $\mathbf{Q}$. Hence, a Williamson–Hall like plot³⁵ can be utilized to separate $L_{||}$ and α_{tilt} . By considering the relations linking the angular space coordinates to the reciprocal space ones, a Williamson–Hall like plot will, in this case, become: $\beta \times (\sin \theta)/\lambda$ vs. $\sin \theta/\lambda$, where β is the transverse ω -scan integral breadth expressed in rad, θ the corresponding Bragg angle, and λ the $\text{CuK}\alpha_1$ wavelength. Then, α_{tilt} corresponds to the slope of the linear dependence, while $L_{||}$ can be extracted from the intercept with the ordinate, y_0 , according to the relation $L_{||} = 1/2y_0$.³⁶ The resulting Williamson–Hall like plots for samples A and B, obtained by using the β of the Voigt function modeling the ω -scan presented in Fig. 3, are shown in Fig. 4. As given in Table I, $L_{||}$ and α_{tilt} are found equal to $\sim 2.5 \mu\text{m}$ and (90 ± 10) arc sec for sample A and to (120 ± 30) nm and (1300 ± 100) arc sec for sample B. In order to substantiate these values, which suffer from a low signal to noise ratio for the high-order reflections of sample B, also a single 00.2 transverse ω -scan profile analysis has been performed.³⁷ According to this analysis, the Voigt function is related to $L_{||}$ and α_{tilt} via the Lorentzian and Gaussian component of the peak, respectively, assuming a random distribution of mosaic blocks around the growth direction.³⁷ A fairly good agreement between the two methods is found for both samples, as illustrated in Table I. The values of α_{tilt} for sample A are comparable to those reported (~ 20 arc sec) for ZnO layers grown on *c*-sapphire by

FIG. 4. (a) Graphical separation of the contributions from the lateral correlation length, $L_{||}$, and the angular tilt misorientation, α_{tilt} , to the broadening of the transverse ω -scans integral breadth, β , based on a Williamson–Hall like plot.

PA-MBE utilizing a MgO/ZnO buffer bilayer followed by annealing at 750°C prior to the ZnO film deposition.³⁴ Similarly, also the large $L_{||} \sim 3 \mu\text{m}$ confirms the good crystallographic property of sample A. On the other hand, for sample B, both α_{tilt} and $L_{||}$ are in the range of the values generally reported for heteroepitaxially grown ZnO layers.^{34,38,39}

The RSM results of the asymmetrical -10.5 reflection are shown in Figs. 5(a) and 5(b). For sample B, the film node is clearly separated from the substrate peak and occurs at smaller Q_y . The elliptic shape of the ZnO node is elongated along the Q_x axis, indicating that the dominant broadening is due to the limited lateral correlation length, $L_{||}$.⁴⁰ In contrast, no distinct epilayer peak occurs for sample A, see Fig. 5(b), consistent with the symmetrical reflection shown in Fig. 2. Furthermore, a factor of ~ 3 reduction both in the Q_x and Q_y extension of the signal tails is observed, corroborating the overall better crystal quality of sample A relative to sample B. From the -10.5 asymmetrical scans shown in Fig. 5 and the $2\theta - \omega$ scans 00.6 peak position (not shown), the lattice constants a and c have been evaluated and are listed in Table I. Corrections for refraction effects due to the difference in refractive index between the sample and air, have been omitted in these calculations.³² Here, it is interesting to notice that the a lattice constant is identical for the two samples within the experimental errors, while for sample B, the c lattice constant is found $\sim 0.7\%$ elongated with respect to the substrate/sample A, as already discussed.

Figs. 6(a) and 6(b) show selected area diffraction patterns (SAED) of the samples A and B, respectively. A sharply defined spot pattern is observed for both samples consistent with single crystalline homoepitaxial layers. HR-TEM images of the substrate-film interface taken along the a -axis reveal a more defective interface in sample B (Fig. 4(d)) compared to sample A (Fig. 4(c)). In addition, the presence of threading dislocations originating from the substrate-film interface and reaching the surface has been revealed by two-beam bright field imaging close to the m -axis in sample A, as shown in Fig. 6(e). Diffraction contrast analysis suggest that the Burgers vector, $\mathbf{b}$, of these defects are of edge-type and parallel to the $\{11.0\}$ directions. The presence of these

FIG. 5. Reciprocal scan maps, *RSM*, relative to the -10.5 reflection for sample *A* and *B*. Note that the scale for sample *B* is a factor 4 larger in each direction than that of sample *A*, while the absolute differences in intensity involve the use of a two bounce hybrid Ge(220) monochromator and a double axis geometry with a $1/4^\circ$ receiving slit placed in front of the detector for samples *A* and *B*, respectively.

dislocations confirms that the film is a relaxed single crystal layer and they have been reported as the most abundant type of threading dislocations in *PA-MBE* grown ZnO films deposited on *c*-sapphire with and without a MgO buffer layer.³⁴ It is important to note that such pure edge dislocations will affect only $(hk.l)$ planes with at least h or k non-zero, i.e., the $FWHM_V$ of the transverse ω -scans corresponding to symmetric reflections in Fig. 3(a) will not be influenced and hence not reveal the presence of the pure edge dislocations. A similar analysis of sample *B* did neither unveil any distinct dislocations, see, for example, Fig. 6(f) where the *TEM* image along the *a*-axis is shown, nor evidence for other extended defects, like basal stacking faults. Note also that a comparison between these two cross sectional two-beam bright field images (Figs. 6(e) and 6(f)) reveals a substantial difference in thickness between the epilayers grown on the Zn face (sample *A* ~ 800 nm) and the O face (sample *B* ~ 400 nm). This occurs despite that the two layers were prepared simultaneously and is far beyond the $\sim 5\%$ thickness fluctuations observed for previous polycrystalline films.²¹ Furthermore, in both cases, the film thicknesses deviate significantly from the expected one of ~ 560 nm, based on films deposited on glass substrates using the same growth conditions.²¹

FIG. 6. (a) and (b) SAED patterns from the as-deposited films. (c)–(f) HR-TEM and TEM images of the interfacial region and of the overall film. (a), (c), (e) and (b), (d), (f) correspond to samples *A* and *B*, respectively. All the images shown were taken along the *a*-axis.

Comparison of the *TEM* cross section images of the films with those of the substrates reveals that sample *B* exhibits a darker contrast than the bulk (see Fig. 6(f)). Further investigations based on *STEM* analysis using high angle annular dark field (*HAADF-STEM*) imaging reveal a higher atomic number (*Z*) contrast with respect to the substrate, Fig. 7. This indicates a slightly Zn rich and/or denser layer, leading to the darker appearance in the *TEM* cross section image (Fig. 6(f)). Comparison with the *RBS/R* results suggests that in the former case the Zn excess has to be within the measurement accuracy of ≤ 1 at. %. In addition, a close look to the sample *B* cross section *HAADF-STEM* images reveal subtle contrasts variations. This may point to non-homogeneity in the composition and/or to slightly denser areas due to strain within the layer as well as close to the substrate interface. However, no evidence for the

FIG. 7. (a) and (b) Cross section *HAADF-STEM* images for samples A and B, respectively.

presence of Zn precipitates has been found. On the other hand, no significant *Z*-contrast difference is observed between the substrate and the epitaxial layer of sample A. This is in agreement with the superior quality of sample A with structural characteristics closer to those of the substrate, as presented above. On the contrary, Zn excess has been previously reported as substantially affecting the structural properties of ZnO single crystal epitaxial films⁴¹ consistently with the poorer crystal quality of sample B observed here.

AFM measurements in tapping mode were performed on both the A and B samples prior and after the deposition. The surface of the bare wafer (not shown) appears to be atomically flat with no clear step and terrace structure and a root mean square (*RMS*) roughness equal to (0.3 ± 0.1) nm and (0.2 ± 0.1) nm for the Zn- and O-face, respectively, in agreement with what previously reported by the vendor.³⁰ On the contrary, the morphology of the deposited films result strikingly different, thus suggesting a growth mechanism diverse on the Zn- and O-face as shown in Fig. 8, where two typical surface images are displayed. For sample A, large elongated grains of micrometer size with the presence of submicrometer features are clearly visible and a *RMS* surface roughness equal to (12.2 ± 0.6) nm is obtained. For sample B, a smoother surface with a uniform distribution of more circular grains with diameter of ~ 100 nm and (1.0 ± 0.1) nm *RMS* surface roughness is observed. For both samples, the grain sizes measured by *AFM* are in fairly good agreement with the values of $L_{\parallel}$ extracted from the *XRD* measurements, indicating that the surface morphology correlates with the underlying mosaic structure of the films.

IV. DISCUSSION

The results evidence striking differences in the crystal quality, crystallographic defects present, surface morphology, and even epilayer thickness depending on the surface polarity of the ZnO wafer used as a substrate.

Concerning the ~ 400 nm thickness difference observed between samples A and B, epitaxial ZnO growth has been reported to depend significantly on the surface polarity in the case of *PA-MBE* depositions.⁶ In fact, the observed difference in thickness follows the trend expected: on the O polar surface, Zn species are incorporated at the step edges, while on the Zn polar one, the Zn atoms are incorporated directly on the surface due to the three-bond configuration of the

FIG. 8. (a) and (b) Tapping mode *AFM* images for samples A and B, respectively. The *z*-scale is given on the right hand side of the respective figure, and for sample B, it is 10 times smaller than for sample A.

underlying O-layer. This results in a higher growth rate in the latter case and for amorphous substrates, like glass, yielding randomly oriented grains, an intermediate growth rate is anticipated.⁴² Hence, the deviations from a polycrystalline ZnO film growth rate are fully consistent with an epitaxial growth regime, where a one to one correlation between the mass transfer and deposition rate does not apply. A high homoepitaxial deposition rate has also been observed in the related study where the *RF*-magnetron sputtered ZnO films, deposited on the Zn-face of ZnO single crystals, were compared with polycrystalline ones grown simultaneously on Si (100) RCA cleaned substrates.²²

In addition, the 3-dimensional growth observed for sample A (Zn face) by *AFM* suggests a too high Zn/O ratio, considering the low Zn mobility due to the three-bond configuration of the underlying O-layer.⁶ In the case of O-face because of the step edges incorporation of the Zn species, the growth will be less affected by the Zn/O ratio. However, a reduction in island size from ~ 3 μm to ~ 200 nm with the Zn/O ratio increasing from 0.2 to 2 has been reported in Ref. 6. This finding is in qualitative agreement with the submicrometer features observed here in Fig. 8(b) for sample B. Hence, using an optimal mixture of Ar and O as “working” gas is anticipated to further improve the film structural characteristics.

Sample A is found exhibiting a fully relaxed structure with edge-type threading dislocations parallel to the $\{11.0\}$ directions. On the contrary, sample B is found to be $\sim 0.7\%$ elongated in the *c*-direction, while there is in plane matching

between the substrate and epilayer. This indicates that the film is not purely biaxially strained as generally found for polycrystalline magnetron sputtered ZnO films deposited on amorphous substrates⁴³ and it is specular to what was reported, for example, in the case of PLD grown ZnO on AlN.⁴⁴ Moreover, the HAADF-STEM imaging suggests that sample *B* is slightly Zn rich within the RBS/R accuracy of ≤ 1 at. % and/or denser. Since no evidence of extended defects is revealed by TEM, these results suggest a distribution of small size defects like single or clusters of point defects. They are presumably Zn related and anticipated to introduce hydrostatic strain,⁴⁵ contributing to the extension of the lattice in the *c*-direction. Here, it is worth noticing that similar *c*-lattice constant extension for DC- and RF-sputtered polycrystalline ZnO:Al films has been reported.⁴⁶ It was ascribed to O⁻ ions (with energy in the 60–450 eV range) being implanted into the growing ZnO film with a subsequent formation of acceptor-like oxygen interstitials. The surface polarity is, however, expected to have minor effect on the amount of atoms, ions, or molecules peening/implanted and in our case they are excluded as main reason for the striking differences between samples *A* and *B*.

Because of the lower growth rate (longer exposure time), the O-face is anticipated to be more affected by re-sputtering as well as surface atomic displacements produced by the bombarding ions. Therefore, during O-face depositions, a higher density of surface defects occurs, and they may play a major role being nucleation sites for the incorporation of excess Zn atoms at step edges. Hence, the growth process in itself may be enhancing the evolution of a more defective (strained) and/or denser as well as Zn rich epilayer on the O-face. Here, it is important to underline that the Zn rich structure of sample *B* cannot be attributed to the Zn rich growth conditions since the growth on the O face is almost independent on the Zn/O ratio, as discussed above. Moreover, in addition to a higher density of generated defects on the O-face, the nature of the defects is also likely to differ from that on the Zn-face.^{47,48} This will, indeed, affect the epitaxial growth mechanisms on the two faces. Further investigations with variable Ar gas pressure during the sputtering process should be pursued to elucidate the importance of the different physical mechanisms involved.

V. CONCLUSIONS

In conclusion, single crystal homoepitaxial ZnO layers were grown at 400 °C by conventional RF-sputtering on both Zn and O polar faces of commercially available hydrothermally grown substrates. A $FWHM_V$ of the 00.2 transverse ω -scan (modeled as a Voigt function) as low as (70 ± 10) arcsec was obtained for the Zn face film. These results together with a smooth epi-layer/bulk interface show that RF-magnetron sputtering is a viable alternative to more complex techniques like PA-MBE or MOCVD to grow epitaxial ZnO films of device-worthy quality on the Zn face. In contrast, a much broader $FWHM_V$ of the 00.2 transverse ω -scan equal to (1400 ± 100) arcsec for the layer deposited on the O-face has been measured with HAADF-STEM revealing a Zn rich and/or denser film. Further, the Zn-face film is

relaxed exhibiting threading dislocations, while the O-face film is highly strained. These results imply two different optimal windows for the O and Zn-face homoepitaxial growth of ZnO films by RF-magnetron sputtering, linked to the polarity dependence of the growth mechanism.

Finally, the present study shows the prospective for RF-magnetron sputtered homoepitaxially grown ZnO layers of even higher crystallographic quality by further fine tuning of the deposition conditions.

ACKNOWLEDGMENTS

This work has been performed within “The Norwegian Research Centre for Solar Cell Technology” Project No. 193829, a Centre for Environment-friendly Energy Research co-sponsored by the Norwegian Research Council and research and industry partners in Norway and the Frienergi program. R.S. acknowledges the partial support from the EU 7th Framework Programme Project No. REGPOT-CT-2013-316014 (EAgLE).

¹C. F. Klingshirn, B. K. Meyer, A. Waag, A. Hoffmann, and J. Geurts, *Zinc Oxide From Fundamental Properties Towards Novel Applications* (Springer-Verlag, Berlin Heidelberg, 2010).

²C. Jagadish and S. J. Pearton, *Zinc Oxide Bulk, Thin Films and Nanostructures* (Elsevier, Oxford, 2006).

³S. Ramachandran, A. Tiwari, and J. Narayan, *Appl. Phys. Lett.* **84**, 5255 (2004).

⁴A. Tiwari, C. Jin, A. Kvit, D. Kumar, J. Muth, and J. Narayan, *Solid State Commun.* **121**, 371 (2002).

⁵K. Sakurai, M. Kanehiro, K. Nakahara, T. Tanabe, S. Fujita, and S. Fujita, *J. Cryst. Growth* **209**, 522 (2000).

⁶H. Kato, M. Sano, K. Miyamoto, and T. Yao, *J. Cryst. Growth* **265**, 375 (2004).

⁷H. Xu, K. Ohtani, M. Yamao, and H. Ohno, *Appl. Phys. Lett.* **89**, 071918 (2006).

⁸T. P. Smith, H. McLean, D. J. Smith, and R. F. Davis, *J. Cryst. Growth* **265**, 390 (2004).

⁹S. Heinze, A. Krtischil, J. Bläsing, T. Hempel, P. Veit, A. Dadgar, J. Christen, and A. Krost, *J. Cryst. Growth* **308**, 170 (2007).

¹⁰T. Ive, T. Ben-Yaacov, C. G. V. de Walle, U. K. Mishra, S. P. Denbaars, and J. S. Speck, *Phys. Status Solidi C* **6**, 1460 (2009).

¹¹C. Neumann, S. Lautenschläger, S. Graubner, J. Sann, N. Volbers, B. K. Meyer, J. Bläsing, A. Krost, F. Bertram, and J. Christen, *Phys. Status Solidi B* **244**, 1451 (2007).

¹²D. J. Rogers, F. H. Teherani, A. Largeau, G. Demazeau, C. Moisson, D. Turover, J. Nause, G. Garry, R. Kling, T. Gruber, A. Waag, F. Jomard, P. Galtier, A. Lussion, T. Monteiro, M. J. Soares, A. Neves, M. C. Carmo, M. Peres, G. Leronde, and C. Hubert, *Appl. Phys. A* **88**, 49 (2007).

¹³H. von Wenckstern, H. Schmidt, C. Hanisch, M. Brandt, C. Czekalla, G. Benndorf, G. Biehne, A. Rahm, H. Hochmuth, M. Lorenz, and M. Grundmann, *Phys. Status Solidi RRL* **1**, 129 (2007).

¹⁴L. Wachnicki, A. Duzynska, J. Z. Domagala, B. S. Witkowski, T. A. Krajewski, E. Przewdzicka, M. Guzewicz, A. Wierzbicka, K. Kopalko, S. Figge, D. Hommel, M. Godlewski, and E. Guzewicz, *Acta Phys. Pol. A* **120**, A7 (2011).

¹⁵H. Morkoç and Ü. Özgür, *Zinc Oxide: Fundamentals, Materials and Device Technology* (Wiley-VCH Verlag GmbH & Co., Weinheim, 2009).

¹⁶K. Ellmer, A. Klein, and B. Rech, *Transparent Conductive Zinc Oxide* (Springer-Verlag, Berlin, Heidelberg, 2008).

¹⁷S. Eisermann, J. Sann, A. Polity, and B. K. Meyer, *Thin Solid Films* **517**, 5805 (2009).

¹⁸A. Bikowski and K. Ellmer, *J. Appl. Phys.* **114**, 063709 (2013).

¹⁹I. Kim, S. Jeong, and B. Lee, *Semicond. Sci. Technol.* **22**, 683 (2007).

²⁰S. Zhu, C.-H. Su, S. L. Lehoczky, M. T. Harris, M. J. Callahan, P. McCarty, and M. A. George, *J. Cryst. Growth* **219**, 361 (2000).

²¹R. Schifano, M. Schofield, L. Vines, S. Diplas, E. V. Monakhov, and B. G. Svensson, *IOP Conf. Ser.: Mater. Sci. Eng.* **34**, 012007 (2012).

- ²²H. N. Riise, V. S. Olsen, A. Y. Azarov, A. Galeckas, T. N. Sky, B. G. Svensson, and E. V. Monakhov, *Thin Solid Films* **601**, 18 (2016).
- ²³J. A. Leavitt, L. C. McIntyre, M. D. Ashbaugh, J. G. Oder, Z. Lin, and B. Dezfouly-Arjomandy, *Nucl. Instrum. Methods Phys. Res., Sect. B* **44**, 260 (1990).
- ²⁴A. Y. Azarov, A. Hallén, B. Svensson, X. Du, and A. Y. Kuznetsov, *Nucl. Instrum. Methods B* **272**, 426 (2012).
- ²⁵See <http://www.srim.org/> for details on the SRIM code.
- ²⁶T. H. D. Keijser, J. I. Langford, E. J. Mittemeijer, and A. B. P. Vogels, *J. Appl. Cryst.* **15**, 308 (1982).
- ²⁷See <http://home.mpcdf.mpg.de/~mam/index.html> for details on the SIMRA code.
- ²⁸L. Vines, R. Schifano, M. Schofield, and B. G. Svensson, *Phys. Scr. T* **2012**, 014005.
- ²⁹A. Y. Azarov, A. Hallén, X. Du, P. Rauwel, A. Kuznetsov, and B. Svensson, *J. Appl. Phys.* **115**, 073512 (2014).
- ³⁰K. Maeda, M. Sato, I. Niikura, and T. Fukuda, *Semicond. Sci. Technol.* **20**, S49 (2005).
- ³¹M. Lorenz, G. Wagner, A. Rahm, H. Schmidt, H. Hochmuth, H. Schmid, W. Mader, M. Brandt, H. von Wenckstern, and M. Grundmann, *Phys. Status Solidi C* **5**, 3280 (2008).
- ³²M. A. Moram and M. E. Vickers, *Rep. Prog. Phys.* **72**, 036502 (2009).
- ³³P. F. Miceli and C. J. Palmström, *Phys. Rev. B* **51**, 5506 (1995).
- ³⁴M. W. Cho, A. Setiawan, H. J. Ko, S. K. Hong, and T. Yao, *Semicond. Sci. Technol.* **20**, S13 (2005).
- ³⁵M. Birkholz, *Thin Films Analysis by X-Ray Scattering* (Wiley-VCH Verlag GmbH & Co., Weinheim, 2006).
- ³⁶T. Metzger, R. Höpler, E. Born, O. Ambacher, M. Stutzmann, R. Stömmers, M. Schuster, H. Göbel, S. Christiansen, M. Albrecht, and H. P. Strunk, *Philos. Mag. A* **77**, 1013 (1998).
- ³⁷T. H. D. Keijser, E. J. Mittemeijer, and H. C. F. Rozendaal, *J. Appl. Cryst.* **16**, 309 (1983).
- ³⁸O. Durand, A. Letoublon, D. J. Rogers, and F. H. Teherani, *Thin Solid Films* **519**, 6369 (2011).
- ³⁹M. Guziewicz, R. Schifano, E. Przezdziecka, J. Z. Domagala, W. Jung, T. A. Krajewski, and E. Guziewicz, *Appl. Phys. Lett.* **107**, 101105 (2015).
- ⁴⁰R. Chierchia, T. Böttcher, H. Heinke, S. Einfeldt, S. Figge, and D. Hommel, *J. Appl. Phys.* **93**, 8918 (2003).
- ⁴¹J. F. Muth, R. M. Kolbas, A. K. Sharma, S. Oktyabrsky, and J. Narayan, *J. Appl. Phys.* **85**, 7884 (1999).
- ⁴²W. Zhang, Ph.D. thesis, Forschungszentrum Jülich GmbH, 2012.
- ⁴³R. Cebulla, R. Wendt, and K. Ellmer, *J. Appl. Phys.* **83**, 1087 (1998).
- ⁴⁴C. Jin, R. Narayan, A. Tiwari, H. Zhou, A. Kvit, and J. Narayan, *Mater. Sci. B* **117**, 348 (2005).
- ⁴⁵C. Kisielowski, J. Krüger, S. Ruvimov, T. Suski, J. W. Ager III, E. Jones, Z. Liliental-Weber, M. Rubin, E. R. Weber, M. D. Bremser, and R. F. Davis, *Phys. Rev. B* **54**, 17745 (1996).
- ⁴⁶A. Bikowski, T. Welzel, and K. Ellmer, *Appl. Phys. Lett.* **102**, 242106 (2013).
- ⁴⁷T. Ohnishi, A. Ohtomo, M. Kawasaki, K. Takahashi, M. Yoshimoto, and H. Koinuma, *Appl. Phys. Lett.* **72**, 824 (1998).
- ⁴⁸M. W. Allen, D. Y. Zemlyanov, G. I. N. Waterhouse, J. B. Metson, T. D. Veal, C. F. McConville, and S. M. Durbin, *Appl. Phys. Lett.* **98**, 101906 (2011).

PAPER VI

Thin film Cu₂O for solar cell applications

K. Bergum, H. N. Riise, S. Gorantla, E. Monakhov and B. G. Svensson

Conference record of the Photovoltaic Specialists Conference 2016 (2016)
2770

PAPER VII

Improving carrier transport in Cu_2O thin films by
rapid thermal annealing

K. Bergum, H. N. Riise, S. Gorantla, P. F. Lindberg, I. J. T. Jensen,
A. E. Gunnæs, A. Galeckas, S. Diplas, B. G. Svensson and E. Monakhov

Submitted to Journal of Physics: Condensed Matter

PAPER VIII

Strain induced defect ionization energy variation in Cuprous Oxide

H. N. Riise, K. Bergum, T. N. Sky, B. G. Svensson and E. Monakhov

In manuscript