UiO : **University of Oslo**

Ymir Kalmann Frodason

Hybrid functional investigations of point defects in ZnO and β -Ga₂O₃

Thesis submitted for the degree of Philosophiae Doctor

Department of Physics

Faculty of Mathematics and Natural Sciences

2020

© Ymir Kalmann Frodason, 2020

*Series of dissertations submitted to the
Faculty of Mathematics and Natural Sciences, University of Oslo
No. 2352*

ISSN 1501-7710

All rights reserved. No part of this publication may be
reproduced or transmitted, in any form or by any means, without permission.

Cover: Hanne Baadsgaard Utigard.

Print production: Reprosentralen, University of Oslo.

Acknowledgements

I would like to express my sincere gratitude to the many people that made this work possible. First and foremost, I want to thank my excellent supervisors Prof. Lasse Vines and Dr. Klaus Magnus Håland Johansen for providing steady guidance throughout this time. Your dedication, enthusiasm and curiosity as scientists inspired me to become immersed in my work. Besides all that you have taught me scientifically, you arranged for me to travel and connect with other researchers in the field. I am very grateful to have had you as my supervisors.

I am also grateful to my late supervisor Prof. Bengt Gunnar Svensson, who unfortunately left us under very sad circumstances in 2018. Bengt sparked my interest in semiconductor physics through his lectures. With his vast experience, he was an invaluable source of knowledge and inspiration. Bengt had an engaging personality and always carried a warm smile. He is deeply missed.

International collaboration had a very positive impact on this work, including visits to Prof. Audrius Alkauskas and Dr. Joel B. Varley. Thank you so much for sharing your knowledge on first-principles defect calculations, patiently answering my questions, and making me feel welcome when I visited your groups.

I would also like to thank the many people at the University of Oslo that I had the pleasure of collaborating with. A special thanks to Dr. Christian Z. for many scientific discussions, and our joint work on gallium oxide, which I found really exciting; Dr. Thomas N. S. and Dr. Alexander H. for our collaborations, and for helping me out with experiments; Dr. Tor S. Bjørheim for guidance, helpful discussions and feedback on manuscripts; Dr. Augustinas Galeckas for all the photoluminescence measurements you performed; and Marianne, my office mate for four years, for sharing many conversations and discussing ideas.

To all my colleagues at LENS, I would like to thank you for making it such a great community, both professionally and socially. I want to thank my family and friends for supporting and cheering me on, and, last but not least, I want to thank Oda for her love and encouragement—I love you!

Tusen takk!

• **Ymir Kalmann Frodason**
Oslo, December 2020

Preface

This thesis is submitted in partial fulfillment of the requirements for the degree of *Philosophiae Doctor* at the University of Oslo. The research presented here was mainly conducted at the University of Oslo, under the supervision of Prof. Lasse Vines, Dr. Klaus Magnus Håland Johansen and Prof. Bengt Gunnar Svensson. Part of the research was conducted at the Center for Physical Sciences and Technology (FTMC) under the supervision of Prof. Audrius Alkauskas, and at Lawrence Livermore National Laboratory (LLNL) under the supervision of Dr. Joel Basile Varley. Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (No. 251131, FriPro ToppForsk-program). The computations were performed on resources provided by UNINETT Sigma2 - the National Infrastructure for High Performance Computing and Data Storage in Norway.

The thesis is a collection of ten papers, presented in chronological order of writing. The papers are preceded by six introductory chapters that relate the papers together, and provide background information and motivation for the work. Chapter 1 introduces and motivates the research topic. Chapter 2 provides background information on the oxide semiconductors ZnO and β -Ga₂O₃, including basic materials properties, potential for applications in semiconductor devices, and a brief review of relevant previous studies of defects. Chapter 3 presents density functional theory and hybrid functionals, while the computational details and formalism for first-principles defect calculations are given in Chapter 4. Chapter 5 provides an overview of the results in the papers, followed by concluding remarks and suggestions for future work in Chapter 6.

List of Papers

Papers appended

Paper I

Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, A. Alkauskas “Zn vacancy as a polaronic hole trap in ZnO”. In: *Physical Review B*. Vol. 95, no. 9 (2017), pp. 094–105. DOI: 10.1103/PhysRevB.95.094105.

Contribution: Hybrid functional calculations with guidance from T.S.B. and A.A., calculation of luminescence lines with guidance from A.A., writing of manuscript with input from co-authors.

Paper II

Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, A. Alkauskas “Zn vacancy-donor impurity complexes in ZnO”. In: *Physical Review B*. Vol. 97, no. 10 (2018), pp. 104–109. DOI: 10.1103/PhysRevB.97.104109.

Contribution: Hybrid functional calculations with guidance from T.S.B. and A.A., calculation of luminescence lines with guidance from A.A., writing of manuscript with input from co-authors.

Paper III

Y. K. Frodason, K. M. Johansen, A. Alkauskas, L. Vines “Negative- U and polaronic behavior of the Zn-O divacancy in ZnO”. In: *Physical Review B*. Vol. 99, no. 17 (2019), pp. 174–106. DOI: 10.1103/PhysRevB.99.174106.

Contribution: Hybrid functional calculations and construction of configuration-coordinate diagrams with guidance from A.A., writing of manuscript with input from co-authors.

Paper IV

Y. K. Frodason, K. M. Johansen, A. Galeckas, L. Vines “Broad luminescence from donor-complexed Li_{Zn} and Na_{Zn} acceptors in ZnO”. In: *Physical Review B*. Vol. 99, no. 17 (2019), pp. 174–106. DOI: 10.1103/PhysRevB.100.184102.

Contribution: Hybrid functional calculations, calculation of luminescence lines, planning of experiments, sample preparation, writing of manuscript with input from co-authors.

Paper V

Y. K. Frodason, K. M. Johansen, L. Vines, J. B. Varley “Self-trapped hole and impurity-related broad luminescence in $\beta\text{-Ga}_2\text{O}_3$ ”. In: *Journal of Applied Physics*. Vol. 127, no. 7 (2020), pp. 075–701. DOI: 10.1063/1.5140742.

Contribution: Hybrid functional calculations and calculation of luminescence lines with guidance from J.B.V., writing of manuscript with input from co-authors.

Paper VI

C. Zimmermann, Y. K. Frodason, A. W. Barnard, J. B. Varley, K. Irmscher, Z. Galazka, A. Karjalainen, W. E. Meyer, F. D. Auret, L. Vines “Ti- and Fe-related charge transition levels in β -Ga₂O₃”. In: *Applied Physics Letters*. Vol. 116, no. 7 (2020), pp. 072–101. DOI: 10.1063/1.5139402.

Contribution: Hybrid functional calculations with guidance from J.B.V., discussion and analysis, contribution to writing and proof-reading of manuscript.

Paper VII

C. Zimmermann, Y. K. Frodason, V. Rønning, J. B. Varley, L. Vines “Combining steady-state photo-capacitance spectra with first-principles calculations: the case of Fe and Ti in β -Ga₂O₃”. In: *New Journal of Physics*. Vol. 22, no. 6 (2020), pp. 063–033. DOI: 10.1088/1367-2630/ab8e5b.

Contribution: Hybrid functional calculations and construction of configuration-coordinate diagrams with guidance from J.B.V., discussion and analysis, proof-reading of manuscript.

Paper VIII

C. Zimmermann, E. F. Verhoeven, Y. K. Frodason, P. M. Weiser, J. B. Varley, L. Vines “Formation and control of the E_2^* center in implanted β -Ga₂O₃ by reverse-bias and zero-bias annealing”. In: *Journal of Physics D: Applied Physics*. Vol. , no. (2020), pp. 5. DOI: 10.1088/1361-6463/aba64d.

Contribution: Discussion and analysis, proof-reading of manuscript.

Paper IX

Y. K. Frodason, C. Zimmermann, E. F. Verhoeven, P. M. Weiser, L. Vines, J. B. Varley “Multistability of isolated and hydrogenated Ga–O divacancies in β -Ga₂O₃”. *In manuscript*. (2020).

Contribution: Hybrid functional calculations and nudged elastic band calculations with guidance from J.V.B., writing of manuscript with input from co-authors.

Paper X

C. Zimmermann, E. F. Verhoeven, P. M. Weiser, Y. K. Frodason, J. B. Varley, I. Kolevator, L. Vines “Hydrogenation of β -Ga₂O₃: Influence on deep-level defects”. Submitted to *Physical Review Materials*. (2020).

Contribution: Hybrid functional calculations with guidance from J.B.V., discussion and analysis, contribution to writing and proof-reading of manuscript.

The published papers are reprinted with permission from APS Publishing, AIP Publishing and IOP Publishing. All rights reserved.

Related work by the author, not presented in the thesis

T. N. Sky, K. M. Johansen, Y. K. Frodason, T. Aarholt, H. N. Riise, Ø. Prytz, B. G. Svensson, L. Vines “Diffusion of indium in single crystal zinc oxide: a comparison between group III donors” In: *Semiconductor Science and Technology*. Vol. 34, no. 2 (2019), pp. 025–011. DOI: 10.1088/1361-6641/aafa4c.

T. N. Sky, K. M. Johansen, Y. K. Frodason, B. G. Svensson, L. Vines “The interaction between lithium acceptors and gallium donors in zinc oxide” In: *Journal of Applied Physics*. Vol. 124, no. 24 (2018), pp. 245–702. DOI: 10.1063/1.5063326.

T. Aarholt, Y. K. Frodason Ø. Prytz “Imaging defect complexes in scanning transmission electron microscopy: Impact of depth, structural relaxation, and temperature investigated by simulations” In: *Ultramicroscopy*. Vol. 209, (2019), pp. 112–884. DOI: 10.1016/j.ultramic.2019.112884.

M. E. Bathen, J. Coutinho, H. M. Ayedh, J. Ul Hassan, I. Farkas, S. Öberg, Y. K. Frodason, B. G. Svensson, and L. Vines “Anisotropic and plane-selective migration of the carbon vacancy in SiC: Theory and experiment” In: *Physical Review B*. Vol. 100, no. 1 (2019), pp. 014–103. DOI: 10.1103/PhysRevB.100.014103.

M. E. Bathen, A. Galeckas, J. Müting, H. M. Ayedh, U. Grossner, J. Coutinho, Y. K. Frodason, L. Vines “Electrical charge state identification and control for the silicon vacancy in 4H-SiC” In: *npj Quantum Information*. Vol. 5, no. 111 (2019), DOI: 10.1038/s41534-019-0227-y.

C. Zimmermann, V. Rønning, Y. K. Frodason, V. Bobal, J. B. Varley, L. Vines “Primary intrinsic defects and their charge transition levels in β -Ga₂O₃”. In: *Physical Review Materials*. Vol. 4, no. 7 (2020), pp. 074–605. DOI: 10.1103/PhysRevMaterials.4.074605.

J. Borgersen, L. Vines, Y. K. Frodason, A. Kuznetsov, H. von Wenckstern, M. Grundman, M. W. Allen, J. Zuniga-Pérez, K. M. Johansen “Experimental exploration of the amphoteric defect model by cryogenic ion irradiation of a range of wide band gap oxide materials” In: *Journal of Physics: Condensed Matter*. Vol. , no. (2020), DOI: 10.1088/1361-648X/abac8b.

V. M. Reinertsen, P. M. Weiser, Y. K. Frodason, M. E. Bathen, L. Vines, K. M. Johansen “Anisotropic and trap-limited diffusion of hydrogen/deuterium in monoclinic gallium oxide”. Submitted to *Applied Physics Letters* Special Topic on Ultrawide Bandgap Semiconductors. (2020).

List of Papers

Y. K. Frodason, M. E. Bathen, A. J. Hupfer, L. Vines, C. Persson “Hydrogen clustering at cation vacancies in covalent semiconductors: Stabilization by self-passivation”. *In manuscript*. (2020).

Contents

Preface	iii
List of Papers	v
Contents	ix
1 Introduction	1
2 Oxide Semiconductors	5
2.1 Zinc oxide	5
2.2 Gallium sesquioxide	10
3 Density Functional Theory	17
3.1 The many-body problem	17
3.2 Density functional theory and the Kohn-Sham equation . .	18
3.3 Conventional functionals and their shortcomings	19
3.4 Hartree-Fock theory and hybrid functionals	20
4 Point defect calculations	25
4.1 Computational details and the supercell approach	25
4.2 Defect formation energies	26
4.3 Thermodynamic charge-state transition levels	28
4.4 Configuration coordinate diagrams	30
4.5 Dealing with supercell finite-size errors	34
5 Summary of Results	39
5.1 Small hole polarons and polaronic acceptors	40
5.2 Charge-state transition levels of Fe and Ti impurities . . .	50
5.3 Negative- U behavior of O vacancies and divacancies	54
6 Conclusions and outlook	63
References	67
Papers	82
I Zn vacancy as a polaronic hole trap in ZnO	83
II Zn vacancy-donor impurity complexes in ZnO	93

III	Negative- U and polaronic behavior of the Zn-O divacancy in ZnO	103
IV	Broad luminescence from donor-complexed Li_{Zn} and Na_{Zn} acceptors in ZnO	113
V	Self-trapped hole and impurity-related broad luminescence in $\beta\text{-Ga}_2\text{O}_3$	127
VI	Ti- and Fe-related charge transition levels in $\beta\text{-Ga}_2\text{O}_3$	139
VII	Combining steady-state photo-capacitance spectra with first-principles calculations: the case of Fe and Ti in $\beta\text{-Ga}_2\text{O}_3$	147
VIII	Formation and control of the E_2^* center in implanted $\beta\text{-Ga}_2\text{O}_3$ by reverse-bias and zero-bias annealing	165
IX	Multistability of isolated and hydrogenated Ga-O divacancies in $\beta\text{-Ga}_2\text{O}_3$	177
X	Hydrogenation of $\beta\text{-Ga}_2\text{O}_3$: Influence on deep-level defects	193

Chapter 1

Introduction

Point defects in semiconductors

Point defects are zero-dimensional structural imperfections in a crystal lattice, such as a missing atom (vacancy), an atom located at a site that is not normally occupied (interstitial), or the presence of a foreign atom (impurity)¹. In the model of the ideal crystal, every constituent atom resides at its prescribed lattice site, and there are no defects. In real crystals, however, the incorporation of a certain equilibrium concentration of defects is energetically favored due to the configurational entropy [1]. Interestingly, these unavoidable imperfections do not merely alter the local crystal structure, but can have a profound impact on the macroscopic physical properties of the host, even to the point of determining its functionality. An extraordinary example is the effect of defects on the electrical conductivity of semiconductors. The introduction of shallow donors or acceptors—defects that can easily release electrons (n) or holes (p) to the host, respectively—can be used to tune the electrical conductivity across several orders of magnitude. Controllably fabricated n - and p -type conductive layers serve as building blocks for making the (opto)electronic semiconductor devices that we rely on today. Control is a key point here, as a wide variety of defects can form, in addition to those incorporated intentionally, and have undesired effects. For example, some defects introduce energy levels deep within the forbidden electronic band gap, which can act as efficient recombination centers. Such defects can be detrimental to device performance, e.g., by annihilating photogenerated electron-hole pairs in solar cells or by offering nonradiative recombination routes in light-emitting diodes (LEDs). However, deep-level defects can also be functionalized for applications, e.g., as luminescence centers that emit or absorb light at specific wavelengths, as compensating centers to produce semi-insulating material for use as buffer layers in devices, or as artificial atoms to serve as qubits in future quantum information technology [2]. Defects are also important for fundamental processes like solid-state diffusion, serving as vehicles for atomic diffusion. Defects can indeed be both constructive and destructive, depending on the application, and the key to utilizing defects as enablers is control.

Motivation for the present work

Semiconducting materials have been at the core of technological advances that have revolutionized our society, and will play an increasingly important role as part of the green shift. When it comes to technological maturity, no other

¹In the following, the word defect will refer specifically to a point defect, as extended defects (like dislocations, grain boundaries, clusters) are outside the main scope of this thesis.

semiconductor comes close to silicon (Si). Decades of research have allowed a superb control of defects and processing, growth of nearly flawless crystals, and tuning of the electrical conductivity and electronic structure. However, Si is approaching the pinnacle of its performance, and fundamental limitations on its materials properties mean that certain applications are out of reach. For instance, the indirect band gap energy of 1.1 eV leads to poor light absorption and radiative recombination efficiency, making its applications in optoelectronics limited. Of course, this has not stopped Si from playing a dominant role in the photovoltaics industry, underlining the importance of technological maturity and cost. More recently, compound semiconductors, especially the group III-Nitrides, including gallium nitride (GaN), aluminium nitride (AlN) and indium nitride (InN), have seen large-scale commercial success in energy-efficient optoelectronic devices. This success culminated in the Nobel prize in physics in 2014, awarded to Akasaki, Amano and Nakamura for inventing the GaN-based blue LED.

Oxide semiconductors, including the zinc oxide (ZnO) and monoclinic gallium sesquioxide (β -Ga₂O₃) studied in the present thesis, are widely recognized as prime materials for future technology to harvest, deliver, convert and store energy in an efficient manner. While generally being abundant, environmentally friendly, and chemically robust, they exhibit a diverse set of functional properties, most notably a wide range of band gap energies. This makes them attractive for applications in several different technology fields, e.g., photovoltaics, LEDs, power electronics, photodetectors, fuel cells, batteries and photocatalysis. However, all of those applications require control over the defect structure, which has proven to be challenging for this materials system. Indeed, most oxide semiconductors exhibit an asymmetry with respect to doping, e.g., ZnO and β -Ga₂O₃ show a preference towards *n*-type conductivity, where even as-grown crystals typically exhibit an unintentional *n*-type conductivity. Moreover, intentional doping can be counteracted by compensating intrinsic defects, which limits the doping efficiency, e.g., cation vacancies act as compensating acceptors in *n*-type doped ZnO and β -Ga₂O₃. Thus, while this materials system exhibits attractive intrinsic properties, its amenability for device applications is currently limited due to insufficient control and understanding of the defect structure.

Defect control requires accurate knowledge of the identity and characteristics of defects, how they are incorporated, and how they affect the materials properties. A wide variety of electrical, optical and magnetic characterization techniques have been developed to study defects in semiconductors. However, identification and characterization of defects based on experimental techniques alone is often very demanding and time-consuming, and conclusive answers often require clever combinations of different techniques [3]. With the rapid advances in computational and electronic structure methods, it is now feasible to predict many materials properties directly from the fundamental Schrödinger equation (within a set of approximations), i.e., from *first-principles*. Approaches based on the density functional theory (DFT) are among the most popular electronic structure methods, and are nowadays used routinely in several different fields within chemistry and materials science. This includes defects in semiconductors, where it has proven to be a valuable aid, both as a predictive tool to complement

and guide experimental studies, and by providing novel insights [4]. A well-established thermodynamic formalism has been developed to study the physical properties of defects from electronic structure calculations [3].

However, when applied to oxide semiconductors, first-principles modeling of defects has until recently had only limited success. Indeed, the conventional semilocal approximations to the exchange-correlation functional suffer from so-called delocalization errors, which result in a general underestimation of band gaps and a poor description of localized defect states [3]. These errors are particularly severe for oxides, as they typically exhibit wide band gaps and deep-level defects with a high degree of charge localization. More recently, hybrid functionals that combine DFT and Hartree-Fock theory have provided a way to overcome the abovementioned limitations of conventional DFT, allowing more accurate predictions of defect properties [5–9], albeit at a higher computational cost. Furthermore, recent methodological advances, particularly based on the calculation of one-dimensional (1D) configuration coordinate (CC) diagrams for defect charge-state transitions [10], have allowed increasingly detailed and direct comparisons with experimental data [11–14]. Such comparisons can provide valuable information to reveal the defect origin of signatures observed in experimental defect spectroscopic techniques, as well as important feedback with regards to the limitations of the employed electronic structure method.

In the present work, hybrid functional calculations have been applied to investigate point defects in ZnO and β -Ga₂O₃. The combination of theory and experiment described above is a major theme in the thesis. Notably, the 1D CC model has been used to predict defect properties related to charge-state transitions involving defects, including radiative and nonradiative capture and emission of charge carriers [4]. Papers I, II, IV and V investigate small hole polarons, polaronic acceptors, and their complexes with shallow donor impurities in ZnO and β -Ga₂O₃. The main focus of these papers is the simulation of luminescence lines resulting from radiative transitions involving polaronic defect states, which can be compared directly with experimental luminescence spectroscopy. Papers VI and VII identify thermodynamic and optical charge-state transition levels of Ga substitutional Fe and Ti impurities in β -Ga₂O₃, which are technologically important impurities in this material. Finally, Papers III, IX and X investigate the thermodynamic and electronic properties of close-associate cation-oxygen divacancies in ZnO and β -Ga₂O₃ (the experimental results in Paper VIII provided motivation for Paper IX). Interestingly, the divacancies are shown to be highly electrically active, retaining key properties of their monovacancy constituents, namely the polaronic nature of the cation vacancy, and the negative- U behavior of the oxygen vacancy.

Chapter 2

Oxide Semiconductors

Zinc oxide (ZnO) and monoclinic gallium sesquioxide (β -Ga₂O₃) are members of the oxide semiconductor family. Both materials hold great promise for next-generation optical, electrical and energy applications, but they are not new. The lattice parameters of wurtzite ZnO were reported already in 1935 [15], and various materials characterization was done in the 1950-1960s [16], coinciding with early reported studies on β -Ga₂O₃ crystals [17–19]. However, as evidenced by the increasing number of publications per year, shown in Fig. 2.1, both materials have recently seen a rapid surge of interest. For both materials, this interest has been sparked by a combination of unique materials properties, and availability of relatively inexpensive high-quality single-crystal substrates. The following subsections will provide information on their basic properties, potential for applications, and a brief review of reported studies on point defects.

Figure 2.1: Number of articles containing the words ZnO or Zinc Oxide (red) and Ga₂O₃ or Gallium Oxide (green) in the title. Data from *Web of Science*.

2.1 Zinc oxide

Basic properties and applications

ZnO is a binary group II–VI compound semiconductor. The hexagonal wurtzite crystal structure (space group 186, $P6_3mc$) is the thermodynamically stable phase under typical growth conditions, but zinc blende and rocksalt structures can be obtained through growth on cubic substrates and under high pressure,

2. Oxide Semiconductors

respectively [16]. Only the wurtzite structure, shown in Fig. 2.2, is considered here. The primitive unit cell contains four basis atoms, and has one basal ($a = 3.24 \text{ \AA}$) and one axial ($c = 5.19 \text{ \AA}$) lattice parameter [20]. The c/a ratio of 1.603 deviates from the ideal one of 1.633 for the hexagonal close-packed structure. The lack of an inversion plane perpendicular to the c axis results in crystallographic polarity [21]. ZnO in the (0001) orientation can have two different surface terminations, Zn or O, which are conventionally referred to as (0001) and (000 $\bar{1}$) ZnO, respectively [21]. Each Zn (O) is surrounded by four O (Zn) with approximate tetrahedral (T_d) local point group symmetry. The Zn–O bond along the c axis is denoted as axial (ax), and is slightly longer than the three Zn–O bonds in the basal plane, denoted as azimuthal (az) or non-axial. This slight difference lowers the local point group symmetry from T_d to C_{3v} . In addition to the primitive unit cell, an orthorhombic cell is shown in Fig. 2.2, because it was used to construct the 96-atom supercell used for the first-principles defect calculations (this is discussed in Sec. 4.1).

Figure 2.2: Ball-and-stick model of the primitive (left) and an orthorhombic (middle) ZnO unit cell, where Zn/O atoms are represented by the grey/red balls. The polyhedra (right) show the approximately tetrahedral local symmetry of the Zn and O sites. Lattice parameters [20] and bond lengths are shown. The figure was generated using the crystal structure visualization software VESTA [22].

Regarding the electronic structure, ZnO exhibits a direct band gap at the Γ -point with an experimental value of 3.44 eV, as determined from optical measurements at 2 K [23]; this band gap value includes the large free exciton binding energy of about 60 meV. Theoretical electronic structure calculations show that the upper part of the valence band (VB) of ZnO is mainly composed of O $2p$ states, whereas the lowest conduction band (CB) states are mainly derived from Zn $4s$ states [3, 24]. The experimentally determined values for the static dielectric constant are $\epsilon_0 = 7.77$ and 8.91 in the directions perpendicular and parallel to the c -axis, respectively; the corresponding high-frequency values are $\epsilon_\infty = 3.70$ and 3.78 [25]. ZnO can be doped n -type by a wide range of elements, including Zn substitutional (Al, Ga, In, Si, Ge and B) and O substitutional

(Cl, F) donors [26]. Among these dopants, Al and Ga are the most commonly used, with reported resistivities in the low $10^{-4} \Omega \text{ cm}$ for intentionally doped samples [27, 28]. As already mentioned, oxide semiconductors normally exhibit an asymmetry with respect to doping, and achieving stable, reliable and efficient *p*-type conductive ZnO has so far eluded researchers. Zn substitutional Li (Li_{Zn}) and O substitutional N (N_{O}) acceptors have long been touted as promising candidates, but have been unsuccessful so far. Understanding and overcoming the *p*-type obstacle of ZnO remains a subject of research, but is not studied as intensively nowadays. Interestingly, a recent theoretical study by Goyal *et al.* [29] shows that the rocksalt phase of ZnO is *p*-type dopable by Li_{Zn} .

Achieving *p*-type ZnO would certainly unlock some highly attractive applications, especially as an alternative or complement to GaN-based optoelectronics. In fact, GaN and ZnO share many relevant features, including the same crystal structure, similar band gap energies, and possibilities for band gap engineering by alloying with AlN/InN and CdO/MgO, respectively. Actually, efficient *p*-type doping is also a challenge for GaN. There is only one moderately effective dopant (on which the entire GaN-based optoelectronics industry hinges), namely Mg, which reportedly exhibits a dual (shallow and deep) nature [30, 31]. However, ZnO has some advantages, such as a greater exciton binding energy, amenability to wet chemical etch processing, and less demanding single-crystal growth [32]. Thus, should *p*-type ZnO be achieved, it would likely result in optoelectronic devices that are both cheaper and more efficient than those based on GaN.

Despite the lack of *p*-type material, ZnO shows high potential for unipolar device applications. Notably, the large band gap energy, high level of *n*-type conductivity, and availability of large-scale thin film deposition techniques makes it useful as a transparent conductive oxide (TCO). TCOs are used as transparent electrodes in, e.g., liquid crystal displays, touchscreens and solar cells. At present, indium tin oxide (ITO) is the most commonly used TCO, but alternatives are being explored due to concerns about the cost of In, which is especially problematic for large area applications such as solar cells. Al or Ga doped ZnO is considered as a viable option [33, 34], and is already used routinely in, e.g., thin film solar cells based on $\text{Cu}(\text{In,Ga})\text{Se}_2$ [35]. However, improved control of the *n*-type conductivity is desired. For example, sputter deposited films show spatial inhomogeneity in the resistivity [36]. Furthermore, it has been shown that Al and Ga doping leads to self-compensation, imposing an upper limit on the conductivity. Isolated Zn vacancy (V_{Zn}) acceptors and their complexes with donor dopants have been shown to play an important role in this compensation [37–40], and such defects have been explored in the present work. Finally, it should be noted that there is significant interest in ZnO beyond the solid-state physics and electronics community. Notably, nanostructured ZnO is a highly active research field, with many nanomorphologies available [32].

Crystal growth, impurities and defects

Focusing on single-crystal material, ZnO is primarily grown using one of three different methods: (i) pressurized melt growth (MG), (ii) vapor phase (VP)

growth, and (iii) hydrothermal (HT) solution growth [26]. MG ZnO is achieved by using a modified Bridgman process, where ZnO powder in a crucible is heated above its melting point of 1975 °C, under an overpressure of oxygen to prevent decomposition, and then slowly cooled to allow crystallization [41]. MG ZnO has the advantage of high growth rate (1–5 mm/h for ingots with diameters up to 50 mm [41]), but spatial variation in crystal quality due to large temperature gradients is an issue that can result in low-angle grain boundaries [26]. During VP growth, ZnO powder is sublimed, followed by transport and deposition onto a seed crystal. The preferred method is seeded chemical vapour transport (SCVT), where hydrogen is used as a carrier gas to decompose ZnO at temperatures above 1150 °C and transport it to a growth zone with lower temperature [26]. High crystal quality can be achieved by VP growth, but the low growth rate (e.g., 1 mm/day [26]) is a major drawback. HT ZnO is grown at relatively low temperatures (300–400 °C) and a high pressure (about 80 GPa) from a supercritical aqueous solution, which contains mineralizers (typically a mixture of LiOH and KOH) to increase the solubility of ZnO [26]. The HT method is scalable, and produces crystals of excellent quality, but they usually show a high residual content of Li, which acts as a compensating acceptor (Li_{Zn}) [26].

As-grown ZnO crystals normally show n -type conductivity. Historically, the O vacancy (V_{O}) was frequently assumed to be the source of this unintentional conductivity, but presently there is broad consensus that residual shallow donor impurities are responsible [42, 43]. Indeed, photo-EPR measurements on electron-irradiated ZnO, e.g., by Evans *et al.* [44], provides strong experimental evidence for the deep donor nature of V_{O} , which means that it cannot cause n -type conductivity. Meanwhile, electron-nuclear double resonance (ENDOR) measurements have provided unambiguous proof that Zn substitutional Al (Al_{Zn}) is a shallow single donor [45]. Furthermore, electron paramagnetic resonance (EPR) and secondary ion mass spectrometry (SIMS) studies have established a correlation between Al_{Zn} and the neutral-donor-bound exciton line labeled I_6 , as observed by photoluminescence (PL) spectroscopy [45–47]. Similarly, the shallow single donors Ga_{Zn} and In_{Zn} have been assigned to exciton lines labeled I_8 and I_9 , respectively [47–49]. Hybrid functional calculations additionally show that Si_{Zn} and Ge_{Zn} act as shallow double donors. According to SIMS data [26, 50], Al and Si are common impurities for all of the growth techniques mentioned above, with typical concentrations in the $10^{15} - 10^{17} \text{ cm}^{-3}$ range.

Hydrogen is an omnipresent impurity that can also contribute to the unintentional conductivity. Indeed, increased n -type conductivity after diffusing H into ZnO was reported already in the 1950s [51]. A theoretical study by Van de Walle *et al.* [52] later showed that H interstitials (H_{i}) act exclusively as shallow donors, which is unusual because H is normally found to be amphoteric in most semiconductors [42]. This prediction was soon after confirmed by Muon spin rotation and magnetic resonance experiments [53, 54]. However, H_{i} is highly mobile, even at room temperature [55], with reported migration barriers of $0.85 \pm 0.19 \text{ eV}$ based on deuterium diffusion experiments [56] and $0.5 \pm 0.1 \text{ eV}$ based on nudged elastic band calculations [57]. Hence, thermally stable H donors are more likely to be trapped by other defects. Notably, O substitutional H

(H_O) has been theoretically predicted to act as a shallow single donor [58]. This has been supported by experiments performed by Lavrov *et al.* [59], where H_O was assigned to the exciton line labeled I_4 . H is also known to form complexes with and passivate compensating acceptors. For example, $V_{\text{Zn}}n\text{H}$ complexes with $n = 1, 2, 3$ have been observed by infrared (IR) [60–64] and EPR [44, 65] spectroscopy. The concentration of H in as-grown material is normally below the SIMS detection limit of $5 \times 10^{17} \text{ H cm}^{-3}$, and depends on the growth method. Despite the high growth temperatures, some H is incorporated into MG ZnO from the precursor material as the growth system is closed [66]. This is evident from the presence of the I_4 line [47, 66]. The use of H as a carrier gas leads to a higher H content in SCVT ZnO; based on ENDOR and Hall measurements, Hofmann *et al.* [54] reported a concentration of $6 \times 10^{16} \text{ cm}^{-3}$ for the so-called *D1* donor (assigned to H) in a SCVT sample grown by Eagle-Picher. H is also present in HT ZnO, as evidenced by the presence of a dominant O–H related IR absorption line at 3577 cm^{-1} , which has been attributed to the $\text{Li}_{\text{Zn}}\text{H}$ complex [67–69]. Interestingly, the emergence of O–H related IR absorption lines upon annealing as-grown ZnO without an external source of H has led to suggestions that there is a H source in ZnO that is concealed from IR spectroscopy. Interstitial H_2 molecules have been proposed as a candidate for this “hidden hydrogen” [70].

Li is another important impurity in ZnO, and is predominantly present in HT grown material (from the LiOH mineralizer) with typical concentrations of about 10^{17} cm^{-3} according to SIMS data [26]. The behavior of Li in ZnO has long been a subject of interest, both from a scientific and technological point of view. Li exhibits an electrically amphoteric behavior, acting as a Li_i donor or a Li_{Zn} acceptor depending on the Fermi level position. The Li_{Zn} configuration is dominant in HT grown ZnO [71], where it acts as a compensating acceptor. For this reason, HT grown material is often resistive [72]. Many initial attempts to produce *p*-type ZnO involved Li_{Zn} as a potential shallow donor, but there is now broad consensus that it introduces a deep rather than a shallow acceptor level [73–75], as was suggested by EPR experiments already in the 1960s [76]. Indeed, the EPR results indicated that the neutral charge state of Li_{Zn} corresponds to a hole that is highly localized at one of the O ions adjacent to Li, as also predicted by contemporary first-principles defect calculations [73, 77].

Certain transition metal impurities are also commonly found in ZnO, most notably Fe [50, 72]. EPR signals from Mn^{2+} , Co^{2+} , Fe^{3+} and Ni^{3+} have been observed in HT ZnO [78]. Note that the oxidation state notation is normally used in the context of magnetic resonance, e.g., Fe^{3+} corresponds to Fe_{Zn}^+ . Fe acts as a deep donor and has been assigned to a defect level labeled E_2 , which is located about 0.19 eV below the CB, as observed by deep-level transient spectroscopy (DLTS) [79]. This is close to the 0.24 eV deduced from the temperature dependence of the Fe^{3+} EPR signal [78]. As a donor, Fe_{Zn} has been found to form a complex with Li_{Zn} , which is present in HT grown ZnO [80].

There is a plethora of first-principles studies on native defects in ZnO in the literature (see, e.g., the review in Ref. [42] and references therein). Even though the results scatter widely, most studies (spanning several different levels of theory) qualitatively agree that V_{O} is a deep negative- U (explained in Sec.

5.3.2) donor, V_{Zn} is a deep double acceptor, Zn_i is a shallow double donor, and O_i in the octahedral site is a deep double acceptor [24, 42, 43, 81]. The interstitials are not expected to play an important role in n -type material due to exceedingly high formation energies and low migration barriers. The antisites (Zn_{O} and O_{Zn}) similarly exhibit high formation energies, and are thus not usually considered [24, 43]. Focusing our attention on the more recent calculations based on hybrid functionals, the formation energy of V_{O} , and especially V_{Zn} , is low enough to allow high equilibrium concentrations in Zn- and O-rich growth/annealing environments, respectively. However, relatively low concentrations of isolated vacancies are expected under realistic single-crystal growth conditions [82], at least when compared to the typical impurity content. This is supported by EPR and positron annihilation spectroscopy (PAS) measurements on different as-grown ZnO samples [39, 83, 84]. In EPR studies of V_{O} and V_{Zn} , the vacancies are usually introduced by high-energy electron irradiation [44, 85, 86]. However, as mentioned above, V_{Zn} (and its complexes with donor impurities) play an important role as a source of self-compensation when ZnO is doped n -type.

Despite the large body of work on defects in ZnO, there are still controversies surrounding the defect identity of many spectroscopic signatures. For example, the PL spectrum of ZnO normally shows a broad green luminescence (GL), which consists of several overlapping luminescence bands. Reschikov *et al.* [87, 88] have compiled detailed information on the characteristics of several unique PL bands observed in different samples. However, only a few of those bands have been firmly identified. The orange luminescence (OL) band peaking at 1.95 eV has been attributed to Li_{Zn} [89], and the characteristic fine-structured GL band peaking at 2.47 eV has been attributed to Cu_{Zn} [90, 91]. The OL band is observed in HT ZnO, but is overlapped by a broad GL band of unknown origin [75], which was investigated in the present thesis. There are also several commonly observed DLTS defect signatures that remain unidentified [92]. Most relevant for this work is the defect level labeled E_4 , which is located ~ 0.55 eV below the CB, and frequently associated with a V_{O} -related defect exhibiting Negative- U behavior [92, 93]. The E_3 level, located ~ 0.3 eV below the CB, is another prominent signature that can be found in most ZnO samples, regardless of growth method. Recent studies on E_3 indicate a H-related origin [55, 94].

2.2 Gallium sesquioxide

Basic properties and applications

At least five different polymorphs exist for crystalline Ga_2O_3 , including corundum α - Ga_2O_3 (space group 161, $R3c$), monoclinic β - Ga_2O_3 (space group 12, $C2/m$), defective-spinel γ - Ga_2O_3 (space group 227, $Fd\bar{3}m$), bixbyite δ - Ga_2O_3 (space group 227, $Fd\bar{3}m$) and orthorhombic κ - Ga_2O_3 (space group 33, $Pna2_1$) structures [17, 95]. A sixth hexagonal ε - Ga_2O_3 polymorph (space group 186, $P6_3mc$) has also been reported, but was recently identified as κ - Ga_2O_3 exhibiting pronounced disorder [95]. Moreover, the orthorhombic phase is interchangeably denoted by κ and ε in the literature [95, 96]. This thesis explores only the β - Ga_2O_3 structure,

which is the thermodynamically stable phase under typical growth conditions, and has received the bulk of recent attention. Figure 2.3 shows the conventional unit cell of β -Ga₂O₃, which contains 20 atoms (the primitive unit cell contains 10), and is characterized by the lattice parameters $a = 12.23 \text{ \AA}$, $b = 3.04 \text{ \AA}$ and $c = 5.80 \text{ \AA}$, and the angle of $\beta = 138.8^\circ$ between the a and c axes [97]. The local symmetry of the five nonequivalent lattice sites is also shown in Fig. 2.3. There is one fourfold- (Ga1) and one sixfold-coordinated (Ga2) Ga site. One of the three O sites is fourfold-coordinated (O3), while the other two (O1 and O2) are threefold-coordinated, where O2 is almost planar. The increased number of lattice sites and low degree of symmetry generally means that a larger number defect configurations have to be considered in β -Ga₂O₃ compared to ZnO.

Figure 2.3: Left: Ball-and-stick model of the conventional β -Ga₂O₃ unit cell, where Ga/O atoms are represented by the green/red balls. Lattice parameters and angles are shown. Right: Polyhedra showing the local symmetry of the five different lattice sites, with bond lengths and sites indicated.

The electronic band structure of β -Ga₂O₃ exhibits a fundamental band gap value of around 4.9 eV [98–104]. Because of the low symmetry of the monoclinic structure, the optical absorption strongly depends on the polarization of the light [100, 102, 105, 106]. Schubert *et al.* [107] reported experimental values for the static and high frequency dielectric tensor, and there are several theoretical studies on the nature of single-electron and excitonic band-to-band transitions [101–103]. Figure 2.4 shows the electronic band structure, calculated using a hybrid functional (in good agreement with the one reported in Ref. [108]). The VB is mainly composed of O 2p states, while the CB is predominantly derived from Ga 4s orbitals. As highlighted by the red and green dots, the CB minimum (CBM) is located at the Γ -point, and the VB maximum (VBM) occurs at a low-symmetry point that is only slightly higher in energy compared to the Γ -point value [103, 108, 109]. Thus, β -Ga₂O₃ can basically be considered as a direct band gap material. Notably, the VB shows very little dispersion compared to the

CB; this is a common feature for all polymorphs, where some exhibit even flatter VBs [108]. This results in a large hole effective-mass, high VB density of states, and the formation of small hole polarons [110], as discussed in more detail in Sec. 5.1. This behavior, in addition to the lack of shallow acceptor dopants [111], likely poses an insurmountable obstacle for efficient *p*-type doping of β -Ga₂O₃ [110] (and the other polymorphs [108]). However, similar to ZnO, *n*-type doping of β -Ga₂O₃ can be easily achieved, where Ga substitutional Group-IV elements (Si, Sn and Ge) have been demonstrated to be effective *n*-type dopants [112, 113]. It has also been reported that C [114], and certain transition metal elements like Nb, Ta, Zr, and Hf can act as shallow donors on the Ga site [115, 116]. Carrier concentrations up to 10^{19} cm^{-3} and electron mobilities close to the theoretical limit of $\sim 200 \text{ cm}^2/\text{V}$ due to phonon scattering have been achieved [117].

Figure 2.4: Band structure of β -Ga₂O₃, calculated using the Heyd-Scuseria-Ernzerhof hybrid functional with the fraction of screened Hartree-Fock exchange adjusted to 0.33, and the semicore *d*-electrons included as valence states. The VB and CB is represented by blue and orange lines, respectively, and the band edges are highlighted. The band structure path and symmetry points are based on the **SeeK-path** algorithm [118], and was generated using the **sumo** code [119].

The availability of relatively cheap, high-quality and large-area single-crystal substrates, as well as the high level of *n*-type conductivity and ultra-wide band gap, makes β -Ga₂O₃ a highly attractive material for unipolar devices in power electronics that can operate at high voltages and frequencies. The suitability of materials for power devices is often expressed by a figure of merit (e.g., Baliga or Johnson), which incorporates the major requirements for efficient power devices, including (i) low on-state resistance (ii) low off-state leakage current, (iii) fast switching recovery time, (iv) large breakdown voltage, and (v) operation at high temperatures [120]. The reported values for the figure of merit of β -Ga₂O₃ suggest that it can outperform big players like Si, GaN and SiC for many applications [121]. Notably, the breakdown electric field of

β -Ga₂O₃ is estimated to be 5–9 MV/cm [122], which is a few times higher than the values reported for GaN and SiC. In the renewable energy transition, harvesting and storage technologies such as solar cells and batteries have received much attention, but improving the conversion efficiency in power electronics can potentially save a tremendous amount of energy, which is also very important. Functional power devices based on β -Ga₂O₃, including switching transistors and rectifying diodes, are currently being developed at an exciting pace. The first metal-semiconductor field-effect transistor based on single-crystal β -Ga₂O₃ was developed in 2011 [123]. Since then, several structures have been developed (as reviewed in Ref. [124]), e.g., Schottky barrier diodes [125] and metal-oxide semiconductor field-effect transistors [126]. One major weakness of β -Ga₂O₃ for power devices is the low thermal conductivity, with reported experimental values in the 0.1–0.3 W/cm K range at room temperature, which is an order of magnitude lower than for SiC and GaN. Hence, thermal management and packaging solutions to improve heat dissipation are required.

The ultra-wide band gap also makes β -Ga₂O₃ attractive for deep ultraviolet (UV) photodetectors for the 200–280 nm range [127]. Finally, alloying β -Ga₂O₃ with Al ([Al_xGa_{1-x}]₂O₃) has also attracted interest as an *n*-type dopable system with band gap engineering possibilities [116]. Indeed, the thermodynamically stable corundum α -Al₂O₃ phase exhibits a band gap of 8.82 eV [104, 128]. Such alloys could enable even higher breakdown electric fields in power electrons, or be used in modulation-doped Ga₂O₃/Al₂O₃ heterostructures [129].

In order to bring out the full potential of β -Ga₂O₃, improving control of the conductivity and defects is critically important. This includes, e.g., finding the most suitable dopants, and identifying prominent deep-level defects. The latter can be harmful during device operation, for example by pinning the Fermi level, increasing the on-resistance, lowering the breakdown voltage, acting as efficient recombination centers, and influencing transport through charge carrier scattering. Unwanted deep-level defects can be present in as-grown material, or be introduced during fabrication or operation, for instance by diffusion between different layers in devices. As an example, McGlone *et al.* [130] recently found that the so-called E_2^* signature observed by DLTS is limiting the performance of field-effect transistors based on β -Ga₂O₃. This defect signature was investigated in Papers. VIII and IX. The defect structure of β -Ga₂O₃ is currently being studied intensely, but our understanding is still in the early stages.

Crystal growth, impurities and defects

A major benefit for β -Ga₂O₃ is the availability of cost-effective and large area single-crystal substrates that can be grown from melt, as previously mentioned. A number of MG techniques are available, such as Czochralski (CZ), float zone and edge-defined film-fed growth (EFG). Epitaxial β -Ga₂O₃ thin-films of high quality can also be grown, e.g., using molecular beam epitaxy (MBE), halide vapor-phase epitaxy (HVPE), metalorganic chemical vapor deposition (MOCVD) and pulsed laser deposition (PLD). Similar to ZnO, as-grown β -Ga₂O₃ crystals are normally unintentionally *n*-type conductive. This was historically attributed

to V_O , mostly based on correlation between the measured conductivity and the oxygen partial pressure during heat treatments, but it is now widely agreed that residual shallow donor impurities (most notably Si) are responsible [131], whereas formation of compensating V_{Ga} acceptors upon annealing in oxygen-rich environments is the cause of the reduction in conductivity [132, 133].

Si is the dominant background impurity found in β - Ga_2O_3 , both in high-purity (6N) powders and as-grown crystals [134]. Other common impurities include Al, Sn, H, Fe, Mg, Cr and Ir [134–137]. The latter is introduced from the Ir crucible used in MG techniques [134]. Hybrid functional calculations show that Ir preferentially substitutes on the Ga2 site (see Fig. 2.3), where it acts as a deep double donor. Fe and Mg are commonly used as compensating acceptor dopants to produce semi-insulating material, which is required, e.g., for field-effect transistors based on β - Ga_2O_3 [120]. Notably, Ingebrigtsen *et al.* [138] have attributed the commonly observed DLTS signature labeled E_2 , which is located ~ 0.78 eV below the CB, to Fe impurities, based on a linear correlation with the Fe concentration measured by SIMS. This assignment was supported by hybrid functional calculations, which show that Fe_{Ga} exhibits a $(0/-)$ charge-state transition level in good agreement with the measured E_2 level [138]. In a computational survey of acceptor dopants, Lyons *et al.* [111] predicted that Ga substitutional group 2 and 12 elements act as deep acceptors, and Mg_{Ga} was found to exhibit the lowest formation energy. This deep acceptor behavior is consistent with experimental EPR data [139, 140], which shows that the paramagnetic ($S = 1/2$) charge-neutral Mg_{Ga2}^0 has the unpaired spin localized on a single O ion adjacent to the Mg ion.

Despite the large band gap of β - Ga_2O_3 , hybrid functional calculations show that H_i acts exclusively as a shallow donor also in this material, preferentially forming a bond with O1 or O2 [131, 141, 142]. However, the thermodynamic $(+/-)$ transition level was predicted to occur only slightly above the CBM [131]. This is consistent with the experimentally observed shallow donor nature from muon-spin rotation and relaxation spectroscopy measurements [143]. The H_O complexes were also predicted to act as shallow donors, albeit with a relatively low thermal stability [131]. As a highly mobile donor, H can easily form stable complexes with acceptors in β - Ga_2O_3 . Most notably, a dominant O–H related IR absorption line at 3437 cm^{-1} has been observed after hydrogenation, and assigned to a specific configuration of $V_{Ga}2H$ [144], as corroborated by hybrid functional calculations [145]. An IR absorption line at 3492 cm^{-1} has also been observed in hydrogenated Mg doped material, and attributed to a $Mg_{Ga2}H$ complex. Qin *et al.* [142] observed several other IR absorption lines in hydrogenated material, which could be converted into the dominant 3437 cm^{-1} line by annealing in an inert environment at 400°C . Different configurations of $V_{Ga}nH$ with $n = 1, 2, 3$ were tentatively invoked as candidates for the additional lines [142].

Considering the large number of lattice sites and configurations for defects in β - Ga_2O_3 , first-principles defect calculations have been particularly useful to elucidate the properties of native defects in this material. Below, we focus on hybrid functional calculations reported by, e.g., Varley *et al.* [132]. Such calculations show that V_O behaves as a deep negative- U donor for all three O

sites, with thermodynamic ($2+/0$) transition levels in excess of 1 eV below the CBM, where V_{O2} and V_{O3} are the lowest energy configurations in the 0 and $2+$ charge states, respectively. Under n -type conditions, the formation energy of V_O is relatively high, suggesting a low equilibrium concentration. In compensated material, however, e.g., during intentional acceptor doping, high equilibrium concentrations can be expected. V_{Ga} is found to act as an exceedingly deep triple acceptor, with formation energies that are low enough to allow sizeable equilibrium concentrations under n -type conditions, especially in oxygen-rich environments [132]. Indeed, EPR signals ascribed to V_{Ga} have been observed in EFG β -Ga₂O₃ after annealing in O₂ ambient at 1450 °C [133]. Interestingly, in addition to the V_{Ga1} and V_{Ga2} configurations, three split-vacancy configurations have been predicted, where a Ga_i³⁺ interstitial is sandwiched between two regular V_{Ga} . These configurations were discovered by Varley *et al.* [141] when exploring V_{Ga} migration barriers from nudged elastic band calculations, and are denoted as V_{Ga}^{ia} , V_{Ga}^{ib} and V_{Ga}^{ic} [145, 146]. The latter exhibits the lowest formation energy among V_{Ga} in n -type material, and the aforementioned $V_{Ga}2H$ complex adopts the $V_{Ga}^{ib}2H$ configuration [144]. Split-vacancy configurations of V_{Ga} were recently observed by scanning transmission electron microscopy [147], and have been assigned to EPR signals observed in irradiated β -Ga₂O₃ [133, 148, 149].

Owing to high formation energies and/or high mobilities [145], the native interstitials have not been studied to the same extent as the vacancies. However, O_i acts as a deep donor in the split-interstitial configuration, and a deep double acceptor in other interstitial configurations. Ga_i is a shallow donor, but shows a thermodynamic ($3+/+$) transition level at least 0.6 eV below the CBM [145].

Interestingly, the PL spectrum of β -Ga₂O₃ does not exhibit any near-band-edge (NBE) emission, which is in stark contrast to ZnO, where a sharp and intense NBE is observed [47]. Instead, the PL spectrum of β -Ga₂O₃ is usually dominated by a broad ultraviolet luminescence (UVL) band peaking between 3.1 and 3.6 eV. This UVL band is widely attributed to self-trapped exciton recombination, as discussed in more detail in Sec. 5.1.1. However, red, blue and green luminescence bands have also been observed, the specific defect origins of which is unclear [150]. Deep acceptors such as V_{Ga} , $V_{Ga}VO$, Mg_{Ga} , Be_{Ga} , Li_{Ga} and Zn_{Ga} have been suggested [19, 84, 150]. The luminescence properties of polaronic acceptor impurities were investigated in the present work.

Using DLTS, several deep-level defects have been observed and labeled, including E_1 (0.6 eV), E_2 (0.78 eV), E_2^* (0.75 eV), E_3 (1.01 eV) and E_4 (1.48 eV), E_4^* (1.4 eV), where the numbers in parenthesis are the deduced energy level positions below the CBM [130, 135, 138, 145, 151–155]. For the majority of these levels, the defect origin is not firmly established. As already mentioned, Fe_{Ga} was identified as the origin of E_2 [138], but there was still questions concerning the Ga site preference. E_2^* is widely associated with an intrinsic defect origin, as it responds to proton irradiation [138], and an intrinsic defect complex origin has been proposed [145]. Notably, Ingebrigtsen *et al.* [135] have reported on a number of defect signatures that are introduced at elevated temperatures under an applied reverse bias voltage, which can be annealed out and regenerated by subsequent heat treatments. Understanding such phenomena

2. Oxide Semiconductors

is of crucial importance, as the defects could potentially be generated during device operation and cause performance instabilities [130]. The most relevant DLTS defect signatures for the present work are the E_1 , E_2 , E_2^* centers, which were investigated by using a combined experimental and theoretical approach.

Chapter 3

Density Functional Theory

In the present work, the influence of point defects and impurities on the properties of crystalline ZnO and β -Ga₂O₃ were investigated based on a first-principles (also known as *ab initio*) approach. This entails starting from the most fundamental equation in solid-state physics, namely the many-body Schrödinger equation, and solving it – without any assumptions or empirical fittings – for the electronic structure and materials properties. In practice, a number of simplifications and assumptions are required to make this computationally tractable. Some of the most popular methods today are based on DFT, including the hybrid functional approach used in the present work. The many-body Schrödinger equation, DFT and hybrid functionals are introduced briefly below.

3.1 The many-body problem

The behavior of a system comprising N_n nuclei and N_e electrons (such as a defect in a semiconductor) is entirely described by the many-body Schrödinger equation. In the following, we consider the time-independent and non-relativistic case. The first simplification we will use is the commonly applied Born-Oppenheimer approximation, where the nuclei are treated as a fixed external potential, and we limit ourselves to the electronic Hamiltonian, which is given by [156]

$$\hat{H}^e = \hat{T}_e + \hat{V}_{ee} + \hat{V}_{\text{ext}}.$$

The $\hat{T}$ term is the electronic kinetic energy operator, and the two $\hat{V}$ terms are potential energy operators for electron–electron interactions and for the external field produced by the stationary nuclei, respectively, that is, [156]

$$\hat{T}_e = -\frac{\hbar^2}{2m_e} \sum_{j=1}^{N_e} \nabla_j^2 \quad \hat{V}_{ee} = \frac{e^2}{4\pi\epsilon_0} \frac{1}{2} \sum_{j \neq j'}^{N_e} \frac{1}{|\mathbf{r}_j - \mathbf{r}_{j'}|} \quad \hat{V}_{\text{ext}} = -\frac{e^2}{4\pi\epsilon_0} \frac{1}{2} \sum_{j=1}^{N_e} \sum_{\alpha=1}^{N_n} \frac{Z_\alpha}{|\mathbf{r}_j - \mathbf{R}_\alpha|}.$$

Here, the indices j and j' are used for electrons and α for nuclei, m_e is the electron mass, e is the elementary charge, $\mathbf{r}_j$ and $\mathbf{R}_\alpha$ are electron and nuclear coordinates, respectively, and Z_α is the atomic number. Solving the Schrödinger equation with this Hamiltonian for the many-electron wave function $\Psi(\mathbf{R}, \mathbf{r})$ is not computationally feasible, as it depends on the position of all electrons in the system, and the number of terms increases rapidly with the number of electrons. Even storing $\Psi(\mathbf{R}, \mathbf{r})$ for a few electrons, quickly becomes prohibitively expensive [157]. There is also the conceptual issue of how $\Psi(\mathbf{R}, \mathbf{r})$ depends on the single-electron wave functions. This problem can be tackled by (i) attempting to describe $\Psi(\mathbf{R}, \mathbf{r})$ in terms of single-electron wave functions (Hartree and Hartree-Fock approach), (ii) finding a direct relation between $\Psi(\mathbf{R}, \mathbf{r})$ and the total energy (DFT), or (iii) combining approach (i) and (ii) (Kohn-Sham).

3.2 Density functional theory and the Kohn-Sham equation

Density functional theory is a method that greatly simplifies the many-body problem by reformulating it in terms of the electron density $n(\mathbf{r})$ rather than the wave function; the two are connected through the relation $n(\mathbf{r}) = |\Psi(\mathbf{R}, \mathbf{r})|^2$. Indeed, while the wave function depends on the positions of all electrons in the system, resulting in $3N_e$ variables, the electron density depends on only three spatial coordinates. The rationale behind this reformulation is given by two theorems that were put forward by Pierre Hohenberg and Walter Kohn in 1964 [158], and can be summarized with the following three statements [159]:

1. **Uniqueness:** The ground-state properties of a many-electron system is a unique functional of the exact ground state electron density $n_0(\mathbf{r})$.
2. **Variational principle:** Only the exact ground-state electron density delivers the global minimum of the total energy functional $E[n]$.
3. **Universality:** For a given external potential, the total energy functional will have the same form for any many-electron system.

This unique total energy functional can be written as

$$\begin{aligned} E[n] &= T_e[n] + U_{ee}[n] + U_{\text{ext}}[n] \\ &= T_e[n] + U_{ee}[n] + \int V_{\text{ext}}(\mathbf{r})n(\mathbf{r})d\mathbf{r} \\ &= F[n] + \int V_{\text{ext}}(\mathbf{r})n(\mathbf{r})d\mathbf{r}, \end{aligned}$$

where $T_e[n]$, $U_{ee}[n]$ and $U_{\text{ext}}[n]$ are the energy functionals for the kinetic energy, the electron–electron interactions and the external potential V_{ext} , respectively. $F[n]$ is the Hohenberg–Kohn (HK) functional, commonly referred to as the universal functional. The global minimum of this energy functional corresponds to the ground-state energy E_0 of the system, and the density that results in this minimum is the exact ground-state density $n_0(\mathbf{r})$, i.e., $E_0 = E[n_0]$. The density, rather than the electron wave functions, is the defining variable of the system.

Although the treatment in terms of the electron density simplifies the problem, the HK theorems do not provide any practical information on how to obtain the ground-state density, or tell us the actual form of $F[n]$. Walter Kohn and Lu Jeu Sham elaborated on this aspect in a second paper [160]. Their approach was to use an auxiliary system of non-interacting particles in an effective potential chosen such that it reproduces the ground-state density. The full wave function is expressed in terms of N_e Hartree-like single-particle wave functions

$$\Psi(\mathbf{r}_1, \mathbf{r}_2, \mathbf{r}_3, \dots, \mathbf{r}_{N_e}) = \psi_1(\mathbf{r}_1)\psi_2(\mathbf{r}_2)\psi_3(\mathbf{r}_3) \dots \psi_{N_e}(\mathbf{r}_{N_e}),$$

which relate to the density through $n(\mathbf{r}) = \sum_j |\psi_j(\mathbf{r})|^2$. If the exact ground-state density can be found with this approach, then the HK theorems guarantee that the corresponding ground-state total energy is exact. To proceed further, the total energy functional above is rewritten in the Kohn–Sham (KS) form as

$$E_{\text{KS}} = T_e^s + U_{ee}^s + U_{\text{ext}} + E_{\text{XC}},$$

where the first two terms are given by the Hartree approximation

$$T_e^s = \sum_{j=1}^{N_e} \int \psi_j^* \frac{\hbar^2 \nabla^2}{2m_e} \psi_j d\mathbf{r} \quad U_{ee} = \frac{1}{2} \frac{e^2}{4\pi\epsilon_0} \iint \frac{n(\mathbf{r})n(\mathbf{r}')}{|\mathbf{r} - \mathbf{r}'|} d\mathbf{r}d\mathbf{r}',$$

and describe the kinetic energy of the single-particle wave functions, and the Hartree energy of a classical charge density interacting with itself, respectively. We introduce the index s for single particle in order to differentiate them from their full many-electron counterparts (T_e and U_{ee}). The first three terms of E_{KS} can be calculated relatively easily, but they do not capture all of the contributions to the energy. One such contribution comes from the correlated motions of electrons, which are responsible for, e.g., dispersion forces. A special kind of correlation is called exchange, which occurs due to the Pauli exclusion principle. There are also many-electron contributions to the kinetic energy. Moreover, U_{ee}^s includes an unphysical electron self-interaction. Every contribution to the energy that is not included in the first three terms of E_{KS} is cast into the final term, known as the exchange–correlation (XC) energy.

To minimize the total energy, one can use the variational principle under the constraint that the number of electrons must be conserved. This can be accomplished by using the Lagrange multiplier method. The derivation will not be shown here, but results in the famed KS eigenvalue equation [160]

$$\left[-\frac{\hbar^2 \nabla^2}{2m_e} + V_{\text{eff}}(\mathbf{r}) \right] \psi_j(\mathbf{r}) = \varepsilon_j^{\text{KS}} \psi_j(\mathbf{r}).$$

Here, $\varepsilon_j^{\text{KS}}$ are the KS eigenvalues, and $V_{\text{eff}}(\mathbf{r})$ is the effective potential in which the non-interacting electrons are moving, given by

$$V_{\text{eff}}(\mathbf{r}) = V_H(\mathbf{r}) + V_{\text{ext}}(\mathbf{r}) + V_{\text{XC}}(\mathbf{r}),$$

where $V_H(\mathbf{r}) = \frac{e^2}{4\pi\epsilon_0} \int \frac{n(\mathbf{r}')}{|\mathbf{r} - \mathbf{r}'|} d\mathbf{r}'$ is the Hartree potential, and V_{XC} is the exchange–correlation potential. The KS eigenvalue equation is solved self-consistently and will, in principle, deliver the exact ground-state density. However, the exact form of E_{XC} is unknown, and probably very complicated since it retains in its core all the difficulties of the many-body problem [159]. Nevertheless, the KS eigenvalue equation provides a useful framework to perform practical calculations.

3.3 Conventional functionals and their shortcomings

The KS approach relies on being able to approximate the XC energy functional accurately. In their paper, Kohn and Sham also put forward the so-called local density approximation (LDA) [160], where E_{XC} at each point $\mathbf{r}$ with density $n(\mathbf{r})$ is assumed to be equal to that of a uniform electron gas with the same density. For a uniform electron gas, the exchange energy has a known analytical form, and the correlation has been accurately determined from Monte Carlo calculations [156, 161]. The next rung [162] of approximations include terms

3. Density Functional Theory

dependent on the gradient of the density $\nabla n(\mathbf{r})$, and are thus called generalized gradient approximations (GGA). A popular type of GGA is the non-empirical Perdew–Burke–Ernzerhof (PBE) functional [163], and the related version of the functional revised for solids (PBEsol) [164]. So-called meta-GGA functionals use the second derivative of the electron and kinetic energy density, or attempt to satisfy known constraints that the exact XC functional should fulfil, e.g., the Strongly Constrained and Appropriately Normed (SCAN) functional [165].

Semilocal approximations to the XC energy functional, including those described above, have been incredibly successful at predicting various materials properties, especially in terms of accuracy versus cost, and have served as the workhorse for solid-state electronic structure calculations for many years. Nevertheless, they have several shortcomings—some of these are particularly severe for oxide semiconductors, and will be discussed below.

First and foremost, semilocal approximations suffer from the so-called band gap problem, where the band gaps of semiconductors and insulators are significantly underestimated [166]. For ZnO and β -Ga₂O₃, the GGA-PBE functional underestimates the band gaps by about 80% and 60%, respectively. This leads to large errors in defect formation energies and charge-state transition levels (these defect properties are introduced in Sec. 4.2 and 4.3, respectively), and makes it challenging to interpret and compare the results with experimental data [3, 82]. Sometimes, the properties can even be qualitatively wrong, e.g., a deep level defect is erroneously predicted to be shallow. Secondly, defect states are typically too delocalized [3]. This error notably manifests itself in the failure to describe polarons, which are often present in oxides [110]. Polarons involve localization of excess charge at atomic sites. In the conventional XC approximations, partial occupation tends to be favored over integer occupation of electronic levels, and the charge is spread over several atomic sites. Both of these problems are largely caused by the residual self-interaction error [3].

3.4 Hartree–Fock theory and hybrid functionals

In the present work, a hybrid functional was used to mitigate the shortcomings described in the previous section. Hybrid functionals incorporate a certain portion of nonlocal exchange from Hartree–Fock (HF) theory in the conventional approximations to the XC energy. In the HF method, the many-electron wave function is expressed as a Slater determinant consisting of antisymmetric single-particle wavefunctions (thus satisfying the Pauli exclusion principle) [156]

$$\Psi(\mathbf{r}_1, \mathbf{r}_2, \mathbf{r}_3, \dots, \mathbf{r}_{N_e}) = \frac{1}{\sqrt{N!}} \begin{vmatrix} \psi_1(\mathbf{r}_1) & \psi_2(\mathbf{r}_1) & \dots & \psi_{N_e}(\mathbf{r}_1) \\ \vdots & \vdots & & \vdots \\ \psi_1(\mathbf{r}_{N_e}) & \psi_2(\mathbf{r}_{N_e}) & \dots & \psi_{N_e}(\mathbf{r}_{N_e}) \end{vmatrix},$$

and $\langle \Psi | \hat{H} | \Psi \rangle$ is minimized. This results in the HF eigenvalue equation [3]

$$\left[-\frac{\hbar^2 \nabla^2}{2m_e} + V_H(\mathbf{r}) + V_{\text{ext}}(\mathbf{r}) + V_X^{\text{HF}}(\mathbf{r}, \mathbf{r}') \right] \psi_j(\mathbf{r}) = \varepsilon_j^{\text{HF}} \psi_j(\mathbf{r}),$$

which is orders of magnitude more computationally expensive than standard DFT due to the orbital dependence in the HF exchange potential, given by

$$V_X^{\text{HF}}(\mathbf{r}, \mathbf{r}') = -\frac{e^2}{4\pi\epsilon_0} \sum_i^{N_e} \delta_{\sigma_j \sigma_i} \int \frac{\psi_i^*(\mathbf{r}') \psi_j(\mathbf{r}')}{|\mathbf{r} - \mathbf{r}'|} \psi_i(\mathbf{r}) d\mathbf{r}',$$

which acts only on electrons with the same spin σ . Since the integral involves both ψ_i and ψ_j , V_X^{HF} cannot be expressed in terms of the density (like V_H). The HF method benefits from being one-electron self-interaction free. An instructive example is the H_2^+ molecule, for which the correlation energy vanishes and the exchange energy should exactly cancel the Hartree energy. This is indeed the case for HF theory, but not for conventional DFT. However, HF theory ignores correlation effects for many-electron systems, resulting in significant underbinding and a large overestimation of band gaps.

Hybrid functionals intermix exact HF exchange with exchange and correlation from LDA/GGA. The concept was initially developed by Becke [167], based on the adiabatic connection formula [168]. As an example, the XC energy can be expressed as a linear combination of HF and LDA/GGA exchange

$$E_{\text{XC}} = \alpha E_X^{\text{HF}} + (1 - \alpha) E_X^{\text{LDA/GGA}} + E_C^{\text{LDA/GGA}},$$

where α is the mixing parameter controlling the fraction of E_X^{HF} . Becke also developed the B3LYP functional, containing three such parameters which were empirically optimized to reproduce thermochemistry data. B3LYP has been a standard choice for quantum chemistry calculations since its introduction. For solids, HF exchange is commonly mixed with the non-empirical PBE functional, resulting in PBE hybrids (PBEh). However, due to high computational cost and a lack of efficient implementations, it took longer for hybrid functionals to be routinely applied to solid-state systems [3]. Wider-spread use came with the Heyd–Scuseria–Ernzerhof (HSE) hybrid functional [169], used in the present work, where the HF exchange is screened by the complementary error function $\text{erfc}(\mu|\mathbf{r} - \mathbf{r}'|)$, where μ is the screening parameter. The exchange interaction is given by HF in the short-range (SR), and PBE in the long-range (LR) part

$$E_{\text{XC}}^{\text{HSE}} = \alpha E_X^{\text{HF,SR}}(\mu) + (1 - \alpha) E_X^{\text{PBE,SR}}(\mu) + E_X^{\text{PBE,LR}}(\mu) + E_C^{\text{PBE}}.$$

Such functionals are often referred to as range-separated hybrid functionals. The screening of the exchange interaction can be motivated by the fact that exchange effects occur on a short-range scale [169], and it comes with the additional benefit of reducing the computational cost. The parametrization $\alpha = 0.25$ and $\mu = 0.2 \text{ \AA}^{-1}$ was suggested to be the optimal choice for band gaps and thermochemistry, and is usually referred to as the HSE06 functional [170]. However, higher α values are often required to describe wide-band-gap semiconductors such as ZnO and $\beta\text{-Ga}_2\text{O}_3$. When performing calculations for point defects in semiconductors, it is common practice to empirically adjust the mixing parameter to reproduce the experimental band gap. As such, it is not a first-principles method in the

3. Density Functional Theory

strictest sense. However, there are arguments as to why the parametrization should not be equal for all materials. Alkauskas *et al.* [7] and Marques *et al.* [171] noticed a connection between α and the inverse high-frequency dielectric constant ϵ_∞^{-1} , i.e., a smaller α is needed for narrow band-gap semiconductors, as they typically show a stronger electronic screening than wide band-gap materials [172]. Motivated by this observation, setting $\alpha = \epsilon_\infty^{-1}$ results in so-called dielectric-dependent hybrid (DDH) functionals. Recently, Chen *et al.* [172] developed a non-empirical range-separated hybrid functional, parametrized by using *ab-initio* dielectric-function calculations, which was found to reproduce the electronic and structural properties of a wide range of semiconductors and insulators.

Before moving on, it is worth dwelling for a moment on why hybrid functionals lead to an improved description of the electronic structure of semiconductors and charge-localization at defects. We focus on the band gap and the (de)localization error, following the discussion by Mori-Sánchez *et al.* [173]. Starting with a finite system (such as a molecule), the fundamental (or integer) band gap is

$$E_g^{\text{int}} = I - A = [E(N_e - 1) - E(N_e)] - [E(N_e) - E(N_e + 1)],$$

that is, the difference between the ionization energy (energy cost to remove one electron) and electron affinity (energy gained upon adding one electron). Alternatively, the band gap can be expressed as a difference of derivatives

$$E_g^{\text{der}} = \lim_{\delta \rightarrow 0} \left. \frac{\partial E}{\partial N} \right|_{N_e + \delta} - \lim_{\delta \rightarrow 0} \left. \frac{\partial E}{\partial N} \right|_{N_e - \delta}.$$

However, the integer and derivative gap will only be equal if the total energy is a piecewise linear function of the fractional electron number, as it should be for exact DFT [174]. For conventional DFT, it turns out to be convex, as the present approximations are unable to compensate for the self-interaction. For HF theory, on the other hand, the function is concave [3, 175]. Figure 3.1 illustrates the straight-line (exact), convex (LDA/GGA) and concave (HF) behavior.

To explain the underestimation of band gaps by conventional DFT, we move on from the finite system to an extended one. Then, there is an apparent paradox, because straight-line behavior is observed [173, 176]. In order to understand this, we consider what happens when an electron is added to two separate finite systems. Owing to the convex behavior of conventional DFT, the total energy will be lower if the electron is divided equally between the two systems, relative to placing it in only one of them, and the integer band gap will be lowered. As the number of finite systems M increases, the integer band gap will approach the derivative one, as indicated by the dotted line in Fig. 3.1. This result carries over into extended periodic systems, as shown by Lany and Zunger for the case of ZnO [176]. In HF theory, dividing the electron equally results in an energy penalty due to the concave behavior. Thus, the electron will always be placed in one system, and the concave function will persist as M increases. Conventional DFT and HF theory show delocalization and localization errors, respectively. This provides an idea of why hybrid functionals generally lead to an improved

Figure 3.1: Total energy of a finite (solid lines) and extended (dashed line) N_e -electron system as a function of fractional electron number, shown for functionals exhibiting straight-line (black), convex (blue) and concave (orange) behavior.

description of band gaps and charge-localization at defects, as the combination will lead to a partial cancellation of the delocalization and localization errors.

The expected straight-line behavior of the exact functional has also motivated another direction to obtain non-empirically parametrized hybrid functionals for point defect calculations. This is done by enforcement of the generalized Koopmans' theorem (gKT) for defect states [31, 77, 177, 178]. The gKT is an exact physical constraint by which the total energy is a piece-wise linear function of fractional electron occupation of the defect state. Based on Janak's theorem [179], this implies that the single-particle energy level of the defect state should not shift in energy upon electron addition or removal. Tuning the hybrid functional to satisfy the gKT for a particular type of defect state, as well as reproduce the experimental band gap, was explored in the present work.

Chapter 4

Point defect calculations

The preceding chapter outlined the framework of the generalized KS theory. Here, we shall deal with the practical and computational aspects of its implementation, introduce the formalism for first-principles defect calculations, and explain how the results relate to data from experimental defect spectroscopic techniques. The methodology for first-principles defect calculations has evolved considerably over the last two decades. Recent reviews by Freysoldt *et al.* [3], Dreyer *et al.* [180] and Alkauskas *et al.* [4] are recommended for newcomers to the field.

4.1 Computational details and the supercell approach

All first-principles calculations in this thesis were performed using the Vienna *ab-initio* simulation package (VASP) [181], specifically the VASP.5.X branch. To numerically solve the KS eigenvalue equation in an efficient manner, VASP expands the wave functions in a plane wave basis set, which is truncated by setting a cutoff energy. An issue with this approach is that high cutoff energies are required to describe the short-ranged oscillations typically associated with core electron wave functions. However, since such states are largely unchanged upon going from isolated atom to solid, they can often be replaced by a pseudo-potential acting on the valence electrons, which reproduces the behavior of the full all-electron potential [182]. The pseudo-potentials used here were generated for VASP using the projector augmented wave (PAW) method [183, 184].

As implied by the use of plane waves, the calculations are performed under periodic boundary conditions, and the KS equation is solved in reciprocal space by sampling a number of different $\mathbf{k}$ -points in the first Brillouin zone. Because the computational cost increases with the number of sampled $\mathbf{k}$ -points, care must be taken to choose the optimal ones to obtain converged results at minimal cost. These *special* $\mathbf{k}$ -points can be determined based on the symmetry of the system, as shown by Balderecchi [185], and later by Monkhorst and Pack [186]. The latter procedure is used in VASP, and provides the optimal $\mathbf{k}$ -points for a given $\mathbf{k}$ -grid. The symmetry can also be used to significantly lower the numerical effort, i.e., by using the irreducible Brillouin Zone. Another important point on convergence is the difference between absolute (e.g., total energy) and relative (e.g., total energy difference between a pristine and defect-containing supercell) quantities; the latter tend to converge much faster due to error cancellation.

A major advantage of the periodic boundary conditions is that bulk crystals can be readily simulated by using a unit cell consisting of relatively few atoms. Point defects can also be simulated in this way. However, since the defect is also periodically repeated, care must be taken to ensure that enough bulk material is included to prevent the defect from interacting with its periodic images. To

this end, the primitive unit cell is expanded into a larger *supercell* for defect calculations. In this work, 96- and 160-atom supercells were mostly used for defect calculations in ZnO and β -Ga₂O₃, respectively. These were constructed by stacking 3×2×2 orthorhombic ZnO unit cells and 1×4×2 conventional β -Ga₂O₃ unit cells (unit cells shown in Figs. 2.2 and 2.3). Avoiding finite-size errors can be challenging, especially when using high-cost hybrid functionals, and when dealing with charged defects. This will be discussed in more detail in Sec. 4.5.

When a defect is introduced into a crystal structure, it will usually distort the surrounding lattice to some extent. This ionic relaxation can be included by calculating the Hellmann-Feynman forces acting on each atom in the supercell at the end of the self-consistent field cycle, updating their positions according to an ionic relaxation algorithm, and repeating until the forces are below a selected threshold value. It is important to keep in mind that the ground-state ionic configuration of a defect may have a lower degree of symmetry than that of the crystal. For example, to model a vacancy, it might not be sufficient to simply remove an atom from the supercell and perform ionic relaxation, as the defect may end up in a metastable state. Therefore, one should introduce random small displacements, or manually move atoms to check different configurations.

4.2 Defect formation energies

The defect formation energy E^f is the energy cost for creating a defect in an otherwise perfect crystal, and is a key quantity for understanding the properties of defects. By accounting for the configurational entropy, it can be shown that the equilibrium concentration of a defect in the dilute regime is given by [3]

$$c^{\text{eq}} = N_{\text{sites}} g \exp\left(-\frac{E^f}{k_B T}\right), \quad (4.1)$$

where N_{sites} is the density of available sites in the host crystal, g is a degeneracy factor, and T is the temperature. When the temperature, volume and pressure dependence is taken into account, E^f should be replaced by the Gibbs free energy of formation G^f , which includes the vibrational and electronic entropy [3]. However, since the entropy contributions are computationally demanding to include, and small enough not to affect the conclusions for most purposes, they are typically omitted (and have been in the present work) [187].

The formation energy of a defect X^q in charge state q is calculated as [3]

$$E^f(X^q) = E_{\text{tot}}(X^q) - E_{\text{tot}}(\text{bulk}) - \sum_i n_i \mu_i + q(E_{\text{VBM}} + E_F), \quad (4.2)$$

where $E_{\text{tot}}(X^q)$ and $E_{\text{tot}}(\text{bulk})$ are the total energies of the relaxed defect-containing and pristine supercell, respectively. The third term accounts for the energy cost to exchange n_i atoms of species i with their energy reservoir, which is represented by a chemical potential μ_i . Charges added or removed from the supercell are similarly exchanged with the electron reservoir, given by the Fermi level E_F position, taken with respect to the valence band maximum E_{VBM} . In

practice, a finite-size correction term E_{cor} is also included in Eq. 4.2 (the E_{cor} term is explained in more detail in Sec. 4.5).

The chemical potential is a variable that depends on the conditions under which the defect is created. However, it is not an entirely free variable, because it is subject to bounds set by the formation of secondary phases [187]. To exemplify this, we consider growth of $\beta\text{-Ga}_2\text{O}_3$. The chemical potentials are conventionally referenced to those of the element i in their standard state, i.e.,

$$\mu_i = \mu_i^0 + \Delta\mu_i, \quad (4.3)$$

where μ_i^0 is the fixed reference and $\Delta\mu_i$ is the value of the chemical potential for a specific experimental condition relative to the reference. The standard reference state is the phase of the element under standard conditions, i.e., metal Ga and molecular O, here denoted as μ_{Ga}^0 and μ_{O}^0 , respectively. In first-principles calculations, the standard states are given by the calculated total energy (per atom) at $T = 0$ K. The upper bounds on μ_{Ga} and μ_{O} are given by μ_{Ga}^0 and μ_{O}^0 , corresponding to Ga- and O-rich limits, respectively. Assuming thermodynamic equilibrium, these upper bounds impose lower bounds on the corresponding other species, given by the thermodynamic stability condition

$$2\Delta\mu_{\text{Ga}} + 3\Delta\mu_{\text{O}} = \Delta H_{\text{f}}(\beta\text{-Ga}_2\text{O}_3), \quad (4.4)$$

where $\Delta H_{\text{f}}(\beta\text{-Ga}_2\text{O}_3)$ is the formation enthalpy per formula unit of $\beta\text{-Ga}_2\text{O}_3$ with respect to the standard states of Ga and O. This leads to a linear range of stability, where $\Delta\mu_{\text{Ga}}$ and $\Delta\mu_{\text{O}}$ can vary within the following ranges

$$\begin{aligned} \frac{1}{2}\Delta H_{\text{f}}(\beta\text{-Ga}_2\text{O}_3) \leq \Delta\mu_{\text{Ga}} \leq 0 & \quad \text{Ga-rich} \\ \text{O-rich} \quad 0 \geq \Delta\mu_{\text{O}} \geq \frac{1}{3}\Delta H_{\text{f}}(\beta\text{-Ga}_2\text{O}_3). \end{aligned} \quad (4.5)$$

In the literature, the defect formation energy in such a case would typically be presented for both the Ga- and O-rich limits. For ternary and higher order compounds, determining the range of stability can be more cumbersome, as many competing phases may need to be considered [188]. For impurities, upper bounds on their chemical potentials are similarly set by the formation of their standard states or mixed secondary phases, corresponding to the solubility limit. For example, when H is present in the growth environment, μ_{H} is limited under O-rich conditions due to the formation of H_2O . For Mg, μ_{Mg} is limited by the spinel phase MgGa_2O_4 in both the Ga- and O-rich limits [109].

For charged defects, the formation energy acquires a Fermi level dependence; it increases (decreases) with the Fermi level for a positively (negatively) charged defect. At the same time, the Fermi level position depends on the concentration of electrons, holes and charged defects (which must obey charge neutrality). This means that, knowing the formation energy of the ruling defects, the Fermi level and equilibrium defect concentrations can be determined self-consistently [189].

Figure 4.1: a) Formation energy of a defect (exhibiting three charge-states) as a function of Fermi level position within the band gap. The regions of stability for the charge states, and the positions of thermodynamic charge-state transition levels, are indicated. The black curve traces the lowest formation energy. b) Optical μ versus thermodynamic ϵ charge-state transition levels. The dashed lines are the formation energies calculated in the relaxed configuration of the corresponding other charge state, i.e., the $\mu(-/0)$ and $\mu(0/-)$ transitions occur in the equilibrium configuration for the $-$ and 0 charge state, respectively.

4.3 Thermodynamic charge-state transition levels

In crystalline semiconductors, defects will normally introduce discrete levels in the band gap, and can thus often assume more than one charge state depending on their occupation. The formation energy of the defect in each of its stable charge states can be conveniently plotted as a function of the Fermi level position from the VBM to the conduction band minimum (CBM). Figure 4.1 a) shows the formation energy diagram of a hypothetical defect in charge states $q = +1, 0$ and -1 , where the regions of stability for the charge states have been highlighted. To avoid clutter, the formation energy is usually only plotted for the most favorable charge state for a given Fermi level position, as traced by the black curve in Fig. 4.1 a). The slope of the linear segments correspond to the charge state, and kinks in the curve occur at Fermi level positions for which the formation energy of the defect in two different charge states is equal. The position of the thermodynamic transition level between charge states q_1 and q_2 is given by [3]

$$\epsilon(q_1/q_2) = \frac{E^f(X^{q_1}; E_F = 0) - E^f(X^{q_2}; E_F = 0)}{q_2 - q_1}.$$

These levels are of crucial importance because they govern the electronic behavior of the defect, e.g., whether it will act as an acceptor or a donor. If a defect exhibits a donor (acceptor) level that is close enough to the CBM (VBM) for the defect to be thermally ionized at room temperature, it will act as a shallow donor (acceptor), and can be used as an n -type (p -type) dopant. Otherwise, it will act as a deep-level defect, which can potentially compensate dopants.

Figure 4.2: Schematic of shallow versus deep defects. Si_{Ga} is a shallow donor, where the donor electron (yellow isosurface) occupies a delocalized host-like state close to the CBM (yellow dotted line) in the sketched band structure. N_{O} introduces an empty acceptor level deep within the band gap (blue line), and the hole (blue isosurface) is localized mostly at the N impurity itself.

As sketched in Fig. 4.2, the difference between a deep and a shallow level can also be explained based on the degree of spatial localization of the electron or hole bound to the defect [4]. A shallow donor, such as Si_{Ga} in $\beta\text{-Ga}_2\text{O}_3$ [116], introduces a filled electronic state energetically located above the CBM, which means that the electron will be donated to the CB. The electron will occupy a perturbed host state slightly below the CBM, which can be described by hydrogenic effective-mass theory [176]. The electron is only loosely bound to the ionized donor, and spatially delocalized over several lattice constants. A deep acceptor, such as N_{O} in $\beta\text{-Ga}_2\text{O}_3$ [109], introduces an empty electronic state that is deep in the band gap, i.e., energetically far away from the VBM. The empty defect state is spatially localized mainly on the defect itself. In contrast to shallow defects, changing the charge state of a deep defect tends to induce a strong relaxation of the local lattice. This large difference in equilibrium configuration leads to the definition of two distinct types of charge-state transitions: (i) A *thermodynamic* charge-state transition occurs when the defect in the initial q_1 and final q_2 charge state is relaxed to the equilibrium configuration, i.e., they involve the $\varepsilon(q_1/q_2)$ level defined above. (ii) An *optical* (or *vertical*) charge-state transition occurs with no change in ionic coordinates, and thus require the energy of the final charge state in the configuration of the initial one. Optical levels are here denoted as $\mu(q_1/q_2)$. The position of an optical level depends on the direction of the charge-state transition, i.e., $\mu(q_1/q_2) \neq \mu(q_2/q_1)$. This can be illustrated in a formation energy diagram, as shown in Fig. 4.1 b).

Comparing charge-state transition levels with experimental data

Charge-state transition levels are not only important for the properties of defects, but also provide the basis for many defect spectroscopic techniques. When comparing results from such experiments with first-principles calculations, one must consider which type of charge-state transition level that applies, i.e., thermodynamic or optical. For example, DLTS [190] is an electrical defect

characterization technique that uses the capacitance of a p - n junction or a Schottky barrier as a probe to monitor changes in the charge state of deep-level defects in the space charge region. In the case of n -type material, the defect levels are first filled with electrons by applying a voltage pulse. When the voltage returns to its quiescent state, the electrons will be thermally emitted from the defect levels to the CBM. By repeatedly measuring the resulting capacitance transient as a function of temperature, using several different rate windows, the activation energy for the thermally driven emission can be extracted from an Arrhenius plot of the emission rate. In the absence of a capture barrier (see Sec. 4.4), this activation energy corresponds to the energy required to reach the final charge state in its equilibrium configuration (adiabatic ionization energy), and can thus, to a good approximation, be compared directly with the Fermi level positions of calculated thermodynamic charge-state transition levels relative to the CBM (a modification to this statement will be discussed in Sec. 4.4).

Charge-state transition levels can also be obtained from optical characterization techniques. In photoluminescence (PL) spectroscopy, a laser is used to excite electron-hole pairs in the semiconductor. When these carriers recombine, e.g., via defect levels, they emit light to conserve energy, resulting in a luminescence spectrum. Needless to say, optical/vertical charge-state transition levels should be used for comparison with experimental data in this case. This is because the radiative electronic transition is instantaneous compared to the time scale of ionic motion, i.e., the geometry is essentially frozen in the initial state [3]. This is the classical formulation of the so-called Franck-Condon (FC) principle.

4.4 Configuration coordinate diagrams

The *configuration coordinate* (CC) diagram is a useful concept to describe the coupling between the electronic and ionic structure, which, as already touched upon, is an important aspect of defect charge-state transitions. CC diagrams were originally used to explain processes such as light absorption, luminescence and nonradiative capture and emission at deep-level defects, as observed experimentally [191]. However, the emergence of more accurate electronic structure methods has enabled CC diagrams to be derived solely from first-principles calculations, allowing them to be used predictively. This approach will be explained briefly in this section, with special emphasis on optical emission involving defects. For more details, see Refs. [4, 11–14].

First, we briefly consider thermally driven emission of an electron from a deep single donor D to the CBM, as this is relevant for DLTS. Figure 4.3 a) shows a CC diagram for the process, where the total energy of the ground (g) and excited (e) state is given by the blue and red curve, respectively. The horizontal axis is a one-dimensional (1D) parametrization of the collective displacement of all ions in the supercell. The equilibrium configurations of D^0 and D^+ are indicated by labels Q_g and Q_e in the CC diagram, and differ by ΔQ . The ionization energy E_i of D^0 is given by the total energy difference between the excited and ground state in their equilibrium configurations, which corresponds to the difference in Fermi

Figure 4.3: 1D CC diagrams for the process of a) nonradiative capture and emission of an electron between the $(+/0)$ level of a deep donor D and the CBM. The capture barrier and ionization energy is indicated. b) Optical absorption and emission between the $(0/-)$ level of a deep acceptor A and the CBM. The absorption, emission, ZPL and FC relaxation energies are indicated. The CB and thermodynamic charge-state transition level is shown in the background (gray) in both cases. The excited and ground state equilibrium configuration coordinates, and the difference between them, is indicated.

level position between the CBM and the thermodynamic $(+/0)$ transition level. For electron emission to occur, D^0 must traverse the potential energy surface to reach the intersection point with the $D^+ + e_{\text{CBM}}^-$ curve in the CC diagram. After the emission, the defect will relax to its new equilibrium configuration. In this picture, the activation energy extracted from DLTS includes, not just the ionization energy, but a capture barrier E_b , as indicated in the CC diagram. This barrier can be large in some cases, and should be considered when comparing calculated thermodynamic charge-state transition levels with DLTS. The capture barrier can also be estimated experimentally from the temperature dependence of the rate of electron capture.

Next, we consider optical absorption and emission at a deep acceptor, as shown in Fig. 4.3 b), where the ground state of the system corresponds to the negatively charged acceptor (A^-), and the excited state corresponds to the charge-neutral acceptor plus an electron at the CBM ($A^0 + e_{\text{CBM}}^-$). Again, the curves are offset in energy by the thermodynamic $(0/-)$ level referenced to the CBM. In the context of luminescence, this energy difference is called the zero-phonon line (ZPL) energy E_{ZPL} —the reason will become clear shortly. In the classical FC approximation, optical transitions occur with no change in configuration coordinate, i.e., the transitions are vertical in the CC diagram, which results in optical absorption E_{abs} and emission E_{em} energies that correspond to the vertical $\mu(-/0)$ and $\mu(0/-)$ levels, respectively, as defined previously. In this example, these transition energies are very different from the ZPL energy. After

4. Point defect calculations

Figure 4.4: Left: 1D CC model for optical emission, showing the vibrational sub-levels $\hbar\omega_{gm}$ and $\hbar\omega_{en}$. Right: Spectral function $A(\hbar\omega)$ due to vibronic transitions from the $n = 0$ level to the m levels. The peak position (PP) occurs at a photon energy corresponding to the vibronic transition to the $m = 12$ level. Additional broadening result in an overall smooth line shape (green curve).

an optical charge-state transition, the defect can lower its energy by relaxing to the equilibrium configuration of the final charge state. The amount of energy that is lost is the FC shift d_{FC} , or relaxation energy, and the difference between the absorption and emission energy is called the Stokes shift. In this model, E_{abs} and E_{em} correspond to the onset of absorption and peak position of the defect luminescence spectrum, respectively, as observed experimentally by, e.g., PL excitation (PLE) and PL spectroscopy. However, defects showing large FC shifts typically result in *broad* luminescence bands rather than distinct peaks. This is due to vibrational broadening, which is not captured in this classical picture.

To include the effect of vibrational broadening, and describe the full defect luminescence spectrum, we need to go beyond the classical FC approximation [192–194]. The broadening is an effect of electron–phonon coupling, which can be included in the 1D CC diagram by treating the ground and excited state potential energy surfaces as quantum harmonic oscillators with effective frequencies ω_g and ω_e . Figure 4.4 shows the resulting CC diagram with the vibrational sub-levels $\hbar\omega_{gm}$ and $\hbar\omega_{en}$ included. Focusing on the emission process, we must now consider vibronic transitions between the vibrational sub-levels n and m in the excited and ground electronic state, respectively. The rate of spontaneous emission depends on the transition dipole matrix element between the ground and excited states μ_{eg} , and can be described by Fermi’s Golden rule. The quantum variant of the FC principle assumes that μ_{eg} is independent of ionic coordinates Q . Considering all vibronic transitions, the absolute luminescence intensity (number of photons per unit time per unit energy) can then be expressed as [180, 191]

$$I(\hbar\omega, T) = \frac{n_r \omega^3 |\mu_{eg}|^2}{3\pi\epsilon_0 \hbar c^3} \sum_{n,m} w_n(T) |\langle \chi_{gm} | \chi_{en} \rangle|^2 \delta(E_{ZPL} - \hbar\omega_{gm} + \hbar\omega_{en} - \hbar\omega) \quad (4.6)$$

$$= \frac{n_r \omega^3 |\mu_{eg}|^2}{3\pi\epsilon_0 \hbar c^3} A(\hbar\omega, T), \quad (4.7)$$

where n_r is the index of refraction, c is the speed of light, χ_{en} and χ_{gm} are the vibrational wave functions of the n and m sub-levels in the excited and ground electronic states with energies $\hbar\omega_{en}$ and $\hbar\omega_{gm}$, respectively, and $\langle\chi_{gm}|\chi_{en}\rangle$ is the FC overlap integral. $w_n(T)$ gives the thermal occupation of the vibrational sub-levels in the excited electronic state, which leads to additional broadening at elevated temperatures. However, one should keep in mind that E_{ZPL} is also temperature dependent. $A(\hbar\omega, T)$ is called the normalized spectral function. Based on Eq. 4.6, the normalized luminescence intensity (line shape) can be expressed as $G(\hbar\omega, T) = C\omega^3 A(\hbar\omega, T)$, where C is a normalization factor [11]. Only $G(\hbar\omega, T)$ was considered in this thesis. Dreyer *et al.* [14] recently presented a method to calculate radiative carrier capture coefficients for deep defects.

Figure 4.4 shows $A(\hbar\omega, T)$ for the low temperature case, i.e., vibronic transitions from the $n = 0$ level to the m levels. The resulting spectral function consists of a series of spikes at photon energies given by the delta-function, which are weighted by the FC overlap integral. The transition from $n = 0$ to $m = 0$, which involves zero phonons, is unlikely to occur due to the low overlap between their vibrational wave functions. For transitions to $m > 0$, the defect ends up in an excited vibrational state which subsequently decays to the lowest level by emitting m phonons; these transitions are called phonon replicas. In Fig. 4.4, the $m = 12$ transition is most likely to occur, and corresponds to a photon energy close to the classical E_{em} . To simulate additional broadening mechanisms, i.e., inhomogeneous broadening, the delta functions in the spectrum are replaced by Gaussians, resulting in a smooth lineshape (green curve in Fig. 4.4).

Calculating the luminescence line requires the four parameters that define the 1D CC diagram, namely E_{ZPL} , $\hbar\omega_g$, $\hbar\omega_e$ and ΔQ . The latter is given by

$$(\Delta Q)^2 = \sum_{\alpha} m_{\alpha} \Delta \mathbf{R}_{\alpha}^2, \quad (4.8)$$

where, m_{α} is the mass of atom α in the supercell, and $\Delta \mathbf{R}_{\alpha}$ is the change in the coordinates defining its position. The effective vibrational frequencies in the ground/excited state require the corresponding FC shifts, and are given by

$$\omega_{g/e} = \frac{\sqrt{2d_{FC}^{g/e}}}{\Delta Q} \quad (4.9)$$

in the harmonic approximation. Luminescence lines were obtained by using a Fortran script written by Alkauskas *et al.* [11]. For anharmonic potential energy surfaces, the luminescence lines were calculated using a Julia Language script (adapted from the `CarrierCapture.jl` package by Kim *et al.* [195]).

The 1D CC diagram might seem overly simplistic. Indeed, in reality, there is a large number of vibrational modes associated with a point defect in a solid, leading to a highly multidimensional problem. However, it can be shown that the

1D approximation, where a single effective mode (not necessarily corresponding to any actual vibrational mode in the excited or ground state) is sufficient for defects exhibiting strong electron–phonon coupling [4, 11, 180] (which is the case for the defects studied in the present work). The strength of the electron–phonon coupling can be quantified in terms of a so-called Huang–Rhys (HR) factor [192], which is given by $S_g = d_{\text{FC}}^2 / \hbar \omega_g$ for emission, and corresponds to the average number of phonons created during an optical transition. In the case of strong electron–phonon coupling, i.e., $S_g \gg 1$, the luminescence line will be smooth and broad, and contributions from individual modes cannot be resolved. The 1D CC approximation is then sufficient to describe the line shape, as demonstrated numerically by Alkauskas *et al.* [4, 11].

In the opposite limit of weak electron–phonon coupling, the majority of the luminescence spectrum will be in the ZPL. The relative weight of the ZPL in the spectral function is approximately given by e^{-S_g} [194]. When this weight is close to one, the intensity of the phonon side band will be weak, and the spectrum will be dominated by a distinct ZPL peak. For intermediate electron–phonon coupling, i.e., when the spectrum consists of the ZPL and a phonon side band with clear fine-structure originating from phonons of various frequencies, the 1D CC approach is inadequate to describe the detailed lineshape [7].

A similar quantum treatment of 1D CC diagrams is possible for the process of nonradiative carrier capture via multiphonon emission, and can yield the capture cross section as a function of temperature [12]. Combined with the temperature dependence of E_i , this can be used to calculate the temperature dependence of the activation energy for carrier emission, allowing a more rigorous comparison with DLTS data [13]. Keeping this in mind, the aforementioned classical activation energy ($E_i + E_b$) should be considered as an upper limit.

4.5 Dealing with supercell finite-size errors

A disadvantage with the supercell method for defect calculations is that computationally affordable supercell sizes (up to few hundred atoms for hybrid functionals) correspond to unrealistically high defect concentrations, leading to spurious interactions of the defect with its periodic images. If the aim is to calculate the properties of an isolated defect (single defect in an otherwise pristine crystal), these interactions cannot be disregarded. These interactions can be quantum mechanical, electrostatic, elastic and magnetic; the former two are typically dominant in terms of the magnitude of finite-size error in the formation energy and will be discussed in the following subsections [3].

4.5.1 Quantum mechanical interactions

Isolated deep-level defects introduce discrete energy levels in the band gap with no dispersion. For small supercells, however, the defect wave function can overlap with its periodic images, turning the defect level into a dispersive band. If this band is occupied, the total energy will depend on the employed $\mathbf{k}$ -point(s). If

$\Delta\varepsilon_d(\mathbf{k})$ is the difference between the energy of the dispersive and isolated KS defect state, the finite-size error in the total energy is given by [3]

$$\Delta E = \sum_{\mathbf{k}} w_{\mathbf{k}} f_{\mathbf{k}} \Delta\varepsilon_d(\mathbf{k}), \quad (4.10)$$

where $w_{\mathbf{k}}$ and $f_{\mathbf{k}}$ is the weight and occupation of the $\mathbf{k}$ -point, respectively. The defect band dispersion is typically strongest at the Γ -point, which means that a Γ -only $\mathbf{k}$ -point sampling can lead to large errors for defect calculations [187]. The error will be smaller if many $\mathbf{k}$ -points are sampled, since the average will be closer to the level of the isolated defect. However, this averaging can be achieved at lower computational cost by selecting special $\mathbf{k}$ -points [187]. As an extreme case, we consider the cell-size dependence of the formation energy of the unrelaxed $V_{\text{O}_2}^0$ in $\beta\text{-Ga}_2\text{O}_3$. The band structures in Fig. 4.5 show that $V_{\text{O}_2}^0$ introduces a fully occupied KS defect state in the band gap with strong dispersion. The magnitude of this dispersion decreases when the number of atoms N_{atom} in the supercell is increased from 80 to 160. As demonstrated by the cell-size dependence of the formation energy, shown on the right side in Fig. 4.5, convergence is reached significantly faster when the special $\mathbf{k}$ -point at (0.25,0.25,0.25) is used, compared to the Γ -only $\mathbf{k}$ -point sampling. Indeed, comparing the band structures, the energy sampled by the special $\mathbf{k}$ -point is relatively stable, and is presumably close to the level of the isolated defect state. In contrast, the Γ -point samples an extreme value of the band which approaches the special $\mathbf{k}$ -point as N_{atom} is increased. Thus, Γ -only sampling should generally be avoided, even though it allows larger supercells to be employed.

As explained in Sec. 4.2, shallow defects exhibit extended states. Such states cannot be adequately described within computationally affordable supercells [3, 176]. For example, in a tight-binding study of the shallow P donor in Si, a cubic supercell with $N_{\text{atom}} = 125\,000$ was required to fit the defect state and converge the binding energy [196]. For this reason, formation energy diagrams typically only show the charge state(s) corresponding to full ionization of the shallow defect, e.g., for the shallow Si_{Ga} single donor in $\beta\text{-Ga}_2\text{O}_3$, only the positive charge state would be shown, even though there should be a $\varepsilon(+/0)$ level very close to the CBM [131]. For the same reason, excitonic effects have been ignored when calculating optical transition energies in the present thesis.

4.5.2 Electrostatic interactions

Calculations for charged defects can be performed by simply adding or removing electrons from the defect-containing supercell. However, because the electrostatic energy diverges for a charged periodic supercell, a compensating background charge (or jellium) must be included, which is accomplished by setting the average electrostatic potential to zero [156]. As explained in Ref. [8], this can introduce nonphysical shifts in the electrostatic potential, which effectively leads to a shift in E_{VBM} and an error in the defect formation energy (Eq. 4.2). The addition or removal of atoms from the bulk supercell to create the defect can also introduce shifts in the average electrostatic potential, which is neglected

4. Point defect calculations

Figure 4.5: Left: Band structure of the 80- and 160-atom supercells, showing the VB and the deep KS defect state of $V_{\text{O}_2}^0$. Dashed lines correspond to the energy of the defect state for Γ and Special $\mathbf{k}$ -point sampling. The dispersion of the defect state is reduced as the cell-size increases. Right: Cell-size dependence of the formation energy of the unrelaxed $V_{\text{O}_2}^0$ in $\beta\text{-Ga}_2\text{O}_3$ for Γ - and special $\mathbf{k}$ -point sampling. The numbers of atoms in the different supercells are indicated.

by the convention of setting the average electrostatic potential to zero [197]. These shifts result in the electrostatic potential of the bulk supercell not being recovered far from the defect, and so a potential alignment must be performed. Furthermore, the electrostatic interaction of the charged defect with its periodic images and the background charge (image charge interaction) is long-ranged and leads to a slowly converging cell-size dependence in the formation energy. For charged defect calculations, this interaction is typically the dominant finite-size error contribution, unless the dielectric constant of the host material is large enough to screen it. The magnitude of the interaction can be estimated by the Madelung energy of a periodically repeated point charge (PC) immersed in a compensating background charge, which is given by [198, 199]

$$E_{\text{iso}}^{\text{PC}} = \frac{\alpha q^2}{2\epsilon L}, \quad (4.11)$$

for a cubic supercell, where L is the side length of the supercell and α is the Madelung constant for the relevant Bravais lattice. Note that this is only the leading term of the Makov-Payne correction [200], which includes a further term scaling as L^{-3} , arising from the quadrupole moment of the charge distribution. Due to the slow $q^2/\epsilon L$ decay in Eq. 4.11, the brute force approach of increasing the cell-size is not viable, and the error must be removed after the calculation. Several correction schemes based on electrostatics for model systems have been proposed [176, 197, 200–204]. In the present work, the anisotropic [204] Freysoldt–Neugebauer–Van de Walle (FNV) correction [201] has been employed. Several reviews have concluded that this scheme is reliable, provided that the defect

state is well-localized within the supercell [197, 203, 204]. The correction is given by two terms

$$E_{\text{cor}}^{\text{FNV}} = E_{\text{aniso}}^{\text{PC}} - q\Delta V_{q/\text{bulk}|\text{far}}^{\text{PC}}. \quad (4.12)$$

The first term is similar to $E_{\text{iso}}^{\text{PC}}$ (Eq. 4.11), but has been adapted for materials with anisotropic dielectric response (such as ZnO and β -Ga₂O₃). $E_{\text{aniso}}^{\text{PC}}$ is calculated by using Ewald summation [204, 205], and is usually the dominant $E_{\text{cor}}^{\text{FNV}}$ term. Note that the static $\bar{\epsilon}_0$ (high-frequency $\bar{\epsilon}_\infty$) dielectric tensor should be employed when the defect is relaxed (unrelaxed). The second term uses the calculated DFT potential to align the potentials in the charged defect-containing and bulk supercells, after subtracting the PC model potential [201, 202], i.e.,

$$\Delta V_{q/\text{bulk}}^{\text{PC}} = V_{\text{defect},q}^{\text{DFT}} - V_{\text{bulk}}^{\text{DFT}} - V_{\text{aniso}}^{\text{PC}}, \quad (4.13)$$

in a region far away from the defect. The efficacy of the correction, and thus the validity of the underlying assumptions, can be checked by verifying that this potential difference reaches a plateau far away from the defect. Following the recommendation of Kumagai and Oba, the atomic site potential was used as the marker to determine the alignment-term in the present thesis [204].

The development of finite-size corrections for charged defects has been instrumental to improve the accuracy of first-principles defect calculations based on the supercell approach, and continues to be an active research topic. Indeed, Gake *et al.* [206] recently proposed a method to correct the finite-size error in optical charge-state transition energies [206]. It is not immediately obvious why this would require a separate correction scheme, e.g., when an electron is added to a relaxed positively charged deep-level defect, one would perhaps not expect any spurious electrostatic interactions for the resulting charge-neutral defect. However, this is not correct, because the interaction of the added charge ($q_{\text{add}} = -1$) with the periodic images of the initial state ($q_1 = +1$) is screened by ϵ_0 , whereas the interaction with its own image is screened by ϵ_∞ , and these interactions do not cancel [206]. The Gake–Kumagai–Oba–Freysoldt (GKFO) correction for the optical transition energy $\mu(q_1/q_2)$ is given by [206]

$$E_{\text{cor}}^{\text{GKFO}} = \frac{2q_{\text{add}}}{q_1} E_{\text{aniso}}^{\text{PC},q_1}(\bar{\epsilon}_0) + E_{\text{aniso}}^{\text{PC},q_{\text{add}}}(\bar{\epsilon}_\infty) - \left(q_{\text{add}} \Delta V_{q_{\text{add}}/q_1|\text{far}}^{\text{PC}} + q_{\text{add}} \Delta V_{q_1/\text{bulk}|\text{far}}^{\text{PC}} + \frac{\langle \epsilon_0 \rangle}{\langle \epsilon_\infty \rangle} q_1 \Delta V_{q_{\text{add}}/q_1|\text{far}}^{\text{PC}} \right), \quad (4.14)$$

which is again divided into PC energy and potential alignment terms. The first two terms are PC energies for q_1 and q_{add} screened by the static and high-frequency dielectric tensors $\bar{\epsilon}_0$ and $\bar{\epsilon}_\infty$, respectively, while the parenthesis contains the potential alignment terms. $\langle \epsilon \rangle$ is the averaged dielectric constant.

For a discussion on the elastic and magnetic interactions, the reader is referred to Ref. [3] and references therein. The errors in formation energy resulting from these interactions scale approximately as $1/L^3$, and are usually small compared to the abovementioned errors for typical supercell-sizes. However, this is not always the case, e.g., as discussed in paper III, V_{O} in ZnO induces large lattice

4. Point defect calculations

distortions (and thus significant elastic interactions) owing to its negative- U behavior, and therefore requires a larger supercell to obtain converged results. When studying a new type of defect or material, it is recommended to perform supercell-size tests with a conventional functional (as exemplified by Fig. 4.5) to verify that the corrections are valid and the results are converged.

Chapter 5

Summary of Results

This thesis investigates point defects in ZnO and β -Ga₂O₃ from hybrid functional calculations, with special emphasis on obtaining results that can be compared directly with experimental data. Comparison between theory and experiment can be a valuable aid in the identification of defect spectroscopic signatures, and provide additional insight into the defect physics (beyond the property that is compared), but it can also shed light on the limitations of the employed electronic structure method. The approach of using 1D CC diagrams derived from hybrid functional calculations, as explained in Sec. 4.4, was used in many cases for comparison with experimental data in the present work. Prof. Audrius Alkauskas has been involved in the development this approach over the last years [4, 11–14], and contributed to its use in the present work, providing guidance as well as code to calculate the luminescence lines in the harmonic approximation (see Sec. 4.4). Some of the appended papers are entirely theoretical studies, where the results are compared with experimental data from the literature only, and some are combined theoretical and experimental efforts, as detailed below.

The properties of the defects explored in ZnO and β -Ga₂O₃ are similar in many regards, and the results can be roughly divided into three groups:

- (i) *Small polarons and polaronic acceptors* (Papers I, II, IV and V). Here, the theoretical predictions were mostly compared with experimental data from the literature. The exception is Paper IV, where the calculations were supplemented by experimental SIMS and PL measurements.
- (ii) *Charge-state transition levels of Fe and Ti impurities* (Papers VI and VII). Here, the hybrid functional calculations were compared with DLTS measurements (Paper VI), and used as input to model experimental steady-state photo-capacitance spectra (Paper VII).
- (iii) *Negative- U behavior of O vacancies and divacancies* (Papers III, VIII, IX and X). Paper III is a theoretical study, where the results were compared with experimental data from the literature. Paper VIII is an experimental study of a DLTS signature, where the proposed defect model was separately investigated from hybrid functional calculations in Paper IX. In Paper X, the calculations were compared with DLTS measurements.

The results from each group above will be presented separately below, allowing comparison of results on defects in ZnO and β -Ga₂O₃.

The results from the appended papers were also used in related work, not included in the present thesis. Notably, calculated formation energy diagrams and defect complex binding energies were used as input to model the diffusion of In [207] and Li [208] impurities in ZnO, as measured by SIMS on sequentially

heat treated samples. The experimental In and Li depth distribution profiles could be well described by reaction-diffusion models. Specifically, the diffusion of In in *n*-type material was described as being mediated by V_{Zn}^{2-} through the intermediate formation and dissociation of $(\text{In}_{\text{Zn}}\text{V}_{\text{Zn}})^-$ complexes [207]. For the diffusion of Li in Ga-doped ZnO at 850–1050 °C, the model invoked the dissociation of $(\text{Ga}_{\text{Zn}}\text{Li}_{\text{Zn}})^0$ into $(\text{Ga}_{\text{Zn}}\text{V}_{\text{Zn}})^-$ and highly mobile Li_i^+ [208].

5.1 Small hole polarons and polaronic acceptors

Charge carriers associated with deep level defects are generally localized at the defect. Interestingly, such charge localization can in some cases occur in the absence of defects, i.e., in the perfect crystal lattice. This phenomenon is commonly observed in polar semiconductors, e.g., metal oxides [209]. The charge carrier becomes spatially localized and displaces the nearby ions, resulting in a polarization cloud that acts as a potential well for the carrier [209]. The localized charge and lattice distortion constitutes a quasiparticle called a polaron [210, 211], and they can be large or small, with respect to their spatial extent.

Small hole polarons, also commonly referred to as self-trapped holes (STHs), are formed in $\beta\text{-Ga}_2\text{O}_3$ (and are predicted to form in other polymorphs [108]), but not in ZnO [110]. However, hole polarons can be further stabilized at defects, especially acceptors (e.g., Li_{Zn} [76]), and are thus present in both materials. The following subsections will summarize the results on polaronic defects in ZnO and $\beta\text{-Ga}_2\text{O}_3$ (Papers I, II, IV, V). The calculations for this group of defects were mainly focused on their luminescence properties, and thus comparison with experimental data from optical characterization will be emphasized here.

5.1.1 Self-trapped holes

The HSE hybrid functional is capable of describing small hole polaron formation in a host of different oxide semiconductors, including $\beta\text{-Ga}_2\text{O}_3$ [110]. In contrast, semilocal functionals erroneously prefer to delocalize the excess charge (due to the residual self-interaction error). Figure 5.1 shows the relaxed structures of the three possible STH configurations, owing to the presence of three symmetrically inequivalent O sites in $\beta\text{-Ga}_2\text{O}_3$. The localized hole is accompanied by a local lattice distortion, which mostly involves the nearest-neighbor Ga atoms. To stabilize the localized hole onto different sites, ionic displacements must be introduced manually before initiating the ionic relaxation, as discussed in Sec. 4.1. Moreover, if no displacements are introduced, hole localization will not occur. In line with previous HSE calculations by Varley *et al.* [110] and Gake *et al.* [108], the hole is localized at a single O1 atom for STH_{O1} , and shared between two O2 atoms for STH_{O2} . As revealed in Paper V, hole localization onto the O3 site is also possible, albeit metastable, and requires breaking the Ga1–O3 bond. Notably, an EPR signal observed in irradiated $\beta\text{-Ga}_2\text{O}_3$ samples was attributed to the STH_{O1} model by Kananen *et al.* [212]. However, this assignment has later been contested by a model invoking V_{Ga2} as the origin [213].

Figure 5.1: Relaxed STH structures for the three possible O sites. The hole (blue isosurface) can be localized at a single O atom (STH_{O1}, STH_{O3}), or shared between two (STH_{O2}) O atoms. STH_{O3} is metastable and requires breaking the O3-Ga1 bond, where the Ga1 displacement is indicated by an arrow.

STH formation has profound implications for the electrical and optical properties of β -Ga₂O₃. Even if *p*-type material could be achieved, the resulting holes would exhibit low mobility [110]. As mentioned in Sec. 2.2, the STH formation is also evident from the PL spectrum of β -Ga₂O₃, which does not exhibit any NBE emission, but is dominated by a broad ultraviolet luminescence (UVL) band peaking between 3.1 and 3.6 eV that is widely attributed to STHs. In ZnO, photogenerated electron-hole pairs form free excitons at low temperatures, which recombine and give rise to a sharp and intense NBE. In β -Ga₂O₃, however, self-trapped excitons (STEs) are primarily formed, giving rise to broad UVL. The broadness of the UVL band is indicative of strong electron-phonon coupling, consistent with highly localized charge carriers taking part in recombination.

In Paper V, the UVL band in β -Ga₂O₃ was used to benchmark the accuracy of luminescence lines calculated using 1D CC diagrams derived from hybrid functional calculations (approach outlined in Sec. 4.4). Figure 5.2 shows the calculated luminescence lines for STH_{O1} and STH_{O2}. The broad lineshapes are consistent with experimental observations for the UVL. The peak positions (PPs) occur at 3.11 and 3.05 eV for STH_{O1} and STH_{O2}, respectively. These are near the lower end of the range reported in the experimental literature, which may indicate that they are somewhat underestimated. Nevertheless, the results are encouraging for the prospect of applying this approach to other polaronic defects as an aid in the identification of other broad PL bands in β -Ga₂O₃.

5.1.2 Ga and Zn vacancies

The small hole polarons described above can be stabilized further by binding to defects, and significantly so for negatively charged acceptors due to Coulomb attraction. The defect can also locally increase the structural flexibility, making the necessary polaronic lattice relaxations energetically less costly [209, 214]. Defects that trap charge-carriers in polaron-like states are termed polaronic.

Figure 5.2: Luminescence lines calculated for optical transitions involving recombination of STH_{O1} or STH_{O2} with a free electron at the CBM.

Cation vacancies are exceedingly deep traps for small hole polarons in $\beta\text{-Ga}_2\text{O}_3$ and ZnO . We begin with V_{Zn} in ZnO , which is the subject of Paper I. Figure 5.3 shows the formation energy diagram of V_{Zn} . Under n -type conditions, the 2^- charge state is energetically preferred, which means that V_{Zn} will act as a compensating acceptor [82, 215]. As the Fermi level is lowered, V_{Zn} can capture up to four holes, and thus assume charge states ranging from 2^+ to 2^- within the band gap. Each hole resides in a polaronic state, which consists of hole localization at one of the four nearest-neighbor O ions and a characteristic polaronic distortion. This distortion mostly involves the O^- ion with the localized hole and the three adjacent Zn ions, which relax away from the vacancy. This is consistent with experimental EPR data [44, 85, 86, 216]. Figure 5.4 shows the relaxed structure of V_{Zn}^{2+} , which corresponds to four bound hole polarons.

As discussed in Paper I, the thermodynamic charge-state transition levels of V_{Zn} are approximately equidistant in Fermi level position. This reflects the approximate T_d local symmetry, and can be rationalized from a simple polaron energetics model. When $E_F = 0$, adding a hole polaron to V_{Zn}^{2-} lowers the formation energy by $\varepsilon_{\text{polaron}}$, which implies $\varepsilon(-/2-) = \varepsilon_{\text{polaron}}$. Because of the local symmetry, subsequent hole capture lowers the energy by the same amount, minus an additional hole-hole Coulomb repulsion energy U_{hole} for each polaron already present at V_{Zn} . Thus, the separation between levels is approximately given by U_{hole} . In fact, same trend holds for V_{Ga} in GaN [217], which similarly exhibits polaronic defect states and the wurtzite structure.

The formation energy diagram of V_{Ga} in $\beta\text{-Ga}_2\text{O}_3$, shown in Fig. 5.3, was not included in any of the appended papers, but will be discussed briefly here for sake of comparison with ZnO . V_{Ga} in $\beta\text{-Ga}_2\text{O}_3$ is a triple rather than a double acceptor, but its properties are much the same as those of V_{Zn} in ZnO . Indeed, V_{Ga} can also bind up to four hole polarons, resulting in charge-states ranging from $+$ to 3^- within the band gap, as shown in Fig. 5.3. However, V_{Ga} in $\beta\text{-Ga}_2\text{O}_3$ can occur in five different configurations [145], including three

Figure 5.3: Formation energy diagram for V_{Zn} in ZnO and the five different V_{Ga} configurations in $\beta\text{-Ga}_2\text{O}_3$ under O-rich and Zn/Ga-rich conditions.

split-vacancy configurations, as depicted in Fig. 5.4. Transformation of the simple vacancies into the ib and ic configurations lowers the formation energy considerably, particularly under n -type conditions (see Fig. 5.3). Unlike V_{Zn} in ZnO, the thermodynamic charge-state transition levels of V_{Ga} in $\beta\text{-Ga}_2\text{O}_3$ are not equidistant. This is due to the low degree of symmetry of $\beta\text{-Ga}_2\text{O}_3$, as well as the variation in coordination numbers between different O sites. However, there are still some notable trends in terms of which O ions are energetically preferred for hole localization. Generally, holes trapped at V_{Ga} prefer to localize onto the nearest-neighbor O ion with the lowest coordination number. Furthermore, when more than one hole polaron is captured, the holes will prefer to maximize their mutual distance (to minimize U_{hole}). For example, the two holes bound to $(V_{\text{Ga}}^{\text{ib}})^-$ are localized on opposite sides of the complex (at the O ions with coordination number two in Fig. 5.4), resulting in a small separation between $\varepsilon(-/2-)$ and $\varepsilon(2-/3-)$. This happens for $(V_{\text{Ga}}^{\text{ic}})^-$ as well, but in this case the O ions are three- rather than two-fold coordinated, making the $\varepsilon(-/2-)$ and $\varepsilon(2-/3-)$ levels significantly shallower than the corresponding levels of $V_{\text{Ga}}^{\text{ib}}$.

As primary intrinsic defects exhibiting low formation energy in n -type ZnO and $\beta\text{-Ga}_2\text{O}_3$, especially under O-rich conditions, cation vacancies are commonly invoked to explain experimental results, e.g., as defect candidates for various broad luminescence bands observed by PL spectroscopy. In ZnO, V_{Zn} has been suggested as the defect origin of the commonly observed GL [81, 218, 219], and

Figure 5.4: Relaxed structures for V_{Zn} in ZnO, and V_{Ga} in β -Ga₂O₃. The 2+ charge state of V_{Zn} is shown, which corresponds to a hole polaron (blue isosurface) trapped at each nearest-neighbor O ion; the axial (ax) and azimuthal (az) O-ions are indicated. The 3- charge state is shown for all V_{Ga} configuration, and the coordination numbers of the nearest-neighbor O ions are indicated. The vacancies (white spheres) are highlighted with translucent dotted circles.

the high-energy electron irradiation induced red luminescence (RL) band peaking at 1.8 eV [83, 86, 220]. In β -Ga₂O₃, V_{Ga} has been suggested to be involved in blue luminescence (BL) bands [150, 221–223]. The possibility of cation vacancies being involved in broad visible luminescence was investigated in Papers I and V by using CC diagrams derived from hybrid functional calculations.

In n -type ZnO and β -Ga₂O₃, optical transitions involving the capture of an electron at the CBM by V_{Zn}^{2-} and V_{Ga}^{2-} could occur. However, the resulting luminescence bands are predicted to occur in the infrared region (~ 0.7 eV for V_{Zn} and 0.1–1.2 eV for the different V_{Ga} configurations), as shown for V_{Zn} in Fig. 5.5. These transitions will likely exhibit a significant nonradiative component due to crossing between the ground- and excited-state potential energy curves in the CC diagrams (as shown for V_{Zn} in Paper I). Radiative capture of a photogenerated hole by V_{Zn}^{2-} and V_{Ga}^{3-} is also a possibility. However, the former results in an emission energy of ~ 1.3 eV, which is also relatively low, and the latter is improbable due to STH formation in β -Ga₂O₃. Furthermore, this process would have to compete with efficient nonradiative hole capture by shallower acceptors, like Li_{Zn} in ZnO [12, 88]. Hence, under n -type conditions, isolated V_{Zn} and V_{Ga} are not expected to cause visible broad luminescence.

Figure 5.5: A selection of luminescence lines for optical transitions involving V_{Zn} in ZnO and V_{Ga} in $\beta\text{-Ga}_2\text{O}_3$, calculated using 1D CC diagrams derived from hybrid functional calculations (from Papers I and V).

In high-resistive ZnO, V_{Zn} could occur in the $-$ and 0 charge-states, as observed in electron-irradiated material by EPR [86], enabling transitions involving the $(0/-)$ and possibly the $(+/0)$ levels. Capture of electrons at the CBM by V_{Zn}^0 and V_{Zn}^+ results in emission energies of 1.25 and 1.75 eV, respectively. The latter is thus a good candidate for the defect origin of the high-energy electron irradiation induced RL band at 1.8 eV, as suggested previously in the experimental literature [83, 84, 86]. However, this is hard to reconcile with the *in-situ* PL and optically detected magnetic resonance (ODMR) measurements on high-energy electron irradiated VP ZnO at 4.2 K by Vlasenko *et al.* [224]; the irradiation produced a double-humped infrared band peaking at 1.38 and 1.65 eV, which disappeared after subsequent annealing at ~ 65 –150 K. Vlasenko *et al.* [224], attributed the double-humped PL band to V_{Zn} or close Frenkel pairs. The RL band was not produced immediately by the irradiation, but appeared during subsequent annealing at ~ 180 K, which suggests a complex rather than a primary intrinsic defect origin, unless the ~ 180 K anneal caused a large shift in the Fermi level position (enabling transitions involving the $(+/0)$ level of V_{Zn}). Other candidates for the RL band will be discussed in Sec. 5.1.4.

In high-resistive $\beta\text{-Ga}_2\text{O}_3$, the emission from V_{Ga} can similarly shift towards higher energies, as the $1-$ and $2-$ charge states become favorable for Fermi-level positions near mid gap. For example, the luminescence resulting from optical transitions between the CBM and the $(0/-)$ level of $V_{\text{Ga}}^{\text{ib}}$ (the most favorable V_{Ga} configuration) is predicted to peak at 1.93 eV, as shown in Fig. 5.5.

5.1.3 Acceptor impurities

Cation substitutional acceptor impurities in ZnO and $\beta\text{-Ga}_2\text{O}_3$ can also trap holes in polaronic states. Paper IV explored Li_{Zn} and Na_{Zn} acceptors in ZnO, which are particularly common impurities in HT grown material. Both of these

5. Summary of Results

Figure 5.6: Luminescence lines for the optical transitions involving electron capture from the CBM by charge-neutral polaronic acceptor impurities Li and Na in ZnO (Paper IV), and Mg, Ca, Cd and Zn in β -Ga₂O₃ (Paper V). A fit of the OL band from experimental PL data [75] is included for comparison.

acceptors introduce a deep $\varepsilon(0/-)$ acceptor level, where the neutral charge state corresponds to a small hole polaron bound to the axial or azimuthal nearest-neighbor O ion, similar to V_{Zn} [73, 76, 77]. As mentioned in Sec. 2.1, Li_{Zn} has been ascribed to an OL band peaking at 1.95 eV at 10 K, which is present in HT grown material [88]. Na_{Zn} has similarly been linked with a broad yellow luminescence (YL) band peaking at 2.18 eV at 50 K [225]. The $\varepsilon(0/-)$ levels of Li_{Zn} and Na_{Zn} are predicted to occur at 0.67 and 0.68 eV above the VBM, respectively. This translates into a ZPL energy of 2.77 eV for Li_{Zn} , consistent with the experimental value of ~ 2.8 eV for the OL band [88]. Figure 5.6 shows the luminescence lines calculated for optical transitions between the CBM and the $(0/-)$ levels. The shape and position of the OL band has been characterized experimentally; a Gaussian fit of the OL band from PL measurements at 10 K is included in Fig. 5.6 [75]. The PP and FWHM of the calculated luminescence lines for Li_{Zn} (1.90 and 0.43 eV) and Na_{Zn} (2.11 and 0.36 eV) are underestimated compared to the corresponding experimental values for the OL (1.95 and 0.5 eV [75]) and YL (2.18 and 0.4 eV [225]) band. Nevertheless, the agreement with the experimental data is good, which is reassuring for the possibility of using the 1D CC approach to aid in the identification of other PL bands in ZnO.

Paper IV similarly explored the luminescence properties of acceptor impurities in β -Ga₂O₃. The aforementioned UVL band ascribed to STHs (see Sec. 5.1.1) is sometimes overlapped by other broad bands on its low energy side, in the visible part of the emission spectrum. Experimental characterization of the visible broad luminescence in β -Ga₂O₃ is still in the early stages, but single acceptor impurities like Mg_{Ga}, Be_{Ga}, Li_{Ga} and Zn_{Ga} have been suggested as candidates responsible for GL and BL bands based on correlation with impurity content and electrical conductivity in different samples [19, 84, 150]. Luminescence lines calculated for Mg_{Ga2}, Ca_{Ga2}, Cd_{Ga2} and Zn_{Ga1} are shown in Fig. 5.6. The results indeed suggest that polaronic acceptor impurities can give rise to luminescence bands peaking in the visible part of the spectrum, specifically the 1.5–2.6 eV range. For example, an increase in the BL intensity (at around 2.8 eV) was observed in a cathodoluminescence study on Mg-doped β -Ga₂O₃ [150]. The calculated PP for Mg_{Ga} is 2.3–2.5 eV, depending on the hole location. This is reasonably close to the experimental data, especially considering the possible underestimation in the calculated peak positions for the STHs relative to the UVL band.

5.1.4 Complexes with shallow donor impurities

As-grown ZnO and β -Ga₂O₃ crystals normally show unintentional *n*-type conductivity due to residual shallow donor impurities (Sec. 2). Attractive electrostatic interaction makes it likely for such donor impurities to form stable complexes with acceptors. Paper II explored the thermodynamic and optical properties of complexes between V_{Zn} and shallow donor impurities Al, Ga, Si and H in ZnO. The low formation energy of V_{Zn} under *n*-type conditions means that such complexes are likely to form, especially for intentionally *n*-doped material, making it important to understand their properties [39, 82, 215, 226]. Figure 5.7 shows the formation energy diagram for V_{Zn} and several V_{Zn} –donor impurity complexes. Complexing V_{Zn} with shallow donors successively removes its charge-state transition levels. For the remaining levels, the close proximity of the donor leads only to modest shifts in their Fermi level position, as highlighted by the grey bars in Fig. 5.7. Upon closer inspection, the levels of complexes involving H (Zn substitutional donors) shift down (up) in Fermi level position, relative to those of the isolated V_{Zn} . This can be understood from the aforementioned polaron energetics model, taking into account the magnitude of the hole–donor repulsion. For example, the Al⁺_{Zn} donor in the $(V_{Zn}Al_{Zn})^0$ complex is located far away from the hole polaron, compared to the hole–hole separation in V_{Zn}^0 , resulting in $U_{Al^+} < U_{hole}$ and a deeper $\varepsilon(0/-)$ level for the complex. This trend holds for the other complexes shown in Fig. 5.7, as discussed in Paper II, and thus the polaron energetics model can be conveniently used to qualitatively predict the Fermi level positions of charge-state transition levels for complexes relative to those of V_{Zn} . The same trend is found for V_{Ga} –donor impurity complexes in β -Ga₂O₃. For example, Fig. 5.7 shows the formation energy of V_{Ga}^{ib} and the aforementioned $V_{Ga}^{ib}2H$ complex, where the thermodynamic charge-state transition levels of the complex are close to those of the corresponding isolated V_{Ga}^{ib} .

5. Summary of Results

Figure 5.7: Formation energy of a selection of V_{Zn} - and V_{Ga} -donor impurity complexes in ZnO and $\beta\text{-Ga}_2\text{O}_3$ under O-rich conditions. The grey vertical bars show the Fermi level range of the different charge-state transition levels.

V_{Zn} -donor impurity complexes can take part in optical transitions, just like the isolated V_{Zn} . As shown in Fig. 5.8, the successive passivation of the V_{Zn} defects states by the shallow donors has the effect of shifting its luminescence away from the IR region and towards the visible part of the spectrum. Notably, the luminescence lines predicted for complexes with two single donors (or one double) peak close to the aforementioned high-energy electron irradiation induced RL band, which has been associated with a V_{Zn} related origin. Figure. 5.8 includes experimental PL data from Ref. [83], which shows the RL band that appears after 1.2 MeV electron irradiation. The calculated $V_{\text{Zn}}2\text{H}$ luminescence line, in particular, is an excellent fit for the RL band, both in shape and position. An assignment to such a complex could also explain why the RL band emerges only after annealing at ~ 180 K, as found by Vlasenko *et al.* [220, 224], e.g., by migration of H_i and trapping at V_{Zn} formed by the electron irradiation. Indeed, the appearance of EPR signals from V_{Zn} -donor complexes after high-energy electron irradiation has been reported by several groups [39, 44, 65, 86].

Complexes between polaronic acceptor and shallow donor impurities are also known to form in ZnO. For example, the $\text{Li}_{\text{Zn}}\text{H}$ complex has been assigned to an IR absorption line at 3577 cm^{-1} , which is the dominant O-H-related line in HT grown ZnO [67]. Complexing Li_{Zn} with a single shallow donor impurity results in an overall charge-neutral pair. However, in Paper IV, it was shown that such complexes are not necessarily fully passivated, as the $\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Li}_{\text{Zn}}\text{H}$ and $\text{Li}_{\text{Zn}}\text{H}_2\text{O}$ complexes (and the corresponding complexes with Na_{Zn}) exhibit thermodynamic (+/0) transition levels occurring 80-370 meV above the VBM.

Figure 5.8: Luminescence lines for optical transitions involving V_{Zn} -donor complexes in ZnO, calculated using 1D CC diagrams (Paper II). PL data from Ref. [83] is also included, showing the RL band in a ZnO sample under 325 nm excitation at 10 K after irradiation by 1.2 MeV electrons.

The positive charge state corresponds to a small hole polaron at one of the O ions adjacent to the Li ion, similar to the isolated acceptors.

The emergence of the (+/0) transition levels for the complexes has important consequences for the optical properties of Li and Na in ZnO. As shown in Fig. 5.9, electron capture from the CBM by the positively charged complexes results in luminescence bands peaking at the high-energy side of those originating from the corresponding isolated acceptors. The OL band in HT grown ZnO is usually overlapped by a broad GL at its high energy side (peaking at around ~ 2.4 eV) [75, 87, 88]. The complexes are potential candidates for the origin of this GL. The overlap in shape and position for the luminescence originating from the isolated and donor-complexed acceptors could make experimental identification challenging. However, as discussed in Paper IV, the isolated and donor-complexed acceptors are expected to show differences in other band characteristics, e.g., carrier capture coefficients, lifetime, and temperature dependence, which could be revealed by performing temperature- and time-resolved PL measurements. This is discussed in detail in Paper IV. The overall picture is remarkably similar to the C_N acceptor and C_NH complex in GaN, which have been assigned to the well-studied YL and BL bands in C doped GaN [88, 227].

The possibility of the GL in HT ZnO being related to Li was also explored by experimental PL and SIMS data in Paper IV. The Li concentration in a HT ZnO sample was lowered from 2×10^{17} to 2×10^{14} cm^{-3} by annealing at 900 °C at 1 h in a sealed quartz ampoule containing a piece of Zn foil. The change in Li concentration was accompanied by a strong reduction in intensity of the entire broad luminescence band, which may suggest that Li is involved not only in the OL band, but also in the broad GL at its high-energy side.

The luminescence properties of polaronic acceptors complexed with H donors in $\beta\text{-Ga}_2\text{O}_3$ were also studied in this thesis (see Paper V). For example, the

Figure 5.9: Luminescence lines for optical transitions involving complexes between Li_{Zn} and Na_{Zn} acceptors, and donor impurities in ZnO , calculated using 1D CC diagrams derived from hybrid functional calculations (Paper IV).

luminescence line predicted for the $\text{Mg}_{\text{Ga}2}\text{H}$ complex peaks at 2.71 eV, i.e., shifted up in energy relative to the isolated $\text{Mg}_{\text{Ga}2}$. Together with the isolated acceptor impurities, such complexes are potential candidates for the visible luminescence bands observed at the low energy side of the UVL band in $\beta\text{-Ga}_2\text{O}_3$.

5.2 Charge-state transition levels of Fe and Ti impurities

An important objective in the work presented in this thesis is to bridge the gap between theoretical modeling and experimental studies. To this end, it is important to be able to assess the accuracy of the predictions by comparing them with experimental data. However, valid comparison requires a defect signature that has been firmly identified experimentally. There is now strong experimental evidence that the E_2 and E_3 centers, which are commonly observed by DLTS in $\beta\text{-Ga}_2\text{O}_3$, originate from Fe_{Ga} and Ti_{Ga} , respectively, as explained in Sec. 5.2.1 below. Moreover, the optical absorption of Fe_{Ga} has recently been studied experimentally by photo-EPR [228]. Hence, Fe_{Ga} and Ti_{Ga} can serve as a model system to benchmark the accuracy of the hybrid functional and 1D CC approach. In Papers VI and VII, the thermodynamic and optical charge-state transition levels of Fe_{Ga} and Ti_{Ga} were compared with experimental DLTS and steady-state photo-capacitance spectroscopy measurements, respectively.

5.2.1 Thermodynamic charge-state transition levels

Paper VI investigated the E_2 and E_3 centers in as-received bulk $\beta\text{-Ga}_2\text{O}_3$ crystals grown by the EFG-, CZ-method, and thin-films grown by HVPE. DLTS spectrum simulations indicated that the E_2 signature, observed as a single peak in previous studies, actually consists of two centers, labeled E_{2a} and E_{2b} , exhibiting activation energies of 0.66 and 0.73 eV, respectively. The E_3 signature, on the

other hand, could be modeled as a single center with an activation energy of 0.95 eV. The presence of two distinct overlapping peaks in the E_2 signature was confirmed by performing Laplace DLTS measurements, which allow superior resolution compared to that of conventional DLTS [229]. The trap concentrations associated with E_{2a} and E_{2b} were found to exhibit a ratio of 1:5. A similar ratio has been reported between the EPR signals of Fe^{3+} on the tetrahedral and octahedral Ga sites [230], and so E_{2a} and E_{2b} were assigned to $\text{Fe}_{\text{Ga}1}$ and $\text{Fe}_{\text{Ga}2}$, respectively. The concentrations of E_{2a} , E_{2b} and E_3 varied over a wide range in the bulk material. The concentrations of impurities in the samples (Ti, Fe, Mg, Al and Si), as measured by SIMS, confirmed the previously reported correlation between Fe and E_2 [138], while the concentration of E_3 was revealed to be correlated solely with the Ti concentration, which strongly suggests a $\text{Ti}_{\text{Ga}2}$ origin, considering the reported EPR signal from $\text{Ti}_{\text{Ga}2}$ in $\beta\text{-Ga}_2\text{O}_3$ [231].

To gain insight into the formation of defects involving Ti and Fe impurities in $\beta\text{-Ga}_2\text{O}_3$, hybrid functional calculations were performed. In n -type material, both Fe and Ti impurities prefer to substitute on the Ga site. Figure 5.10 shows the formation energy of the two different configurations of Fe_{Ga} and Ti_{Ga} . Both configurations exhibit thermodynamic charge-state transition levels in the band gap close to the CBM, i.e., an exceedingly deep (0/-) acceptor level for Fe_{Ga} , and a (+/0) donor level for Ti_{Ga} . The 1- and 0 charge states of Fe_{Ga} and Ti_{Ga} , respectively, correspond to an electron trapped in a defect state located mainly at the impurity itself and showing 3d orbital character; $\text{Fe}_{\text{Ga}1}^-$ is shown as an example in Fig. 5.10. The Fe_{Ga} configurations also exhibit a (+/0) donor level close to the VBM, but the positive charge state is actually associated with a polaronic defect state. Indeed, as shown in Fig. 5.10, $\text{Fe}_{\text{Ga}1}^+$ can be viewed as a $\text{STH}_{\text{O}1}$ located next to a $\text{Fe}_{\text{Ga}1}^0$. The 1:5 ratio between the concentrations of E_{2a} and E_{2b} suggests a formation energy difference of ~ 0.3 eV at the melting point temperature [232], which is reasonably close to the calculated formation energy difference of 0.39 eV between $\text{Fe}_{\text{Ga}1}^-$ and $\text{Fe}_{\text{Ga}2}^-$. For Ti_{Ga} , however, the corresponding difference is 0.87 eV, which indicates that $\text{Ti}_{\text{Ga}2}$ should be the dominant configuration, consistent with previously reported EPR data [233].

The positions of the thermodynamic charge-state transition levels near the CBM for $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$ are close to the measured activation energies of the E_{2a} , E_{2b} and E_3 centers, respectively. As discussed in Sec. 4.4, the capture barrier (shown in Fig. 4.3 a)) should be considered when comparing calculated charge-state transition levels with DLTS data. Table 5.1 compares the activation energies measured by DLTS for E_2 , E_{2a} , E_{2b} and E_3 with the hybrid functional calculations (ionization energies and capture barriers) for $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$. Previously reported numbers from the literature are also included. Overall, the agreement between theory and experiment is good, strengthening the assignments of the E_2 and E_3 centers to Fe_{Ga} and Ti_{Ga} , respectively.

5.2.2 Optical charge-state transition levels

Paper VI considered the thermodynamic (0/-) and (+/0) charge-state transition levels of Fe_{Ga} and Ti_{Ga} , respectively. These levels can also be probed optically,

5. Summary of Results

Figure 5.10: Left: Relaxed structure of $\text{Fe}_{\text{Ga}1}$, showing the deep defect state (blue isosurface) associated with the 1+ and 1- charge states. Right: Formation energy of Fe_{Ga} and Ti_{Ga} in $\beta\text{-Ga}_2\text{O}_3$ under intermediate conditions.

Table 5.1: Measured activation energies E_A (from Papers VI, VII and previous reports [138, 145, 151]) for the DLTS centers E_2 , E_{2a} , E_{2b} and E_3 in $\beta\text{-Ga}_2\text{O}_3$, proposed origin (defect and charge-state transition level), theoretically predicted ionization energy E_i , and capture barrier E_b obtained from the 1D CC diagram.

Signature	E_A (eV)	Proposed origin	E_i (E_b) (eV)
E_2	0.78 [138]	$\text{Fe}_{\text{Ga}}^{0/-}$	-
	0.74 [151]	-	
E_{2a}	0.66 [VI,VII]	$\text{Fe}_{\text{Ga}1}^{0/-}$	0.62 (0.05)
E_{2b}	0.73 [VI], 0.79 [VII]	$\text{Fe}_{\text{Ga}2}^{0/-}$	0.72 (0.02)
	0.95 [VI], 1.03 [VII]	$\text{Ti}_{\text{Ga}2}^{+/0}$	1.13 (0.00)
E_3	1.01 [145]	-	-
	1.04 [151]	-	-

e.g., by photoionization. Recently, Bhandari *et al.* [228] performed photo-EPR experiments to determine the optical charge-state transition level associated with the Fe^{2+} to Fe^{3+} transition, i.e., the transition of an electron from Fe_{Ga}^- to the CBM. An absorption spectrum was recorded by measuring the intensity of the Fe^{3+} EPR signal as a function of photon energy. Illumination with light of photon energy between 1.2 and 2.0 eV increased the amount of Fe^{3+} .

Within the CC model, the optical and thermal ionization energies differ by

the FC shift, as explained in Sec. 4.4. Figure 5.11 shows CC diagrams derived from hybrid functional calculations for transitions between the (0/-) transition levels of $\text{Fe}_{\text{Ga}1}$ and $\text{Fe}_{\text{Ga}2}$, and the CBM. The predicted FC shift is 1.10 and 1.05 eV for $\text{Fe}_{\text{Ga}1}$ and $\text{Fe}_{\text{Ga}2}$, respectively, resulting in corresponding absorption energies of 1.76 and 1.78 eV. Due to vibrational broadening, the onset of the absorption spectrum can differ significantly from the classical absorption energy in the CC model. The shape of the absorption onset can be simulated, with and without including the effect of temperature-dependent vibrational broadening, by using the expression derived by Kopylov and Pikhtin [234], using calculated CC parameters as input, as explained in Ref. [4]. Figure 2 in Paper VII shows the resulting absorption profiles for $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$. For Fe_{Ga} , the profiles have an onset at about 1.0 eV, and peak position at about 2.1 eV, which is consistent with the photo-EPR results reported by Bhandari *et al.* [228].

Figure 5.11: 1D configuration coordinate diagrams for electronic transitions between the CBM, and the (0/-) levels of $\text{Fe}_{\text{Ga}1}$ and $\text{Fe}_{\text{Ga}2}$.

In Paper VII, steady-state photo-capacitance spectroscopy (SSPC) measurements were performed on samples with known concentrations of $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$ (from DLTS measurements of the E_{2a} , E_{2b} and E_3 centers). SSPC measures the optically-induced emission of charge carriers from defect states by recording the change in the capacitance of a Schottky junction, after illuminating the junction for a certain time, as a function of photon energy. An SSPC signature labelled T_1^{EFG} was observed with a photon energy position and trap concentration close to the expected absorption energy of $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$, and concentrations of E_{2a} , E_{2b} and E_3 from DLTS. The calculated CC diagrams for $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$ were used as input (together with the recorded photon flux for the optical excitation used for the SSPC measurements, and the E_{2a} , E_{2b} and E_3 trap concentrations measured by DLTS) to simulate their SSPC spectra. Based on these simulations, the T_1^{EFG} signature was ascribed to overlapping defect signatures from $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$.

5.3 Negative- U behavior of O vacancies and divacancies

As donors and acceptors, $V_{\text{Zn/Ga}}$ and V_{O} , respectively, are likely to form stable $V_{\text{Zn/Ga}}V_{\text{O}}$ complexes, hereby referred to as divacancies. There are several reports on divacancies (and larger vacancy clusters) in ZnO in the experimental literature [235], especially based on positron annihilation spectroscopy (PAS) measurements [236, 237]. Furthermore, Paper VIII studied the formation of the E_2^* center in $\beta\text{-Ga}_2\text{O}_3$ samples implanted with H and/or He, followed by heat treatments under an applied reverse-bias voltage. Based on the results, divacancies were proposed as a potential candidate for the defect origin of E_2^* . On the theoretical side, hybrid functional calculations on divacancies are scarcely available in the literature [145, 238]. This provided motivation for Papers III and IX, where the divacancies in ZnO and $\beta\text{-Ga}_2\text{O}_3$ were investigated using hybrid functional calculations. The results are summarized in the following subsections. In both materials, the divacancies were found to be highly electrically active, retaining the polaronic nature of the cation vacancy and the Negative- U behavior of the O vacancy. The thermodynamic charge-state transition levels associated with the Negative- U behavior occur at Fermi level positions close to the CBM. This indicates that the divacancies can be observed by DLTS, which will be emphasized here when comparing the results with experimental data.

5.3.1 Isolated O vacancies

Figure 5.12 shows the formation energy of V_{O} in ZnO and the three different configurations of V_{O} in $\beta\text{-Ga}_2\text{O}_3$ (V_{O1} , V_{O2} and V_{O3}). In both materials, V_{O} acts as a deep double donor, and the thermodynamic charge-state transition goes directly from $2+$ to 0 , i.e., the $1+$ charge state is not stable for any Fermi level position [81]. This behavior is referred to as negative- U , where U is the effective correlation energy, which, in the case of V_{O} , is given by [10, 239]

$$U(V_{\text{O}}) = \varepsilon(+/0) - \varepsilon(2+/+) = E^{\text{f}}(V_{\text{O}}^{2+}) + E^{\text{f}}(V_{\text{O}}^0) - 2E^{\text{f}}(V_{\text{O}}^{+}). \quad (5.1)$$

The calculated U value is -0.49 eV for V_{O} in ZnO, and -0.45 , -0.58 and -0.63 eV for V_{O1} , V_{O2} and V_{O3} in $\beta\text{-Ga}_2\text{O}_3$, respectively. For all defects considered in the two preceding sections, a positive- U behavior was found for all charge-state transitions. This is normally the case, as the filling of deep defect states leads to strong repulsive electrostatic interactions between the electrons [3]. It is the lattice relaxation upon changing the charge state that makes negative- U behavior possible [239]. The charge-neutral V_{O} induces a fully occupied KS defect state inside the band gap, and the Negative- U behavior indeed occurs due to the large difference in local lattice relaxation for the three possible occupations of this defect state, as shown for V_{O2} in $\beta\text{-Ga}_2\text{O}_3$ in Fig. 5.13. When the defect state is fully occupied, V_{O} undergoes an inward relaxation, and the electrons are shared between the cations associated with the vacancy. For V_{O2}^0 , shown in Fig. 5.13, the electrons are mainly shared between the two Ga1 atoms, which form a Ga1–Ga1 dimer. Conversely, when the defect state is empty (i.e., for V_{O2}^{2+}), the Ga atoms undergo a large relaxation away from the vacancy.

Figure 5.12: Formation energy diagram for V_O in ZnO and the three different V_O configurations in β -Ga₂O₃ under O-rich and Zn/Ga-rich conditions.

Figure 5.13: Relaxed structures for V_{O2} in β -Ga₂O₃. The negative- U behavior is a result of the strong lattice relaxation associated with electron pairing at the O vacancy, i.e., when going from the 2+ to the 0 charge state. The O vacancies are highlighted by translucent circles with dashed outlines.

5.3.2 Ga/Zn–O divacancies

When a Zn–O divacancy ($V_{Zn}V_O$) is formed in ZnO, it can potentially occur in two symmetrically inequivalent configurations, namely the axial (aligned along the c axis) or azimuthal (lying in the basal plane) configuration. Only the lowest energy azimuthal configuration was presented in Paper III, as the electronic properties of the two configurations were found to be very similar. For $V_{Ga}V_O$ in β -Ga₂O₃, however, a multitude of different configurations can occur, as there are five V_{Ga} and three V_O configurations. Considering only close-

5. Summary of Results

associate vacancy pairs, 19 different $V_{\text{Ga}}V_{\text{O}}$ were explored in Paper IX. Figure 5.14 shows the formation energy of $V_{\text{Zn}}V_{\text{O}}$ in ZnO and a selection of the lowest energy $V_{\text{Ga}}V_{\text{O}}$ configurations in $\beta\text{-Ga}_2\text{O}_3$, respectively. Having already seen that shallow donor impurities passivate the acceptor levels of cation vacancies (Sec. 5.1.4), one might expect V_{O} to passivate two acceptor levels, resulting in a charge-neutral $V_{\text{Zn}}V_{\text{O}}$ in ZnO and singly negatively charged $V_{\text{Ga}}V_{\text{O}}$ in $\beta\text{-Ga}_2\text{O}_3$ under n -type conditions. However, V_{O} is a deep rather than a shallow donor, and, in both materials, the hybrid functional calculations show that V_{O} in the divacancy can still accommodate two electrons in a deep defect state. The resulting thermodynamic charge-state transition levels retain the negative- U behavior of V_{O} (i.e., the $(0/2-)$ level of $V_{\text{Zn}}V_{\text{O}}$ in ZnO and $(-/3-)$ levels of $V_{\text{Ga}}V_{\text{O}}$ in $\beta\text{-Ga}_2\text{O}_3$), but occur closer to the CBM relative to the negative- U level of the corresponding isolated V_{O} . Furthermore, the magnitude of the U value for the divacancies is lowered relative to the value of the corresponding isolated V_{O} , e.g., from -0.49 to -0.40 eV for $V_{\text{Zn}}V_{\text{O}}$ in ZnO.

Figure 5.14: Formation energy diagrams for the azimuthal configuration of $V_{\text{Zn}}V_{\text{O}}$ in ZnO and a selection of the lowest energy $V_{\text{Ga}}V_{\text{O}}$ configurations in $\beta\text{-Ga}_2\text{O}_3$ under O-rich conditions. The vertical grey bars highlight the $(-/3-)$ transition levels of divacancies exhibiting Ga1-Ga1 and Ga1-Ga2 dimers in $\beta\text{-Ga}_2\text{O}_3$. Under O-poor conditions, the formation energy of $V_{\text{Ga}}V_{\text{O}}$ in $\beta\text{-Ga}_2\text{O}_3$ increases by 1.71 eV. $V_{\text{Zn}}V_{\text{O}}$ maintains the stoichiometry of ZnO, which means the formation energy is independent of the host chemical potential.

In $\beta\text{-Ga}_2\text{O}_3$, the Fermi level positions of the thermodynamic $(-/3-)$ transition levels divide the divacancies into three groups, as highlighted in Fig. 5.14. On closer inspection, the common feature for the divacancies in each group is that they form the same type of Ga-Ga dimer in the $3-$ charge state and exhibit no

such level. The divacancies with a Ga1–Ga1 or Ga1–Ga2 dimer exhibit $(-/3-)$ levels at about 1.4 or 0.5 eV below the CBM, whereas those with a Ga2–Ga2 dimer can not be stabilized in the $3-$ charge state. The defect states involving Ga1 tend to be deeper, which is likely due to the lower coordination number of the Ga1 site compared to the Ga2 site. This is also consistent with the results for the isolated V_O , where the deepest V_{O2} configuration has two Ga1 atoms (as shown in Fig. 5.13), while the shallower V_{O1} and V_{O3} configurations have one Ga1 atom. In ZnO, however, there is little difference between the local environment of the axial and azimuthal Zn ions associated with the V_O , and the electrons occupying the defect state are shared more equally between the Zn ions.

5.3.3 Complexes with hydrogen

As shown in Sec. 5.1.4, H can form complexes with cation vacancy acceptors by terminating O dangling bonds at the vacancy. However, H can also form complexes with O vacancies in ZnO and β -Ga₂O₃. In this case, the H resides at the vacant O site and exhibits anionic (acceptor) character, and bonds to the surrounding cations [58]. Fig. 5.15 shows the formation energy of H_O complexes in ZnO and β -Ga₂O₃. In ZnO, previously reported theoretical and experimental studies have shown that the H_O complex acts as a single shallow donor [58, 59]. In β -Ga₂O₃, all three configurations of the complex (H_{O1} , H_{O2} and H_{O3}) were similarly predicted to act as shallow donors based on hybrid functional calculations [131]. However, Paper X revealed a DX -like [240] behavior for the H_{O2} complex, where two electrons can be trapped in a deep state under n -type conditions, as shown in Fig. 5.15. The resulting negative charge state of H_{O2} was likely missed previously because a large lattice relaxation is required to stabilize it, as shown in Fig. 5.16. When going from H_{O2}^+ to H_{O2}^- , the H moves off-site, forming a bond with the Ga2 ion associated with V_{O2} , allowing two electrons to be captured in a deep state involving a Ga1–Ga1 dimer (similar to V_{O2}^0 in Fig. 5.13) and the Ga2–H bond. Notably, the transition exhibits negative- U behavior, i.e., charge-neutral H_{O2} is not stable for any Fermi level position.

Papers III and IX explored the interaction between divacancies and H. Seeing as both the cation and O vacancy presents a potential trapping site for H, several different configurations were explored. Fig. 5.15 shows the formation energy of the lowest energy hydrogenated divacancy configurations in ZnO and β -Ga₂O₃. When H occupies V_O , the deep donor state (and the negative- U level of the divacancy) is lost. However, when H forms an O–H bond at the cation vacancy, it acts as a shallow donor, passivating one of the cation vacancy acceptor states, and the negative- U behavior of the divacancy persists. For $V_{Zn}V_O$ in ZnO, the first two H atoms prefer to form an O–H bond at V_{Zn} , and, under n -type conditions, a third H can be trapped in the H_O configuration. For $V_{Ga}V_O$ in β -Ga₂O₃, the energy differences between different H configurations depend on the divacancy orientation. However, for the first H, the O–H configuration is lowest in energy for all divacancy configurations. For certain divacancy configurations, the second H prefers the H_O configuration under n -type conditions, but the

5. Summary of Results

Figure 5.15: Formation energy of H_O and the lowest energy hydrogenated divacancy configurations in ZnO and β -Ga₂O₃ under Zn/Ga-rich conditions.

Figure 5.16: Relaxed structures of $H_{O_2}^q$ for $q = -$ and $+$ in β -Ga₂O₃. In the negative charge-state, the H forms a bond with the Ga2 atom associated with the O vacancy, and two electrons are trapped in a deep defect state (blue isosurface).

O-H configuration becomes preferred for all configurations when the Fermi level position is lowered. For example, the lowest energy doubly hydrogenated divacancy under n -type conditions is $V_{Ga}^{ib}H-H_O$, but when the Fermi level is lowered the $V_{Ga}^{ib}2H-V_O$ configuration becomes more favorable (Fig. 5.15).

5.3.4 Comparison with experimental DLTS data

The formation energy diagrams (Figs. 5.14 and 5.15) show that divacancies exhibit thermodynamic charge-state transition levels in the band gap that are close to the CBM, which indicates that they should be measurable by DLTS. However, the corresponding transition levels exhibit negative- U behavior, which

must be considered when comparing with experimental DLTS data. During conventional DLTS measurements, the activation energy obtained for a negative- U center will correspond to the thermal emission of the first electron [13, 241]. The second electron is bound less strongly, and will be emitted immediately after the first electron. Thus, two electrons will be emitted, and a single DLTS peak will be observed. However, in some cases it is possible to use DLTS to measure the activation energy associated with one-electron emission from a negative- U center. If a sufficiently short filling pulse duration is employed, and all centers are photoionized before each pulse, most centers will be unable to capture more than one electron, allowing the DLTS peak associated with one-electron to be observed at a lower temperature than for the two-electron emission. This method was used to reveal the negative- U system of the C vacancy in 4H-SiC [65, 241]. In Papers III, IX and X, divacancy-related defects were discussed as potential origins of three different DLTS centers reported in the literature, namely the E_4 center in ZnO and the E_2^* and E_1 centers in β -Ga₂O₃. The measured activation energies for these centers, and results from hybrid functional calculations for their proposed origins are summarized in Table 5.2. A brief discussion on the DLTS centers and suggested defect candidates is given below.

Table 5.2: Measured activation energies E_A (from Papers X, VIII and previous reports [92, 93, 138, 145, 151, 155]) for E_4 in ZnO, and E_2^* and E_1 in β -Ga₂O₃, proposed origin (defect and charge-state transition level), theoretically predicted ionization energy E_i , and capture barrier E_b obtained from the 1D CC diagram.

DLTS center	E_A (eV)	Proposed origin	E_i (E_b) (eV)
E_4 (two-electron)	0.55 [92]	$(V_{\text{Zn}}V_{\text{O}})^{-/2-}$	0.42 (0.10)
E_4 (one-electron)	0.14 [93]	$(V_{\text{Zn}}V_{\text{O}})^{0/-}$	0.02 (0.20)
E_2^*	0.71 [VII]	$(V_{\text{Ga}_2}V_{\text{O}_1})^{2-/3-}$	0.63 (0.16)
		$(V_{\text{Ga}}^{\text{ib}}2\text{H}-V_{\text{O}_1})^{0/-}$	0.70 (0.08)
	0.75 [145]	-	-
E_1	0.50-0.63 [X]	$\text{H}_{\text{O}_2}^{0/-}$	0.68 (0.10)
		$(V_{\text{Ga}}^{\text{ib}}\text{H}-V_{\text{O}_1})^{-/2-}$	0.52 (0.19)
	0.56 [138, 145]	-	-
	0.55 [151]	-	-
	0.6 [155]	-	-

The E_4 center in ZnO exhibits an activation energy of about 0.55 eV [92, 242], and shows negative- U behavior [93, 243, 244], where an activation energy of about 0.14 eV has been reported for the one-electron emission [93, 243]. The E_4 center is not usually present in as-grown material, but can be introduced by high-energy electron irradiation [93], H^+/He^+ irradiation or implantation [242, 245–247], or high-temperature annealing [79, 93, 243]. For the latter, the E_4

5. Summary of Results

concentration tends to be higher for Zn-rich annealing ambients. As such, E_4 is commonly assigned to a V_O -related defect. However, an isolated V_O origin for E_4 is difficult to reconcile with the photo-EPR experiments by Evans *et al.* [44] and Wang *et al.* [84], where the absorption spectrum related to the optically induced EPR signal of V_O^+ (due to photoionization of V_O^0) was measured to peak at ~ 2.6 eV, with an onset at ~ 2.1 eV. This suggests that the thermodynamic (+/0) transition level is significantly deeper than the ~ 0.55 eV activation energy measured for E_4 , unless the Franck–Condon shift is extremely large. Furthermore, first-principles defect calculations predict deeper thermodynamic (+/0) transition levels [42, 43, 81], and the CC diagram derived from hybrid functional calculations by Lyons *et al.* [43] are in good agreement with the photo-EPR data [44, 84].

In Paper III, $V_{Zn}V_O$ was proposed as an alternative defect model, as it fulfils many of the experimental findings on E_4 : (i) The thermodynamic ($-/2-$) and ($0/-$) transition levels of $V_{Zn}V_O$ are predicted to occur at 0.42 (0.52) and 0.02 (0.24) eV below the CBM, respectively, where the numbers in parenthesis include the capture barrier obtained from the 1D CC model (Fig. 3 in Paper III). These energies are close to the measured activation energies for two- and one-electron emission from E_4 . (ii) Hupfer *et al.* [247] obtained an experimental capture barrier of about 0.15 eV for E_4 , which is close to the 0.22 eV barrier obtained from the CC diagram of $V_{Zn}V_O$. (iii) Based on the low generation rate for E_4 after proton irradiation, Auret *et al.* [242] suggested a high-order intrinsic defect (such as the divacancy) rather than a primary intrinsic defect origin. (iv) After proton implantation at room temperature, Hupfer *et al.* reported that the E_4 center anneals out at a rate that fits well with a model invoking migration of H_i and reaction with E_4 . $V_{Zn}V_O$ can form stable complexes with H. An argument against the divacancy model would be that the concentration of E_4 produced by high-temperature anneals tends to be higher for Zn-rich ambients.

The E_2^* center in β -Ga₂O₃ exhibits an activation energy of about 0.75 eV [145], and has been observed in β -Ga₂O₃ layers grown by plasma-assisted molecular beam epitaxy [130, 248]. The center can be generated by proton irradiation with a close to linear dose dependence after subsequent heat treatments at around 650 K, suggesting an activated intrinsic-related defect origin [138, 145]. In Paper VIII, it was shown that the introduction of E_2^* in samples subjected to H and/or He implantation, is promoted when performing a subsequent annealing at 650 K under an applied reverse-bias voltage (reverse-bias annealing). Conversely, heat treatments without an applied reverse-bias voltage (zero-bias annealing) leads to a decrease in the E_2^* concentration, which is more pronounced for H implantation. Moreover, simulations of the DLTS spectra suggested that the E_2^* signature consists of several overlapping peaks. Based on these experimental results, it was proposed that the most likely origin of E_2^* is a defect complex involving intrinsic defects, which can interact with H donors, and exist in several different configurations, where the configuration giving rise to E_2^* is more likely to form when the Fermi level is shifted away from the conduction band minimum (CBM). Based on previously reported theoretical calculations on intrinsic defects [145], divacancy complexes were put forward as a potential origin for E_2^* .

Paper IX discussed the divacancy model as a potential origin of the E_2^*

center in β -Ga₂O₃. The divancies with Ga1–Ga2 dimers in Fig. 5.14 exhibit thermodynamic charge-state transitions that are close to the measured activation energy for E_2^* . For example, the $V_{\text{Ga}2}V_{\text{O}1}$ configuration exhibits a thermodynamic (2–/3–) transition level at 0.63 eV below the CBM, which increases to 0.79 eV when the capture barrier is included. For this model, the formation and removal of E_2^* under reverse- and zero-bias annealing can be explained by considering the Fermi level dependence of the kinetics of transformation between different divacancy configurations, as explored by nudged elastic band calculations (not shown here). The removal of E_2^* by zero-bias annealing is strongly promoted in the presence of H. This suggests that E_2^* is passivated by H under n -type conditions, and that the resulting complex becomes unstable under reverse-bias conditions, resulting in reorientation of the hydrogenated center, and reappearance of E_2^* . As shown in Fig. 5.15, the most energetically favorable configuration of the doubly hydrogenated divacancy is $V_{\text{Ga}}^{\text{ib}}\text{H-H}_{\text{O}1}$, for which the deep negative- U transition level is passivated. However, under reverse-bias annealing conditions, the closely related $V_{\text{Ga}}^{\text{ib}}2\text{H-V}_{\text{O}1}$ configuration is lower in formation energy, and exhibits an E_2^* compatible thermodynamic (0/–) transition level at 0.70 eV below the CBM (0.78 eV with the capture barrier).

Finally, the E_1 center in β -Ga₂O₃ exhibits an activation energy of about 0.6 eV, and has been observed in as-received EFG- and CZ-grown bulk crystals [138, 145, 151]. Polyakov *et al.* [155] observed an increase in the E_1 concentration after subjecting EFG-grown crystals with a surface orientation of (010) to a H-plasma. In Paper X, the concentration of E_1 in EFG- and HVPE-grown samples was observed to increase after heat treatments at 900 °C in closed ampoules filled with approximately 0.5 bar of H₂ gas. The introduction of H was confirmed by a linear correlation between the annealing duration and the integrated absorbance of the 3437 cm^{–1} line (associated with $V_{\text{Ga}}^{\text{ib}}2\text{H}$ [144]) as measured by FTIR. This suggests a H-related defect origin for E_1 , and hybrid functional calculations were performed to explore potential candidates. The $V_{\text{Ga}}^{\text{ib}}\text{H-V}_{\text{O}1}$ and $\text{H}_{\text{O}2}$ complexes in Fig. 5.15 exhibit thermodynamic charge-state transition levels close to the 0.6 eV activation energy measured for the E_1 center. Specifically, the thermodynamic $\varepsilon(-/2-)$ level of $V_{\text{Ga}}^{\text{ib}}\text{H-V}_{\text{O}1}$ occurs at 0.52 eV (0.71 eV) below the CBM, and the (0/–) level of $\text{H}_{\text{O}2}$ is located 0.68 eV (0.78 eV) below the CBM, where the numbers in parenthesis include the capture barrier from their CC diagrams.

Chapter 6

Conclusions and outlook

The aim of this PhD project was to investigate defects in the metal oxide semiconductors ZnO and β -Ga₂O₃ by performing first-principles defect calculations based on DFT. Hybrid functionals were employed to overcome the major limitations of the conventional XC functionals for describing defects in this materials system, namely the general underestimation of band gaps and delocalization error. Furthermore, recent methodological advances, particularly based on 1D CC diagrams derived from the hybrid functional calculations, were employed to provide more direct comparisons between theoretically predicted defect properties and experimental data from defect spectroscopic techniques. Here, the main focus was on properties related to charge-state transitions involving defects, including defect luminescence, optical absorption and nonradiative capture and emission of charge carriers. Thermodynamic quantities such as defect formation energies and binding energies were also calculated in order to assess the likelihood of defect incorporation and the relative stability of defects and complexes. The defects investigated in this thesis can be divided into three groups, where the main results for each group is briefly summarized below.

(i) *Small hole polarons and polaronic acceptors:* This includes the cation vacancies (V_{Zn} and V_{Ga}), cation substitutional acceptor impurities (Li_{Zn} and Na_{Zn} , Be_{Ga} , Mg_{Ga} , Ca_{Ga} , Zn_{Ga} and Cd_{Ga}), and their complexes with shallow donor impurities (H_i , H_O , Al_{Zn} , Ga_{Zn} , Si_{Ga}). Here, the main results involved the prediction of defect luminescence lines resulting from optical transitions of charge carriers between the band edges and polaronic defect states. The STHs in β -Ga₂O₃ and the Li_{Zn} and Na_{Zn} acceptors in ZnO have previously been attributed to experimentally observed luminescence bands, respectively, and were thus used to benchmark the accuracy of the calculated luminescence lines. Generally, the results were found to be consistent with experimental data. The same approach was applied to explore possible defect origins of yet unidentified luminescence bands observed in ZnO and β -Ga₂O₃. Isolated cation vacancies were found to most likely act as nonradiative recombination centers under *n*-type conditions. However, complexing of polaronic acceptors with shallow donor impurities (commonly present in both materials) was found to shift the luminescence to higher energies compared to the corresponding isolated polaronic acceptor. This is because the shallow donors successively remove the polaronic acceptor charge-state transition levels in the band gap, starting from the most negative one. The relative positions of the charge-state transition levels of the isolated and donor-complexed polaronic acceptors was interpreted from a polaron energetics model. The results highlight the importance of donor complexed polaronic defects, which should be considered when interpreting experimental data. Specifically, the $V_{\text{Zn}}2\text{H}$ complex was proposed as a potential

candidate for the defect origin of the high-energy electron irradiation induced RL band observed in ZnO, while donor complexed Li_{Zn} and Na_{Zn} acceptors were suggested as candidates for the GL observed in HT ZnO.

(ii) *Ti and Fe impurities in gallium sesquioxide*: Motivated by experimental DLTS and SIMS results pointing to a Fe and Ti impurity origin for the $E_{2a/2b}$ and E_3 centers, respectively, hybrid functional calculations were performed to explore Fe- and Ti-related defects in $\beta\text{-Ga}_2\text{O}_3$. Under n -type conditions, the Ga substitutional configurations were found to be the lowest energy configurations for Fe and Ti impurities. Both Fe_{Ga} and Ti_{Ga} were found to exhibit thermodynamic charge-state transition levels in the band gap close to the CBM. 1D CC diagrams were obtained to compare these levels with the measured activation energies of the E_{2a} , E_{2b} and E_3 centers, and the estimated activation energies for $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$ were found to be in excellent agreement with the experimental data. Moreover, the difference in formation energy between Ga1 and Ga2 substitutional Fe and Ti was consistent with the observed 1:5 ratio for the trap concentrations of E_{2a} and E_{2b} , as well as the E_3 signature being related to a single trap. Thus, the hybrid functional calculations lend support to the assignment, and suggest specific defect origins for the E_{2a} ($\text{Fe}_{\text{Ga}1}$), E_{2b} ($\text{Fe}_{\text{Ga}2}$) and E_3 ($\text{Ti}_{\text{Ga}2}$) centers. Photoionization of the same defects was explored by performing SSPC measurements on EFG $\beta\text{-Ga}_2\text{O}_3$ samples with known Fe and Ti content based on DLTS and SIMS data. The SSPC spectrum resulting from photoionization of $\text{Fe}_{\text{Ga}1}^-$, $\text{Fe}_{\text{Ga}2}^-$ and $\text{Ti}_{\text{Ga}2}^0$ was simulated based on input from hybrid functional calculations (CC diagrams) and the experimental conditions (trap concentrations from DLTS and recorded photon flux). The SSPC signature T_1^{EFG} was attributed to overlapping defect signatures related to $\text{Fe}_{\text{Ga}1}$, $\text{Fe}_{\text{Ga}2}$ and $\text{Ti}_{\text{Ga}2}$ based in comparison between measured and simulated SSPC spectra

(iii) *Negative- U behavior of O vacancies and divacancies*: Close-associate divacancies in ZnO ($V_{\text{Zn}}V_{\text{O}}$) and $\beta\text{-Ga}_2\text{O}_3$ ($V_{\text{Ga}}V_{\text{O}}$) were explored using hybrid functional calculations. In both materials, the divacancy was predicted to retain the polaronic nature of the cation vacancy and the negative- U behavior of V_{O} . The latter result was of particular interest, as it shows that the isolated V_{O} is not the only intrinsic defect exhibiting negative- U behavior in ZnO and $\beta\text{-Ga}_2\text{O}_3$. For $V_{\text{Ga}}V_{\text{O}}$ in $\beta\text{-Ga}_2\text{O}_3$, 19 symmetrically inequivalent divacancy configurations were explored, and trends in their electronic properties and stability were revealed. In both materials, the thermodynamic charge-state transition levels associated with the negative- U behavior of certain isolated and hydrogenated divacancy configurations were predicted to occur in the band gap close to the CBM, which means they should be observable by DLTS. Based on comparison with experimental data, divacancy-related defect origins were proposed for the DLTS centers E_4 ($V_{\text{Zn}}V_{\text{O}}$) in ZnO, E_2^* ($V_{\text{Ga}2}V_{\text{O}1}$ and $V_{\text{Ga}}^{\text{ib}}2\text{H}-V_{\text{O}1}$) in $\beta\text{-Ga}_2\text{O}_3$, and E_1 ($V_{\text{Ga}}^{\text{ib}}\text{H}-V_{\text{O}1}$) in $\beta\text{-Ga}_2\text{O}_3$. For the E_1 center, the $\text{H}_{\text{O}2}$ complex was also proposed as a candidate, because this defect was found to exhibit a DX -center-like behavior.

Overall, the results presented here show that hybrid functionals are capable of providing a significantly improved description of defect properties such as the degree of charge localization and thermodynamic or optical charge-state

transition energies, relative to conventional DFT. The comparison between first-principles calculations and experimental data has proven to be a fruitful approach in the study of defects in oxide semiconductors [4].

Suggestions for further work

- The approach of combining of hybrid functional calculations and experimental techniques (e.g., DLTS, SSPC, PL) can be applied to study other defects. For example, hybrid functional calculations suggest that $\text{Fe}_{\text{Ga}}\text{H}$ complexes can form in $\beta\text{-Ga}_2\text{O}_3$ [132], which would passivate the $E_{2a/2b}$ centers. Investigating such complexes, e.g., by performing DLTS and FTIR measurements on different samples with known Fe and H content, could provide further evidence that $E_{2a/2b}$ is indeed related to Fe_{Ga} , and improve the understanding of the behavior of Fe impurities in $\beta\text{-Ga}_2\text{O}_3$.
- New methodological developments within the approach of using 1D CC diagrams derived from hybrid functional calculations can be employed. In particular, methodologies for the calculation of nonradiative carrier capture coefficients and radiative capture rates at defects have been developed [12, 14]. Indeed, Wickramaratne *et al.* [13] have recently shown that the former method can be leveraged to calculate the temperature dependence of the activation energy for carrier emission from a defect, allowing an even more detailed comparison with DLTS data.
- Hybrid functionals lack long-range electron correlation, e.g., van der Waals interactions, which could potentially have an impact on defect properties, especially in layered materials. For example, Gao *et al.* [249] reported that the inclusion of screened van der Waals interactions in the HSE functional significantly improved the description of defect migration barriers in Si. Another method to capture such interactions is the random-phase approximation (RPA) [3]. The application of RPA to study defects has been hindered by high computational cost, but might be explored more in the coming years; VASP. 6 features a low-scaling RPA functional.

References

- [1] Kittel, C., *Introduction to solid state physics*, 8th ed. (Wiley, 2004).
- [2] Bassett, L. C., Alkauskas, A., Exarhos, A. L., and Fu, K.-M. C., *Nanophotonics* vol. 8, no. 11, 1867 (2019).
- [3] Freysoldt, C., Grabowski, B., Hickel, T., Neugebauer, J., Kresse, G., Janotti, A., and Van de Walle, C. G., *Rev. Mod. Phys.* vol. 86, 253 (2014).
- [4] Alkauskas, A., McCluskey, M. D., and Van de Walle, C. G., *J. Appl. Phys.* vol. 119, no. 18, 181101 (2016).
- [5] Oba, F., Togo, A., Tanaka, I., Paier, J., and Kresse, G., *Phys. Rev. B* vol. 77, 245202 (2008).
- [6] Deák, P., Aradi, B., Frauenheim, T., Janzén, E., and Gali, A., *Phys. Rev. B* vol. 81, 153203 (2010).
- [7] Alkauskas, A., Broqvist, P., and Pasquarello, A., *Phys. Status Solidi B* vol. 248, no. 4, 775 (2011).
- [8] Komsa, H.-P. and Pasquarello, A., *Phys. Rev. B* vol. 84, 075207 (2011).
- [9] Chen, W. and Pasquarello, A., *Phys. Rev. B* vol. 96, 020101 (2017).
- [10] Stoneham, A. M. and Sangster, M. J. L., *Radiat. Eff.* vol. 73, no. 1-4, 267 (1983).
- [11] Alkauskas, A., Lyons, J. L., Steiauf, D., and Van de Walle, C. G., *Phys. Rev. Lett.* vol. 109, 267401 (2012).
- [12] Alkauskas, A., Yan, Q., and Van de Walle, C. G., *Phys. Rev. B* vol. 90, 075202 (2014).
- [13] Wickramaratne, D., Dreyer, C. E., Monserrat, B., Shen, J.-X., Lyons, J. L., Alkauskas, A., and Van de Walle, C. G., *Appl. Phys. Lett.* vol. 113, no. 19, 192106 (2018).
- [14] Dreyer, C. E., Alkauskas, A., Lyons, J. L., and Van de Walle, C. G., *Phys. Rev. B* vol. 102, 085305 (2020).
- [15] Bunn, C. W., *Proc. Phys. Soc.* vol. 47, no. 5, 835 (1935).
- [16] Özgür, Ü., Alivov, Y. I., Liu, C., Teke, A., Reshchikov, M. A., Doğan, S., Avrutin, V., Cho, S.-J., and Morkoç, H., *J. Appl. Phys.* vol. 98, no. 4, 041301 (2005).
- [17] Roy, R., Hill, V. G., and Osborn, E. F., *Journal of the American Chemical Society* vol. 74, no. 3, 719 (1952).
- [18] Tippins, H. H., *Phys. Rev.* vol. 140, A316 (1965).

References

- [19] Blasse, G. and Bril, A., *J. Phys. Chem. Solids* vol. 31, no. 4, 707 (1970).
- [20] Albertsson, J., Abrahams, S. C., and Kvik, Å., *Acta Crystallogr. Sect. B* vol. 45, no. 1, 34 (1989).
- [21] Morkoç, H. and Özgür, U., *Zinc oxide : fundamentals, materials and device technology* (Wiley-VCH, Weinheim, 2009).
- [22] Momma, K. and Izumi, F., *Journal of Applied Crystallography* vol. 44, no. 6, 1272 (2011).
- [23] Reynolds, D. C., Look, D. C., Jogai, B., Litton, C. W., Cantwell, G., and Harsch, W. C., *Phys. Rev. B* vol. 60, 2340 (1999).
- [24] Oba, F., Choi, M., Togo, A., and Tanaka, I., *Sci. Technol. Adv. Mater.* vol. 12, no. 3, 034302 (2011).
- [25] Ashkenov, N., Mbenkum, B. N., Bundesmann, C., Riede, V., Lorenz, M., Spemann, D., Kaidashev, E. M., Kasic, A., Schubert, M., Grundmann, M., Wagner, G., Neumann, H., Darakchieva, V., Arwin, H., and Monemar, B., *J. Appl. Phys.* vol. 93, no. 1, 126 (2003).
- [26] Vines, L. and Kuznetsov, A., in *Oxide semiconductors*, Vol. 88, edited by Svensson, B. G., Pearton, S. J., and Jagadish, C., *Semiconductors and Semimetals* (Elsevier, 2013), pp. 67–104.
- [27] Minami, T., Sato, H., Nanto, H., and Takata, S., *Jpn. J. Appl. Phys* vol. 24, no. Part 2, No. 10, L781 (1985).
- [28] Gabás, M., Landa-Cánovas, A., Luis Costa-Krämer, J., Agulló-Rueda, F., González-Elipe, A. R., Díaz-Carrasco, P., Hernández-Moro, J., Lorite, I., Herrero, P., Castellero, P., Barranco, A., and Ramón Ramos-Barrado, J., *J. Appl. Phys.* vol. 113, no. 16, 163709 (2013).
- [29] Goyal, A. and Stevanović, V., *Phys. Rev. Mater.* vol. 2, 084603 (2018).
- [30] Lany, S. and Zunger, A., *Appl. Phys. Lett.* vol. 96, no. 14, 142114 (2010).
- [31] Demchenko, D. O., Diallo, I. C., and Reshchikov, M. A., *Phys. Rev. B* vol. 97, 205205 (2018).
- [32] Borysiewicz, M. A., *Crystals* vol. 9, no. 10 (2019).
- [33] Yamamoto, N., Makino, H., Osone, S., Ujihara, A., Ito, T., Hokari, H., Maruyama, T., and Yamamoto, T., *Thin Solid Films* vol. 520, no. 12, 8th International Conference on Coatings on Glass and Plastics” ICCG8, 4131 (2012).
- [34] Meyer, J., Görrn, P., Hamwi, S., Johannes, H.-H., Riedl, T., and Kowalsky, W., *Appl. Phys. Lett.* vol. 93, no. 7, 073308 (2008).
- [35] Jackson, P., Hariskos, D., Wuerz, R., Kiowski, O., Bauer, A., Friedlmeier, T. M., and Powalla, M., *Phys. Status Solidi RRL* vol. 9, no. 1, 28 (2015).
- [36] Crovetto, A., Ottsen, T. S., Stamate, E., Kjær, D., Schou, J., and Hansen, O., *J. Phys. D: Appl. Phys* vol. 49, no. 29, 295101 (2016).

-
- [37] Look, D. C., Leedy, K. D., Vines, L., Svensson, B. G., Zubiaga, A., Tuomisto, F., Douth, D. R., and Brillson, L. J., *Phys. Rev. B* vol. 84, 115202 (2011).
 - [38] Tuomisto, F., Ranki, V., Saarinen, K., and Look, D. C., *Phys. Rev. Lett.* vol. 91, 205502 (2003).
 - [39] Stehr, J. E., Johansen, K. M., Bjørheim, T. S., Vines, L., Svensson, B. G., Chen, W. M., and Buyanova, I. A., *Phys. Rev. Appl.* vol. 2, 021001 (2014).
 - [40] Stehr, J. E., Chen, W. M., Svensson, B. G., and Buyanova, I. A., *J. Appl. Phys.* vol. 119, no. 10, 105702 (2016).
 - [41] Nause, J and Nemeth, B, *Semicond. Sci. Technol* vol. 20, no. 4, S45 (2005).
 - [42] Janotti, A. and Van de Walle, C. G., *Rep. Prog. Phys.* vol. 72, no. 12, 126501 (2009).
 - [43] Lyons, J. L., Varley, J. B., Steiauf, D., Janotti, A., and Van de Walle, C. G., *J. Appl. Phys.* vol. 122, no. 3, 035704 (2017).
 - [44] Evans, S. M., Giles, N. C., Halliburton, L. E., and Kappers, L. A., *J. Appl. Phys.* vol. 103, no. 4, 043710 (2008).
 - [45] Herklotz, F., Lavrov, E. V., Weber, J., Mamin, G. V., Kutin, Y. S., Volodin, M. A., and Orlinskii, S. B., *Phys. Status Solidi B* vol. 248, no. 6, 1532 (2011).
 - [46] Schilling, M., Helbig, R., and Pensl, G., *J. Lumin.* vol. 33, no. 2, 201 (1985).
 - [47] Meyer, B. K., Alves, H., Hofmann, D. M., Kriegseis, W., Forster, D., Bertram, F., Christen, J., Hoffmann, A., Straßburg, M., Dworzak, M., Haboeck, U., and Rodina, A. V., *Phys. Status Solidi B* vol. 241, no. 2, 231 (2004).
 - [48] Block, D., Hervé, A., and Cox, R. T., *Phys. Rev. B* vol. 25, 6049 (1982).
 - [49] Gonzalez, C., Block, D., Cox, R., and Hervé, A., *J. Cryst. Growth* vol. 59, no. 1, 357 (1982).
 - [50] McCluskey, M. and Jokela, S., *Phys. B Condens. Matter* vol. 401, 355 (2007).
 - [51] Thomas, D. G. and Lander, J. J., *J. Chem. Phys.* vol. 25, no. 6, 1136 (1956).
 - [52] Van de Walle, C. G., *Phys. Rev. Lett.* vol. 85, 1012 (2000).
 - [53] Cox, S. F. J., Davis, E. A., Cottrell, S. P., King, P. J. C., Lord, J. S., Gil, J. M., Alberto, H. V., Vilão, R. C., Piroto Duarte, J., Campos, N. Ayres de, Weidinger, A., Lichti, R. L., and Irvine, S. J. C., *Phys. Rev. Lett.* vol. 86, 2601 (2001).
 - [54] Hofmann, D. M., Hofstaetter, A., Leiter, F., Zhou, H., Henecker, F., Meyer, B. K., Orlinskii, S. B., Schmidt, J., and Baranov, P. G., *Phys. Rev. Lett.* vol. 88, 045504 (2002).

References

- [55] Hupfer, A., Bhoodoo, C., Vines, L., and Svensson, B. G., *Mat. Sci. Semicon. Proc.* vol. 69, 13 (2017).
- [56] Johansen, K. M., Christensen, J. S., Monakhov, E. V., Kuznetsov, A. Y., and Svensson, B. G., *Appl. Phys. Lett.* vol. 93, no. 15, 152109 (2008).
- [57] Wardle, M. G., Goss, J. P., and Briddon, P. R., *Phys. Rev. Lett.* vol. 96, 205504 (2006).
- [58] Van de Walle, C. G. and Janotti, A., *Nat. Mater.* vol. 6, no. 1, 44 (2007).
- [59] Lavrov, E. V., Herklotz, F., and Weber, J., *Phys. Rev. B* vol. 79, 165210 (2009).
- [60] Lavrov, E. V., Weber, J., Börrnert, F., Van de Walle, C. G., and Helbig, R., *Phys. Rev. B* vol. 66, 165205 (2002).
- [61] Lavrov, E., Börrnert, F., and Weber, J., *Physica B* vol. 401-402, 366 (2007).
- [62] Bastin, D., Lavrov, E. V., and Weber, J., *Phys. Rev. B* vol. 83, 195210 (2011).
- [63] Herklotz, F., Lavrov, E. V., Kolkovsky, V., Weber, J., and Stavola, M., *Phys. Rev. B* vol. 82, 115206 (2010).
- [64] Herklotz, F., Hupfer, A., Johansen, K. M., Svensson, B. G., Koch, S. G., and Lavrov, E. V., *Phys. Rev. B* vol. 92, 155203 (2015).
- [65] Son, N. T., Isoya, J., Ivanov, I. G., Ohshima, T., and Janzén, E., *AIP Conf. Proc.* vol. 1583, no. 1, 341 (2014).
- [66] Heinhold, R., Neiman, A., Kennedy, J. V., Markwitz, A., Reeves, R. J., and Allen, M. W., *Phys. Rev. B* vol. 95, 054120 (2017).
- [67] Halliburton, L. E., Wang, L., Bai, L., Garces, N. Y., Giles, N. C., Callahan, M. J., and Wang, B., *J. Appl. Phys.* vol. 96, no. 12, 7168 (2004).
- [68] Lavrov, E. V., Börrnert, F., and Weber, J., *Phys. Rev. B* vol. 71, 035205 (2005).
- [69] Shi, G. A., Stavola, M., and Fowler, W. B., *Phys. Rev. B* vol. 73, 081201 (2006).
- [70] Shi, G. A., Saboktakin, M., Stavola, M., and Pearton, S. J., *Appl. Phys. Lett.* vol. 85, no. 23, 5601 (2004).
- [71] Johansen, K. M., Zubiaga, A., Makkonen, I., Tuomisto, F., Neuvonen, P. T., Knutsen, K. E., Monakhov, E. V., Kuznetsov, A. Y., and Svensson, B. G., *Phys. Rev. B* vol. 83, 245208 (2011).
- [72] Vines, L., Monakhov, E. V., Schifano, R., Mtangi, W., Auret, F. D., and Svensson, B. G., *J. Appl. Phys.* vol. 107, no. 10, 103707 (2010).
- [73] Carvalho, A., Alkauskas, A., Pasquarello, A., Tagantsev, A. K., and Setter, N., *Phys. Rev. B* vol. 80, 195205 (2009).

-
- [74] McCluskey, M. D., Corolewski, C. D., Lv, J., Tarun, M. C., Teklemichael, S. T., Walter, E. D., Norton, M. G., Harrison, K. W., and Ha, S., *J. Appl. Phys.* vol. 117, no. 11, 112802 (2015).
- [75] McNamara, J., Albarakati, N., and Reshchikov, M., *J. Lumin.* vol. 178, 301 (2016).
- [76] Schirmer, O., *J. Phys. Chem. Solids* vol. 29, no. 8, 1407 (1968).
- [77] Lany, S. and Zunger, A., *Phys. Rev. B* vol. 80, 085202 (2009).
- [78] Jiang, Y., Giles, N. C., and Halliburton, L. E., *J. Appl. Phys.* vol. 101, no. 9, 093706 (2007).
- [79] Quemener, V., Vines, L., Monakhov, E. V., and Svensson, B. G., *Appl. Phys. Lett.* vol. 102, no. 23, 232102 (2013).
- [80] Kutin, Y., Mamin, G., and Orlinskii, S., *J. Magn. Reson* vol. 237, 110 (2013).
- [81] Janotti, A. and Van de Walle, C. G., *Phys. Rev. B* vol. 76, 165202 (2007).
- [82] Lyons, J. L. and Van de Walle, C. G., *npj Comput. Mater.* vol. 3 (2017).
- [83] Knutsen, K. E., Galeckas, A., Zubiaga, A., Tuomisto, F., Farlow, G. C., Svensson, B. G., and Kuznetsov, A. Y., *Phys. Rev. B* vol. 86, 121203 (2012).
- [84] Wang, X., Zhang, F., Saito, K., Tanaka, T., Nishio, M., and Guo, Q., *J. Phys. Chem. Solids* vol. 75, no. 11, 1201 (2014).
- [85] Galland, D. and Herve, A., *Phys. Lett. A* vol. 33, no. 1, 1 (1970).
- [86] Kappers, L., Gilliam, O., Evans, S., Halliburton, L., and Giles, N., *Nucl. Instrum. Methods Phys. Res. B* vol. 266, no. 12, Radiat. Eff. in Insulators, 2953 (2008).
- [87] Reshchikov, M., Morkoç, H., Nemeth, B., Nause, J., Xie, J., Hertog, B., and Osinsky, A., *Physica B* vol. 401-402, 358 (2007).
- [88] Reshchikov, M. A., *AIP Conf. Proc.* vol. 1583, no. 1, 127 (2014).
- [89] Zwingel, D., *J. Lumin.* vol. 5, no. 6, 385 (1972).
- [90] Byrne, D., Herklotz, F., Henry, M. O., and McGlynn, E., *J. Phys. Condens. Matter* vol. 24, no. 21, 215802 (2012).
- [91] Lyons, J. L., Alkauskas, A., Janotti, A., and Van de Walle, C. G., *Appl. Phys. Lett.* vol. 111, no. 4, 042101 (2017).
- [92] Monakhov, E. V., Kuznetsov, A. Y., and Svensson, B. G., *J. Phys. D: Appl. Phys* vol. 42, no. 15, 153001 (2009).
- [93] Frank, T., Pensl, G., Tena-Zaera, R., Zúñiga-Pérez, J., Martínez-Tomás, C., Muñoz-Sanjosé, V., Ohshima, T., Itoh, H., Hofmann, D., Pfisterer, D., Sann, J., and Meyer, B., *Appl. Phys. A* vol. 88, no. 1, 141 (2007).
- [94] Hupfer, A., Bhoodoo, C., Vines, L., and Svensson, B. G., *Appl. Phys. Lett.* vol. 104, no. 9, 092111 (2014).

References

- [95] Cora, I., Mezzadri, F., Boschi, F., Bosi, M., Čaplovičová, M., Calestani, G., Dódony, I., Pécz, B., and Fornari, R., *CrystEngComm* vol. 19, no. 11, 1509 (2017).
- [96] Swallow, J. E. N., Vorwerk, C., Mazzolini, P., Vogt, P., Bierwagen, O., Karg, A., Eickhoff, M., Schörmann, J., Wagner, M. R., Roberts, J. W., Chalker, P. R., Smiles, M. J., Murgatroyd, P., Mohamed, S., Lebens-Higgins, Z. W., Piper, L. F. J., Jones, L. A. H., Thakur, P. K., Lee, T.-L., Varley, J. B., Furthmüller, J., Draxl, C., Veal, T. D., and Regoutz, A., *Chem. Mater.* (2020).
- [97] Geller, S., *J. Chem. Phys.* vol. 33, no. 3, 676 (1960).
- [98] Janowitz, C., Scherer, V., Mohamed, M., Krapf, A., Dwelk, H., Manzke, R., Galazka, Z., Uecker, R., Irmscher, K., Fornari, R., Michling, M., Schmeißer, D., Weber, J. R., Varley, J. B., and Van de Walle, C. G., *New J. Phys.* vol. 13, no. 8, 085014 (2011).
- [99] Peelaers, H. and Van de Walle, C. G., *Phys. Status Solidi B* vol. 252, no. 4, 828 (2015).
- [100] Peelaers, H. and Van de Walle, C. G., *Appl. Phys. Lett.* vol. 111, no. 18, 182104 (2017).
- [101] Furthmüller, J. and Bechstedt, F., *Phys. Rev. B* vol. 93, 115204 (2016).
- [102] Ratnaparkhe, A. and Lambrecht, W. R. L., *Appl. Phys. Lett.* vol. 110, no. 13, 132103 (2017).
- [103] Mock, A., Korlacki, R., Briley, C., Darakchieva, V., Monemar, B., Kumagai, Y., Goto, K., Higashiwaki, M., and Schubert, M., *Phys. Rev. B* vol. 96, 245205 (2017).
- [104] Wang, Y., Dickens, P. T., Varley, J. B., Ni, X., Lotubai, E., Sprawls, S., Liu, F., Lordi, V., Krishnamoorthy, S., Blair, S., Lynn, K. G., Scarpulla, M., and Sensale-Rodriguez, B., *Sci. Rep.* vol. 8, no. 1, 182104 (2018).
- [105] Orita, M., Ohta, H., Hirano, M., and Hosono, H., *Appl. Phys. Lett.* vol. 77, no. 25, 4166 (2000).
- [106] Shimamura, K., Villora, E. G., Ujiie, T., and Aoki, K., *Appl. Phys. Lett.* vol. 92, no. 20, 201914 (2008).
- [107] Schubert, M., Korlacki, R., Knight, S., Hofmann, T., Schöche, S., Darakchieva, V., Janzén, E., Monemar, B., Gogova, D., Thieu, Q.-T., Togashi, R., Murakami, H., Kumagai, Y., Goto, K., Kuramata, A., Yamakoshi, S., and Higashiwaki, M., *Phys. Rev. B* vol. 93, 125209 (2016).
- [108] Gake, T., Kumagai, Y., and Oba, F., *Phys. Rev. Mater.* vol. 3, 044603 (2019).
- [109] Peelaers, H., Lyons, J. L., Varley, J. B., and Van de Walle, C. G., *APL Mater.* vol. 7, no. 2, 022519 (2019).
- [110] Varley, J. B., Janotti, A., Franchini, C., and Van de Walle, C. G., *Phys. Rev. B* vol. 85, 081109 (2012).

-
- [111] Lyons, J. L., Semicond. Sci. Tech. vol. 33, no. 5, 05LT02 (2018).
 - [112] Baldini, M., Albrecht, M., Fiedler, A., Irmscher, K., Schewski, R., and Wagner, G., ECS J. Solid State Sci. Technol vol. 6, no. 2, Q3040 (2016).
 - [113] Farzana, E., Ahmadi, E., Speck, J. S., Arehart, A. R., and Ringel, S. A., J. Appl. Phys. vol. 123, no. 16, 161410 (2018).
 - [114] Lyons, J. L., Steiauf, D., Janotti, A., and Van de Walle, C. G., Phys. Rev. Appl. vol. 2, 064005 (2014).
 - [115] Saleh, M., Varley, J. B., Jesenovec, J., Bhattacharyya, A., Krishnamoorthy, S., Swain, S., and Lynn, K., Semicond. Sci. Technol vol. 35, no. 4, 04LT01 (2020).
 - [116] Varley, J. B., Perron, A., Lordi, V., Wickramaratne, D., and Lyons, J. L., Appl. Phys. Lett. vol. 116, no. 17, 172104 (2020).
 - [117] Ma, N., Tanen, N., Verma, A., Guo, Z., Luo, T., Xing, H. G., and Jena, D., Appl. Phys. Lett. vol. 109, no. 21, 212101 (2016).
 - [118] Hinuma, Y., Pizzi, G., Kumagai, Y., Oba, F., and Tanaka, I., Comput. Mater. Sci.e vol. 128, 140 (2017).
 - [119] Ganose, A. M., Jackson, A. J., and Scanlon, D. O., J. Open Source Softw. vol. 3, no. 28, 717 (2018).
 - [120] Higashiwaki, M., “Introduction”, in *Gallium oxide: materials properties, crystal growth, and devices*, edited by Higashiwaki, M. and Fujita, S. (Springer International Publishing, Cham, 2020), pp. 1–12.
 - [121] Pearton, S. J., Yang, J., Cary, P. H., Ren, F., Kim, J., Tadjer, M. J., and Mastro, M. A., Appl. Phys. Rev. vol. 5, no. 1, 011301 (2018).
 - [122] Higashiwaki, M. and Jessen, G. H., Appl. Phys. Lett. vol. 112, no. 6, 060401 (2018).
 - [123] Higashiwaki, M., Sasaki, K., Kuramata, A., Masui, T., and Yamakoshi, S., Appl. Phys. Lett. vol. 100, no. 1, 013504 (2012).
 - [124] Higashiwaki, M. and Fujita, S., eds., *Gallium oxide: materials properties, crystal growth, and devices* (Springer International Publishing, Cham, 2020).
 - [125] Konishi, K., Goto, K., Murakami, H., Kumagai, Y., Kuramata, A., Yamakoshi, S., and Higashiwaki, M., Appl. Phys. Lett. vol. 110, no. 10, 103506 (2017).
 - [126] Wong, M. H., Sasaki, K., Kuramata, A., Yamakoshi, S., and Higashiwaki, M., IEEE Electron Device Lett. vol. 37, no. 2, 212 (2016).
 - [127] Nakagomi, S., Momo, T., Takahashi, S., and Kokubun, Y., Appl. Phys. Lett. vol. 103, no. 7, 072105 (2013).
 - [128] Peelaers, H., Varley, J. B., Speck, J. S., and Van de Walle, C. G., Appl. Phys. Lett. vol. 112, no. 24, 242101 (2018).

References

- [129] Zhang, Y., Neal, A., Xia, Z., Joishi, C., Johnson, J. M., Zheng, Y., Bajaj, S., Brenner, M., Dorsey, D., Chabak, K., Jessen, G., Hwang, J., Mou, S., Heremans, J. P., and Rajan, S., Appl. Phys. Lett. vol. 112, no. 17, 173502 (2018).
- [130] McGlone, J. F., Xia, Z., Joishi, C., Lodha, S., Rajan, S., Ringel, S., and Arehart, A. R., Appl. Phys. Lett. vol. 115, no. 15, 153501 (2019).
- [131] Varley, J. B., Weber, J. R., Janotti, A., and Van de Walle, C. G., Appl. Phys. Lett. vol. 97, no. 14, 142106 (2010).
- [132] Varley, J. B., “First-principles calculations 2”, in *Gallium oxide: materials properties, crystal growth, and devices*, edited by Higashiwaki, M. and Fujita, S. (Springer International Publishing, Cham, 2020), pp. 329–348.
- [133] Son, N. T., Ho, Q. D., Goto, K., Abe, H., Ohshima, T., Monemar, B., Kumagai, Y., Frauenheim, T., and Deák, P., Appl. Phys. Lett. vol. 117, no. 3, 032101 (2020).
- [134] Kuramata, A., Koshi, K., Watanabe, S., Yamaoka, Y., Masui, T., and Yamakoshi, S., Jpn. J. Appl. Phys. vol. 55, no. 12, 1202A2 (2016).
- [135] Ingebrigtsen, M. E., Kuznetsov, A. Y., Svensson, B. G., Alfieri, G., Mihaila, A., and Vines, L., J. Appl. Phys. vol. 125, no. 18, 185706 (2019).
- [136] Ritter, J. R., Huso, J., Dickens, P. T., Varley, J. B., Lynn, K. G., and McCluskey, M. D., Appl. Phys. Lett. vol. 113, no. 5, 052101 (2018).
- [137] Ritter, J. R., Lynn, K. G., and McCluskey, M. D., J. Appl. Phys. vol. 126, no. 22, 225705 (2019).
- [138] Ingebrigtsen, M. E., Varley, J. B., Kuznetsov, A. Y., Svensson, B. G., Alfieri, G., Mihaila, A., Badstübner, U., and Vines, L., Appl. Phys. Lett. vol. 112, no. 4, 042104 (2018).
- [139] Kananen, B. E., Halliburton, L. E., Scherrer, E. M., Stevens, K. T., Foundos, G. K., Chang, K. B., and Giles, N. C., Appl. Phys. Lett. vol. 111, no. 7, 072102 (2017).
- [140] Lenyk, C. A., Gustafson, T. D., Basun, S. A., Halliburton, L. E., and Giles, N. C., Appl. Phys. Lett. vol. 116, no. 14, 142101 (2020).
- [141] Varley, J. B., Peelaers, H., Janotti, A., and Van de Walle, C. G., J. Phys. Condens. Matter vol. 23, no. 33, 334212 (2011).
- [142] Qin, Y., Stavola, M., Fowler, W. B., Weiser, P., and Pearton, S. J., ECS J. Solid State Sci. Technol. vol. 8, no. 7, Q3103 (2019).
- [143] King, P. D. C., McKenzie, I., and Veal, T. D., Appl. Phys. Lett. vol. 96, no. 6, 062110 (2010).
- [144] Weiser, P., Stavola, M., Fowler, W. B., Qin, Y., and Pearton, S., Appl. Phys. Lett. vol. 112, no. 23, 232104 (2018).
- [145] Ingebrigtsen, M. E., Kuznetsov, A. Y., Svensson, B. G., Alfieri, G., Mihaila, A., Badstübner, U., Perron, A., Vines, L., and Varley, J. B., APL Mater. vol. 7, no. 2, 022510 (2019).

-
- [146] Kyrtos, A., Matsubara, M., and Bellotti, E., Phys. Rev. B vol. 95, 245202 (2017).
 - [147] Johnson, J. M., Chen, Z., Varley, J. B., Jackson, C. M., Farzana, E., Zhang, Z., Arehart, A. R., Huang, H.-L., Genc, A., Ringel, S. A., Van de Walle, C. G., Muller, D. A., and Hwang, J., Phys. Rev. X vol. 9, 041027 (2019).
 - [148] Kananen, B. E., Halliburton, L. E., Stevens, K. T., Foundos, G. K., and Giles, N. C., Appl. Phys. Lett. vol. 110, no. 20, 202104 (2017).
 - [149] Bardeleben, H. J. von, Zhou, S., Gerstmann, U., Skachkov, D., Lambrecht, W. R. L., Ho, Q. D., and Deák, P., APL Mater. vol. 7, no. 2, 022521 (2019).
 - [150] Onuma, T., Fujioka, S., Yamaguchi, T., Higashiwaki, M., Sasaki, K., Masui, T., and Honda, T., Appl. Phys. Lett. vol. 103, no. 4, 041910 (2013).
 - [151] Irmischer, K., Galazka, Z., Pietsch, M., Uecker, R., and Fornari, R., J. Appl. Phys. vol. 110, no. 6, 063720 (2011).
 - [152] Polyakov, A. Y., Smirnov, N. B., Shchemerov, I. V., Yakimov, E. B., Pearton, S. J., Fares, C., Yang, J., Ren, F., Kim, J., Lagov, P. B., Stolbunov, V. S., and Kochkova, A., Appl. Phys. Lett. vol. 113, no. 9, 092102 (2018).
 - [153] Polyakov, A. Y., Smirnov, N. B., Shchemerov, I. V., Yakimov, E. B., Yang, J., Ren, F., Yang, G., Kim, J., Kuramata, A., and Pearton, S. J., Appl. Phys. Lett. vol. 112, no. 3, 032107 (2018).
 - [154] Wang, B., Look, D., and Leedy, K., J. Appl. Phys. vol. 125, no. 10, 105103 (2019).
 - [155] Polyakov, A. Y., Lee, I.-H., Miakonkikh, A., Chernykh, A. V., Smirnov, N. B., Shchemerov, I. V., Kochkova, A. I., Vasilev, A. A., and Pearton, S. J., J. Appl. Phys. vol. 127, no. 17, 175702 (2020).
 - [156] Martin, R. M., *Electronic structure: basic theory and practical methods* (Cambridge University Press, 2004).
 - [157] Capelle, K., en, Braz. J. Phys. vol. 36, 1318 (2006).
 - [158] Hohenberg, P. and Kohn, W., Phys. Rev. vol. 136, B864 (1964).
 - [159] Wills, J. M., Alouani, M., Andersson, P., Delin, A., Eriksson, O., and Grechnev, O., “Density functional theory and the kohn–sham equation”, in *Full-potential electronic structure method: energy and force calculations with density functional and dynamical mean field theory* (Springer Berlin Heidelberg, Berlin, Heidelberg, 2010), pp. 7–19.
 - [160] Kohn, W. and Sham, L. J., Phys. Rev. vol. 140, A1133 (1965).
 - [161] Ceperley, D. M. and Alder, B. J., Phys. Rev. Lett. vol. 45, 566 (1980).
 - [162] Perdew, J. P., MRS Bull. vol. 38, no. 9, 743–750 (2013).

References

- [163] Perdew, J. P., Burke, K., and Ernzerhof, M., Phys. Rev. Lett. vol. 77, 3865 (1996).
- [164] Perdew, J. P., Ruzsinszky, A., Csonka, G. I., Vydrov, O. A., Scuseria, G. E., Constantin, L. A., Zhou, X., and Burke, K., Phys. Rev. Lett. vol. 100, 136406 (2008).
- [165] Sun, J., Ruzsinszky, A., and Perdew, J. P., Phys. Rev. Lett. vol. 115, 036402 (2015).
- [166] Perdew, J. P. and Levy, M., Phys. Rev. Lett. vol. 51, 1884 (1983).
- [167] Becke, A. D., J. Chem. Phys. vol. 98, no. 2, 1372 (1993).
- [168] Harris, J., Phys. Rev. A vol. 29, 1648 (1984).
- [169] Heyd, J., Scuseria, G. E., and Ernzerhof, M., J. Chem. Phys. vol. 118, no. 18, 8207 (2003).
- [170] Krukau, A. V., Vydrov, O. A., Izmaylov, A. F., and Scuseria, G. E., J. Chem. Phys. vol. 125, no. 22, 224106 (2006).
- [171] Marques, M. A. L., Vidal, J., Oliveira, M. J. T., Reining, L., and Botti, S., Phys. Rev. B vol. 83, 035119 (2011).
- [172] Chen, W., Miceli, G., Rignanese, G.-M., and Pasquarello, A., Phys. Rev. Mater. vol. 2, 073803 (2018).
- [173] Mori-Sánchez, P., Cohen, A. J., and Yang, W., Phys. Rev. Lett. vol. 100, 146401 (2008).
- [174] Perdew, J. P., Parr, R. G., Levy, M., and Balduz, J. L., Phys. Rev. Lett. vol. 49, 1691 (1982).
- [175] Perdew, J. P., Ruzsinszky, A., Csonka, G. I., Vydrov, O. A., Scuseria, G. E., Staroverov, V. N., and Tao, J., Phys. Rev. A vol. 76, 040501 (2007).
- [176] Lany, S. and Zunger, A., Phys. Rev. B vol. 78, 235104 (2008).
- [177] Deák, P., Duy Ho, Q., Seemann, F., Aradi, B., Lorke, M., and Frauenheim, T., Phys. Rev. B vol. 95, 075208 (2017).
- [178] Miceli, G., Chen, W., Reshetnyak, I., and Pasquarello, A., Phys. Rev. B vol. 97, 121112 (2018).
- [179] Janak, J. F., Phys. Rev. B vol. 18, 7165 (1978).
- [180] Dreyer, C. E., Alkauskas, A., Lyons, J. L., Janotti, A., and Van de Walle, C. G., Annu. Rev. Mater. Res. vol. 48, no. 1, 1 (2018).
- [181] Kresse, G. and Furthmüller, J., Phys. Rev. B vol. 54, 11169 (1996).
- [182] Sholl, D. S. and Steckel, J. A., *Density functional theory – a practical introduction* (Wiley, Hoboken, N.J, 2009).
- [183] Blöchl, P. E., Phys. Rev. B vol. 50, 17953 (1994).
- [184] Kresse, G. and Joubert, D., Phys. Rev. B vol. 59, 1758 (1999).
- [185] Baldereschi, A., Phys. Rev. B vol. 7, 5212 (1973).

-
- [186] Monkhorst, H. J. and Pack, J. D., Phys. Rev. B vol. 13, 5188 (1976).
 - [187] Van de Walle, C. G. and Neugebauer, J., J. Appl. Phys. vol. 95, no. 8, 3851 (2004).
 - [188] Buckeridge, J., Scanlon, D., Walsh, A., and Catlow, C., Comput. Phys. Commun. vol. 185, no. 1, 330 (2014).
 - [189] Buckeridge, J., Comput. Phys. Commun. vol. 244, 329 (2019).
 - [190] Lang, D. V., J. Appl. Phys. vol. 45, no. 7, 3023 (1974).
 - [191] Stoneham, A., *Theory of defects in solids: electronic structure of defects in insulators and semiconductors*, Oxford classic texts in the physical sciences (Clarendon Press, 2001).
 - [192] Huang, K., Rhys, A., and Mott, N. F., Proc. R. Soc. A vol. 204, no. 1078, 406 (1950).
 - [193] Lax, M., J. Chem. Phys. vol. 20, no. 11, 1752 (1952).
 - [194] Markham, J. J., Rev. Mod. Phys. vol. 31, 956 (1959).
 - [195] Kim, S., Hood, S. N., Gerwen, P. van, Whalley, L. D., and Walsh, A., *Carriercapture.jl: anharmonic carrier capture*, version v0.3, Mar. 2020.
 - [196] Martins, A. S., Boykin, T. B., Klimeck, G., and Koiller, B., Phys. Rev. B vol. 72, 193204 (2005).
 - [197] Durrant, T. R., Murphy, S. T., Watkins, M. B., and Shluger, A. L., J. Chem. Phys. vol. 149, no. 2, 024103 (2018).
 - [198] Fuchs, K. and Fowler, R. H., Proc. R. Soc. A vol. 151, no. 874, 585 (1935).
 - [199] Leslie, M and Gillan, N. J., J. Phys. C: Solid State Phys. vol. 18, no. 5, 973 (1985).
 - [200] Makov, G. and Payne, M. C., Phys. Rev. B vol. 51, 4014 (1995).
 - [201] Freysoldt, C., Neugebauer, J., and Van de Walle, C. G., Phys. Rev. Lett. vol. 102, 016402 (2009).
 - [202] Freysoldt, C., Neugebauer, J., and Van de Walle, C. G., Phys. Status Solidi B vol. 248, no. 5, 1067 (2011).
 - [203] Komsa, H.-P., Rantala, T. T., and Pasquarello, A., Phys. Rev. B vol. 86, 045112 (2012).
 - [204] Kumagai, Y. and Oba, F., Phys. Rev. B vol. 89, 195205 (2014).
 - [205] Rurali, R. and Cartoixa, X., Nano Lett. vol. 9, no. 3, PMID: 19206213, 975 (2009).
 - [206] Gake, T., Kumagai, Y., Freysoldt, C., and Oba, F., Phys. Rev. B vol. 101, 020102 (2020).
 - [207] Sky, T. N., Johansen, K. M., Frodason, Y. K., Svensson, B. G., and Vines, L., J. Appl. Phys. vol. 124, no. 24, 245702 (2018).

References

- [208] Sky, T. N., Johansen, K. M., Frodason, Y. K., Aarholt, T., Riise, H. N., Prytz, Ø, Svensson, B. G., and Vines, L, *Semicond. Sci. Technol.* vol. 34, no. 2, 025011 (2019).
- [209] Reticcioli, M., Diebold, U., Kresse, G., and Franchini, C., “Small polarons in transition metal oxides”, in *Handbook of materials modeling: applications: current and emerging materials*, edited by Andreoni, W. and Yip, S. (Springer International Publishing, Cham, 2019), pp. 1–39.
- [210] Pekar, S. I., *Zh. Eksp. Teor. Fiz* vol. 16, 335 (1946).
- [211] Landau, L. D., *Phys. Z Sowjetunion* vol. 3, 644 (1933).
- [212] Kananen, B. E., Giles, N. C., Halliburton, L. E., Foundos, G. K., Chang, K. B., and Stevens, K. T., *J. Appl. Phys.* vol. 122, no. 21, 215703 (2017).
- [213] Skachkov, D., Lambrecht, W. R. L., Bardeleben, H. J. von, Gerstmann, U., Ho, Q. D., and Deák, P., *J. Appl. Phys.* vol. 125, no. 18, 185701 (2019).
- [214] Setvin, M., Franchini, C., Hao, X., Schmid, M., Janotti, A., Kaltak, M., Van de Walle, C. G., Kresse, G., and Diebold, U., *Phys. Rev. Lett.* vol. 113, 086402 (2014).
- [215] Look, D. C., Leedy, K. D., Vines, L., Svensson, B. G., Zubiaga, A., Tuomisto, F., Dutt, D. R., and Brillson, L. J., *Phys. Rev. B* vol. 84, 115202 (2011).
- [216] Galland, D. and Herve, A., *Solid State Commun.* vol. 14, no. 10, 953 (1974).
- [217] Lyons, J. L., Alkauskas, A., Janotti, A., and Van de Walle, C. G., *Phys. Status Solidi B* vol. 252, no. 5, 900 (2015).
- [218] Børseth, T. M., Svensson, B. G., Kuznetsov, A. Y., Klason, P., Zhao, Q. X., and Willander, M., *Appl. Phys. Lett.* vol. 89, no. 26, 262112 (2006).
- [219] Reynolds, D., Look, D., Jogai, B., Van Nostrand, J., Jones, R., and Jenny, J., *Solid State Commun.* vol. 106, no. 10, 701 (1998).
- [220] Vlasenko, L. S. and Watkins, G. D., *Phys. Rev. B* vol. 71, 125210 (2005).
- [221] Harwig, T. and Kellendonk, F., *J. Solid State Chem* vol. 24, no. 3, 255 (1978).
- [222] Shimamura, K., VÁllora, E. G., Ujiie, T., and Aoki, K., *Appl. Phys. Lett.* vol. 92, no. 20, 201914 (2008).
- [223] Gao Hantian an Muralidharan, S., Pronin, N., Karim, M. R., White, S. M., Asel, T., Foster, G., Krishnamoorthy, S., Rajan, S., Cao, L. R., Higashiwaki, M., Wenckstern, H. von, Grundmann, M., Zhao, H., Look, D. C., and Brillson, L. J., *Appl. Phys. Lett.* vol. 112, no. 24, 242102 (2018).
- [224] Vlasenko, L. S. and Watkins, G. D., *Phys. Rev. B* vol. 71, 125210 (2005).
- [225] Zwingel, D. and Gärtner, F., *Solid State Commun.* vol. 14, no. 1, 45 (1974).

-
- [226] Demchenko, D. O., Earles, B., Liu, H. Y., Avrutin, V., Izyumskaya, N., Özgür, U., family=c., given=H., giveni=H., „ and, Phys. Rev. B vol. 84, 075201 (2011).
- [227] Demchenko, D. O., Diallo, I. C., and Reshchikov, M. A., J. Appl. Phys. vol. 119, no. 3, 035702 (2016).
- [228] Bhandari, S., Zvanut, M. E., and Varley, J. B., J. Appl. Phys. vol. 126, no. 16, 165703 (2019).
- [229] Dobaczewski, L., Kaczor, P., Hawkins, I. D., and Peaker, A. R., J. Appl. Phys. vol. 76, no. 1, 194 (1994).
- [230] Büscher, R. and Lehmann, G., Z. Naturforsch. vol. 42, no. 1, 67 (1987).
- [231] Mentink-Vigier, F., Binet, L., Vignoles, G., Gourier, D., and Vezin, H., Phys. Rev. B vol. 82, 184414 (2010).
- [232] Hoshikawa, K., Ohba, E., Kobayashi, T., Yanagisawa, J., Miyagawa, C., and Nakamura, Y., J. Cryst. Growth vol. 447, 36 (2016).
- [233] Binet, L., Gourier, D., and Minot, C., J. Solid State Chem. vol. 113, no. 2, 420 (1994).
- [234] Kopylov, A. A. and Pikhtin, A. N., Sov. Phys. Solid State vol. 16, no. 7, 1200 (1975).
- [235] Holston, M. S., Golden, E. M., Kananen, B. E., McClory, J. W., Giles, N. C., and Halliburton, L. E., J. Appl. Phys. vol. 119, no. 14, 145701 (2016).
- [236] Makkonen, I., Korhonen, E., Prozheeva, V., and Tuomisto, F., J. Phys. Condens. Matter vol. 28, no. 22, 224002 (2016).
- [237] Johansen, K., Tuomisto, F., Makkonen, I., and Vines, L., Mater Sci Semicond Process vol. 69, 23 (2017).
- [238] Bang, J., Kim, Y.-S., Park, C. H., Gao, F., and Zhang, S. B., Appl. Phys. Lett. vol. 104, no. 25, 252101 (2014).
- [239] Anderson, P. W., Phys. Rev. Lett. vol. 34, 953 (1975).
- [240] Chadi, D. J. and Chang, K. J., Phys. Rev. Lett. vol. 61, 873 (1988).
- [241] Hemmingsson, C. G., Son, N. T., Ellison, A., Zhang, J., and Janzén, E., Phys. Rev. B vol. 58, R10119 (1998).
- [242] Auret, F. D., Goodman, S. A., Hayes, M., Legodi, M. J., Laarhoven, H. A. van, and Look, D. C., Appl. Phys. Lett. vol. 79, no. 19, 3074 (2001).
- [243] Hofmann, D., Pfisterer, D., Sann, J., Meyer, B., Tena-Zaera, R., Munoz-Sanjose, V., Frank, T., and Pensl, G., Appl. Phys. A vol. 88, no. 1, 147 (2007).
- [244] Ellguth, M., Schmidt, M., Pickenhain, R., Wenckstern, H. V., and Grundmann, M., Phys. Status Solidi B vol. 248, no. 4, 941 (2010).

References

- [245] Hayes, M., Auret, F., Rensburg, P. J. van, Nel, J., Wesch, W., and Wendler, E., Nucl. Instrum. Methods Phys. Res. B vol. 257, no. 1-2, 311 (2007).
- [246] Hayes, M., Auret, F. D., Rensburg, P. J. J. van, Nel, J. M., Wesch, W., and Wendler, E., Phys. Status Solidi B vol. 244, no. 5, 1544 (2007).
- [247] Hupfer, A., Bhoodoo, C., Vines, L., and Svensson, B. G., J. Appl. Phys. vol. 119, no. 18, 181506 (2016).
- [248] Mcglone, J. F., Xia, Z., Zhang, Y., Joishi, C., Lodha, S., Rajan, S., Ringel, S. A., and Arehart, A. R., IEEE Electron Device Lett. vol. 39, no. 7, 1042 (2018).
- [249] Gao, W. and Tkatchenko, A., Phys. Rev. Lett. vol. 111, 045501 (2013).

Papers

Paper I

Zn vacancy as a polaronic hole trap in ZnO

Ymir Kalmann Frodason, Klaus Magnus Johansen, Tor Svendsen Bjørheim, Bengt Gunnar Svensson, Audrius Alkauskas

Published in *Physical Review B*, March 2017 volume 95, issue 9, pp. 094–105.
DOI: 10.1103/PhysRevB.95.094105.

Zn vacancy as a polaronic hole trap in ZnO

Y. K. Frodason,* K. M. Johansen, T. S. Bjørheim, and B. G. Svensson

Centre for Materials Science and Nanotechnology, University of Oslo, N-0318 Oslo, Norway

A. Alkauskas

Center for Physical Sciences and Technology, LT-10257 Vilnius, Lithuania

(Received 16 December 2016; revised manuscript received 15 February 2017; published 10 March 2017)

This work explores the Zn vacancy in ZnO using hybrid density functional theory calculations. The Zn vacancy is predicted to be an exceedingly deep polaronic acceptor that can bind a localized hole on each of the four nearest-neighbor O ions. The hole localization is accompanied by a distinct outward relaxation of the O ions, which leads to lower symmetry and reduced formation energy. Notably, we find that initial symmetry breaking is required to capture this effect. We present a simple model to rationalize our findings with regard to the approximately equidistant thermodynamic charge-state transition levels. Furthermore, by employing a one-dimensional configuration coordinate model with parameters obtained from the hybrid density functional theory calculations, luminescence line shapes were calculated. The results show that the isolated Zn vacancy is unlikely to be the origin of the commonly observed luminescence in the visible part of the emission spectrum from *n*-type material, but rather the luminescence in the infrared region.

DOI: [10.1103/PhysRevB.95.094105](https://doi.org/10.1103/PhysRevB.95.094105)**I. INTRODUCTION**

Although there is a plethora of density functional theory (DFT) studies addressing various aspects of intrinsic defects in ZnO, precise determination of properties like the formation energy and thermodynamic charge-state transition levels has been difficult, and the results scatter widely in the literature. This is especially evident for the Zn vacancy V_{Zn} , where the reported thermodynamic charge-state transition levels spread over more than 2 eV [1–13]. The main reason for this large variation can be divided into two categories [3,14]: (i) the choice of exchange-correlation functional and (ii) the choice (or omission) of finite-size corrections. Despite this spread in results, DFT calculations have provided valuable insights into the properties of many defects in ZnO. The majority of studies conclude that V_{Zn} is a deep acceptor, the dominant “native” acceptor-type defect, acting as a compensating center in *n*-type material [1,2]. However, theoretical studies that relied on semilocal and local density functionals, while providing valuable information, could not properly describe the localization of holes at V_{Zn} as observed experimentally in, e.g., electron paramagnetic resonance (EPR) studies [15–18].

By employing the Heyd-Scuseria-Ernzerhof (HSE) hybrid functional [19,20], which intermixes a portion of screened Hartree-Fock (HF) exchange with the standard generalized gradient approximation (GGA) Perdew-Burke-Ernzerhof (PBE) exchange-correlation functional, we are able to capture the hole localization at V_{Zn} , which drastically modifies its properties. Furthermore, by using a one-dimensional configuration coordinate model [21], defect luminescence line shapes and positions for all optical transitions involving V_{Zn} and the band edges are calculated. The results show that the isolated V_{Zn} is unlikely to be the origin of the luminescence in the visible part of the emission spectrum from *n*-type material.

This paper is organized as follows. In Sec. II, we present computational details, outline how the various quantities are calculated, and elaborate on the accuracy of the calculations. In Sec. III, the results are presented and discussed, including thermodynamics, electronic structure, a simple model for the energetics of V_{Zn} , and optical properties. Section IV concludes the paper.

II. THEORETICAL FRAMEWORK**A. Computational details**

All calculations were performed using the projector augmented-wave (PAW) method [22–24], as implemented in the Vienna Ab initio Simulation Package (VASP) [25,26], using a plane-wave energy cutoff of 500 eV. The Zn $3d$, $4s$, $4p$ and O $2s$, $2p$ electrons were considered as valence electrons. The α -tuned HSE hybrid functional was used with a screening parameter [19,20] of $0.2 \text{ \AA}^{-1}$, and the amount of exact exchange was set to $\alpha = 37.5\%$ [2]. The resulting lattice parameters for wurtzite ZnO ($a = 3.244 \text{ \AA}$ and $c = 5.194 \text{ \AA}$) and band gap (3.42 eV) are in excellent agreement with experimental data. Defect calculations were performed with a 96-atom supercell by relaxing all ionic positions but keeping its shape and volume fixed to those of the pristine supercell. Ionic optimization was performed until all forces were smaller than $5 \text{ meV/\AA}$, and the break condition for the electronic self-consistent loop was set to 10^{-6} eV . Due to the periodic boundary conditions, defect wave functions may overlap, causing an artificial dispersion of defect states. This may lead to an error in the defect formation energy for small supercells, particularly if a Γ -only k -point sampling is used [14,27]. In this work, a special off- Γ k point at $k = (\frac{1}{4}, \frac{1}{4}, \frac{1}{4})$ was employed in order to minimize this error within the bounds of computational cost. This setup was checked for several defects in ZnO against a 72-atom supercell with a $2 \times 2 \times 2$ Γ -centered k mesh, yielding an average energy difference of

*ymirkf@fys.uio.no

merely 0.02 eV. Spin-polarized calculations were performed for all charge states.

B. Defect thermodynamics

The formation energy of a defect in charge state q is given by [14,28]

$$E^f(q) = E_{\text{defect}}^{\text{tot}}(q) - E_{\text{bulk}}^{\text{tot}} - \sum_i \Delta n_i \mu_i + q(\varepsilon_{\text{VBM}} + \varepsilon_F) + E^{\text{FNV}}, \quad (1)$$

where E^{tot} are the electronic total energies, Δn_i is the change in the number of atoms i (Zn, O) with chemical potential μ_i , ε_F is the Fermi level relative to the bulk valence-band (VB) maximum ε_{VBM} , and E^{FNV} is an electrostatics-based finite-size correction term used to obtain the formation energy of the isolated defect from the finite-sized supercell calculation. We have employed the extended Freysoldt, Neugebauer, and Van de Walle (FNV) correction scheme [29–31]

$$E^{\text{FNV}} = E^{\text{PC}} + q \Delta V_{q/\text{bulk|far}}^{\text{PC}}, \quad (2)$$

where E^{PC} is the anisotropic Madelung energy for a periodic array of point charges immersed in a neutralizing background charge. The potential alignment term $\Delta V_{q/\text{bulk|far}}^{\text{PC}}$ is the difference between the defect-induced potential and point-charge potential in a region far away from the defect,

$$\Delta V_{q/\text{bulk|far}}^{\text{PC}} = (V_{\text{defect},q} - V_{\text{bulk}}) - V_q^{\text{PC}}. \quad (3)$$

Since the atomic structure is allowed to relax when defects are introduced, the atomic site electrostatic potential is used as a potential marker, as discussed in detail by Kumagai and Oba [30]. A small uncertainty in the alignmentlike term arises due to the limited supercell size (less than 0.1 eV). The Madelung energy is estimated by an Ewald summation, and the macroscopic dielectric constant, valid for cubic systems, is replaced by a dielectric tensor. Both ion-clamped and ionic contributions to the dielectric tensor of the bulk system were calculated from the self-consistent response of the system to a finite electric field [32], resulting in the static dielectric tensor $\varepsilon_{\perp} = 7.19$ and $\varepsilon_{\parallel} = 8.23$. These values are lower than the experimental ones [33] but closer than those obtained from density functional perturbation theory with the GGA-PBE functional [30].

By varying the chemical potential, different experimental conditions can be explored. Upper and lower bounds are given by the stability of the phases that constitute the reservoir, which is expressed by the thermodynamic stability condition $\Delta H^f(\text{ZnO}) = \mu_{\text{Zn}} + \mu_{\text{O}}$. The upper bound of μ_{O} (and thus the lower bound of μ_{Zn}) is given by half the total energy of an O_2 molecule and corresponds to O-rich conditions. Likewise, the lower limit of μ_{O} (and the upper limit of μ_{Zn}) is given by the reduction of ZnO to metallic Zn, corresponding to Zn-rich conditions [1]. The hybrid functional yields a ZnO heat of formation of $\Delta H^f(\text{ZnO}) = -3.49$ eV, which is close to the experimental value of -3.61 eV [34].

From the calculated defect formation energies, thermodynamic charge-state transition levels are given by the Fermi

FIG. 1. Configuration coordinate diagram illustrating vibronic transitions between the neutral and singly positive charge state of a defect. E_{ZPL} gives the thermodynamic charge-state transition level relative to the conduction-band (CB) minimum (shown in the band diagram on the right). The horizontal lines in each normal mode are vibrational energy levels, and the probability of any given vibronic transition is proportional to the vibrational wave function overlap between the initial level and final level.

level position for which the formation energy of the defect in two charge states q_1 and q_2 is equal, i.e. [14],

$$\varepsilon(q_1/q_2) = \frac{E^f(q_1; \varepsilon_F = 0) - E^f(q_2; \varepsilon_F = 0)}{q_2 - q_1}. \quad (4)$$

C. Defect luminescence

Defect luminescence line shapes were calculated by using the methodology described in Ref. [21], wherein the multidimensional vibrational problem is mapped onto an effective one-dimensional configuration coordinate diagram [21,35] (Fig. 1).

The parameters that enter the model are the effective phonon frequencies $\Omega_{g/c}$, the zero-phonon line E_{ZPL} , and the change in configuration coordinate ΔQ , which is defined as

$$(\Delta Q)^2 = M \Delta R^2 = \sum_{i\alpha} m_\alpha (R_{c,i\alpha} - R_{g,i\alpha})^2. \quad (5)$$

Here, M is the effective modal mass in atomic units and ΔR is the magnitude of the displacement in angstroms for all atoms α in the supercell ($i = \{x, y, z\}$) between the excited (e) and ground (g) states. Thus, the configuration coordinate represents the collective motion of all atoms in the supercell between the different charge states, meaning that the various individual vibrational modes are replaced by a single effective mode. All parameters are obtained from the hybrid DFT calculations by using finite differences. Within the Franck-Condon approximation, classical absorption and emission energies may then be defined as $E_{\text{abs}} = E_{\text{ZPL}} - \Delta E_g$ and $E_{\text{em}} = E_{\text{ZPL}} + \Delta E_c$, respectively. Here, ΔE_g and ΔE_c are relaxation energies, often referred to as Franck-Condon shifts. Huang-Rhys (HR) factors [35,36] describe the average number of phonons that are involved in a transition and can be expressed as $S_g = \Delta E_g / \hbar \Omega_g$ for emission. The effective one-dimensional configuration coordinate model is a good approximation for broad luminescence bands with

strong electron-phonon coupling ($S \gg 1$), as demonstrated in Refs. [21,37].

D. The self-interaction error

While the value of the fraction of HF exchange used (37.5%) reproduces the lattice parameters and bulk band gap of ZnO, this does not necessarily mean that the defect states of V_{Zn} are described correctly [38]. In order to elaborate on possible overlocalization, all charge states were also calculated using the original HSE06 functional (25% HF exchange). However, the results remained qualitatively unaffected regarding the localization of holes. The VB shifted upward by 0.6 eV, but the charge-state transition levels remained almost unchanged when aligned to the average electrostatic potential [39,40]. Moreover, we found the so-called non-Koopmans energy for V_{Zn}^0 , defined in Refs. [38,41] as

$$E_{\text{NK}} = \varepsilon(N) - E_A = \varepsilon(N) - [E(N+1) - E(N)], \quad (6)$$

to be small (0.12 eV). Here, $\varepsilon(N)$ is the single-particle energy of the polaronic state, and E_A is the electron addition energy of the system, i.e., the difference in total energy between the $(N+1)$ - and N -electron systems, keeping the ions fixed to their N -electron ground-state positions. The electrostatic finite-size correction was applied only to $E(N+1)$, using the ion-clamped dielectric tensor, since the two remaining terms are for the neutral defect. E_{NK} may still contain a small finite-size error. We conclude, however, that the self-interaction error is small in the calculations, and importantly, the qualitative results do not hinge on the specific value used for the exchange parameter.

III. RESULTS AND DISCUSSION

In wurtzite ZnO, four O ions form a tetrahedron around every Zn ion and vice versa. In these tetrahedra, we shall refer to the ions in the three corners of the basal plane as azimuthal (az) ions, while the ion in the fourth corner will be referred to as the axial (ax) ion (Fig. 2). When a Zn vacancy is formed, four Zn-O bonds are broken. The dangling O $2p$ bonds that remain are partially filled by six electrons and can accommodate two more. This simple chemical picture dictates that V_{Zn} acts as a double acceptor. However, it can also trap holes in polaronic states, as will be shown in Secs. III A and III B.

A. Thermodynamics of the Zn vacancy

Figure 3 shows the formation energy of V_{Zn} as a function of the Fermi level position under O-rich conditions. The formation energy approaches ~ 0.06 eV near the CB minimum, which indicates that V_{Zn} should be the dominating intrinsic acceptor in n -type ZnO, acting as a compensating center. This is in agreement with positron annihilation spectroscopy (PAS) measurements [42] and previous DFT studies [1,2]. However, the majority of previous DFT studies have included only acceptor charge states of V_{Zn} (two examples are shown in Fig. 3). As shown previously [41,43], V_{Zn} can display positive charge states as well. Indeed, we find both the $+$ and $2+$ states, with thermodynamic transitions located at 0.25 ($2+/+$), 0.89 ($+/0$), 1.40 ($0/-$), and 1.96 eV ($-/2-$) above the VB maximum (note that the transitions are approximately

FIG. 2. Probability density for holes occupying polaronic KS eigenstates in V_{Zn} (blue). When the HSE functional is used, holes lock onto separate O ions (red). When a semilocal functional is used, the holes delocalize over several O ions due to the self-interaction error. The wave functions have a distinct O $2p$ orbital character. The probability density isosurface was set to $0.02 r_{\text{Bohr}}^{-3}$. The azimuthal (az) and axial (ax) O ions are indicated with arrows for V_{Zn}^- .

equidistant). The emergence of both positive and negative charge states means that V_{Zn} is an amphoteric defect. Although the formation energy is rather high in p -type material, V_{Zn} is predicted to act as a compensating donor in a frozen-in, out-of-equilibrium scenario.

One might question why the previous hybrid calculations by Oba *et al.* [2] deviate so much from our results. The reason for this is mainly due to the fact that spin polarization was taken into account only for V_{Zn}^- in Ref. [2] (due to computational constraints), but minor differences may also arise because a

FIG. 3. The formation energy of V_{Zn} (red line) as a function of the Fermi level position (from the VB maximum to the CB minimum) under O-rich conditions. Thermodynamic charge-state transition levels are labeled. Results from two previous DFT studies are included for comparison (black lines), and the formation energy of V_{O} (blue line) is included as a benchmark (see text).

FIG. 4. Configuration coordinate diagrams and luminescence lines for optical transitions involving the Zn vacancy. The respective transitions are color matched and labeled from (a) to (f) in the configuration coordinate diagrams and luminescence spectrum. From left to right, the peak positions of the luminescence bands are at 0.71, 0.85, 1.26, 1.40, 1.73, and 2.39 eV.

plane-wave energy cutoff of 300 eV and a Γ -only k -point sampling were used in Ref. [2]. We elaborate on this in Sec. III B.

The calculated position of the $(0/-)$ transition agrees well with photo-EPR data; Evans *et al.* [18] inferred that the threshold energy to excite an electron from V_{Zn}^- to the CB (to observe the EPR signal of V_{Zn}^0) is ~ 2.5 eV. We obtain an absorption energy of 2.67 eV for V_{Zn}^- , as shown in Fig. 4(b). This is somewhat higher than the photo-EPR data, but the onset shifts down due to vibrational broadening. This can be shown by simulating the absorption profile, as demonstrated in Ref. [37].

The O vacancy V_O is also included in Fig. 3 for comparison since the $(2+/0)$ transition level of this defect has become a

benchmark case for defects in ZnO [44]. In fact, the defect state of V_O is fairly well described by a wide range of different functionals. While there is a large spread in the reported thermodynamic charge-state transition levels relative to the VB maximum, the agreement becomes decent when they are aligned to a common reference level, such as the average electrostatic potential [44]. We obtain 2.1 eV above the VB maximum for the $(2+/0)$ transition, which is in good agreement with previous calculations based on hybrid functionals [2,3,44]. The defect wave function of V_{Zn} , on the other hand, is poorly described at the (semi)local level, implying that the energy positions of the thermodynamic charge-state transition levels depend strongly on the choice of functional.

B. Polaronic charge localization

The emergence of the positive charge states of V_{Zn} can be understood by taking a closer look at its electronic and atomic structure. First, V_{Zn}^{2-} is considered, where the O $2p$ dangling bond states are completely filled with electrons. By examining the *spd*- and site-projected wave-function character of each KS state, one can deduce that the dangling bonds introduce three states in the band gap close to the VB maximum and one resonant with the VB. When one electron is removed, the spin degeneracy of the resulting half-filled defect state is broken, and the empty state moves deep into the band gap. As more electrons are removed, additional empty states exhibiting polaronic nature appear deep in the band gap until all four dangling bond states are half filled (V_{Zn}^{2+}). The probability density of the empty defect states, shown in Fig. 2, illustrates that each hole localizes onto a single nearest-neighbor O^{2-} ion in the form of a small hole polaron. This spontaneous localization of holes is accompanied by a distinct outward relaxation of the O^- ion, which further moves the polaronic state into the band gap, lowering the total defect energy. The azimuthal O^- ions with trapped holes move away from the vacancy by approximately 14% of the bulk Zn-O bond length, which is about twice as far as the azimuthal O^{2-} ions without trapped holes. This behavior (hole localization with local lattice distortion) is common for many oxide semiconductors [45,46].

As pointed out by Janotti *et al.* [1], the (semi)local functionals are unable to describe the Zn vacancy (and thus fail to stabilize V_{Zn}^+ and V_{Zn}^{2+}). This is because of the self-interaction error; a lower total energy occurs by dividing the hole between multiple O ions. Lany and Zunger [41] removed this delocalization bias by using a hole-state potential to enforce fulfillment of the generalized Koopmans condition, ensuring a linear behavior of the total energy and a constant behavior of the highest-occupied single-particle level with respect to fractional occupation [38,41]. This correction stabilized V_{Zn}^+ and V_{Zn}^{2+} , but it does not remedy the severe band gap underestimation of GGA ($E_g = 0.73$ eV), leading to an ambiguity in the energy position of the thermodynamic charge-state transition levels with respect to the band edges. It must be noted, however, that the overall result of Lany and Zunger is in good agreement with our result.

Incorporating a fraction of exact exchange, hybrid functionals cancel (at least in part) the self-interaction error and provide accurate band gaps. However, previous hybrid DFT studies employing the HSE, PBE0, and screened-exchange (sX) functionals did not reveal the positive charge states of V_{Zn} [2,3]. Here, we demonstrate that initial symmetry-breaking operations, like moving the O ions slightly or specifying their initial magnetic moment, are a prerequisite to obtain localization of the holes onto single O ions. Indeed, symmetry breaking is often necessary to capture polaronic effects [47–49]. It is also crucial that the ions are relaxed with the hybrid functional and that spin-polarized calculations are performed for all charge states. Otherwise, the ground state will not be obtained; the holes may instead delocalize over more than one O ion, with no polaronic effects. By breaking the symmetry, all metastable localized hole configurations were investigated.

The azimuthal configuration of holes, shown in Fig. 2, was found to be the most stable one, in agreement with EPR data [15–18]. In addition, a separation of 3.69 Å between the two O^- ions with trapped holes in V_{Zn}^0 was obtained, which is close to the 3.75 Å inferred from EPR measurements [16,18]. Finally, we find that the high-spin configuration of V_{Zn} is energetically preferred, which means that $S = 1/2$ for V_{Zn}^- , $S = 1$ for V_{Zn}^0 , $S = 3/2$ for V_{Zn}^+ , and $S = 2$ for V_{Zn}^{2+} .

Polaronic hole localization is not unique for V_{Zn} in ZnO. While lattice deformation alone is not sufficient to induce hole localization [45], polarons can form when an acceptorlike defect exists at a neighboring Zn site [46]. Indeed, substitutional group-I impurities (Li_{Zn} , Na_{Zn}) exhibit the same tendency to stabilize anion-trapped hole polarons [43,50,51]. Moreover, anion-site substitutional impurities can lead to deep atomlike localized states [46]. These effects, in combination with the very low position of the ZnO VB on an absolute energy scale and the heavy-hole effective masses, render *p*-type doping of ZnO challenging at equilibrium conditions.

C. A simple model for the Zn vacancy energetics

As mentioned in Sec. III A, the charge-state transition levels of the Zn vacancy are almost equidistant from each other, i.e., $\varepsilon(-/2-) - \varepsilon(0/-) \approx \varepsilon(0/-) - \varepsilon(+/0) \approx \varepsilon(+/0) - \varepsilon(2+/+)$. Analysis of the results in Ref. [52] shows that the same holds for the Ga vacancy and Ga vacancy complexes with O and H in GaN that similarly exhibit polaronic properties. Therefore, this indicates a more fundamental reason for such behavior beyond mere coincidence. In this section we describe a simple model that helps us understand why charge-state transition levels for V_{Zn} in ZnO (as well as gallium vacancy and its complexes in GaN) are approximately equidistant.

First, assume the Fermi level position at the VB maximum ($\varepsilon_F = 0$ eV in Fig. 3), and as a starting point consider V_{Zn}^{2-} . Adding a hole to the defect lowers the formation energy by ε_0 , which includes the polaron formation energy. Subsequently,

$$E^f(V_{\text{Zn}}^-) = E^f(V_{\text{Zn}}^{2-}) - \varepsilon_0.$$

According to Eq. (4), this translates into the $\varepsilon(-/2-)$ charge-state transition level being located at

$$\varepsilon(-/2-) = \varepsilon_0$$

above the VB maximum. Adding another hole lowers the formation energy of V_{Zn}^- by $\varepsilon_0 - U$, where U is the hole-hole repulsion energy, that is,

$$\varepsilon(0/-) = \varepsilon_0 - U.$$

Adding a third hole lowers the energy even less, as now the hole is repelled by two other holes:

$$\varepsilon(+/0) = \varepsilon_0 - 2U.$$

Similarly, for the fourth hole

$$\varepsilon(2+/+) = \varepsilon_0 - 3U.$$

TABLE I. Effective parameters for the calculated Zn vacancy luminescence transitions in ZnO: total mass-weighted distortion ΔQ , effective ground- and excited-state normal-mode frequencies $\hbar\Omega_{g/e}$, zero-phonon-line energy E_{ZPL} , peak position (PP), full width at half maximum of the luminescence band (FWHM), and ground- and excited-state Huang-Rhys factors $S_{g/e}$.

Transition	ΔQ (amu ^{1/2} Å)	$\hbar\Omega_g$ (meV)	$\hbar\Omega_e$ (meV)	E_{ZPL} (eV)	PP (eV)	FWHM (eV)	S_g	S_e
(a) $V_{Zn}^- + e^- = V_{Zn}^{2-}$	2.60	34	27	1.48	0.71	0.39	23.4	23.1
(b) $V_{Zn}^0 + e^- = V_{Zn}^-$	2.77	31	25	2.04	1.26	0.40	25.2	24.7
(c) $V_{Zn}^+ + e^- = V_{Zn}^{2+}$	2.90	30	25	2.55	1.73	0.40	26.8	26.4
(d) $V_{Zn}^{2+} + e^- = V_{Zn}^+$	3.00	28	24	3.19	2.39	0.39	27.2	27.5
(e) $V_{Zn}^{2-} + h^+ = V_{Zn}^-$	2.60	27	34	1.96	1.40	0.27	23.2	23.5
(f) $V_{Zn}^- + h^+ = V_{Zn}^0$	2.77	25	31	1.40	0.85	0.25	24.7	25.2

This simple model explains why the V_{Zn} charge-state transition levels are approximately equidistant since

$$\varepsilon(-/2-) - \varepsilon(0/-) \cong U, \quad (7)$$

$$\varepsilon(0/-) - \varepsilon(+/0) \cong U, \quad (8)$$

$$\varepsilon(+/0) - \varepsilon(2+/+) \cong U. \quad (9)$$

Of course, this is only approximately true. The hole-hole repulsion U corresponds to the so-called Hubbard correlation energy [53]. By taking the average of Eqs. (7)–(9), the value can be derived as $U \simeq 0.57$ eV. Additionally, the fact that the in-plane configuration of holes is energetically preferred explains why the separation between the (2+ / +) and (+ / 0) levels is somewhat larger than the other two; the fourth hole must localize on the remaining axial O ion (lower hole addition energy). Taking this into account, i.e., considering only Eqs. (7) and (8), the hole-hole repulsion energy becomes $U \simeq 0.53$ eV. These considerations help rationalize our findings with reference to the energetics of V_{Zn} .

D. Optical properties of the Zn vacancy

Optical transitions involving V_{Zn} and the band edges have been investigated. The configuration coordinate diagrams and calculated line shapes and positions are shown in Fig. 4, and all the effective parameters for the various transitions are given in Table I. We find effective normal-mode frequencies $\hbar\Omega_{g/e}$ between 24 and 34 meV, total mass-weighted distortions between 2.6 and 3.0 amu^{1/2}Å, and large HR factors between 23 and 28, resulting in broad luminescence lines. This is expected for optical transitions involving polaronic acceptors like V_{Zn} because of the sizable changes in the atomic geometry between different charge states [21,46]. Indeed, the main contribution to ΔQ comes from the four Zn ions nearest the O⁻ ions with trapped holes.

Considering ZnO as primarily an n -type material, optical transitions involving V_{Zn}^+ and V_{Zn}^{2+} require V_{Zn}^{2-} to rapidly trap three and four holes, respectively. This is perhaps an unlikely scenario (unless the concentration of photogenerated holes is extremely high). Accordingly, we restrict the following discussion primarily to transitions involving V_{Zn}^{2-} , V_{Zn}^- , and V_{Zn}^0 .

The capture of an electron located at the CB minimum by V_{Zn}^- results in a broad luminescence line shape peaking at

an energy of 0.71 eV. Note, however, that the excited- and ground-state normal modes overlap close to the minimum of the excited state [illustrated in Fig. 4(a)]. The energy barrier from the minimum of the excited state up to the point of intersection is only 90 meV, implying that the transition is likely to be nonradiative. Hole capture by V_{Zn}^0 and V_{Zn}^+ is expected to be nonradiative for the same reason and has been omitted from Fig. 4. In fact, in the latter case, the effective normal modes intersect at $Q < \Delta Q$, i.e., before the minimum of the excited state is reached. In contrast, electron capture by V_{Zn}^{2-} will have both radiative and nonradiative components since the energy barrier is 0.46 eV. The resulting luminescence line shape peaks at 1.26 eV.

The capture of a hole located at the VB maximum by V_{Zn}^{2-} results in a somewhat narrower luminescence band peaking at 1.40 eV [Fig. 4(e)]. Strictly speaking, since the VB in ZnO and the defect states of V_{Zn} both have O 2p character, this transition should be forbidden. However, just like for hole capture by V_{Ga}^{3-} in GaN [52], the transition may be allowed because of the strong polaronic relaxation. Nevertheless, this transition has to compete with shallower negatively charged acceptors like Li_{Zn}^- , which captures holes nonradiatively in an efficient manner [54]. Following this logic, the luminescence might be weak in reality, depending on the purity of the sample and the concentration of V_{Zn} .

Finally, it should be pointed out that the simulation results in Fig. 4, revealing prevalent V_{Zn} -related luminescence at low energies close to the infrared region in n -type material, are consistent with recent experimental data by Dong *et al.* [55] and Knutsen *et al.* [56]. Through a combination of cathodoluminescence and PAS measurements, it was found in Ref. [55] that the emission from large V_{Zn} clusters peaks at ~ 1.9 eV and shifts to lower energies with decreasing cluster size. Similarly, using samples irradiated with electrons with energies below and above the threshold for displacement of Zn atoms, as well as samples annealed in Zn-rich and O-rich ambients, Knutsen *et al.* [56] demonstrated that the luminescence in the near-infrared region arises from V_{Zn} or defects containing V_{Zn} . Especially in the case where V_{Zn} forms a complex with a donor, e.g., V_O [57], the most negative thermodynamic charge-state transition levels would be passivated by the donor electrons. Hence, one could speculate that a transition similar to (c) in Fig. 4, peaking in the 1.6–1.9 eV range, would prevail for such a complex, consistent with the experimental data [55,56].

IV. CONCLUSION

Based on the present calculations, we conclude that V_{Zn} in ZnO is a deep polaronic acceptor that can bind a localized hole on each of its four nearest-neighbor O ions. The distinct outward relaxation of these O ions is a key feature of the polaronic nature of V_{Zn} , in agreement with experimental EPR data [15–18].

By employing a one-dimensional configuration coordinate model [21], luminescence positions and line shapes from V_{Zn} were simulated. In contrast to what has been previously suggested [1,9,58–60], the present results show that the isolated V_{Zn} is unlikely to be a major source of luminescence in the visible range for n -type material. All transitions involving V_{Zn}^{2-} , V_{Zn}^{-} , and V_{Zn}^0 are nonradiative and/or lead to luminescence line shapes that are very low in energy (near-infrared region). Electron capture by V_{Zn}^{+} and V_{Zn}^{2+} leads to red and green luminescence, respectively, but these transitions are unlikely to occur in n -type material unless the concentration of photogenerated holes is extremely high. These results are consistent with recent experimental data [55,56].

The luminescence lines arising from V_{Zn} are broad. This is because of the large relaxation associated with hole capture by

one of the nearest-neighbor O ions, i.e., the strong electron-phonon coupling. This highlights the important role of hybrid functionals, which, unlike (semi)local functionals, are able to predict charge localization associated with local lattice distortions around defects [14].

ACKNOWLEDGMENTS

We wish to thank Prof. F. Oba for helpful discussions. Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (No. 251131, FriPro ToppForsk-program). K.M.J. would like to thank the Research Council of Norway for support for the DYNASOX project (No. 221992). A.A. was supported by Marie Skłodowska-Curie Action of the European Union (project NITRIDE-SRH, Grant No. 657054). UNINETT Sigma2 and the Department for Research Computing at the University of Oslo are acknowledged for providing computational resources and support under Projects No. NN4604K, No. NN9180K, and No. NN9136K.

-
- [1] A. Janotti and C. G. Van de Walle, *Phys. Rev. B* **76**, 165202 (2007).
 - [2] F. Oba, A. Togo, I. Tanaka, J. Paier, and G. Kresse, *Phys. Rev. B* **77**, 245202 (2008).
 - [3] S. J. Clark, J. Robertson, S. Lany, and A. Zunger, *Phys. Rev. B* **81**, 115311 (2010).
 - [4] D. O. Demchenko, B. Earles, H. Y. Liu, V. Avrutin, N. Izyumskaya, U. Özgür, and H. Morkoç, *Phys. Rev. B* **84**, 075201 (2011).
 - [5] K. M. Johansen, L. Vines, T. S. Bjørheim, R. Schifano, and B. G. Svensson, *Phys. Rev. Appl.* **3**, 024003 (2015).
 - [6] S. B. Zhang, S.-H. Wei, and A. Zunger, *Phys. Rev. B* **63**, 075205 (2001).
 - [7] A. F. Kohan, G. Ceder, D. Morgan, and C. G. Van de Walle, *Phys. Rev. B* **61**, 15019 (2000).
 - [8] F. Oba, S. R. Nishitani, S. Isotani, H. Adachi, and I. Tanaka, *J. Appl. Phys.* **90**, 824 (2001).
 - [9] J.-L. Zhao, W. Zhang, X.-M. Li, J.-W. Feng, and X. Shi, *J. Phys. Condens. Matter* **18**, 1495 (2006).
 - [10] A. Janotti and C. G. V. de Walle, *Rep. Prog. Phys.* **72**, 126501 (2009).
 - [11] S. Lany and A. Zunger, *Phys. Rev. Lett.* **98**, 045501 (2007).
 - [12] R. Vidyā, P. Ravindran, H. Fjellvåg, B. G. Svensson, E. Monakhov, M. Ganchenkova, and R. M. Nieminen, *Phys. Rev. B* **83**, 045206 (2011).
 - [13] A. A. Sokol, S. A. French, S. T. Bromley, C. R. A. Catlow, H. J. J. van Dam, and P. Sherwood, *Faraday Discuss.* **134**, 267 (2007).
 - [14] C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
 - [15] D. Galland and A. Herve, *Phys. Lett. A* **33**, 1 (1970).
 - [16] D. Galland and A. Herve, *Solid State Commun.* **14**, 953 (1974).
 - [17] L. Kappers, O. Gilliam, S. Evans, L. Halliburton, and N. Giles, *Nucl. Instrum. Methods Phys. Res., Sect. B* **266**, 2953 (2008).
 - [18] S. M. Evans, N. C. Giles, L. E. Halliburton, and L. A. Kappers, *J. Appl. Phys.* **103**, 043710 (2008).
 - [19] J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
 - [20] J. Heyd, G. E. Scuseria, and M. Ernzerhof, *J. Chem. Phys.* **118**, 8207 (2003).
 - [21] A. Alkauskas, J. L. Lyons, D. Steiauf, and C. G. Van de Walle, *Phys. Rev. Lett.* **109**, 267401 (2012).
 - [22] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
 - [23] G. Kresse and J. Hafner, *J. Phys. Condens. Matter* **6**, 8245 (1994).
 - [24] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
 - [25] G. Kresse and J. Hafner, *Phys. Rev. B* **47**, 558 (1993).
 - [26] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
 - [27] G. Makov, R. Shah, and M. C. Payne, *Phys. Rev. B* **53**, 15513 (1996).
 - [28] S. B. Zhang and J. E. Northrup, *Phys. Rev. Lett.* **67**, 2339 (1991).
 - [29] C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
 - [30] Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
 - [31] H.-P. Komsa, T. T. Rantala, and A. Pasquarello, *Phys. Rev. B* **86**, 045112 (2012).
 - [32] I. Souza, J. Íñiguez, and D. Vanderbilt, *Phys. Rev. Lett.* **89**, 117602 (2002).
 - [33] N. Ashkenov, B. N. Mbenkum, C. Bundesmann, V. Riede, M. Lorenz, D. Spemann, E. M. Kaidashev, A. Kasic, M. Schubert, M. Grundmann, G. Wagner, H. Neumann, V. Darakchieva, H. Arwin, and B. Monemar, *J. Appl. Phys.* **93**, 126 (2003).
 - [34] G. S. Parks, C. E. Hablutzel, and L. E. Webster, *J. Am. Chem. Soc.* **49**, 2792 (1927).

- [35] A. M. Stoneham, *Theory of Defects in Solids* (Oxford University Press, Oxford, 1975).
- [36] K. Huang and A. Rhys, *Proc. R. Soc. London, Ser. A* **204**, 406 (1950).
- [37] A. Alkauskas, M. D. McCluskey, and C. G. Van de Walle, *J. Appl. Phys.* **119**, 181101 (2016).
- [38] V. Ivády, I. A. Abrikosov, E. Jánzén, and A. Gali, *Phys. Rev. B* **87**, 205201 (2013).
- [39] A. Alkauskas, P. Broqvist, and A. Pasquarello, *Phys. Rev. Lett.* **101**, 046405 (2008).
- [40] A. Alkauskas, P. Broqvist, and A. Pasquarello, *Phys. Status Solidi B* **248**, 775 (2011).
- [41] S. Lany and A. Zunger, *Phys. Rev. B* **80**, 085202 (2009).
- [42] F. Tuomisto, V. Ranki, K. Saarinen, and D. C. Look, *Phys. Rev. Lett.* **91**, 205502 (2003).
- [43] T. S. Bjørheim, S. Erdal, K. M. Johansen, K. E. Knutsen, and T. Norby, *J. Phys. Chem. C* **116**, 23764 (2012).
- [44] A. Alkauskas and A. Pasquarello, *Phys. Rev. B* **84**, 125206 (2011).
- [45] J. B. Varley, A. Janotti, C. Franchini, and C. G. Van de Walle, *Phys. Rev. B* **85**, 081109 (2012).
- [46] J. L. Lyons, A. Janotti, and C. G. Van de Walle, *J. Appl. Phys.* **115**, 012014 (2014).
- [47] N. A. Deskins, R. Rousseau, and M. Dupuis, *J. Phys. Chem. C* **115**, 7562 (2011).
- [48] T. Shibuya, K. Yasuoka, S. Mirbt, and B. Sanyal, *J. Phys. Condens. Matter* **24**, 435504 (2012).
- [49] X. Hao, Z. Wang, M. Schmid, U. Diebold, and C. Franchini, *Phys. Rev. B* **91**, 085204 (2015).
- [50] M.-H. Du and S. B. Zhang, *Phys. Rev. B* **80**, 115217 (2009).
- [51] A. Carvalho, A. Alkauskas, A. Pasquarello, A. K. Tagantsev, and N. Setter, *Phys. Rev. B* **80**, 195205 (2009).
- [52] J. L. Lyons, A. Alkauskas, A. Janotti, and C. G. Van de Walle, *Phys. Status Solidi B* **252**, 900 (2015).
- [53] J. Hubbard, *Proc. R. Soc. London, Ser. A* **276**, 238 (1963).
- [54] A. Alkauskas, Q. Yan, and C. G. Van de Walle, *Phys. Rev. B* **90**, 075202 (2014).
- [55] Y. Dong, F. Tuomisto, B. G. Svensson, A. Yu. Kuznetsov, and L. J. Brillson, *Phys. Rev. B* **81**, 081201 (2010).
- [56] K. E. Knutsen, A. Galeckas, A. Zubiaga, F. Tuomisto, G. C. Farlow, B. G. Svensson, and A. Yu. Kuznetsov, *Phys. Rev. B* **86**, 121203 (2012).
- [57] K. Johansen, F. Tuomisto, I. Makkonen, and L. Vines, *Mater. Sci. Semicond. Process.* (2016), doi:10.1016/j.mssp.2016.11.030.
- [58] Z. Wang, S. C. Su, M. Younas, F. C. C. Ling, W. Anwand, and A. Wagner, *RSC Adv.* **5**, 12530 (2015).
- [59] X. D. Wang, S. Y. He, D. Z. Yang, and P. F. Gu, *Radiat. Res.* **176**, 264 (2011).
- [60] X. J. Wang, L. S. Vlasenko, S. J. Pearton, W. M. Chen, and I. A. Buyanova, *J. Phys. D* **42**, 175411 (2009).

Paper II

Zn vacancy-donor impurity complexes in ZnO

Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, A. Alkauskas

Published in *Physical Review B*, March 2018, volume 97, issue 10, pp. 104–109.
DOI: 10.1103/PhysRevB.97.104109.

Zn vacancy-donor impurity complexes in ZnO

Y. K. Frodason,* K. M. Johansen, T. S. Bjørheim, and B. G. Svensson

University of Oslo, Centre for Materials Science and Nanotechnology, N-0318 Oslo, Norway

A. Alkauskas

Center for Physical Sciences and Technology, Vilnius LT-10257, Lithuania

(Received 24 January 2018; published 27 March 2018)

Results from hybrid density functional theory calculations on the thermodynamic stability and optical properties of the Zn vacancy (V_{Zn}) complexed with common donor impurities in ZnO are reported. Complexing V_{Zn} with donors successively removes its charge-state transition levels in the band gap, starting from the most negative one. Interestingly, the presence of a donor leads only to modest shifts in the positions of the V_{Zn} charge-state transition levels, the sign and magnitude of which can be interpreted from a polaron energetics model by taking hole-donor repulsion into account. By employing a one-dimensional configuration coordinate model, luminescence lineshapes and positions were calculated. Due to the aforementioned effects, the isolated V_{Zn} gradually changes from a mainly nonradiative defect with transitions in the infrared region in n -type material, to a radiative one with broad emission in the visible range when complexed with shallow donors.

DOI: [10.1103/PhysRevB.97.104109](https://doi.org/10.1103/PhysRevB.97.104109)

I. INTRODUCTION

Zinc oxide—a II–VI compound semiconductor with a wide direct band gap of 3.44 eV [1]—has been studied quite extensively over the past decade. Its unique optical and electrical properties, including an exceptionally large free exciton binding energy of 60 meV, make it attractive for optoelectronic devices. An ongoing issue holding back this development, however, is the lack of stable and reproducible p -type ZnO material. A prerequisite for a successful application of any semiconductor is a good understanding of native defects, common impurities, dopants, and their interplay. To this end, unambiguous spectroscopic identification of key defects is essential.

Using photoluminescence (PL) spectroscopy, several broad luminescence bands peaking in the visible part of the emission spectrum have been observed, both in as-grown and processed ZnO samples. These bands are known to originate from deep level centers, but very few have been unambiguously identified. One example is the characteristic red luminescence band, hereby referred to as the RL [2], peaking at about 1.8 eV and exhibiting a low activation energy of thermal quenching of 10–20 meV [3–9]. The RL has been the subject of numerous experimental studies as its intensity can be raised significantly via high-energy electron irradiation at room temperature (RT) [3–6]. While a number of native defects have been invoked as candidates, a large body of evidence has accumulated towards a donor-acceptor pair (DAP) transition involving the V_{Zn} acceptor and a residual shallow donor [4–7]. However, the exact configuration and nature of the defect responsible for the RL remains elusive.

V_{Zn} is the dominant native acceptor-type defect in ZnO [10], acting as a compensating center in n -type material.

Moreover, V_{Zn} can trap a localized hole polaron on each of its four nearest-neighbor O ions [11,12]. Previously, we have shown that subsequent electron capture by V_{Zn} can give rise to broad luminescence bands in the infrared (IR) part of the emission spectrum in n -type material, although the transitions are predominantly most likely nonradiative [12]. In the present paper, we investigate the thermodynamic and optical properties of V_{Zn} complexed with shallow donor impurities that are commonly present in as-grown ZnO crystals, namely H, Al, Ga, and Si. Specifically, we have studied ($V_{\text{Zn}}\text{Al}_{\text{Zn}}$), ($V_{\text{Zn}}\text{Ga}_{\text{Zn}}$), ($V_{\text{Zn}}\text{Si}_{\text{Zn}}$), and ($V_{\text{Zn}}n\text{H}$) with $n = 1, 2, 3$, as well as three complexes with a combination of different donors, namely ($V_{\text{Zn}}\text{Al}_{\text{Zn}}\text{H}$), ($V_{\text{Zn}}\text{Al}_{\text{Zn}}2\text{H}$), and ($V_{\text{Zn}}\text{Si}_{\text{Zn}}\text{H}$). Many of these V_{Zn} -donor complexes have already been identified in processed ZnO samples by electron paramagnetic resonance (EPR) [4,5,13–15] and infrared (IR) spectroscopy [16–20]. Our theoretical predictions are consistent with such experimental data, and, importantly, provide a guide for future studies of the broad luminescence bands observed in ZnO and identification of V_{Zn} -donor complexes.

II. METHODOLOGY

A comprehensive description of the employed first-principles methodology and computational details can be found in Ref. [12]. A brief summary is given here.

Unless specified, all calculations were based on the generalized Kohn-Sham theory with the Heyd-Scuseria-Ernzerhof (HSE) [21] hybrid functional and the projector augmented wave method [22–24], as implemented in the VASP code [25,26]. The amount of screened Hartree-Fock exchange was set to $\alpha = 37.5\%$, giving band gap (3.42 eV) and lattice parameters ($a = 3.244 \text{ \AA}$ and $c = 5.194 \text{ \AA}$) in excellent agreement with experimental data [1,27]. Defect calculations were performed using a 96-atom-sized supercell, a plane-wave

*ymirkf@fys.uio.no

FIG. 1. A configuration coordinate diagram is shown on the left side, illustrating vibronic transitions between the ground (neutral) and excited (singly positive) charge state of a defect. Free electrons (e) and holes (h) are located at the conduction band (CB) minimum and valence band (VB) maximum, respectively. E_{ZPL} gives the thermodynamic charge-state transition level relative to the CB minimum (shown in the band diagram on the right). E_b is the barrier for capture of a free hole by the neutral defect, E_{A1} gives the thermodynamic charge-state transition level relative to the VB maximum, i.e., the energy required for thermal emission of a hole from the defect to the VB, and E_{A2} is the barrier for nonradiative capture of an electron at the CB minimum [38].

energy cutoff of 500 eV, and a special off- Γ k point at $k = (\frac{1}{4}, \frac{1}{4}, \frac{1}{4})$ [28]. Ionic relaxation was carried out consistently with the hybrid functional, and spin polarization was explicitly included.

Defect formation energies and thermodynamic charge-state transition levels were determined by following the standard formalism [29,30]. The chemical potential of Ga, Al, Si, and H were referenced to $\text{Ga}_2\text{O}_3(\text{s})$, $\text{Al}_2\text{O}_3(\text{s})$, $\text{SiO}_2(\text{s})$, and $\text{H}_2\text{O}(\text{g})/\text{H}_2(\text{g})$, respectively. Corrections for the spurious long-range Coulomb interactions between charged defects, their periodic images, and the neutralizing jellium were included by employing the extended [31] Freysoldt-Neugebauer-Van de Walle scheme [32,33].

As in Ref. [12], defect luminescence lineshapes and positions were calculated by utilizing the effective one-dimensional configuration coordinate (CC) model [34,35], shown in Fig. 1, where the configuration coordinate Q connects the initial and final states. The parameters that enter the model are the effective phonon frequencies $\Omega_{g/e}$, the zero phonon line (ZPL) energy E_{ZPL} , and the change in configuration coordinate ΔQ , all of which are obtained from the hybrid density functional theory calculations. Within the classical Franck-Condon approximation, emission (em) and absorption (abs) energies may be defined as $E_{\text{em}} = E_{ZPL} - \Delta E_g$ and $E_{\text{abs}} = E_{ZPL} + \Delta E_e$, respectively. Here, ΔE_g and ΔE_e are the ground (g) and excited (e) state relaxation energies, often referred to as Franck-Condon shifts. Finally, Huang-Rhys (HR) factors [35,36]

describe the average number of phonons that are involved in a transition and can be expressed as $S_{g/e} = \Delta E_{g/e}/\hbar\Omega_{g/e}$ for emission/absorption. The effective one-dimensional CC model is a good approximation for defects with strong electron-phonon coupling (large HR factors), as numerically shown in Refs. [34,37], and this is indeed the case for V_{Zn} in ZnO [12,34].

III. RESULTS AND DISCUSSION

A. Defect complex configuration

V_{Zn} is tetrahedrally surrounded with a dangling O 2p bond at each corner. In the neutral charge state, V_{Zn}^0 has two holes, which occupy polaronic states on the nearest-neighbor O ions and can be filled by electrons. By forming a complex with V_{Zn} , a donor may directly supply one or both of these electrons. Thus, e.g., $(V_{\text{Zn}}2\text{H})^0$ will be neutral with all defect levels filled. As shown in Fig. 2, such complexes can still trap holes in polaronic states.

Donors can bind to V_{Zn} in several different configurations. Al, Ga, and Si substitute on a neighboring Zn site and can either share the same Zn (001) plane as V_{Zn} or reside in one of the two nearest neighbor Zn (001) planes. As shown for $(V_{\text{Zn}}\text{Al}_{\text{Zn}})$ and $(V_{\text{Zn}}\text{Si}_{\text{Zn}})$ in Fig. 2, we have explored the shared Zn-plane configuration, since this is the lowest energy configuration determined by the generalized gradient approximation in the Perdew-Burke-Ernzerhof [39] parametrization. Our calculations indicate that hole localization occurs on the O ion furthest away from the positively charged donor, as also found experimentally for $(V_{\text{Zn}}\text{Al}_{\text{Zn}})^0$ using EPR [14].

H can bind to V_{Zn} by terminating one of the four dangling O 2p bonds [16]. Both axial and azimuthal O-H bond configurations of $(V_{\text{Zn}}n\text{H})$ complexes with $n = 1, 2, 3$ have been assigned to IR local vibrational modes [16–20]. We obtain very small differences in total energy between these configurations for the $(V_{\text{Zn}}\text{H})$, $(V_{\text{Zn}}2\text{H})$, and $(V_{\text{Zn}}3\text{H})$ complexes. Hence, both configurations are expected to occur, in agreement with IR spectroscopy data [19,20]. In principle, $(V_{\text{Zn}}3\text{H})$ can capture a fourth H, but we find $(V_{\text{Zn}}4\text{H})^{2+}$ to be unstable with respect to $(V_{\text{Zn}}3\text{H})^+$ and H_2^+ . Moreover, its formation will likely be suppressed by Coulomb repulsion as both constituents are positively charged in the entire range of Fermi level positions in the band gap [40,41]. This logic holds for other singly positively charged complexes as well, i.e., $(V_{\text{Zn}}\text{Al}_{\text{Zn}}2\text{H})^+$ and $(V_{\text{Zn}}\text{Si}_{\text{Zn}}\text{H})^+$ are unlikely to accept one more donor. These complexes are considered as saturated with donors.

B. Defect complex charge-state transition levels

Figure 3 shows the formation energy of the isolated V_{Zn} and the V_{Zn} -donor complexes as a function of the Fermi level position in the O-rich limit. Before addressing the complexes, we note that the results for the isolated V_{Zn} scatter widely in the literature with regard to the position and number of thermodynamic charge-state transition levels. The main reasons for these variations were discussed previously in Ref. [12]. Furthermore, the $(V_{\text{Zn}}\text{Ga}_{\text{Zn}})$ complex is omitted from further discussion, as its charge-state transition levels are identical to those of the $(V_{\text{Zn}}\text{Al}_{\text{Zn}})$ complex (albeit with a 0.2 eV lower formation energy). Regarding the positions of the charge-state transition levels in Fig. 3, there are two clear trends:

FIG. 2. Four representative V_{Zn} -donor complexes are shown with a single hole trapped in a polaronic O $2p$ -like state (blue isosurface at $0.01 r_{\text{Bohr}}^{-3}$). Subsequent capture of an electron at the CB can potentially give rise to broad luminescence.

(i) Complexing V_{Zn} with donors successively removes its charge-state transition levels in the band gap, starting from the most negative one. Al_{Zn} , Ga_{Zn} , and H are single donors and remove one transition level, while Si_{Zn} is a double donor and removes two transition levels. If the number of donor electrons exceeds two, the complex becomes a donor with characteristics similar to those of the isolated donor. For instance, $(V_{\text{Zn}}3\text{H})$ becomes a shallow single donor where the third donor electron occupies a hydrogenic effective mass state just below the CB [41].

(ii) Similar to V_{Ga} -donor complexes in GaN [42], the thermodynamic charge-state transition levels of the isolated V_{Zn} are not overly affected by the presence of donors; the respective levels shift within narrow ranges in the band gap, as indicated in Fig. 3. Interestingly, the transition levels of complexes containing H shift down, while those containing other donors shift up, relative to the isolated V_{Zn} levels. This behavior can be interpreted through the polaron energetics

model introduced in Ref. [12], by also considering the electrostatic repulsion between hole polarons and donors. For example, consider the $(0/-)$ transition levels. Adding a hole polaron to V_{Zn}^- lowers its energy by the hole polaron addition energy ε_0 minus the hole-hole repulsion U_{hole} . When adding a hole polaron to the $(V_{\text{Zn}}\text{Al}_{\text{Zn}})^-$ complex, however, U_{hole} is replaced by the hole- Al_{Zn}^+ repulsion U_{Al} . Since Al_{Zn} is located outside the vacancy, $U_{\text{Al}} < U_{\text{hole}}$, and thus the $(0/-)$ transition level of $(V_{\text{Zn}}\text{Al}_{\text{Zn}})$ shifts up in energy, relative to the isolated V_{Zn} . Similar arguments apply to the $(V_{\text{Zn}}\text{H})$ complex; since H^+ resides within the vacancy, it causes the O^{2-} tetrahedron surrounding the vacancy to contract. As a result, the hole- H^+ distance in $(V_{\text{Zn}}\text{H})^0$ is significantly shorter than the hole-hole distance in V_{Zn}^0 , and so $U_{\text{H}} > U_{\text{hole}}$, and the $(0/-)$ level shifts down in energy. Estimating the hole-donor repulsion, the polaron energetics model can be used to qualitatively predict the energy position of the charge-state transition levels of any V_{Zn} -donor complex, relative to those of V_{Zn} .

For $(V_{\text{Zn}}3\text{H})$, we find that the hole-donor repulsion is too strong for a hole polaron to become trapped, i.e., $(V_{\text{Zn}}3\text{H})^{2+}$ is unstable. However, based on the polaron energetics model, the hole-donor repulsion is anticipated to be smaller if one or two H^+ ions in $(V_{\text{Zn}}3\text{H})$ are replaced by Al_{Zn}^+ , Ga_{Zn}^+ , or Si_{Zn}^+ . For this reason, we have investigated the $(V_{\text{Zn}}\text{Al}_{\text{Zn}}2\text{H})$ and $(V_{\text{Zn}}\text{Si}_{\text{Zn}}\text{H})$ complexes. Interestingly, we find that a hole polaron can be stabilized for $(V_{\text{Zn}}\text{Al}_{\text{Zn}}2\text{H})$, with the $(2+ / +)$ level occurring 0.13 eV above the VB maximum. Similarly, when replacing two H^+ ions in $(V_{\text{Zn}}3\text{H})$ with Si_{Zn}^+ , the $(2+ / +)$ level of the resulting $(V_{\text{Zn}}\text{Si}_{\text{Zn}}\text{H})$ complex is located even deeper in the gap, at 0.43 eV above the VB maximum. To complete the picture, $(V_{\text{Zn}}\text{Al}_{\text{Zn}}\text{H})$ was also investigated. The $(+ / 0)$ level of this complex occurs 0.90 eV above the VB maximum, approximately halfway between the $(+ / 0)$ level of $(V_{\text{Zn}}\text{Al}_{\text{Zn}})$ and $(V_{\text{Zn}}\text{H})$ as expected.

The calculated $(0/-)$ transition level of $(V_{\text{Zn}}\text{Al}_{\text{Zn}})$ exhibits close agreement with recent photo-EPR data; Stehr *et al.* [14] detected the EPR signal of $(V_{\text{Zn}}\text{Al}_{\text{Zn}})^0$ only when the photon energy exceeded ~ 2.4 eV. Based on the CC model, we obtain a classical absorption energy of 2.54 eV. However, the absorption onset will be lower due to vibrational broadening [37]. To enable a more valid comparison, we have simulated the absorption profile, including vibrational broadening, by following the scheme outlined in Ref. [43]. As shown by the relative comparison in Fig. 4, the resulting absorption profile is in good agreement with the photo-EPR data [14]. Moreover,

FIG. 3. Formation energy of V_{Zn} -donor complexes as a function of the Fermi level position from the VB maximum to the CB minimum, under O-rich conditions. The shaded vertical bars in the left panel indicate the Fermi level range of the charge-state transition levels of V_{Zn} and the complexes.

FIG. 4. Simulated absorption cross section for $(V_{Zn}Al_{Zn})^-$ and EPR signal of $(V_{Zn}Al_{Zn})^0$ as a function of the photon energy of light illumination [14]. The peak of the calculated profile is normalized to the maximum EPR data point.

Stehr *et al.* [14,44] detected a signal from the isolated V_{Zn}^- under illumination with photon energies exceeding ~ 2.1 eV. If one assumes that the vibrational broadening for $(V_{Zn}Al_{Zn})$ and V_{Zn} is similar, the experimental data suggest a difference of ~ 0.3 eV between the $(0/-)$ level of $(V_{Zn}Al_{Zn})$ and $(-/-2-)$ level of V_{Zn} , which is in good agreement with our calculations (0.40 eV) and consistent with the polaron energetics model ($U_{Al} < U_{hole}$). The calculated $(0/-)$ transition level of $(V_{Zn}H)$ similarly exhibits close agreement with photo-EPR data by Evans *et al.* [5].

C. Defect complex thermodynamics

An important question is whether V_{Zn} -donor complexes are likely to be present in as-grown ZnO samples and not just in post-growth processed ones, and if they are stable at RT. A stable complex implies that the defect reaction to form the complex lowers the total energy, i.e., the defect complex must have a positive “removal” energy. The removal energy is defined as the difference in formation energy between the defect complex and the isolated constituents (in their most stable configuration) when one donor is removed from the complex. For instance, the removal energy of $(V_{Zn}2H)$ is given by

$$E^r[(V_{Zn}2H)^0] = E^f[(V_{Zn}H)^-] + E^f(H_i^+) - E^f[(V_{Zn}2H)^0],$$

which is well defined, as all terms in the equation pertain to the lowest-energy charge configuration for n -type conditions. The removal and formation energy of the V_{Zn} -donor complexes and their constituents, for n -type conditions (ϵ_F at CBM), are provided in Table I. In the case of V_{Zn} -donor complexes with a combination of different donors, the energy for removal of H is given. The removal energies of $(V_{Zn}Al_{Zn})$, $(V_{Zn}Ga_{Zn})$, $(V_{Zn}H)$, and $(V_{Zn}2H)$ are in good agreement with previous HSE calculations by Steiauf *et al.* [45] and Lyons *et al.* [46].

All the removal energies are positive and large, meaning that the complexes are expected to be stable at RT. However, assuming thermodynamic equilibrium at the growth temperature, a positive removal energy does not necessarily mean that a sizable fraction of constituents will form complexes during materials growth [47]. This is because complex formation

TABLE I. Formation and removal energy of V_{Zn} -donor complexes and their constituents under n -type conditions. Formation energies are provided for O-rich, O-poor, and intermediate (halfway between O-rich and O-poor) conditions.

Defect	E^f (ϵ_F at CBM) (eV)			E^r (eV)
	O-rich	intermediate	O-poor	
H_i^+	2.79	2.05	1.31	
Al_{Zn}^+	1.99	1.12	0.25	
Ga_{Zn}^+	1.76	0.89	0.02	
Si_{Zn}^{2+}	4.90	3.16	1.41	
V_{Zn}^{2-}	0.02	1.77	3.51	
$(V_{Zn}H)^-$	-0.23	1.01	1.78	3.04
$(V_{Zn}2H)^0$	0.39	0.67	0.92	2.17
$(V_{Zn}3H)^+$	1.80	1.33	0.85	1.38
$(V_{Zn}Al_{Zn})^-$	0.77	1.65	2.52	1.24
$(V_{Zn}Al_{Zn}H)^0$	1.05	1.19	1.32	2.51
$(V_{Zn}Al_{Zn}2H)^+$	2.07	1.47	0.86	1.77
$(V_{Zn}Ga_{Zn})^-$	0.57	1.45	2.32	1.21
$(V_{Zn}Si_{Zn})^0$	2.46	2.46	2.46	2.46
$(V_{Zn}Si_{Zn}H)^+$	3.02	2.28	1.54	2.23

generally lowers the configurational entropy. In order for the equilibrium concentration of a defect complex to be larger than that of either constituent, its formation energy should generally be lower than that of both constituents [30,47]. Considering the intermediate formation energies given in Table I (the O-rich/poor limits are not usually accessed during materials growth), most of the V_{Zn} -donor complexes have a formation energy that is lower than or at least comparable to that of their constituents. Consequently, such V_{Zn} -donor complexes, and especially the $(V_{Zn}nH)$ ones, are likely to form even during materials growth. Note that the complexes may also form under nonequilibrium conditions. For instance, if the individual constituents are incorporated during growth, complexes can form during cooldown [47]. In this scenario, formation of complexes involving H is anticipated to take place rapidly, because of the high mobility of H_i even at RT [40,48–50].

The absolute and relative concentration of different V_{Zn} -donor complexes will depend on the synthesis method used, governed by the presence of V_{Zn} and impurities during the growth. Indeed, according to secondary ion mass spectrometry (SIMS) data [51], the concentration of Al and Si in as-grown ZnO single crystals typically varies between 10^{15} and 10^{17} cm^{-3} for different growth techniques (Ga is less abundant [52]), while the concentration of H is below the typical SIMS detection limit of 5×10^{17} cm^{-3} . In addition, several kinds of different traps compete with V_{Zn} for H_i , such as Li_{Zn} [20,53,54], a common impurity in hydrothermally grown (HT) ZnO. Moreover, despite V_{Zn} being the most likely intrinsic defect to form under realistic growth conditions [46], a large equilibrium concentration of V_{Zn} is not expected. Assuming the intermediate formation energy value of 1.77 eV in Table I (n -type material), an equilibrium concentration of 2×10^{14} to 4×10^{16} cm^{-3} is obtained at 800–1200 °C. Note that even small changes in the Fermi level position or the chemical potential will change the formation energy of V_{Zn} , and thus the equilibrium concentration, by a significant amount. For instance, intentional n -type doping promotes the formation of

TABLE II. Effective parameters for the calculated luminescence transitions; total mass-weighted distortion (ΔQ), ground- and excited-state normal mode frequencies ($\hbar\Omega_{g/c}$), classical absorption and emission energies ($E_{\text{abs/em}}$), ZPL energy (E_{ZPL}), peak position (PP), full width at half maximum of the luminescence band (FWHM), ground- and excited-state Huang-Rhys factors ($S_{g/c}$), and classical barrier for nonradiative capture of photogenerated holes (E_b). The minor discrepancy between E_{em} and PP is caused by the additional energy term $\frac{1}{2}\hbar(\omega_e - \omega_g)$ in the quantum treatment within the harmonic approximation, as well as the slight anharmonicity of the normal modes obtained from the hybrid DFT calculations.

Transition	ΔQ (amu ^{1/2} Å)	$\hbar\Omega_{g/c}$ (meV)	$E_{\text{abs/em}}$ (eV)	E_{ZPL} (eV)	PP (eV)	FWHM (eV)	$S_{g/c}$	E_b (meV)
(V _{Zn} Al _{Zn}) ^{0/-}	2.70	33/27	2.54/1.07	1.88	1.07	0.41	25/24	620
(V _{Zn} Al _{Zn}) ^{+ /0}	2.66	33/27	3.14/1.69	2.48	1.65	0.43	24/24	50
(V _{Zn} Al _{Zn}) ^{2+ /+}	3.00	28/24	3.70/2.23	3.03	2.21	0.39	28/27	310
(V _{Zn} Al _{Zn} H) ^{+ /0}	3.09	28/25	3.23/1.69	2.54	1.69	0.39	30/28	20
(V _{Zn} Al _{Zn} H) ^{2+ /+}	3.59	25/23	3.91/2.25	3.14	2.22	0.38	35/34	90
(V _{Zn} Al _{Zn} 2H) ^{2+ /+}	3.83	25/23	4.15/2.37	3.31	2.28	0.39	38/37	170
(V _{Zn} Si _{Zn}) ^{+ /0}	2.70	33/27	3.14/1.43	2.24	1.39	0.43	25/25	180
(V _{Zn} Si _{Zn}) ^{2+ /+}	2.67	33/27	3.56/2.10	2.89	2.05	0.43	25/24	10
(V _{Zn} Si _{Zn} H) ^{2+ /+}	2.98	30/26	3.70/2.16	3.01	2.16	0.40	29/27	20
(V _{Zn} H) ^{0/-}	2.95	30/25	2.79/1.30	2.12	1.30	0.39	27/27	240
(V _{Zn} H) ^{+ /0}	3.14	28/25	3.40/1.83	2.66	1.81	0.39	31/29	10
(V _{Zn} H) ^{2+ /+}	3.63	25/22	4.09/2.53	3.37	2.46	0.37	34/35	170
(V _{Zn} 2H) ^{+ /0}	3.42	26/24	3.54/1.85	2.73	1.84	0.37	34/34	10

V_{Zn} and V_{Zn}-donor complexes in ZnO [55–57]. For melt grown (MG) ZnO from Cermet inc., and vapor phase (VP) grown ZnO from EaglePicher, positron annihilation spectroscopy (PAS) measurements show a concentration of open-volume defects related to V_{Zn} below the PAS detection limit of $1 \times 10^{15} \text{ cm}^{-3}$ [6,58]. In addition, EPR measurements show that the concentration of isolated V_{Zn} in MG ZnO from Cermet inc. is below the detection limit of $1 \times 10^{13} \text{ cm}^{-3}$ [14]. This indicates that: (i) very few V_{Zn}'s are formed during materials growth for these techniques, and/or (ii) most V_{Zn}'s are saturated with donors, e.g., (V_{Zn}3H), and thus not detected using PAS and EPR. The latter interpretation is strongly favored by the data in Table I.

D. Defect complex luminescence

Optical transitions involving electron capture from the CB by (V_{Zn}Al_{Zn}), (V_{Zn}Si_{Zn}), (V_{Zn}H), (V_{Zn}2H), (V_{Zn}Al_{Zn}2H), and (V_{Zn}Si_{Zn}H) have been explored. The effective parameters for all transitions are provided in Table II. We find effective normal-mode frequencies $\hbar\Omega_{g/c}$ between 22 and 33 meV, total mass-weighted distortions between 2.6 and 3.9 amu^{1/2} Å, and Huang-Rhys factors between 24 and 37 for these V_{Zn}-donor complexes. Moreover, we obtain quite consistent relaxation energies for V_{Zn} and the V_{Zn}-donor complexes, which is reasonable because the atomic movement is roughly the same in every case, i.e., hole capture is always accompanied by a distinct outward relaxation of the O⁻ ion [12].

We focus on PL experiments carried out at low excitation intensities and thus restrict the following discussion to transitions involving electron capture by complexes with a single trapped hole polaron. The resulting luminescence lines are shown in Fig. 5. As indicated in the figure, complexing V_{Zn} with donors effectively shifts its emission from the infrared region towards the visible range of the spectrum. The main origin of this shift is the electrostatic repulsion between the hole polaron and donor, and its magnitude depends on the nature, configuration, and number of donors in the complex. For instance, the emission

from (V_{Zn}H) shifts to a higher energy than (V_{Zn}Al_{Zn}), mainly because $U_{\text{Al}} < U_{\text{H}}$ (see Sec. IIIB). Notably, the calculated luminescence lines for (V_{Zn}2H), (V_{Zn}Al_{Zn}2H), and (V_{Zn}Si_{Zn}H) are predicted to peak in the visible part of the spectrum. However, the two latter complexes have not been identified experimentally. Moreover, they are positively charged in the ground state, which is likely to have a significant impact on their ability to capture photogenerated holes.

During PL experiments carried out at low excitation intensities, photogenerated holes are more likely to be captured by defects with large nonradiative hole capture coefficients like Li_{Zn} [59]. For this reason, the classical barrier for nonradiative hole capture from the VB (E_b) is included in Table II. As shown in Fig. 1, this barrier corresponds to the energy required to reach the crossing point between the two potential energy surfaces, i.e., the point where their vibronic coupling is most efficient. Based on the calculated E_b values, one can expect the intensity of the luminescence from, e.g., (V_{Zn}2H) to be higher than that of (V_{Zn}Al_{Zn}), since hole capture is anticipated to take place rapidly for (V_{Zn}2H). Furthermore, it should be pointed out that the transitions involving electron capture from the CB by V_{Zn}⁻, (V_{Zn}Al_{Zn})⁰, (V_{Zn}H)⁰, and (V_{Zn}Si_{Zn})⁺ may have significant nonradiative components; the classical barrier for nonradiative electron capture E_{A2} (as shown in Fig. 1) is only 0.09 [12], 0.31, 0.42, and 0.60 eV, respectively. These will be lower in the quantum treatment [59], and so the luminescence from an isolated V_{Zn} [12,60] and V_{Zn} complexed with a single donor might be weak in reality. Indeed, nonradiative recombination is usually stronger than radiative recombination at low emission energies [37,60–62]. Note that nonradiative processes do not interfere with absorption.

E. The red luminescence band

Finally our theoretical predictions are discussed in light of experimental data by Kappers *et al.* [4], Knutsen *et al.* [6], and Vlasenko *et al.* [3], where the aforementioned RL emerges after high-energy electron irradiation:

FIG. 5. PL spectra showing calculated positions and lineshapes for V_{Zn} -donor complexes. Experimental data from Ref. [6] are included, showing optical emission from MG Cermet inc. samples under 325 nm excitation at 10 K before and after irradiation by 1.2 MeV electrons. The peak intensity of the RL from Ref. [6] is normalized to the calculated $(V_{Zn}2H)$ peak intensity.

(i) Kappers *et al.* [4] carried out a PL and EPR study of VP grown EaglePicher ZnO samples before and after irradiation with 2.0 MeV electrons at RT. After irradiation, the carrier concentration was reduced by three orders of magnitude, and an intense RL band peaking at about 1.8 eV was observed; the donor-bound exciton lines commonly attributed to H (I_4), Al (I_6), Ga (I_8), and In (I_9) were strongly suppressed, and the EPR signals of Fe^{3+} and V_{Zn}^- were detected in darkness. Photo-EPR data unveiled additional signals from V_{Zn}^0 , V_{Zn}^+ , and V_{Zn} complexed with H, Al, and Ga [4,5]. Based on these observations, the RL was assigned to a DAP transition involving the V_{Zn} acceptor and shallow donors [4].

(ii) Knutsen *et al.* [6] employed PL, PAS, and Hall effect measurements to study MG Cermet inc. ZnO samples irradiated with electrons with energies below and above the threshold for displacement of Zn atoms, as well as samples annealed in Zn-rich and O-rich ambients. The RL band was assigned to a DAP transition involving V_{Zn} -related acceptors and shallow donors. Two PL spectra from Ref. [6], before and after irradiation by 1.2 MeV electrons, are shown in Fig. 5. Our calculated luminescence line for the $(V_{Zn}2H)$ complex is in excellent agreement with the experimental data. This is also the case for $(V_{Zn}H)^{+/0}$ (Table II), but would require $(V_{Zn}H)^-$ to capture two photogenerated holes in n -type material, which is perhaps unlikely for low excitation intensities.

(iii) Vlasenko and Watkins [3,63] performed a PL and optically detected magnetic resonance (ODMR) study of VP grown EaglePicher ZnO samples before and after irradiation with 2.5 MeV electrons, *in situ* at 4.2 K, followed by sequential isochronal annealing. The irradiation at 4.2 K produced a broad “double-humped” IR band peaking at about 1.38 and 1.65 eV and suppressed the donor-bound exciton lines. The annealing stages were characterized by the disappearance of the double-humped IR band (~ 65 –150 K), emergence of the RL band (~ 180 –230 K), and partial annealing of the RL at RT. This strong evolution below RT suggests migration or

rearrangement of point defects, where Zn_i [64], O_i [65], and H_i [40,48,49] are the most likely candidates. Indeed, Vlasenko and Watkins [3] attributed the first annealing stage (~ 65 –150 K) to Zn_i migration, owing to the disappearance of ODMR signals associated with Zn_i^{2+} and $Zn_i^{2+} - V_{Zn}^{2-}$ Frenkel pairs. No ODMR signal from O_i was observed, but the emergence of the RL band after the second annealing stage was tentatively associated with O_i migration [3].

High-energy electron irradiation at cryogenic temperatures generates predominantly elementary point defects V_{Zn}^{2-} , Zn_i^{2+} , V_{Zn}^0 , and $O_{i,oct}^{2-}$ or $O_{i,split}^0$ [46,66] (n -type material). ZnO is known to exhibit very strong dynamic annealing at RT. Hence, as suggested by Vlasenko and Watkins [3], it seems likely that the double-humped IR band originates from close $Zn_i - V_{Zn}$ Frenkel pairs, which annihilate after the first annealing stage. The second annealing stage, characterized by the emergence of the RL, presumably involves migration or rearrangement of O_i [3] or H_i . However, the RL is only observed to increase when the irradiation energy is above the threshold for displacement of Zn atoms [6,67], which strongly suggests that it is related to V_{Zn} . EPR signals from V_{Zn} complexed with H have been detected by several groups after high-energy electron irradiation at RT [4,5,13]. Migration of H_i and trapping at V_{Zn} , leading to growth of the RL, is consistent with this picture. Moreover, capture of a third H would account for the partial anneal of the RL at RT, which also depends on the electron dose and type of ZnO sample, as observed by Vlasenko and Watkins [3,63]. We underline that further work is required to unravel the microscopic mechanism governing the formation of these complexes [14]. Indeed, while H is an omnipresent impurity in ZnO, most of it is expected to occur in a bound state [48], or as “hidden” H_2 molecules [68]. One could speculate that the O_i generated by the electron irradiation releases free H_i via a reaction with H_2O [66].

The proposed defect model should also provide an explanation for the unusual thermal quenching of the RL band, starting

at about 30 K with a low activation energy of 10–20 meV. Thermal quenching of PL bands caused by DAP transitions in ZnO usually occur through thermal emission of bound holes to the VB, followed by a redistribution of these holes to other recombination channels [38]. However, the activation energy for thermal quenching within this model, corresponding to E_{A2} in Fig. 1, is 0.71 eV for ($V_{Zn}2H$), which is too high. Alternatively, the quenching could occur through a gradual conversion from radiative to nonradiative electron capture, but the activation energy within this model, corresponding to E_{A1} in Fig. 1, is 1.35 eV for ($V_{Zn}2H$). Knutsen *et al.* [6] suggested that the quenching of the RL might occur via thermal delocalization of excitons bound to shallow donors that take part in the transition. By applying Haynes rule, the ionization energy of the shallow donor was estimated to be very close to the H-related I_4 line. However, as pointed out by Reshchikov *et al.* [8], the efficiency of a DAP recombination is normally limited by the rate of hole capture, meaning that ionization of shallow donors is unlikely to cause the PL quenching, even though we expect hole capture by ($V_{Zn}2H$) to be very efficient (E_b is only 10 meV). Knutsen *et al.* [6] also suggested thermal activation of a dominant nonradiative channel, but this model failed to explain why other bands quenched with different activation energies. A detailed study of the RL may be required to understand its thermal quenching behavior. For instance, PL measurements at temperatures above 300 K could be pursued in order to investigate whether a second activation energy, related to thermal emission of bound holes (E_{A2}), can be observed. If ($V_{Zn}2H$) is responsible, the activation energy should be approximately 0.7 eV according to our calculations.

IV. CONCLUSION

Employing hybrid density functional theory calculations, we have shown that V_{Zn} can form highly stable complexes with the residual shallow donors H, Al, Ga, and Si in ZnO. Most of the studied V_{Zn} -donor complexes, and particularly the

($V_{Zn}nH$) ones, have a formation energy that is lower than or at least comparable to their individual constituents, meaning that they are likely to form not only during post-growth processing but even during materials growth. However, the absolute and relative concentration of different complexes is expected to depend strongly on the synthesis method used. Importantly, the results evidence that V_{Zn} -donor complexes can have a crucial impact on the electrical and optical properties of ZnO and should be considered when interpreting corresponding experimental data.

Furthermore, by using an effective one-dimensional CC model, defect complex luminescence positions and lineshapes were calculated. The results show that complexing V_{Zn} with donors effectively shifts the V_{Zn} emission from the IR towards the visible range of the spectrum. The magnitude of the shift depends on the nature, configuration, and number of donors in the complex and can be interpreted from a polaron energetics model. Based on comparison with a compilation of experimental data in the literature [3–7], the ($V_{Zn}2H$) complex is proposed as a potential origin of the high-energy electron irradiation induced RL peaking at about 1.8 eV, which is commonly believed to be V_{Zn} related [4,6,7]. Above all, our theoretical predictions provide useful input for future optical studies of ZnO and V_{Zn} -donor complex defect assignment.

ACKNOWLEDGMENTS

Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (no. 251131, FriPro ToppForsk-program). K.M.J. would like to thank the Research Council of Norway for support to the DYNAXOx project (no. 221992). A.A. was supported by Marie Skłodowska-Curie Action of the European Union (project NITRIDE-SRH, Grant No. 657054). The computations were performed on resources provided by UNINETT Sigma2 - the National Infrastructure for High Performance Computing and Data Storage in Norway.

-
- [1] D. C. Reynolds, D. C. Look, B. Jogai, C. W. Litton, G. Cantwell, and W. C. Harsch, *Phys. Rev. B* **60**, 2340 (1999).
 - [2] This RL should be distinguished from the RL at ~ 1.7 eV, attributed to the N_0 acceptor in ZnO [69].
 - [3] L. S. Vlasenko and G. D. Watkins, *Phys. Rev. B* **72**, 035203 (2005).
 - [4] L. Kappers, O. Gilliam, S. Evans, L. Halliburton, and N. Giles, *Nucl. Instrum. Methods Phys. Res., Sect. B* **266**, 2953 (2008).
 - [5] S. M. Evans, N. C. Giles, L. E. Halliburton, and L. A. Kappers, *J. Appl. Phys.* **103**, 043710 (2008).
 - [6] K. E. Knutsen, A. Galeckas, A. Zubiaga, F. Tuomisto, G. C. Farlow, B. G. Svensson, and A. Yu. Kuznetsov, *Phys. Rev. B* **86**, 121203 (2012).
 - [7] X. J. Wang, L. S. Vlasenko, S. J. Pearton, W. M. Chen, and I. A. Buyanova, *J. Phys. D: Appl. Phys.* **42**, 175411 (2009).
 - [8] M. A. Reshchikov, J. Garbus, G. Lopez, M. Ruchala, B. Nemeth, and J. Nause, *MRS Online Proceedings Library (OPL)* **957**, 0957 (2006).
 - [9] M. A. Reshchikov, H. Morkoç, B. Nemeth, J. Nause, J. Xie, B. Hertog, and A. Osinsky, *Phys. B Condens. Matter* **401**, 358 (2007).
 - [10] F. Tuomisto, V. Ranki, K. Saarinen, and D. C. Look, *Phys. Rev. Lett.* **91**, 205502 (2003).
 - [11] S. Lany and A. Zunger, *Phys. Rev. B* **80**, 085202 (2009).
 - [12] Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **95**, 094105 (2017).
 - [13] N. T. Son, J. Isoya, I. G. Ivanov, T. Ohshima, and E. Janzén, *AIP Conf. Proc.* **1583**, 341 (2014).
 - [14] J. E. Stehr, K. M. Johansen, T. S. Bjørheim, L. Vines, B. G. Svensson, W. M. Chen, and I. A. Buyanova, *Phys. Rev. Appl.* **2**, 021001 (2014).
 - [15] M. S. Holston, E. M. Golden, B. E. Kananen, J. W. McClory, N. C. Giles, and L. E. Halliburton, *J. Appl. Phys.* **119**, 145701 (2016).
 - [16] E. V. Lavrov, J. Weber, F. Börrnert, C. G. Van de Walle, and R. Helbig, *Phys. Rev. B* **66**, 165205 (2002).

- [17] E. Lavrov, F. Börrnert, and J. Weber, *Phys. B Condens. Matter* **401**, 366 (2007).
- [18] D. Bastin, E. V. Lavrov, and J. Weber, *Phys. Rev. B* **83**, 195210 (2011).
- [19] F. Herklotz, E. V. Lavrov, V. Kolkovsky, J. Weber, and M. Stavola, *Phys. Rev. B* **82**, 115206 (2010).
- [20] F. Herklotz, A. Hupfer, K. M. Johansen, B. G. Svensson, S. G. Koch, and E. V. Lavrov, *Phys. Rev. B* **92**, 155203 (2015).
- [21] A. V. Krukau, O. A. Vydrov, A. F. Izmaylov, and G. E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).
- [22] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- [23] G. Kresse and J. Hafner, *J. Phys.: Condens. Matter* **6**, 8245 (1994).
- [24] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- [25] G. Kresse and J. Hafner, *Phys. Rev. B* **47**, 558 (1993).
- [26] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [27] J. Albertsson, S. C. Abrahams, and Å. Kvik, *Acta Crystallogr. Sect. B* **45**, 34 (1989).
- [28] A. Baldereschi, *Phys. Rev. B* **7**, 5212 (1973).
- [29] S. B. Zhang and J. E. Northrup, *Phys. Rev. Lett.* **67**, 2339 (1991).
- [30] C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
- [31] Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
- [32] C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
- [33] H.-P. Komsa, T. T. Rantala, and A. Pasquarello, *Phys. Rev. B* **86**, 045112 (2012).
- [34] A. Alkauskas, J. L. Lyons, D. Steiauf, and C. G. Van de Walle, *Phys. Rev. Lett.* **109**, 267401 (2012).
- [35] A. M. Stoneham, *Theory of Defects in Solids* (Oxford University, New York, 1975).
- [36] K. Huang and A. Rhys, *Proc. R. Soc. London A* **204**, 406 (1950).
- [37] A. Alkauskas, M. D. McCluskey, and C. G. Van de Walle, *J. Appl. Phys.* **119**, 181101 (2016).
- [38] M. A. Reshchikov, *J. Appl. Phys.* **115**, 012010 (2014).
- [39] J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [40] A. Hupfer, C. Bhoddoo, L. Vines, and B. G. Svensson, *Mater. Sci. Semicond. Process.* **69**, 13 (2017).
- [41] C. G. Van de Walle, *Phys. Rev. Lett.* **85**, 1012 (2000).
- [42] J. L. Lyons, A. Alkauskas, A. Janotti, and C. G. Van de Walle, *Phys. Status Solidi B* **252**, 900 (2015).
- [43] A. A. Kopylov and A. N. Pikhtin, *Sov. Phys. Solid State* **16**, 1200 (1975).
- [44] J. E. Stehr, S. L. Chen, N. K. Reddy, C. W. Tu, W. M. Chen, and I. A. Buyanova, *Adv. Funct. Mater.* **24**, 3760 (2014).
- [45] D. Steiauf, J. L. Lyons, A. Janotti, and C. G. Van de Walle, *APL Mater.* **2**, 096101 (2014).
- [46] J. L. Lyons, J. B. Varley, D. Steiauf, A. Janotti, and C. G. V. de Walle, *J. Appl. Phys.* **122**, 035704 (2017).
- [47] C. G. Van de Walle and J. Neugebauer, *J. Appl. Phys.* **95**, 3851 (2004).
- [48] M. G. Wardle, J. P. Goss, and P. R. Briddon, *Phys. Rev. Lett.* **96**, 205504 (2006).
- [49] K. M. Johansen, J. S. Christensen, E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *Appl. Phys. Lett.* **93**, 152109 (2008).
- [50] A. Hupfer, C. Bhoddoo, L. Vines, and B. G. Svensson, *J. Appl. Phys.* **119**, 181506 (2016).
- [51] L. Vines and A. Kuznetsov, *Semicond. Semimet.* **88**, 67 (2013).
- [52] M. McCluskey and S. Jokela, *Phys. B Condens. Matter* **401**, 355 (2007).
- [53] K. M. Johansen, A. Zubiaga, F. Tuomisto, E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *Phys. Rev. B* **84**, 115203 (2011).
- [54] R. Heinhold, A. Neiman, J. V. Kennedy, A. Markwitz, R. J. Reeves, and M. W. Allen, *Phys. Rev. B* **95**, 054120 (2017).
- [55] D. C. Look, K. D. Leedy, L. Vines, B. G. Svensson, A. Zubiaga, F. Tuomisto, D. R. Doutt, and L. J. Brillson, *Phys. Rev. B* **84**, 115202 (2011).
- [56] D. O. Demchenko, B. Earles, H. Y. Liu, V. Avrutin, N. Izyumskaya, Ü. Özgür, and H. Morkoç, *Phys. Rev. B* **84**, 075201 (2011).
- [57] K. M. Johansen, L. Vines, T. S. Bjørheim, R. Schifano, and B. G. Svensson, *Phys. Rev. Appl.* **3**, 024003 (2015).
- [58] A. Zubiaga, F. Plazaola, J. A. García, F. Tuomisto, V. Muñoz Sanjosé, and R. Tena-Zaera, *Phys. Rev. B* **76**, 085202 (2007).
- [59] A. Alkauskas, Q. Yan, and C. G. Van de Walle, *Phys. Rev. B* **90**, 075202 (2014).
- [60] V. A. Nikitenko, *J. Appl. Spectrosc.* **57**, 783 (1992).
- [61] M. A. Reshchikov, *AIP Conf. Proc.* **1583**, 127 (2014).
- [62] C. E. Dreyer, A. Alkauskas, J. L. Lyons, J. S. Speck, and C. G. V. de Walle, *Appl. Phys. Lett.* **108**, 141101 (2016).
- [63] L. S. Vlasenko and G. D. Watkins, *Phys. Rev. B* **71**, 125210 (2005).
- [64] A. Janotti and C. G. Van de Walle, *Phys. Rev. B* **76**, 165202 (2007).
- [65] G.-Y. Huang, C.-Y. Wang, and J.-T. Wang, *J. Phys.: Condens. Matter* **21**, 195403 (2009).
- [66] C. Bhoddoo, A. Hupfer, L. Vines, E. V. Monakhov, and B. G. Svensson, *Phys. Rev. B* **94**, 205204 (2016).
- [67] J. E. Stehr, W. M. Chen, B. G. Svensson, and I. A. Buyanova, *J. Appl. Phys.* **119**, 105702 (2016).
- [68] G. A. Shi, M. Saboktakin, M. Stavola, and S. J. Pearton, *Appl. Phys. Lett.* **85**, 5601 (2004).
- [69] M. C. Tarun, M. Z. Iqbal, and M. D. McCluskey, *AIP Adv.* **1**, 022105 (2011).

Paper III

Negative- U and polaronic behavior of the Zn-O divacancy in ZnO

Y. K. Frodason, K. M. Johansen, A. Alkauskas, L. Vines

Published in *Physical Review B*, May 2019, volume 99, issue 17, pp. 174–106.
DOI: 10.1103/PhysRevB.99.174106.

Negative- U and polaronic behavior of the Zn-O divacancy in ZnO

Y. K. Frodason,^{1,*} K. M. Johansen,¹ A. Alkauskas,² and L. Vines¹

¹Centre for Materials Science and Nanotechnology, University of Oslo, N-0318 Oslo, Norway

²Center for Physical Sciences and Technology (FTMC), LT-10257 Vilnius, Lithuania

(Received 3 March 2019; published 15 May 2019)

Hybrid functional calculations reveal the Zn-O divacancy in ZnO, consisting of adjacent Zn and O vacancies, as an electrically active defect exhibiting charge states ranging from $2+$ to $2-$ within the band gap. Notably, the divacancy retains key features of the monovacancies, namely, the negative- U behavior of the O vacancy and the polaronic nature of the Zn vacancy. The thermodynamic charge-state transition levels associated with the negative- U behavior $\varepsilon(0/2-)$, $\varepsilon(-/2-)$, and $\varepsilon(0/-)$ are predicted to occur at 0.22, 0.42, and 0.02 eV below the conduction band minimum, respectively, resulting in $U = -0.40$ eV. These transition levels are moved closer to the conduction band, and the magnitude of U is lowered compared to the values for the O vacancy. Further, the interaction with hydrogen is explored, and it is shown that the divacancy can accommodate up to three H atoms. The first two H atoms prefer to terminate O dangling bonds at the Zn vacancy, while the geometrical location of the third depends on the Fermi level position. The calculated electrical properties of the divacancy are in excellent agreement with those reported for the E4 center observed by deep-level transient spectroscopy, challenging the O vacancy as a candidate for this level.

DOI: [10.1103/PhysRevB.99.174106](https://doi.org/10.1103/PhysRevB.99.174106)

I. INTRODUCTION

The Zn and O vacancies (V_{Zn} and V_{O}) are among the most widely studied point defects in ZnO and are frequently invoked to explain experimental results. First-principles defect calculations based on semilocal density functional theory, as well as purposely designed extrapolation techniques to alleviate the band-gap problem of this theory, have been indispensable in elucidating various properties of these defects in the past [1,2]. More recently, defect calculations based on optimized hybrid functionals have emerged as a viable, albeit computationally demanding, approach to obtain defect energy levels that generally agree well with experimental data [3,4]. For instance, it is now widely accepted that V_{O} is a deep donor with negative- U character [5–8], i.e., that the energy gain associated with electron pairing at V_{O} coupled with a large lattice relaxation overcomes the Coulomb repulsion of the two electrons resulting in a net attractive interaction [9]. V_{Zn} , on the other hand, is predicted to act as a deep acceptor that can trap up to four holes in polaronic states [10–14]. However, experimental verification related to, e.g., the energy level position and optical signature of V_{O} and V_{Zn} remains controversial.

Several recent experimental studies highlight the close-associate $V_{\text{Zn}}V_{\text{O}}$ pair, hereby referred to as the divacancy, as another important defect in ZnO, especially in processed samples, e.g., after irradiation, annealing, or polishing [15–17]. In contrast to its isolated constituents, however, first-principles calculations on the divacancy are scarcely available in the literature [16,18–22] and are predominantly based on semilocal functionals. In the present work, we apply hybrid functional

calculations to investigate the properties of the divacancy. Since the divacancy combines a donor with an acceptor, one might intuitively expect a passive and overall neutral pair. Interestingly, our calculations unveil the divacancy as a highly electrically active defect. Moreover, we find that the divacancy retains characteristics of both isolated constituents, namely, the negative- U property of V_{O} and the ability of V_{Zn} to trap holes in polaronic states. Furthermore, we investigate the interaction between divacancies and hydrogen—an omnipresent impurity that is known to occupy V_{O} and V_{Zn} in ZnO—and find that the divacancy can accommodate up to three H atoms. Our results are compared with experimental electron paramagnetic resonance (EPR) spectroscopy, deep-level transient spectroscopy (DLTS), and photoluminescence data.

II. METHODOLOGY

Unless specified otherwise, all first-principles calculations were based on the generalized Kohn-Sham (KS) theory with the Heyd-Scuseria-Ernzerhof (HSE) [23] hybrid functional and the projector augmented-wave method [24–26], as implemented in the VASP code [27,28]. The screening parameter was fixed to the standard value $\omega = 0.2 \text{ \AA}^{-1}$ [23], and the amount of screened Hartree-Fock exchange was set to $\alpha = 37.5\%$ [5]. This parametrization of HSE yields a band gap of 3.42 eV and an accurate description of the structural and electronic properties of wurtzite ZnO [29], which is an indispensable requirement for obtaining reliable defect energy levels [30].

Defect formation energies and thermodynamic charge-state transition levels were calculated by following a well-established method [30,31]. For instance, the formation energy of the divacancy in charge state q is given by

$$E_{\text{f}}^q(V_{\text{Zn}}V_{\text{O}}) = E_{\text{tot}}^q(V_{\text{Zn}}V_{\text{O}}) - E_{\text{tot}}^{\text{bulk}} + \mu_{\text{Zn}} + \mu_{\text{O}} + q\epsilon_{\text{F}}, \quad (1)$$

*ymirkf@fys.uio.no

where $E_{\text{tot}}^q(V_{\text{Zn}}V_{\text{O}})$ and $E_{\text{tot}}^{\text{bulk}}$ denote the total energy of the defect-containing and pristine supercells, μ_{Zn} and μ_{O} are the chemical potentials of the removed Zn and O atom, and ϵ_{F} is the Fermi level position relative to the bulk valence band maximum (VBM). The chemical potential depends on the experimental conditions, but upper and lower bounds are placed by the thermodynamic stability condition $\Delta H^{\text{f}}(\text{ZnO}) = \mu_{\text{Zn}} + \mu_{\text{O}}$, where $\Delta H^{\text{f}}(\text{ZnO})$ is the formation enthalpy of ZnO. The upper limit of μ_{O} (O-rich conditions) and μ_{Zn} (O-poor conditions) is given by the total energy per atom of an O_2 molecule and metallic Zn, respectively [2]. Note that the formation energy of the divacancy is independent of the specific conditions, as μ_{Zn} and μ_{O} are connected through the stability condition. The chemical potential of H was referenced to H_2 , including H_2O as a limiting phase under O-rich conditions. For charged defects, we applied the anisotropic [32] Freysoldt–Neugebauer–Van de Walle correction to the formation energy [33,34].

Thermodynamic charge-state transition levels $\epsilon(q_1/q_2)$ are given by the Fermi level position for which the formation energy of a defect in two charge states q_1 and q_2 is equal [30]. The effective correlation energy U for a defect d exhibiting three successive charge states q_1 , q_2 , and q_3 is given by the difference between the corresponding thermodynamic charge-state transition levels, i.e., $U = \epsilon(q_2/q_3) - \epsilon(q_1/q_2) = E_{\text{f}}^{q_1}(d) + E_{\text{f}}^{q_3}(d) - 2E_{\text{f}}^{q_2}(d)$ [9,35]. Optical emission and absorption energies and activation energies for carrier emission are estimated by using the effective one-dimensional configuration coordinate (CC) model, as described in Refs. [30,36,37].

Lyons *et al.* [14] recently pointed out that a 192-atom supercell is required to ensure converged defect energy levels for V_{O} in ZnO. After carrying out supercell size tests for V_{O} and $V_{\text{Zn}}V_{\text{O}}$, we arrive at the same conclusion. The slow convergence for V_{O} is mainly caused by (i) the rather extended defect wave function, which can overlap between neighboring supercells and cause a spurious defect-state dispersion [30], and (ii) the large local lattice relaxation associated with its negative- U behavior. The former issue can be alleviated by sampling special k points [38], but the latter requires an increase in supercell size. For these reasons, we employ the 192-atom supercell with a plane-wave energy cutoff of 500 eV and a special k point at $(\frac{1}{4}, \frac{1}{4}, \frac{1}{4})$ for defect calculations. Due to defect-state dispersion, the formation energy of defects involving V_{O} is found to converge slowly as a function of supercell size if a Γ -only k -point sampling is used.

III. RESULTS

A. Monovacancies

Before addressing the divacancy, we briefly revisit the electronic properties of the isolated monovacancies. As already mentioned, V_{O} is a deep double donor exhibiting negative- U behavior. The charge-neutral O vacancy induces one fully occupied symmetric KS defect state (a_1) inside the band gap and three empty ones resonant with the conduction band [2,8]. The negative- U behavior is caused by the large difference in local lattice relaxation for the three possible occupations of the a_1 state [1]. When a_1 is fully occupied (a_1^2), the vacancy

undergoes an inward relaxation in the breathing mode corresponding to -10% of the bulk Zn-O bond length, whereas when a_1 is half filled (a_1^1) and empty (a_1^0), the relaxation is outward by 6% and 24%. The thermodynamic $\epsilon(2+/0)$, $\epsilon(+/0)$, and $\epsilon(+/2+)$ transition levels are predicted to occur at 1.33, 1.57, and 1.08 eV below the conduction band minimum (CBM), respectively, resulting in $U = -0.49$ eV. These results are in good agreement with the aforementioned calculations by Lyons *et al.* [14] and consistent with photo-EPR data on V_{O} [14,39,40].

The doubly negatively charged Zn vacancy introduces four KS defect states in the band gap, all of which are completely filled with electrons [41]. Upon removal of an electron, the resulting hole is localized at a single nearest-neighbor O ion in the form of a polaron [42]. Up to four hole polarons can be stabilized at V_{Zn} , resulting in charge states ranging from $2+$ to $2-$ in the band gap [10–14]. The calculated $\epsilon(2+/+)$, $\epsilon(+/0)$, $\epsilon(0/-)$, and $\epsilon(-/2-)$ transition levels are positioned at 0.25, 0.89, 1.40, and 1.96 eV above the VBM, respectively [13].

B. Divacancy

The divacancy can nominally exist in two different configurations, axial (aligned along the [0001] direction) and azimuthal (lying in the basal plane). Holston *et al.* [17] assigned an EPR signal to the azimuthal configuration of the divacancy only, and our calculations indicate that this configuration is stabler, although the difference in energy is small. For this reason, we present results for only the azimuthal configuration.

1. Electronic and structural properties and stability

Figure 1 shows the formation energy of V_{Zn} , V_{O} , $V_{\text{Zn}}V_{\text{O}}$, and hydrogenated divacancies with up to three hydrogen atoms as a function of the Fermi level position. Evidently, the divacancy is highly electrically active, displaying charge states ranging from $2+$ to $2-$ in the band gap. Interestingly, it seems to retain certain characteristics of its constituents; the thermodynamic charge-state transition levels in the lower part of the band gap are positioned close to the respective levels of the isolated V_{Zn} , while those in the upper part exhibit negative- U characteristics similar to V_{O} . These results can be understood by inspecting the electronic and atomic structure of the divacancy, as shown in Fig. 2. As a double donor, V_{O} will transfer two electrons to V_{Zn} , thus completely filling its defect states, so the charge-neutral divacancy can be viewed as a V_{Zn}^{2-} and V_{O}^{2+} pair. Starting from the neutral charge state, our calculations show that the divacancy can trap a hole polaron at one or two of the three O ions immediately adjacent to V_{Zn} . The resulting $\epsilon(2+/+)$ and $\epsilon(+/0)$ transition levels occur at 0.43 and 0.96 eV above the VBM. The $+3$ charge state (with a hole polaron at each O ion) could not be stabilized.

We also find that the charge-neutral divacancy can capture two electrons in a deep a_1 KS defect state (blue isosurfaces in Fig. 2) at V_{O} . Notably, the thermodynamic charge-state transition occurs directly from 0 to $2-$ [20]. This is an important result because it demonstrates that the isolated V_{O} is not the only intrinsic defect exhibiting negative U in ZnO; that is, spectroscopic signatures indicating negative U need not necessarily arise from only the isolated V_{O} . The position of the

FIG. 1. Formation energies as a function of the Fermi level position under the most favorable condition for each defect, i.e., O rich for V_{Zn} and O poor for V_O and $V_{Zn}V_OnH$. Formation energies for the opposite limit can be acquired by adding 3.49 eV for V_{Zn} and V_O and $n \times 1.48$ eV for $V_{Zn}V_OnH$.

$\varepsilon(0/2-)$ transition level of the divacancy is shifted strongly up towards the CB, relative to the $\varepsilon(2+/0)$ level of V_O . This shift is mainly caused by the Coulomb repulsion between V_{Zn}^{2-} and the electrons occupying the a_1 state. Again, the negative- U behavior results from the large difference in local lattice relaxation around V_O depending on the occupation of a_1 . The breathing-mode relaxation is inward by -15% for a_1^1 , whereas it is outward by 1% and 21% for a_1^1 and a_1^0 , respectively. Note

that the relaxation is more inward for the divacancy compared to V_O (Sec. III A). Inward relaxation lowers the energy of the a_1 state but increases the strain energy [2]. For the divacancy, this energy balance is altered because the number of Zn ions immediately adjacent to V_O is lowered from four to three. The calculated $\varepsilon(0/2-)$, $\varepsilon(-/2-)$, and $\varepsilon(0/-)$ transition levels occur at 0.22, 0.42, and 0.02 eV below the CBM, respectively, resulting in $U = -0.40$ eV, which means the magnitude of U is lowered relative to the value for V_O .

Holston *et al.* [17] recently assigned a photo-EPR signal [43] to the paramagnetic $(V_{Zn}V_O^{2+})^+$ state ($S = 1/2$) in neutron-irradiated ZnO, with the unpaired spin (hole polaron) residing primarily on one of the three O ions immediately adjacent to V_{Zn} . Our prediction is in line with this result; that is, we find that removing an electron from the neutral divacancy indeed produces a hole polaron at one of the three O ions associated with V_{Zn} (the hole state corresponds to the yellow isosurface in Fig. 2). The same photo-EPR signal has also been observed in ZnO after 1.7, 2.5, and 3.0 MeV electron irradiation [44,45], i.e., for energies above the displacement threshold of both O (310 keV) and Zn (900 keV) in ZnO [46].

Although $(V_{Zn}V_O)^-$ is thermodynamically unstable, it might be possible to create it in a metastable manner, e.g., by optical excitation. In fact, the analogous paramagnetic isolated V_O^+ state is detectable at low temperatures by photo-EPR [39,40]. Holston *et al.* [17] initially envisioned the paramagnetic $(V_{Zn}V_O^+)^-$ state as being responsible for the aforementioned divacancy photo-EPR signal. However, this model was discarded as its EPR spectrum would have negative g shifts and well-resolved hyperfine interactions with the adjacent ^{67}Zn nuclei, similar to the isolated V_O^+ [17]. Moreover, because the Fermi level was lowered by the neutron irradiation [17], the divacancies were most likely charge neutral before illumination.

A pertinent question is whether divacancies are likely to form and if they are stable at room temperature. Since V_{Zn} and V_O favor opposite conditions, the formation energy of $V_{Zn}V_O$ is high, indicating a low equilibrium concentration. Indeed, experimentally, divacancies are typically observed in ZnO after postgrowth processing, e.g., after irradiation, ion implantation, annealing, or polishing [15–17]. Regarding stability, we find that the defect reaction $V_{Zn}^{2-} + V_O^0 \rightarrow (V_{Zn}V_O)^{2-}$ lowers the total energy by 0.83 eV under n -type conditions, which means that the divacancy will be stable at room temperature. Using the climbing nudged elastic band method [47] and the Perdew-Burke-Ernzerhof [48] functional, we have also investigated migration of the divacancy, i.e., nearest-neighbor Zn and O atoms hopping into the vacant Zn and O sites, respectively. The resulting migration barrier is about 1.2 eV, which is lower than those predicted previously for monovacancies in ZnO [2]. Thus, divacancies may diffuse at relatively low temperatures and form larger vacancy clusters [19] or other complexes [17]. Indeed, formation of vacancy clusters in ZnO has been reported in several experimental studies [15,16,49].

2. Dynamics of electron emission and capture

In order to allow comparison of our results with experimental data, e.g., energy level positions obtained by DLTS, we

FIG. 2. Relaxed divacancy structures. The hole (yellow isosurface) is trapped in a polaronic state at one of the three O ions associated with V_{Zn} . The a_1 defect state (blue isosurface) of V_O can accommodate two electrons, with a large difference in relaxation for each occupation.

FIG. 3. CC diagram describing the dynamics of electron emission and capture between the divacancy and the CBM. Optical absorption (E_{abs}), ionization (E_i), and activation (E_a) energies for electron emission are provided (all in eV). The magnitude of Q is given at the minima of the potential energy curves and the crossing points between them.

have constructed a CC diagram (shown in Fig. 3) describing the two-step process of electron emission from the doubly negatively charged divacancy to the CBM. The generalized coordinate Q along the horizontal axis corresponds to the mass-weighted atomic displacement between the equilibrium structure of $V_{Zn}V_O$ for the three different charge states, namely, $2-$, $-$, and 0 [36], and can be loosely viewed as the magnitude of outward-breathing relaxation around V_O . The total energy as a function of Q results in a potential energy curve for each charge state, and the energy is minimized at the equilibrium structure for each curve. The potential energy curves are displaced in energy along the vertical axis by the Fermi level position of the thermodynamic charge-state transition levels relative to the CBM, i.e., the difference in energy between the states in their equilibrium configurations. We will refer to these differences in energy as defect ionization energies E_i [37].

As shown in Fig. 3, we obtain an activation energy E_a of 0.52 eV for electron emission from $(V_{Zn}V_O)^{2-}$ to the CBM. This activation energy corresponds to the sum of E_i and the capture barrier of 0.10 eV, which is taken as the energy required to reach the crossing point between the curves for $(V_{Zn}V_O)^{-} + e_{CBM}^+$ and $(V_{Zn}V_O)^{2-}$. Keep in mind that this barrier should be viewed as an upper estimate [37,50]. Moreover, the temperature effects described in Ref. [37] are also neglected here. For emission from $(V_{Zn}V_O)^{-}$, we obtain a lower activation energy of 0.24 eV for emission and a capture barrier of 0.22 eV.

3. Optical transitions

Several broad luminescence bands have been observed in the visible part of the emission spectrum of ZnO, and there is a plethora of studies linking these to various point defects, including V_{Zn} and V_O . However, consensus is lacking, and the defect origin of most bands remains unknown. Previous

FIG. 4. CC diagram for optical transitions involving the capture of a hole at the VBM by $(V_{Zn}V_O)^{2-}$ and $(V_{Zn}V_O)^{-}$. Zero phonon line (E_{ZPL}), emission (E_{em}), absorption (E_{abs}), and ground-state relaxation (d_g^{FC}) energies (all in eV) and total mass-weighted distortion (in $\text{amu}^{1/2}\text{\AA}$) are provided.

hybrid functional calculations suggest that the isolated vacancies are unlikely to give rise to luminescence in the visible range under n -type conditions [13,14]. However, the optical properties of the divacancy could be very different from those of V_{Zn} and V_O [14,51].

We have considered three different optical transitions for the divacancy, namely, hole capture from the VBM by $(V_{Zn}V_O)^{2-}$ and $(V_{Zn}V_O)^{-}$ and electron capture from the CBM by $(V_{Zn}V_O)^{+}$. Figure 4 shows the calculated CC diagrams for the two former transitions. Again, the potential energy curves in the CC diagrams are vertically displaced in energy by the Fermi level position of the respective thermodynamic charge-state transition levels relative to the VBM. In the context of luminescence, this is usually referred to as the zero-phonon-line energy E_{ZPL} . In the Franck-Condon approximation, optical transitions take place without atomic motion, i.e., emission (E_{em}) and absorption (E_{abs}) energies are given by the vertical arrows in Fig. 4. After an optical transition, the defect will relax to its equilibrium configuration by emitting phonons, losing the Franck-Condon relaxation energy (denoted d_g^{FC} for the ground state).

Interestingly, the difference in E_{ZPL} for the transitions in Fig. 4 is offset by a difference in d_g^{FC} , resulting in close emission energies of 2.07 and 2.11 eV. The capture of an electron at the CBM by the positively charged divacancy results in a lower emission energy of 1.66 eV; the CC diagram is not shown here but is similar to what has been found previously for other V_{Zn} related defects [13,14,51]. Overall, our results show that the divacancy can give rise to broad luminescence peaking in the 1.6–2.1 eV range. We also note that both considered transitions should be dipole allowed. In the case of radiative electron capture the CB electrons have mostly Zn 4s character, while the final states have mostly O 2p [30] character. For radiative hole capture the initial state is a perturbed VB state which is composed mainly of O 2p states, while the defect state has mostly Zn 4s character. A different parity ensures a strong transition dipole moment and thus dipole-allowed transitions. Experimental studies on the optical properties of divacancies are scarce in the literature, but our calculations are consistent with the results reported by Dong *et al.* [52]. Based on cathodoluminescence and positron annihilation spectroscopy (PAS) data, Dong *et al.*

FIG. 5. Relaxed structures for the divacancy containing up to three H atoms. The first two H atoms terminate O dangling bonds, at either the bond-centered axial or azimuthal site. Depending on the Fermi level position, the third H atom will occupy V_O or terminate the final O dangling bond.

[52] suggested that the emission from large vacancy clusters peaks at up to 2.1 eV, which shifts to lower energies with decreasing cluster size.

C. Hydrogen-decorated divacancy

Besides being a ubiquitous impurity, hydrogen strongly influences the electrical and optical properties of ZnO, notably as a source of unintentional n -type conductivity [53–55]. Interstitial hydrogen (H_i) acts exclusively as a donor by forming a strong O-H bond, preferably at the axial bond-centered site [55–57]. However, H_i is mobile at room temperature [58–60] and is thus likely to become trapped at defects. Importantly, the Coulomb attraction between H_i^+ and V_{Zn}^{2-} results in highly stable $V_{Zn}nH$ complexes with $n = 1, 2, 3$, wherein H remains a donor by terminating O dangling bonds; the first two H atoms successively passivate the acceptor levels of V_{Zn} , whereas the third transforms the complex into a shallow single donor. H can also be trapped at V_O , but in this case the hydrogen behaves as an acceptor (H^-) substituting for oxygen (fourfold coordinated). The resulting complex acts as a single shallow donor (H_O^+) [57,61].

Because both V_{Zn} and V_O present potential trapping sites for H in the divacancy, different configurations were explored. Furthermore, to assess the divacancy as a hydrogen trap, removal energies were calculated as the difference in formation energy between the hydrogenated divacancy and the two remaining defects (calculated within separate supercells) when one H is removed and placed in its stablest isolated configuration (H_i^+).

As shown in Fig. 5, the first two H atoms prefer to terminate O dangling bonds at V_{Zn} , resulting in $V_{Zn}H-V_O$ and $V_{Zn}2H-V_O$ complexes. The formation of these complexes lowers the total energy substantially, as evidenced by the large respective H removal energies of 2.84 and 2.02 eV. These are only slightly lower than for the $V_{Zn}H$ and $V_{Zn}2H$ complexes [14]. For comparison, removal energies of 2.08 and 1.26 eV are obtained for the $V_{Zn}-H_O$ and $V_{Zn}H-H_O$

configurations. As indicated in Fig. 1, the location of the third H atom depends on the position of the Fermi level. When $\epsilon_F > 1.63$ eV, the H atom will preferentially occupy V_O , resulting in the $(V_{Zn}2H-H_O)^+$ complex with a calculated H removal energy of 1.26 eV. When $\epsilon_F < 1.63$ eV, the H atom will instead terminate the final dangling bond at V_{Zn} , resulting in $(V_{Zn}3H-V_O)^{3+}$. However, this latter configuration is unstable, as the H removal energy is -0.48 eV.

As can be seen in Fig. 1, the negative- U behavior persists for both $V_{Zn}H-V_O$ and $V_{Zn}2H-V_O$. However, the corresponding transition levels are shifted down in Fermi level position. Indeed, as the acceptor levels of V_{Zn} are passivated by H, the Coulomb repulsion experienced by the electrons occupying the a_1 defect state is successively lowered, and the transition levels shift down towards the VB by ~ 0.4 eV per H atom. Specifically, the $\epsilon(-/+)$ and $\epsilon(2+/0)$ transition levels of $V_{Zn}H-V_O$ and $V_{Zn}2H-V_O$ are predicted to occur at 0.57 and 0.98 eV below the CBM. The magnitude of U is unchanged with respect to the isolated divacancy ($U = -0.40$ eV), which again indicates that it is mainly determined by the number of Zn atoms immediately adjacent to V_O . Note that these trends hold for the $\epsilon(3+/+)$ transition of the unstable $V_{Zn}3H-V_O$ complex as well. Last, the $V_{Zn}2H-H_O$ complex behaves like an effective-mass donor and should be viewed as a $(V_{Zn}2H)^0$ and H_O^+ pair. At this point, the divacancy is fully saturated with H atoms.

D. Comparison with DLTS and the E4 center

As previously discussed, the divacancy is not expected to be present in a substantial amount in as-grown samples but may be formed during processing. Several electrically active defect centers having energy levels in the upper part of the band gap have been reported in n -type ZnO [62]. In this section, we compare our results for the divacancy with experimental DLTS data. We start by envisioning the electron emission from $(V_{Zn}V_O)^{2-}$ during a conventional DLTS measurement for n -type material. After a zero-bias filling pulse at low temperature, all divacancies will be filled with electrons. Subsequently, at some elevated temperature and under reverse bias, the first electron will be thermally emitted from $(V_{Zn}V_O)^{2-}$ with $E_a = 0.52$ eV. Since the electron at $(V_{Zn}V_O)^-$ is bound less strongly ($E_a = 0.24$ eV), emission of the second electron will proceed immediately after the first electron, leaving the defect in the $(V_{Zn}V_O)^0$ state. For this reason, the divacancy will emit always two electrons during a conventional DLTS measurement, resulting in a single peak with $E_a = 0.52$ eV. Indeed, such two-electron emission is common for centers where the electron binding energy shows an inverted order [63,64].

It is sometimes possible to obtain the activation energy associated with one-electron emission from a negative- U center by using DLTS with a short filling pulse and illumination. If the filling pulse is sufficiently short, most charge-neutral divacancies will be prevented from capturing more than one electron. A new DLTS peak, corresponding to the one-electron emission with $E_a = 0.24$ eV, may then be observed at a lower temperature than for the two-electron emission. However, even with a short filling pulse, some divacancies may still capture a second electron, which means that they will

be frozen out in the temperature range where the one-electron emission peak can be observed, and the peak will decrease to zero over time due to the repetitive pulses required by DLTS [63]. This can be avoided by optically “emptying” any divacancies having captured two electrons in the preceding pulse before each filling pulse. This technique has been used, e.g., to observe one-electron emission from the negative- U center $Z_{1/2}$ in 4H-SiC [63].

Interestingly, the calculated $E_a = 0.52$ eV for $V_{Zn}V_O$ is close to the experimental activation energy of ~ 0.55 eV for the E4 center in ZnO, which has been observed by several groups and is commonly assigned to a V_O -related defect exhibiting negative U [62,65]. However, theoretical predictions and experimental photo-EPR data [14,39,40] suggest that the isolated V_O is substantially deeper than the E4 center, and this discrepancy has been a source of a long-standing debate in the community.

Our theoretical predictions for the divacancy conform to many of the experimental findings on the E4 center: (i) Negative- U behavior has been reported for E4 [66,67]. In particular, by using a short filling pulse and illumination as described above, an apparent energy level of ~ 0.14 eV has been obtained for the one-electron emission from E4 [66,68], which is close to our calculated value of 0.24 eV. (ii) Based on the temperature dependence of the rate of electron capture by E4 during the zero-bias filling pulse, Hupfer *et al.* [69] obtained an experimental capture barrier of ~ 0.15 eV, in good agreement with our calculated value of 0.22 eV for the divacancy. (iii) E4 exhibits a low concentration in as-grown material but is prominent after He^+ and H^+ irradiation [65,69–71]. Its concentration hinges linearly on the ion dose but amounts to only $\sim 0.23\%$ of the total vacancy generation obtained from Monte Carlo simulations using the SRIM code [62,72]. Such a low generation rate is uncommon for a primary intrinsic defect, even if strong dynamic annealing is taken into account, and favors E4 as a high-order intrinsic defect such as the divacancy [62]. For comparison, the generation rate is about 1%–2% for the divacancy in Si after high-energy ion irradiation [62]. E4 has also been observed after 2 MeV electron irradiation [66], i.e., above the displacement threshold of both O and Zn in

ZnO. (iv) After H^+ implantation at room temperature, the E4 center anneals out at a rate that fits well with a model invoking migration of H_i and subsequent reaction with E4 [69]; our results show that the divacancy has a strong affinity for H, similar to that of V_{Zn} . Furthermore, E4 is accompanied by a second trap labeled Ep2 after H^+ irradiation, which similarly exhibits a low introduction rate [65]. Indeed, Auret *et al.* [65] suggested that Ep1 (E4) and Ep2 might be high-order rather than primary intrinsic defects. Finally, Ep2 has an apparent energy level at ~ 0.78 eV, which incidentally fits well with our calculated ionization energy of 0.77 eV for $V_{Zn}H-V_O$.

IV. CONCLUSION

Using hybrid functional calculations, we have investigated the divacancy in ZnO. The divacancy is predicted to be a highly electrically active defect, exhibiting charge states ranging from $2+$ to $2-$ in the band gap. Interestingly, it retains both the negative- U behavior of V_O and the polaronic nature of V_{Zn} . The former result is of particular interest, as it demonstrates that the isolated V_O is not the only intrinsic defect exhibiting negative U in ZnO. We have also studied the interaction between divacancies and H and have found that the divacancy can accommodate up to three H atoms, the first two of which prefer to terminate O dangling bonds at V_{Zn} . Based on a comparison of our results with experimental DLTS data in the literature [62,65–67,70,71], $V_{Zn}V_O$ is proposed as a potential origin of the E4 center, which is commonly associated with a V_O -related defect with negative U .

ACKNOWLEDGMENTS

Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (No. 251131, FriPro ToppForsk program). A.A. was supported by the Marie Skłodowska-Curie Action of the European Union (project Nitride-SRH, Grant No. 657054). The computations were performed on resources provided by UNINETT Sigma2, the National Infrastructure for High Performance Computing and Data Storage in Norway.

-
- [1] A. Janotti and C. G. V. de Walle, *Rep. Prog. Phys.* **72**, 126501 (2009).
 - [2] A. Janotti and C. G. Van de Walle, *Phys. Rev. B* **76**, 165202 (2007).
 - [3] W. Chen and A. Pasquarello, *Phys. Rev. B* **96**, 020101(R) (2017).
 - [4] G. Miceli, W. Chen, I. Reshetnyak, and A. Pasquarello, *Phys. Rev. B* **97**, 121112(R) (2018).
 - [5] F. Oba, A. Togo, I. Tanaka, J. Paier, and G. Kresse, *Phys. Rev. B* **77**, 245202 (2008).
 - [6] A. Alkauskas and A. Pasquarello, *Phys. Rev. B* **84**, 125206 (2011).
 - [7] S. J. Clark, J. Robertson, S. Lany, and A. Zunger, *Phys. Rev. B* **81**, 115311 (2010).
 - [8] S. Lany and A. Zunger, *Phys. Rev. B* **81**, 113201 (2010).
 - [9] P. W. Anderson, *Phys. Rev. Lett.* **34**, 953 (1975).
 - [10] S. Lany and A. Zunger, *Phys. Rev. B* **80**, 085202 (2009).
 - [11] T. S. Bjørheim, S. Erdal, K. M. Johansen, K. E. Knutsen, and T. Norby, *J. Phys. Chem. C* **116**, 23764 (2012).
 - [12] G. Petretto and F. Bruneval, *Phys. Rev. B* **92**, 224111 (2015).
 - [13] Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **95**, 094105 (2017).
 - [14] J. L. Lyons, J. B. Varley, D. Steiauf, A. Janotti, and C. G. V. de Walle, *J. Appl. Phys.* **122**, 035704 (2017).
 - [15] I. Makkonen, E. Korhonen, V. Proszhcheva, and F. Tuomisto, *J. Phys. Condens. Matter* **28**, 224002 (2016).
 - [16] K. Johansen, F. Tuomisto, I. Makkonen, and L. Vines, *Mater. Sci. Semicond. Process.* **69**, 23 (2017).
 - [17] M. S. Holston, E. M. Golden, B. E. Kananen, J. W. McClory, N. C. Giles, and L. E. Halliburton, *J. Appl. Phys.* **119**, 145701 (2016).

- [18] R. Vidya, P. Ravindran, H. Fjellvåg, B. G. Svensson, E. Monakhov, M. Ganchenkova, and R. M. Nieminen, *Phys. Rev. B* **83**, 045206 (2011).
- [19] J. Bang, Y.-S. Kim, C. H. Park, F. Gao, and S. B. Zhang, *Appl. Phys. Lett.* **104**, 252101 (2014).
- [20] A. Chakrabarty and C. H. Patterson, *Phys. Rev. B* **84**, 054441 (2011).
- [21] A. Chakrabarty and C. H. Patterson, *J. Chem. Phys.* **137**, 054709 (2012).
- [22] E.-H. Shin and H. Kim, *J. Korean Phys. Soc.* **64**, 543 (2014).
- [23] A. V. Kravau, O. A. Vydrov, A. F. Izmaylov, and G. E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).
- [24] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- [25] G. Kresse and J. Hafner, *J. Phys.: Condens. Matter* **6**, 8245 (1994).
- [26] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- [27] G. Kresse and J. Hafner, *Phys. Rev. B* **47**, 558 (1993).
- [28] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [29] F. Oba, M. Choi, A. Togo, and I. Tanaka, *Sci. Technol. Adv. Mater.* **12**, 034302 (2011).
- [30] C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
- [31] S. B. Zhang and J. E. Northrup, *Phys. Rev. Lett.* **67**, 2339 (1991).
- [32] Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
- [33] C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
- [34] H.-P. Komsa, T. T. Rantala, and A. Pasquarello, *Phys. Rev. B* **86**, 045112 (2012).
- [35] A. M. Stoneham and M. J. L. Sangster, *Radiat. Eff.* **73**, 267 (1983).
- [36] A. Alkauskas, J. L. Lyons, D. Steiauf, and C. G. Van de Walle, *Phys. Rev. Lett.* **109**, 267401 (2012).
- [37] D. Wickramaratne, C. E. Dreyer, B. Monserrat, J.-X. Shen, J. L. Lyons, A. Alkauskas, and C. G. Van de Walle, *Appl. Phys. Lett.* **113**, 192106 (2018).
- [38] C. G. Van de Walle and J. Neugebauer, *J. Appl. Phys.* **95**, 3851 (2004).
- [39] S. M. Evans, N. C. Giles, L. E. Halliburton, and L. A. Kappers, *J. Appl. Phys.* **103**, 043710 (2008).
- [40] X. J. Wang, L. S. Vlasenko, S. J. Pearton, W. M. Chen, and I. A. Buyanova, *J. Phys. D Appl. Phys.* **42**, 175411 (2009).
- [41] S. Lany and A. Zunger, *Phys. Rev. Lett.* **98**, 045501 (2007).
- [42] D. Galland and A. Herve, *Phys. Lett. A* **33**, 1 (1970).
- [43] K. Leutwein and J. Schneider, *Z. Naturforsch. A* **26**, 1236 (1971).
- [44] B. Schallenger and A. Hausmann, *Z. Phys. B* **23**, 177 (1976).
- [45] V. Soriano and D. Galland, *Phys. Status Solidi B* **77**, 739 (1976).
- [46] D. R. Locker and J. M. Meese, *IEEE Trans. Nucl. Sci.* **19**, 237 (1972).
- [47] G. Henkelman, B. P. Uberuaga, and H. Jansson, *J. Chem. Phys.* **113**, 9901 (2000).
- [48] J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [49] K. S. Chan, L. Vines, K. M. Johansen, E. V. Monakhov, J. D. Ye, P. Parkinson, C. Jagadish, B. G. Svensson, and J. Wong-Leung, *J. Appl. Phys.* **114**, 083111 (2013).
- [50] P. Mooney, in *Identification of Defects in Semiconductors, Semiconductors and Semimetals Vol. 51*, edited by M. Stavola (Elsevier, 1999), pp. 93–152.
- [51] Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **97**, 104109 (2018).
- [52] Y. Dong, F. Tuomisto, B. G. Svensson, A. Yu. Kuznetsov, and L. J. Brillson, *Phys. Rev. B* **81**, 081201(R) (2010).
- [53] E. Mollwo, *Z. Phys. A* **138**, 478 (1954).
- [54] D. G. Thomas and J. J. Lander, *J. Chem. Phys.* **25**, 1136 (1956).
- [55] C. G. Van de Walle, *Phys. Rev. Lett.* **85**, 1012 (2000).
- [56] M. G. Wardle, J. P. Goss, and P. R. Briddon, *Phys. Rev. B* **72**, 155108 (2005).
- [57] E. V. Lavrov, F. Herklotz, and J. Weber, *Phys. Rev. B* **79**, 165210 (2009).
- [58] M. G. Wardle, J. P. Goss, and P. R. Briddon, *Phys. Rev. Lett.* **96**, 205504 (2006).
- [59] K. M. Johansen, J. S. Christensen, E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *Appl. Phys. Lett.* **93**, 152109 (2008).
- [60] A. Hupfer, C. Bhodoo, L. Vines, and B. G. Svensson, *Mater. Sci. Semicond. Process.* **69**, 13 (2017).
- [61] C. G. Van de Walle and A. Janotti, *Nat. Mater.* **6**, 44 (2007).
- [62] E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *J. Phys. D* **42**, 153001 (2009).
- [63] C. G. Hemmingsson, N. T. Son, A. Ellison, J. Zhang, and E. Janzén, *Phys. Rev. B* **58**, R10119 (1998).
- [64] N. T. Son, X. T. Trinh, L. S. Løvlie, B. G. Svensson, K. Kawahara, J. Suda, T. Kimoto, T. Umeda, J. Isoya, T. Makino, T. Ohshima, and E. Janzén, *Phys. Rev. Lett.* **109**, 187603 (2012).
- [65] F. D. Auret, S. A. Goodman, M. Hayes, M. J. Legodi, H. A. van Laarhoven, and D. C. Look, *Appl. Phys. Lett.* **79**, 3074 (2001).
- [66] T. Frank, G. Pensl, R. Tena-Zaera, J. Zúñiga-Pérez, C. Martínez-Tomás, V. Muñoz-Sanjose, T. Ohshima, H. Itoh, D. Hofmann, D. Pfisterer, J. Sann, and B. Meyer, *Appl. Phys. A* **88**, 141 (2007).
- [67] M. Ellguth, M. Schmidt, R. Pickenhain, H. V. Wenckstern, and M. Grundmann, *Phys. Status Solidi B* **248**, 941 (2010).
- [68] D. Hofmann, D. Pfisterer, J. Sann, B. Meyer, R. Tena-Zaera, V. Munoz-Sanjose, T. Frank, and G. Pensl, *Appl. Phys. A* **88**, 147 (2007).
- [69] A. Hupfer, C. Bhodoo, L. Vines, and B. G. Svensson, *J. Appl. Phys.* **119**, 181506 (2016).
- [70] M. Hayes, F. Auret, P. J. van Rensburg, J. Nel, W. Wesch, and E. Wendler, *Nucl. Instrum. Methods Phys. Res., Sect. B* **257**, 311 (2007).
- [71] M. Hayes, F. D. Auret, P. J. Janse van Rensburg, J. M. Nel, W. Wesch, and E. Wendler, *Phys. Status Solidi B* **244**, 1544 (2007).
- [72] J. F. Ziegler, M. Ziegler, and J. Biersack, *Nucl. Instrum. Methods Phys. Res., Sect. B* **268**, 1818 (2010).

Paper IV

Broad luminescence from donor-complexed Li_{Zn} and Na_{Zn} acceptors in ZnO

Y. K. Frodason, K. M. Johansen, A. Galeckas, L. Vines

Published in *Physical Review B*, November 2019, volume 100, issue 18, pp. 184–102. DOI: 10.1103/PhysRevB.100.184102.

IV

Broad luminescence from donor-complexed Li_{Zn} and Na_{Zn} acceptors in ZnO

Y. K. Frodason,* K. M. Johansen, A. Galeckas, and L. Vines

Department of Physics/Centre for Materials Science and Nanotechnology, University of Oslo, N-0318 Oslo, Norway

(Received 16 August 2019; revised manuscript received 12 October 2019; published 4 November 2019)

Zn substitutional lithium (Li_{Zn}) and sodium (Na_{Zn}) acceptors and their complexes with common donor impurities (Al_{Zn} , H_i , and H_0) in ZnO have been studied using hybrid functional calculations. The results show that the complexes are not exclusively charge neutral, but rather exhibit a thermodynamic (+/0) transition level close to the valence band maximum. The positive charge states are associated with a polaronic defect state, similar to those of the well-studied charge-neutral isolated acceptors. This incomplete passivation has profound consequences for the optical properties of the complexes. Indeed, electron transitions from the conduction band minimum to the (+/0) transition level of the complexes result in broad luminescence bands that are blueshifted with respect to those originating from the isolated acceptors. Such complexes are proposed as a potential defect origin of the green luminescence observed at the high-energy side of the orange luminescence band (caused by Li_{Zn}) in hydrothermally grown ZnO. This prediction is supported by experimental photoluminescence and secondary ion mass spectrometry data on a hydrothermally grown ZnO sample. We have also explored how the parameters controlling the fraction and screening of exchange in the Heyd-Scuseria-Ernzerhof (HSE) hybrid functional influence the results by comparing two parametrization approaches: (i) the conventional one where the exchange fraction is adjusted to reproduce the experimental band gap, and (ii) tuning both parameters in order to also comply with the generalized Koopmans theorem (gKT). Interestingly, these approaches were found to yield similar results.

DOI: [10.1103/PhysRevB.100.184102](https://doi.org/10.1103/PhysRevB.100.184102)

I. INTRODUCTION

The behavior of Li in ZnO has long been the subject of considerable scientific interest. Early experimental work on Li in ZnO by Lander [1] indicated an electrically amphoteric behavior. Subsequent investigations have confirmed that Li can act as an interstitial donor (Li_i) or a Zn substitutional acceptor (Li_{Zn}) [2–8]. Many initial attempts to achieve *p*-type conductivity in ZnO involved the Li_{Zn} acceptor as a potential shallow dopant, with the amphoteric behavior of Li and consequent Fermi level pinning as the main hindrance. However, it is now widely agreed that Li_{Zn} introduces a deep acceptor level [9,10]. Indeed, the paramagnetic Li_{Zn}^0 state can be observed by electron paramagnetic resonance (EPR) spectroscopy, and corresponds to a small hole polaron localized at one of the four O^{2-} ions immediately adjacent to Li_{Zn} [2,11,12].

The optical properties of Li in ZnO have also been studied extensively. EPR [13,14] and optically detected magnetic resonance studies [9,15,16] have established a correlation between the Li_{Zn}^0 magnetic resonance line and a broad orange luminescence (OL) band with a maximum at 1.95 eV at 10 K [17–19]. The OL band is normally present in the photoluminescence (PL) spectrum of hydrothermally (HT) grown ZnO [18] crystals, which contain Li impurities with concentrations in the $(1\text{--}5) \times 10^{17} \text{ cm}^{-3}$ range [20]. McNamara *et al.* [19] recently performed a detailed experimental analysis of the thermal quenching of the OL band in HT grown ZnO, and

obtained an ionization energy of $0.65 \pm 0.10 \text{ eV}$ for Li_{Zn} . The paramagnetic Na_{Zn}^0 state has similarly been observed by EPR and linked to a broad yellow luminescence (YL) band peaking at 2.18 eV at 50 K [21], but the concentration of Na impurities in HT grown ZnO is typically at least one order of magnitude lower than that of Li.

Holistic understanding of an extrinsic defect in a host semiconductor not only includes its behavior as an isolated defect, but its interplay with other important defects and impurities in the material. For instance, Li_{Zn} is known to form defect complexes with donor impurities in ZnO. Notable examples include: (i) $\text{Li}_{\text{Zn}}\text{H}$, which has been assigned to an infrared (IR) absorption line at 3577 cm^{-1} , the dominant OH-related IR absorption line in HT grown ZnO [22], and (ii) $\text{Li}_{\text{Zn}}\text{Fe}_{\text{Zn}}$, which has been identified by means of high-frequency EPR and electron-nuclear double resonance spectroscopy [23]. Importantly, since Li and donor dopants, primarily Al and H, are the main impurities in HT grown ZnO, such defect complexes may influence, and even dominate, its electrical and optical properties. The behavior of such complexes is not fully understood and reports are scarce in the literature, but they are often assumed to be fully passivated with no charge-state transition levels within the band gap.

Concurrently, despite the large body of work on Li in ZnO, pertinent questions remain. For instance, a structured blue luminescence (BL) band with a zero phonon line (ZPL) at 3.05 eV has been observed in Li-doped ZnO under certain conditions, and attributed to a transition between a shallow donor and a Li-related shallow acceptor with an ionization energy of 300 meV [24–26]. The specific defect origin is unclear, but a transient shallow Li_{Zn} state [27,28], or a

*ymirkf@fys.uio.no

$\text{Li}_{\text{Zn}}\text{-H-Li}_{\text{Zn}}$ complex [24,25] has been suggested. Furthermore, the OL band in HT grown ZnO is normally overlapped by a broad green luminescence (GL) at its high energy side [19]. Broad GL is almost ubiquitous in the PL spectrum of ZnO. However, Reshchikov *et al.* [18,29] have reported specific bands labeled GL1 and GL2 which were observed exclusively in HT grown ZnO. Their defect origins have not been established, but, since a high Li content is the primary difference between HT grown and other forms of ZnO crystals, Li-related defects are reasonable suspects.

In this work we present results from hybrid functional calculations on the thermodynamic, electrical, and optical properties of the Li_{Zn} and Na_{Zn} acceptors, and their complexes with the common donor impurities Al_{Zn} and H in ZnO. The results for Li_{Zn} and Na_{Zn} are found to be in good agreement with experimental data on the OL and YL bands. Interestingly, we find that also the complexes are electrically (and optically) active. This result is further supported by PL and secondary ion mass spectrometry (SIMS) data on a HT grown ZnO sample, before and after annealing in Zn ambient in order to lower the concentration of Li impurities in the sample.

II. METHODOLOGY

A. Computational details

First-principles calculations were performed using the projector augmented wave method [30,31] with the Heyd-Scuseria-Ernzerhof (HSE) [32] range-separated hybrid functional, as implemented in the VASP code [33].

Hybrid functionals satisfying the generalized Koopmans theorem (gKT) have generally been found to describe polaronic localization well [34–37]. For this reason, the HSE(α , ω) functional was parametrized by using two different approaches: (i) conventionally by adjusting the fraction of screened Hartree-Fock exchange α to 0.375 [38] in order to reproduce the experimental band gap of 3.44 eV [39], while keeping the screening parameter ω fixed to the standard value of $0.2 \text{ \AA}^{-1}$, and (ii) tuning α and ω to both satisfy the gKT and reproduce the experimental band gap [37]. We employed the (0/–) transition of polaronic acceptors (V_{Zn} , Li_{Zn} , and Na_{Zn}) to test the gKT. When testing the gKT, it is crucial that finite-size errors are minimized; detailed information on our testing procedure, finite-size corrections, and the supercell-size dependence of the gKT related quantities can be found in the Appendix. We find that the HSE(0.30, 0.05) functional complies with the gKT and reproduces the experimental band gap, whereas the HSE(0.375, 0.20) functional results in a non-Koopmans energy of about 0.1 eV. This energy is small, and may still contain a small finite-size error, which we have estimated based on supercell-size tests in the Appendix. Nevertheless, the difference in results obtained with the two approaches can, at the very least, serve as a proxy for the sensitivity of the results with respect to the choice of α and ω parameters.

Bulk lattice constants were optimized for each functional until the forces were smaller than $1 \text{ meV/\AA}$; the resulting lattice parameters differ by merely $0.01 \text{ \AA}$. Defect calculations were then performed using 96-atom supercells, a plane-wave basis set with an energy cutoff of 500 eV, and a special k

point at $(\frac{1}{4}, \frac{1}{4}, \frac{1}{4})$ for integrations over the Brillouin zone [40]. Ionic relaxation of defects was performed until the forces were reduced to less than $5 \text{ meV/\AA}$, and spin polarization was included. Defect formation energies and thermodynamic charge-state transition levels were calculated by following the well-established formalism described in Refs. [41,42]. For example, the formation energy of Li_{Zn} is given by

$$E_{\text{f}}^q(\text{Li}_{\text{Zn}}) = E_{\text{tot}}^q(\text{Li}_{\text{Zn}}) - E_{\text{tot}}^{\text{bulk}} + \mu_{\text{Zn}} - \mu_{\text{Li}} + q\epsilon_{\text{F}}, \quad (1)$$

where $E_{\text{tot}}^q(\text{Li}_{\text{Zn}})$ and $E_{\text{tot}}^{\text{bulk}}$ denote the total energy of the defect-containing and bulk supercells, q is the charge state of the defect, μ_{Zn} and μ_{Li} are the chemical potentials of the removed Zn and added Li atom, and ϵ_{F} is the Fermi level position referenced to the bulk VBM. The chemical potential can vary between O-rich and Zn-rich conditions, where the upper limit of μ_{O} and μ_{Zn} is given by the total energy per atom of an O_2 molecule and metallic Zn, respectively, and the lower limit is governed by the thermodynamic stability condition $\Delta H^{\text{f}}(\text{ZnO}) = \mu_{\text{Zn}} + \mu_{\text{O}}$ [43], where $H^{\text{f}}(\text{ZnO})$ is the formation enthalpy of ZnO [44]. The chemical potential of impurities is similarly bound by the solubility-limiting phases, i.e., Al_2O_3 , Li_2O , Na_2O , and $\text{H}_2\text{O/H}_2$. We present calculated formation energies under intermediate conditions, i.e., halfway between O-rich and Zn-rich conditions, as the extreme limits are not usually reached under realistic growth conditions [45]. For charged defects we adopt the anisotropic [46] Freysoldt, Neugebauer, and Van de Walle (FNV) correction scheme [47].

Optical transition energies were calculated by using the effective one-dimensional (1D) configuration coordinate (CC) model described in Refs. [42,48–50]. Full luminescence lines were also calculated, including vibronic coupling, by using the methodology outlined in Ref. [48]. The effective 1D CC model is a good approximation for defects exhibiting strong electron-phonon coupling (large Huang-Rhys factor) [48,49], which is the case for all defects studied in the present work. The potential energy surfaces (PESs) in the CC diagrams were calculated by linearly interpolating the ground-state structures of the defect in the initial and final charge state, and computing the energy in the range -1.5 to $1.5 \times \Delta Q$ with steps of $0.1 \times \Delta Q$, where ΔQ is the difference in CC of the structures. We have calculated the vibrational wave functions χ and overlap integrals $\langle \chi_{em} | \chi_{gn} \rangle$, where m and n are the vibrational levels of the excited (e) and ground (g) state, from solutions of the Schrödinger equation for the calculated PESs by using a finite-difference method, as implemented in CarrierCapture.jl [51].

B. Experimental details

Two $5 \times 5 \times 0.5 \text{ mm}^3$ sized samples were cut from a wafer of HT grown ZnO purchased from the MTI Corporation (Richmond, CA). One sample was sealed in a quartz ampoule containing a piece of $\sim 99.9\%$ pure Zn foil, and annealed in a tube furnace at 900°C for 1 h.

A Cameca IMS7f secondary ion mass spectrometer equipped with a 10 keV O_2^+ primary ion beam source was used to measure concentration versus depth profiles of Li, Na, Al, Fe, and Cu impurities in the as-grown and thermally processed samples. Depth calibration was performed by measuring the

sputtered crater depths with a Dektak 8 stylus profilometer and assuming a constant erosion rate. Implanted reference samples were used to calibrate the impurity concentration, resulting in an uncertainty of less than 10% in concentration values.

Steady-state PL was excited using a cw He-Cd laser with a photon energy of 3.81 eV. The emission was collected by a microscope and directed to a fiberoptic spectrometer (HR4000 and USB4000 Ocean Optics). The sample was kept at a temperature of 10 K using a closed-cycle He refrigerator. The PL spectra were corrected for the spectral response of the measurement system. Because the annealing resulted in a build up of impurities at the sample surface (for depths $<3\ \mu\text{m}$), PL was excited inside the sputtered crater formed during the SIMS measurement. All presented impurity concentration values are for the bulk region (for depths $>3\ \mu\text{m}$).

III. RESULTS AND DISCUSSION

A. Formation energies, thermodynamic charge-state transition levels, and structures

Figure 1 shows the calculated formation energy of the acceptors (Li_{Zn} and Na_{Zn}), donors (Al_{Zn} , H_i , and H_O), and their complexes ($\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Li}_{\text{Zn}}\text{H}$, $\text{Li}_{\text{Zn}}\text{H}_\text{O}$, $\text{Na}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Na}_{\text{Zn}}\text{H}$, and $\text{Na}_{\text{Zn}}\text{H}_\text{O}$) as a function of the Fermi level position under intermediate conditions. Interestingly, the results obtained using HSE(0.375, 0.20) and HSE(0.30, 0.05) are very similar; thermodynamic charge-state transition levels differ by 50 meV at most, as shown in Table I.

The isolated donor impurities are shallow, contributing to the commonly observed unintentional n -type conductivity in ZnO [52–55]. For the isolated Li_{Zn} and Na_{Zn} acceptors, we find that both exhibit a dual behavior, as first reported by Lany and Zunger [27,28] using a Koopmans corrected semilocal functional, and later by Sun *et al.* [56] using the HSE(0.375,

FIG. 1. Formation energy of the donors, acceptors, and their complexes as a function of the Fermi level position relative to the VBM under intermediate conditions, calculated using the HSE(0.30, 0.05) and HSE(0.375, 0.20) functionals.

TABLE I. Fermi level position in eV of the thermodynamic charge-state transition levels with respect to the VBM for the isolated and donor-complexed acceptors, calculated using the HSE(0.30, 0.05) and HSE(0.375, 0.20) functionals.

Defect	Transition	HSE(0.375, 0.20)	HSE(0.30, 0.05)
Li_{Zn}	(0/−)	0.72	0.67
	(+/0)	0.04	0.02
$\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$	(+/0)	0.36	0.31
$\text{Li}_{\text{Zn}}\text{H}$	(+/0)	0.12	0.09
$\text{Li}_{\text{Zn}}\text{H}_\text{O}$	(+/0)	0.11	0.08
Na_{Zn}	(0/−)	0.71	0.68
$\text{Na}_{\text{Zn}}\text{Al}_{\text{Zn}}$	(+/0)	0.37	0.34
$\text{Na}_{\text{Zn}}\text{H}$	(+/0)	0.31	0.27
$\text{Na}_{\text{Zn}}\text{H}_\text{O}$	(+/0)	0.29	0.26

0.20) functional. In the negative charge state, the Li and Na atoms reside near the ideal Zn site with approximate tetrahedral local symmetry, and no localized defect states in the band gap [28]. In the neutral charge state, two distinct acceptor states can occur [27,28]: (i) a metastable shallow state, where the hole is bound in an anisotropically delocalized hostlike state [56], and (ii) a deep ground state, which can be reached through a sizable symmetry-breaking lattice distortion. As shown in Fig. 2, the hole is trapped in a polaronic state localized at one of the four O ions immediately adjacent to the Li^+ or Na^+ ion, in agreement with EPR spectroscopy data [2,12,21,57]. Note that, in the deep state, the Li^+ ion moves far away from the hole polaron, towards the tetrahedral interstitial site, whereas the larger Na^+ ion stays near the ideal Zn site. We shall focus on the deep polaronic state, as the shallow state is only metastable [27]. However, our results for the shallow state are in line with the previous reports [27,56].

As shown in Table I, the thermodynamic (0/−) transition levels of Li_{Zn} and Na_{Zn} occur between 0.67–0.72 eV above the VBM. This is consistent with previous calculations for the deep polaronic state [7,8,27,34,56,58,59], and the experimental ionization energy of 0.65 ± 0.10 eV for the OL band [19]. For Li_{Zn} , a second hole polaron can be stabilized at a separate adjacent O ion [34]. However, the resulting thermodynamic (+/0) level occurs merely 0.02–0.04 eV above the VBM, which is within the expected error bar of the finite-size correction [46].

Complexing Li_{Zn} or Na_{Zn} with a single donor results in a charge-compensated neutral pair. Contrary to common assumption, however, our calculations show that the complexes are not fully passivated, as they can be stabilized in the positive charge state for Fermi level positions close to the VBM, making them exceedingly deep donors. Figure 2 shows the relaxed structure of four representative complexes; the positive charge state corresponds to a hole polaron localized at an adjacent O ion, similar to the charge-neutral isolated acceptors. The resulting thermodynamic (+/0) transition levels are provided in Table I and occur between 0.08–0.37 eV above the VBM.

Interestingly, the complexes involving Al_{Zn} and H_i have very low formation energies (regardless of the chemical potential), which indicates that a sizable equilibrium

FIG. 2. Relaxed structure of Li_{Zn}^0 with the hole (blue isosurface, set at $6 \times 10^{-3} r_{\text{Bohr}}^{-3}$) trapped in a polaronic state at the axial O ion, Na_{Zn}^0 with the hole trapped at one of the three azimuthal O ions, and four complexes with H and Al_{Zn} donors.

concentration can be expected when these impurities are incorporated during growth. They are particularly likely to form under compensated growth conditions, i.e., when the Fermi level is pinned close to the crossing point between the formation energy of Li_{Zn} or Na_{Zn} and a donor impurity, as the calculated formation energy of the defect complex is then lower than that of both constituents [60]. HT grown ZnO samples are typically compensated, and so a large fraction of the Li_{Zn} and Na_{Zn} acceptors can be expected to be complexed with donor impurities [22]. The complexes involving H_O exhibit rather high formation energies under intermediate conditions. Under Zn-rich conditions, however, their formation energies (~ 0.6 eV) are comparable to the other complexes.

In order to assess the stability of the defect complexes, we have also calculated removal energies by taking the difference in formation energy between the defect complex and the two remaining entities (in their most stable configuration) when the donor impurity is removed (calculated using separate supercells for each defect). The sign is chosen such that a positive removal energy corresponds to a stable complex. All of the studied complexes are found to be stable, with removal energies of 0.52, 1.17, 1.01, 0.60, 1.08, and 1.09 eV for $\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Li}_{\text{Zn}}\text{H}$, $\text{Li}_{\text{Zn}}\text{H}_\text{O}$, $\text{Na}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Na}_{\text{Zn}}\text{H}$, and $\text{Na}_{\text{Zn}}\text{H}_\text{O}$, respectively.

For $\text{Li}_{\text{Zn}}\text{H}$ and $\text{Na}_{\text{Zn}}\text{H}$, we find that H prefers the bond-centered axial and antibonding azimuthal site, respectively, as shown in Fig. 2. This is consistent with IR absorption data [22] and previous local density functional calculations by Wardle *et al.* [6]. Investigations on the thermal stability of the $\text{Li}_{\text{Zn}}\text{H}$ complex via the IR absorption line at 3577 cm^{-1} has led to conflicting results in the literature [61–63]. In some samples, it starts to disappear at temperatures exceeding about 500°C , while in others it can withstand heat treatments up to around 1200°C [61–63]. The dissociation temperature for the $\text{Li}_{\text{Zn}}\text{H}$ complex can be estimated based on an activated process with a jump rate given by $\Gamma = \Gamma_0 \exp(-E_a/k_B T)$ [43,64]. Here the activation energy (E_a) is taken as the sum of the calculated removal energy of $\text{Li}_{\text{Zn}}\text{H}$ (1.17 eV) and the experimental migration barrier of H_i (0.85 ± 0.19 eV [65]). The attempt frequency (Γ_0) is set to a typical phonon frequency of 10 THz, and the jump rate at which dissociation starts to occur is assumed to be 1 Hz [64]. The resulting dissociation temperature is $510 \pm 75^\circ\text{C}$, consistent with the lower experimental temperature of 500°C . It has been suggested that an apparent stability up to 1200°C is due to retrapping of H_i^+ by Li_{Zn}^+ [61–63].

For $\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$ and $\text{Na}_{\text{Zn}}\text{Al}_{\text{Zn}}$, there are three symmetrically inequivalent configurations for the donor. Kutin *et al.* [23]

observed all three configurations of the analogous $\text{Li}_{\text{Zn}}\text{Fe}_{\text{Zn}}$ complex. We have explored configurations with the donor located on the opposite side from the hole polaron (Fig. 2). We have also explored the analogous complexes with Fe_{Zn} or Ga_{Zn} [66] replacing Al_{Zn} , but these were found to be almost identical in terms of removal energy and position of the (+/0) transition level. Al is also the most common of these impurities; the concentration of Al in as-grown ZnO usually varies between 10^{15} and 10^{17} cm^{-3} for different growth techniques [55]. For these reasons, we have presented results only for Al_{Zn} .

For $\text{Li}_{\text{Zn}}\text{H}_\text{O}$ and $\text{Na}_{\text{Zn}}\text{H}_\text{O}$, we find that the differences in energy between the axial and azimuthal H_O configurations are negligible. Hence, we present results for only the azimuthal configuration of H_O , as shown in Fig. 2.

B. Optical transitions and luminescence lines

We begin by examining the optical properties of the isolated Li_{Zn} and Na_{Zn} acceptors, and comparing the results with experimental data on the OL and YL bands. Figure 3 shows calculated CC diagrams for optical electron transitions between the CBM and the (0/−) transition levels of Li_{Zn} and Na_{Zn} . The vertical axis in the CC diagrams corresponds to the transition energy, and the horizontal axis corresponds to the configuration coordinate (Q) which is a 1D parametrization of the collective motion of all atoms in the supercell between the two different charge states [42,67]. The ground state PES represents the negatively charged acceptor, and the excited state PES represents the neutral acceptor plus an electron at the CBM. The two PESs are vertically displaced by the energy difference between the thermodynamic (0/−) transition level and the CBM, which is commonly referred to as the zero phonon line energy (E_{ZPL}). In the Franck-Condon approximation, optical transitions take place without atomic motion and are thus vertical in the CC diagrams, and the transition energies E_{em} and E_{abs} correspond approximately to the peak of the emission and absorption spectrum [42]. After emission, the defect will relax to its equilibrium atomic configuration, losing the Franck-Condon relaxation energy (d_{g}^{FC}).

The Li_{Zn} and Na_{Zn} acceptors exhibit similar polaronic defect states, and the positions of their thermodynamic (0/−) levels are close, but there are clear differences in their CC diagrams. Strikingly, the ground-state PES of Li_{Zn} is strongly anharmonic compared to Na_{Zn} [59], and the value of d_{g}^{FC} is about 0.2 eV larger for Li_{Zn} , while the CC diagram for Na_{Zn} calculated using HSE(0.375, 0.20) is similar to those calculated previously for V_{Zn} -related defects in ZnO [44,45,50].

FIG. 3. Top panels: CC diagrams for optical electron transitions between the CBM and the $(0/-)$ levels of LiZn and NaZn , calculated using HSE(0.375, 0.20) and HSE(0.30, 0.05). Bottom panel: Luminescence lines of LiZn and NaZn calculated for the HSE(0.30, 0.05) CC diagram using both the computed PES and harmonic approximation (the parabolas shown in the CC diagrams). Experimental data for the OL band from Refs. [14,19] is included for comparison. Experimental OL and YL band labels are positioned at their peak positions.

This difference is caused by the aforementioned large displacement of the Li^+ ion upon hole capture by the acceptor. The resulting difference in E_{em} for LiZn and NaZn (about 0.2 eV) is consistent with the difference in peak position of the experimental OL and YL bands (0.23 eV) [18,21]. Comparing the two different functionals, both the magnitude of the total mass-weighted distortion (ΔQ) and d_g^{FC} is lowered when using HSE(0.30, 0.05) compared to HSE(0.375, 0.20). Moreover, the differences in E_{em} are larger than those in E_{ZPL} .

The calculated E_{abs} values for LiZn (3.38–3.49 eV) are consistent with photo-EPR experiments by Nikitenko [68], where the absorption spectrum related to the optically induced EPR signal of LiZn was measured to peak at about 3.25 eV. When using the HSE(0.375, 0.20) functional, the calculated emission energies of LiZn (1.68 eV) and NaZn (1.89 eV) are

underestimated by about 0.3 eV relative to the peak positions of the experimentally observed OL (1.95 eV at 10 K [18]) and YL (2.18 eV at 50 K [21]) bands. When HSE(0.30, 0.05) is used, the calculated emission energies for LiZn (1.85 eV) and NaZn (2.06 eV) are both shifted up in energy by 0.17 eV. Thus, assuming that the OL and YL bands are indeed caused by electron transitions between the CBM and the $(0/-)$ levels of LiZn and NaZn , the HSE(0.30, 0.05) functional appears to provide the most accurate description of LiZn and NaZn . However, both approaches yield results that agree reasonably well with the experimental data.

Figure 3 also shows the luminescence lines calculated for the CC diagrams obtained using the HSE(0.30, 0.05) functional. When using HSE(0.375, 0.20), the line shapes are similar, but the peak positions are lower in energy. Experimental data is also included in Fig. 3; specifically, the thermoluminescence (TL) band reported by Zwingel [14], the Gaussian curve fit to the OL band in HT grown ZnO reported by McNamara *et al.* [19], and the Gaussian curve fit to the OL band observed in the annealed sample in the present work. In order to assess the impact of the anharmonic PES of LiZn on the line shape, the line shapes were calculated both for the computed PES and a parabola intersecting the relaxation energy (harmonic approximation). The calculated LiZn luminescence line peaks at 1.90 eV and has a full-width at half-maximum (FWHM) of 0.39 eV (0.43 eV for the harmonic line shape), which is lower than the experimental FWHM of about 0.5 eV for the OL band [14,18,19]. Optical transitions involving both axial and azimuthal hole configurations are likely to occur, since both are observed by EPR, which could broaden the overall line shape. However, we find that the azimuthal peak position is only 20 meV higher in energy than the axial one, and the line shapes are almost identical. The NaZn luminescence line associated with the azimuthal hole configuration peaks at 2.11 eV and has a FWHM of 0.36 eV (0.38 eV for the harmonic line shape), whereas the axial one peaks 40 meV higher in energy with a similar line shape. This is in better agreement with experimental data; Zwingel and Gärtner [21] reported a FWHM of 0.4 eV for the YL band at 50 K (TL), but no spectrum was shown.

The emergence of $(+/-0)$ transition levels for the defect complexes has important consequences for their optical properties, as they can potentially give rise to broad luminescence bands. In fact, similar predictions have been made to explain the luminescence bands related to isolated and donor-complexed C_N acceptors in GaN [69–72].

Calculated CC diagrams for optical transitions involving the CBM and the $(+/-0)$ transition level of the complexes are shown in Fig. 4. The emission energies of the complexes are blueshifted with respect to those of the isolated acceptors, which makes the complexes candidates for the defect origin of the broad GL in HT grown ZnO. Interestingly, LiZnAl_Zn and LiZnH_O retain the anharmonicity exhibited by LiZn for the ground-state PES, while LiZnH does not. This can be understood from the structure of the LiZnH complex. The H atom pins the Li^+ ion near the tetrahedral interstitial site (see Fig. 2), and thus Li^+ does not undergo the large displacement along the direction of the axial Li-O bond upon hole capture. Figure 4 shows the calculated luminescence lines for the complexes. Their FWHM values are about 0.37 eV (except for the

FIG. 4. Top panels: CC diagrams for optical electron transitions between the CBM and the $(+ / 0)$ transition level of donor-complexed LiZn and NaZn acceptors, calculated using HSE(0.30, 0.05). The corresponding values of E_{abs} , E_{ZPL} , E_{em} , and ΔQ calculated using HSE(0.375, 0.20) are given in parentheses. Bottom panel: Corresponding luminescence lines of LiZnAlZn , LiZnH , LiZnHo , NaZnAlZn , NaZnH , and LiZnHo .

LiZnHo line which has a FWHM of 0.42 eV). These values are similar to those obtained for the isolated acceptors, which is reasonable because the charge-state transitions occur through the same type of polaronic state with similar magnitudes of ΔQ .

Since all the calculated luminescence lines have similar shapes and peak positions, distinguishing them experimen-

tally could be challenging, especially for the different complexes. It might be possible to discern between isolated and donor-complexed acceptors based on other band characteristics, e.g., carrier capture coefficients, lifetime, and temperature dependence. However, it should be noted that, since the broad luminescence band observed in HT grown ZnO consists of several overlapping bands, obtaining accurate and reliable data for these other band characteristics is also challenging. Thus, a detailed comparison between PL measurements and theory for these properties is beyond the scope of the present work. Qualitatively, however, some differences could be expected between the isolated and donor-complexed acceptors. Indeed, the $(+ / 0)$ levels of the complexes are positioned very close to the VBM, which means that luminescence bands related to the complexes should exhibit lower activation energies of thermal quenching. This is consistent with the GL2 band in HT ZnO reported by Reshchikov *et al.* [18], where GL2 starts to quench at 40 K with a low activation energy of 35 meV.

Furthermore, the OL band in ZnO is characterized by a large hole capture coefficient [72,73]; in the limit of low excitation intensity, the OL band dominates the PL spectrum from HT grown ZnO [29,74]. This is due to the low barrier for nonradiative hole capture by LiZn^- , and its attractive Coulomb interaction with photogenerated holes [59,72]. The subsequent radiative electron capture, however, is slow because LiZn^0 is charge neutral in the excited state [18,29,72]. For transitions involving the $(+ / 0)$ levels of the complexes, however, an opposite behavior can be anticipated [72]. Since the defect complexes are initially charge neutral, they will capture photogenerated holes slowly compared to isolated acceptors [59,72]. The subsequent radiative electron capture, however, will take place rapidly as now the complexes are positively charged. The positively charged complexes will also have a hydrogenic effective-mass state very close to the CBM, which could behave as a so-called giant trap for nonradiative electron capture [71,72,75]. This is consistent with the GL2 band, which exhibits fast and exponential decay after pulse excitation [18], while the OL band exhibits slow and nonexponential decay [29,75].

Finally, Demchenko *et al.* [71,72] have suggested that the $\text{C}_\text{N}\text{H}$ complex in GaN gives rise to a broad BL band, which, upon ultraviolet light exposure, gradually dissociates and leaves behind a broad YL band (C_N) [71,72]. The calculated removal energy for $\text{C}_\text{N}\text{H}$ in Ref. [71] is similar to the ones we obtain for the LiZnH and NaZnH complexes, and the H configuration is the same as the one we obtain for NaZnH . Hence, the luminescence bands originating from LiZnH and NaZnH complexes might also bleach under prolonged ultraviolet light exposure. Indeed, a similar GL band has been observed in melt-grown ZnO, which bleached and gave way to a YL band [76].

C. Experimental PL and SIMS results

Figure 5 shows PL spectra of the as-grown and annealed HT grown ZnO samples. Here we will focus mainly on the broad luminescence band that extends from about 1.5 to 2.9 eV. We find that the temperature and excitation power dependence of this band in the as-grown sample is similar

FIG. 5. Normalized PL spectrum (divided by excitation power) of (a) the as-grown and annealed ZnO samples, and (b) deep level emission of the annealed sample with high and low excitation power density. The dashed line is a Gaussian curve fit peaking at 1.89 eV with a FWHM of 0.47 eV. (c) Near band edge emission of the as-grown and annealed samples. Free and donor-bound exciton lines are indicated (labels and energy positions are taken from Refs. [9,77]), and those that are discussed in the text have been highlighted.

to what has been described in detail previously for several HT grown ZnO samples by Reshchikov *et al.* [18,29,73] and McNamara *et al.* [19]. As already mentioned, the OL band (Li_{Zn}) dominates in the limit of low excitation power (see, e.g., Fig. 3 in Ref. [74]). As the excitation power is increased, the band maximum gradually shifts up in energy, i.e., the OL saturates and the GL grows [29]. In Fig. 5 the overall band maximum is at about 2.3 eV for the as-grown sample.

The concentration of Li_{Zn} -related defects can be lowered significantly via thermal processing in reducing (Zn-vapor) atmosphere, as in-diffusing Zn_i can convert immobile Li_{Zn} acceptors into highly mobile Li_i donors [3,7,78–80]. Thus, if donor-complexed Li_{Zn} acceptors are responsible for the broad GL at the high energy side of the OL band, then the entire broad luminescence band should be strongly suppressed following such thermal treatment.

Table II lists the bulk concentration of Li, Na, and Al impurities in the as-grown and annealed ZnO samples. Annealing in Zn ambient causes the Li concentration to drop from 2×10^{17} to 2×10^{14} cm $^{-3}$, while the concentration of

Na and Al remains unchanged. Al is the dominant donor impurity, whereas the concentration of Fe and Si is below the respective SIMS detection limits for these elements. H is likely present as well, albeit with a concentration below the SIMS detection limit of $\sim 5 \times 10^{17}$ cm $^{-3}$. The concentration of Cu is below the SIMS detection limit in both samples, which is important because the Cu_{Zn} acceptor in ZnO has been assigned to a structured GL band peaking at 2.45 eV [74,81,82] that can interfere with the analysis of overlapping bands. We did not observe this structured GL band in the PL spectrum of the as-grown or annealed samples.

As shown in Fig. 5(a), annealing the sample in Zn ambient causes a dramatic decrease in the intensity of the entire broad luminescence band. This suggests that Li is involved not only in the OL band, but also in the GL at its high energy side. Indeed, the SIMS results show a strong depletion of Li, while the concentration of other impurities is unaffected. The remaining broad luminescence appears to consist of two main bands. As shown in Fig. 5(b), the lower energy band dominates when the excitation power is lowered, similar to the as-grown sample, which may indicate that this is the OL band. The low energy band can be fitted to a Gaussian with a peak position of 1.89 eV and FWHM of 0.47 eV, which is close to the values for the OL band [19].

It should be noted that the SIMS data does not provide any information about the configuration of the impurities, e.g., the fraction of isolated to complexed Li_{Zn} and Na_{Zn} acceptors. Furthermore, the present experimental results cannot rule out intrinsic defects. As an example, the GL could be caused by V_{Zn} -donor complexes [50], the concentration of which would also drop following heat treatment in Zn ambient. However, the concentration of Li is expected to be higher than that of V_{Zn} -related defects in as-grown HT ZnO [83]. In addition, previous hybrid functional calculations show that the only V_{Zn} -donor complexes that can give rise to GL bands are positively charged in the ground state [50], which means that capture of photogenerated holes will be very inefficient compared to the Li_{Zn} -related defects studied here. Finally, the GL1 and GL2 bands were observed exclusively in HT grown ZnO [18,29], which favors extrinsic Li- over intrinsic V_{Zn} -related defects.

Removal of Li from Li_{Zn} -donor complexes upon annealing is also evidenced by changes in the intensity of neutral donor-bound exciton (D_0X) lines in the PL spectrum. Figure 5(c) shows the near band edge emission in the as-grown and annealed samples, with exciton lines indicated. The labels and energies of the exciton lines were taken from Refs. [9,77]. The D_0X line associated with H_0 (I_4) is commonly observed in ZnO [84], but is absent in the as-grown sample. This is consistent with the recent study by Heinhold *et al.* [77], where the I_4 line was replaced by two closely lying D_0X lines labeled $I_{4b,c}$ in HT grown ZnO. These lines were observed exclusively in HT grown ZnO, and were therefore assigned to donors involving the $Li_{Zn}H_0$ complex plus an additional donor (possibly $Li_{Zn}H-H_0$). We also observe the $I_{4b,c}$ lines in the as-grown sample (albeit as a single peak due to a lower resolution). After lowering the Li concentration via annealing, the $I_{4b,c}$ line disappears while I_4 appears, supporting the assignment by Heinhold *et al.* [77], i.e., indiffusing Zn_i converts $Li_{Zn}H_0$ into H_0 . Similarly, the I_{10} line is present only in

TABLE II. Bulk concentration of impurities in the as-grown and annealed samples determined using SIMS. The concentration of Fe, Si, and Cu is below the detection limit.

Element	As-grown (cm $^{-3}$)	Annealed (cm $^{-3}$)
Li	2×10^{17}	2×10^{14}
Na	2×10^{15}	2×10^{15}
Al	8×10^{16}	8×10^{16}

the as-grown sample. Isotope substitution experiments have demonstrated that I_{10} is related to Sn, and a $\text{Sn}_{\text{Zn}}\text{Li}_{\text{Zn}}$ complex has been suggested [85]. This assignment is supported by the present results, as the I_{10} line disappears after annealing.

Finally, a line labeled I^* appears at 3.3545 eV after annealing the sample. To our knowledge, there is no defect assignment for this line in the literature. If the responsible defect is a donor, its donor binding energy (E_{D}) can be estimated from the localization energy (E_{loc}) with reference to the transverse free-exciton ($A_{\text{T}} = 3.3754$ eV) by using Haynes rule [86] with coefficients from Ref. [77], i.e., $E_{\text{loc}} = 0.34E_{\text{D}} - 2.71$ meV. The resulting donor binding energy is 69.4 meV. If I^* is of D_0X nature, one would expect to observe a two-electron satellite signature in the spectral range 3.3024–3.3036 eV [9], but no such signature was observed in this region. However, this does not necessarily disprove a D_0X origin. A neutral acceptor-bound exciton (A_0X) origin has also been suggested for lines observed in this region [9,25,87]. Using Haynes rule for acceptors [88–90], the estimated acceptor binding energy would then be in the range 140–210 meV.

IV. CONCLUSION

Using hybrid functional calculations, we have investigated Li_{Zn} and Na_{Zn} acceptors, and their complexes with common shallow donor impurities Al_{Zn} and H_{i} in ZnO . The complexes have low formation energies, regardless of the chemical potential, which means that a sizable equilibrium concentration can be expected when these impurities are incorporated during materials growth, especially under highly compensated growth conditions.

Interestingly, our calculations show that the $\text{Li}_{\text{Zn}}\text{Al}_{\text{Zn}}$, $\text{Li}_{\text{Zn}}\text{H}$, $\text{Na}_{\text{Zn}}\text{Al}_{\text{Zn}}$, and $\text{Na}_{\text{Zn}}\text{H}$ complexes can be stabilized in the positive charge state, resulting in thermodynamic $(+ / 0)$ transition levels located between 90–370 meV above the VBM. By employing an effective 1D CC model, we predict that these complexes can give rise to broad luminescence bands peaking at the high energy side of the OL (Li_{Zn}) [18] and YL (Na_{Zn}) [21] bands. Since the luminescence bands are similar in shape and position, careful analysis of PL data will be crucial in order to pinpoint specific defects. The overall picture is similar to what has been found previously for the C_{N} acceptor and its complexes with donors in GaN [69–72].

Following heat treatment in Zn ambient, the concentration of Li in HT grown ZnO is lowered by about three orders of magnitude, while the concentration of Na and Al remains basically unchanged. The change in Li concentration is accompanied by a strong reduction in intensity of the entire broad luminescence band, which may suggest that Li is involved not only in the OL band, but also in the broad GL at its high energy side, with donor-complexed Li_{Zn} and Na_{Zn} as a potential origin. However, further work is required in order to verify this hypothesis.

ACKNOWLEDGMENTS

Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (No. 251131, FriPro ToppForsk-program), and the Norwegian Micro- and Nano-

TABLE III. Calculated non-Koopmans energies in eV for the $(0/-)$ transition of polaronic acceptors V_{Zn} , Li_{Zn} , and Na_{Zn} , and the $(+ / 0)$ transition of H_{i} at the octahedral site.

Defect	Transition	E_{NK} (eV)	
		HSE(0.375, 0.20)	HSE(0.30, 0.05)
V_{Zn}	$(0/-)$	0.08	−0.01
Li_{Zn}	$(0/-)$	0.06	0.01
Na_{Zn}	$(0/-)$	0.07	0.00
H_{i}	$(+ / 0)$	0.27	0.07

Fabrication Facility NorFab (No. 245963). The computations were performed on resources provided by UNINETT Sigma2—the National Infrastructure for High Performance Computing and Data Storage in Norway.

APPENDIX

Here we discuss the gKT fitting procedure and the supercell-size dependence of gKT related quantities. The gKT is an exact physical constraint by which the total energy shows a piecewise linear dependence upon addition of electrons, and implies that the single-particle energy level does not shift upon occupation [34,35,91]. To determine whether the gKT is fulfilled, we have used the $(0/-)$ transition of the unrelaxed V_{Zn} and calculated the so-called non-Koopmans energy, which is given by [34]

$$E_{\text{NK}} = E_{\text{add}} - \varepsilon(N). \quad (\text{A1})$$

Here $\varepsilon(N)$ is the KS eigenvalue of the defect state in the neutral charge state (N -electron system), and $E_{\text{add}} = E(N+1) - E(N)$ is the electron addition energy, i.e., the total en-

FIG. 6. Dependence of corrected and uncorrected gKT quantities on supercell size for the $(0/-)$ transition of the unrelaxed V_{Zn} in ZnO using the GGA-PBE+ U functional, where an effective U value of 5 eV was applied to the Zn $3d$ orbitals, and 8 eV to the O $2p$ orbitals of the four O atoms associated with V_{Zn} . A Γ -only k -point sampling was used for all supercells. N_{atom} is the number of atoms in the supercell. The energy is given relative to the $\varepsilon(N)$ value of the largest supercell. The dashed lines are fits of the uncorrected values to a function of the form $aN_{\text{atom}}^{-1} + bN_{\text{atom}}^{-1/3} + c$, and the solid lines correspond to the value obtained for the largest supercell.

FIG. 7. Dependence of corrected and uncorrected gKT quantities on supercell size for the $(0/-)$ transition of the unrelaxed V_{Zn} in ZnO using HSE(0.30, 0.05) and HSE(0.375, 0.20).

ergy difference between the N - and $(N + 1)$ -electron systems, keeping the atoms fixed. The finite-size correction [46,47] for charged defects was applied to the terms pertaining to the negatively charged supercell, namely $E(N + 1)$ and $\epsilon(N + 1)$, using the ion-clamped dielectric tensor. For KS eigenvalues, the correction is given by the relation $\epsilon_c = -2E_c/q$ [92], where q is the charge state and E_c is the total energy correction. When $E_{NK} = 0$, the gKT is fulfilled as $e_N = E_{add} = e_{N+1}$, i.e., the KS eigenvalue does not shift upon occupation.

The test was carried out by using a 300-atom supercell and a Γ -only k -point sampling, which is the largest supercell we could afford. For each set of α and μ parameters tested, the bulk lattice parameters were optimized, and the ion-clamped dielectric tensor calculated from the self-consistent response of the system to a finite electric field [93]. As shown in Table III, we obtain $E_{NK} = 0.08$ eV for the $(0/-)$ transition of V_{Zn} when using the HSE(0.375, 0.20) functional, which means that the defect KS eigenvalue shifts upward in energy upon electron addition. By systematically changing the μ and α parameters and calculating E_{NK} , we find that the HSE(0.30,

0.05) functional both satisfies the gKT for V_{Zn} and reproduces the experimental band gap.

We have calculated E_{NK} also for the $(0/-)$ transitions of Li_{Zn} and Na_{Zn} , and the $(+ / 0)$ transition of H_i with the H atom at the octahedral interstitial site [35]. For Li_{Zn} and Na_{Zn} , however, there is a caveat, because the acceptor state is delocalized when the Li/Na atom is placed at the ideal Zn site, making it unsuitable for gKT testing [35,36]. Instead, we have shifted the Li/Na atom to the O basal plane. This results in a well-localized defect state for both charge states, similar to the defect states shown in Fig. 2. The resulting E_{NK} values for Li_{Zn} and Na_{Zn} are consistent with those obtained for V_{Zn} in Table III, and the HSE(0.30, 0.05) functional satisfies the gKT approximately. For H_i , the calculated E_{NK} is larger and seems to be more sensitive to the α and μ parameters. This result is in line with the trend observed by Miceli *et al.* [35]. The reason for the discrepancy could be due to the different character of the H_i defect state, or a larger remaining finite-size error. The latter can be expected due to the more extended nature of the H_i defect state. In any case, the HSE(0.30, 0.05) functional is found to satisfy the gKT for polaronic O $2p$ -like states, which is the type of defect state investigated in the present work.

Although we have not explored the entire α and ω parameter space, we find that other sets of parameters that comply with the gKT tend to produce similar band gap values, in line with results reported by Miceli *et al.* [35]. For instance, HSE(0.40, 0.20) results in $E_{NK} = -0.01$ eV for V_{Zn} and a band gap of 3.58 eV.

Finally, to investigate the supercell-size dependence of the calculated gKT quantities for V_{Zn} , we have performed a test using the PBE-GGA+ U functional. As shown in Fig. 6, the KS defect state shifts up after electron addition, and E_{add} is located at an average between $\epsilon(N)$ and $\epsilon(N + 1)$ [36]. E_{NK} in the 300-atom supercell is within 13 meV of the value calculated for the largest 980-atom supercell, and, as indicated by the solid and dashed lines in Fig. 6, the terms pertaining to the singly negatively charged supercell are well corrected by the FNV scheme. The supercell-size dependence was also investigated up to the 300-atom supercell using the HSE(0.30, 0.05) and HSE(0.375, 0.20) functionals, as shown in Fig. 7. When using the HSE functionals, E_{NK} converges even faster.

[1] J. Lander, *J. Phys. Chem. Solids*, **15**, 324 (1960).
[2] J. Schneider and O. Schirmer, *Z. Naturforsch. Teil A* **18**, 20 (1963).
[3] P. T. Neuvonen, L. Vines, A. Y. Kuznetsov, B. G. Svensson, X. Du, F. Tuomisto, and A. Hallén, *Appl. Phys. Lett.* **95**, 242111 (2009).
[4] C. H. Park, S. B. Zhang, and S.-H. Wei, *Phys. Rev. B* **66**, 073202 (2002).
[5] S. B. Orlinskii, J. Schmidt, P. G. Baranov, D. M. Hofmann, C. de Mello Donegá, and A. Meijerink, *Phys. Rev. Lett.* **92**, 047603 (2004).
[6] M. G. Wardle, J. P. Goss, and P. R. Briddon, *Phys. Rev. B* **71**, 155205 (2005).

[7] A. Carvalho, A. Alkauskas, A. Pasquarello, A. K. Tagantsev, and N. Setter, *Phys. Rev. B* **80**, 195205 (2009).
[8] T. S. Bjørheim, S. Erdal, K. M. Johansen, K. E. Knutsen, and T. Norby, *J. Phys. Chem. C* **116**, 23764 (2012).
[9] B. K. Meyer, H. Alves, D. M. Hofmann, W. Kriegseis, D. Forster, F. Bertram, J. Christen, A. Hoffmann, M. Straßburg, M. Dworak, U. Haboeck, and A. V. Rodina, *Phys. Status Solidi B* **241**, 231 (2004).
[10] M. D. McCluskey, C. D. Corolewski, J. Lv, M. C. Tarun, S. T. Teklemichael, E. D. Walter, M. G. Norton, K. W. Harrison, and S. Ha, *J. Appl. Phys.* **117**, 112802 (2015).
[11] P. H. Kasai, *Phys. Rev.* **130**, 989 (1963).
[12] O. Schirmer, *J. Phys. Chem. Solids* **29**, 1407 (1968).

- [13] O. Schirmer and D. Zwingel, *Solid State Commun.* **8**, 1559 (1970).
- [14] D. Zwingel, *J. Lumin.* **5**, 385 (1972).
- [15] R. Cox, D. Block, A. Hervé, R. Picard, C. Santier, and R. Helbig, *Solid State Commun.* **25**, 77 (1978).
- [16] R. Laiho, L. S. Vlasenko, and M. P. Vlasenko, *J. Appl. Phys.* **103**, 123709 (2008).
- [17] M. A. Reshchikov, J. Garbus, G. Lopez, M. Ruchala, B. Nemeth, and J. Nause, *Mater. Res. Soc. Symp. Proc.* **957**, K07-19 (2006).
- [18] M. Reshchikov, H. Morkoç, B. Nemeth, J. Nause, J. Xie, B. Hertog, and A. Osinsky, *Phys. B Condens. Matter* **401–402**, 358 (2007).
- [19] J. McNamara, N. Albarakati, and M. Reshchikov, *J. Lumin.* **178**, 301 (2016).
- [20] L. Vines, E. V. Monakhov, R. Schifano, W. Mtangi, F. D. Aurret, and B. G. Svensson, *J. Appl. Phys.* **107**, 103707 (2010).
- [21] D. Zwingel and F. Gärtner, *Solid State Commun.* **14**, 45 (1974).
- [22] L. E. Halliburton, L. Wang, L. Bai, N. Y. Garces, N. C. Giles, M. J. Callahan, and B. Wang, *J. Appl. Phys.* **96**, 7168 (2004).
- [23] Y. Kutin, G. Mamin, and S. Orlinskii, *J. Magn. Reson.* **237**, 110 (2013).
- [24] J. Sann, A. Hofstaetter, D. Pfisterer, J. Stehr, and B. K. Meyer, *Phys. Status Solidi C* **3**, 952 (2006).
- [25] B. K. Meyer, J. Stehr, A. Hofstaetter, N. Volbers, A. Zeuner, and J. Sann, *Appl. Phys. A* **88**, 119 (2007).
- [26] Z. Zhang, K. E. Knutsen, T. Merz, A. Y. Kuznetsov, B. G. Svensson, and L. J. Brillson, *Appl. Phys. Lett.* **100**, 042107 (2012).
- [27] S. Lany and A. Zunger, *Appl. Phys. Lett.* **96**, 142114 (2010).
- [28] S. Lany, *Phys. Status Solidi B* **248**, 1052 (2011).
- [29] M. A. Reshchikov, *Mater. Res. Soc. Symp. Proc.* **1035**, 1035 (2007).
- [30] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- [31] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- [32] A. V. Krukau, O. A. Vydrov, A. F. Izmaylov, and G. E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).
- [33] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [34] S. Lany and A. Zunger, *Phys. Rev. B* **80**, 085202 (2009).
- [35] G. Miceli, W. Chen, I. Reshetnyak, and A. Pasquarello, *Phys. Rev. B* **97**, 121112(R) (2018).
- [36] D. O. Demchenko, I. C. Diallo, and M. A. Reshchikov, *Phys. Rev. B* **97**, 205205 (2018).
- [37] P. Deák, M. Lorke, B. Aradi, and T. Frauenheim, *Phys. Rev. B* **99**, 085206 (2019).
- [38] F. Oba, A. Togo, I. Tanaka, J. Paier, and G. Kresse, *Phys. Rev. B* **77**, 245202 (2008).
- [39] D. C. Reynolds, D. C. Look, B. Jogai, C. W. Litton, G. Cantwell, and W. C. Harsch, *Phys. Rev. B* **60**, 2340 (1999).
- [40] A. Baldereschi, *Phys. Rev. B* **7**, 5212 (1973).
- [41] S. B. Zhang and J. E. Northrup, *Phys. Rev. Lett.* **67**, 2339 (1991).
- [42] C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
- [43] A. Janotti and C. G. Van de Walle, *Phys. Rev. B* **76**, 165202 (2007).
- [44] Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **95**, 094105 (2017).
- [45] J. L. Lyons, J. B. Varley, D. Steiauf, A. Janotti, and C. G. Van de Walle, *J. Appl. Phys.* **122**, 035704 (2017).
- [46] Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
- [47] C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
- [48] A. Alkauskas, J. L. Lyons, D. Steiauf, and C. G. Van de Walle, *Phys. Rev. Lett.* **109**, 267401 (2012).
- [49] A. Alkauskas, M. D. McCluskey, and C. G. Van de Walle, *J. Appl. Phys.* **119**, 181101 (2016).
- [50] Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **97**, 104109 (2018).
- [51] S. Kim, S. N. Hood, and A. Walsh, *Wmdgroup/carriercapture.jl: Carriercapture.jl*, 2019.
- [52] C. G. Van de Walle, *Phys. Rev. Lett.* **85**, 1012 (2000).
- [53] M. McCluskey and S. Jokela, *Phys. B Condens. Matter* **401**, 355 (2007).
- [54] A. Janotti and C. G. Van de Walle, *Rep. Prog. Phys.* **72**, 126501 (2009).
- [55] L. Vines and A. Kuznetsov, *Semicond. Semimet.* **88**, 67 (2013).
- [56] Y. Y. Sun, T. A. Abtew, P. Zhang, and S. B. Zhang, *Phys. Rev. B* **90**, 165301 (2014).
- [57] B. K. Meyer, A. Hofstaetter, and V. V. Laguta, *Phys. B Condens. Matter* **376–377**, 682 (2006).
- [58] M.-H. Du and S. B. Zhang, *Phys. Rev. B* **80**, 115217 (2009).
- [59] A. Alkauskas, Q. Yan, and C. G. Van de Walle, *Phys. Rev. B* **90**, 075202 (2014).
- [60] C. G. Van de Walle and J. Neugebauer, *J. Appl. Phys.* **95**, 3851 (2004).
- [61] E. V. Lavrov, F. Börrnert, and J. Weber, *Phys. Rev. B* **71**, 035205 (2005).
- [62] K. M. Johansen, H. Haug, E. Lund, E. V. Monakhov, and B. G. Svensson, *Appl. Phys. Lett.* **97**, 211907 (2010).
- [63] F. Herklotz, K. M. Johansen, A. Galeckas, T. N. Sky, and B. G. Svensson, *Phys. Status Solidi B* **253**, 273 (2015).
- [64] D. Steiauf, J. L. Lyons, A. Janotti, and C. G. Van de Walle, *APL Mater.* **2**, 096101 (2014).
- [65] K. M. Johansen, J. S. Christensen, E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *Appl. Phys. Lett.* **93**, 152109 (2008).
- [66] T. N. Sky, K. M. Johansen, Y. K. Frodason, B. G. Svensson, and L. Vines, *J. Appl. Phys.* **124**, 245702 (2018).
- [67] C. E. Dreyer, A. Alkauskas, J. L. Lyons, A. Janotti, and C. G. Van de Walle, *Annu. Rev. Mater. Sci.* **48**, 1 (2018).
- [68] V. A. Nikitenko, *J. Appl. Spectrosc.* **57**, 783 (1992).
- [69] D. O. Demchenko, I. C. Diallo, and M. A. Reshchikov, *Phys. Rev. Lett.* **110**, 087404 (2013).
- [70] S. G. Christenson, W. Xie, Y. Y. Sun, and S. B. Zhang, *J. Appl. Phys.* **118**, 135708 (2015).
- [71] D. O. Demchenko, I. C. Diallo, and M. A. Reshchikov, *J. Appl. Phys.* **119**, 035702 (2016).
- [72] M. A. Reshchikov, M. Vorobiov, D. O. Demchenko, U. Özgür, H. Morkoç, A. Lesnik, M. P. Hoffmann, F. Hönig, A. Dadgar, and A. Strittmatter, *Phys. Rev. B* **98**, 125207 (2018).
- [73] M. A. Reshchikov, *AIP Conf. Proc.* **1583**, 127 (2014).
- [74] M. A. Reshchikov, V. Avrutin, N. Izyumskaya, R. Shimada, H. Morkoç, and S. W. Novak, *J. Vac. Sci. Technol. B* **27**, 1749 (2009).
- [75] M. A. Reshchikov, J. D. McNamara, A. Usikov, H. Helava, and Y. Makarov, *Phys. Rev. B* **93**, 081202(R) (2016).

- [76] M. Reshchikov, Y. Moon, X. Gu, B. Nemeth, J. Nause, and H. Morkoç, *Phys. B Condens. Matter* **376–377**, 715 (2006).
- [77] R. Heinhold, A. Neiman, J. V. Kennedy, A. Markwitz, R. J. Reeves, and M. W. Allen, *Phys. Rev. B* **95**, 054120 (2017).
- [78] K. E. Knutsen, K. M. Johansen, P. T. Neuvonen, B. G. Svensson, and A. Y. Kuznetsov, *J. Appl. Phys.* **113**, 023702 (2013).
- [79] P. T. Neuvonen, L. Vines, B. G. Svensson, and A. Y. Kuznetsov, *Phys. Rev. Lett.* **110**, 015501 (2013).
- [80] A. Y. Azarov, K. E. Knutsen, P. T. Neuvonen, L. Vines, B. G. Svensson, and A. Y. Kuznetsov, *Phys. Rev. Lett.* **110**, 175503 (2013).
- [81] R. Dingle, *Phys. Rev. Lett.* **23**, 579 (1969).
- [82] D. Byrne, F. Herklotz, M. O. Henry, and E. McGlynn, *J. Phys. Condens. Matter* **24**, 215802 (2012).
- [83] K. M. Johansen, A. Zubiaga, I. Makkonen, F. Tuomisto, P. T. Neuvonen, K. E. Knutsen, E. V. Monakhov, A. Y. Kuznetsov, and B. G. Svensson, *Phys. Rev. B* **83**, 245208 (2011).
- [84] E. V. Lavrov, F. Herklotz, and J. Weber, *Phys. Rev. B* **79**, 165210 (2009).
- [85] J. Cullen, D. Byrne, K. Johnston, E. McGlynn, and M. O. Henry, *Appl. Phys. Lett.* **102**, 192110 (2013).
- [86] J. R. Haynes, *Phys. Rev. Lett.* **4**, 361 (1960).
- [87] K. Tang, R. Gu, S. Zhu, Z. Xu, Y. Shen, J. Ye, and S. Gu, *Opt. Mater. Express* **7**, 1169 (2017).
- [88] H. Atzmüller, F. Fröschl, and U. Schröder, *Phys. Rev. B* **19**, 3118 (1979).
- [89] D. Pan, *Solid State Commun.* **37**, 375 (1981).
- [90] B. K. Meyer, J. Sann, S. Lautenschläger, M. R. Wagner, and A. Hoffmann, *Phys. Rev. B* **76**, 184120 (2007).
- [91] J. F. Janak, *Phys. Rev. B* **18**, 7165 (1978).
- [92] W. Chen and A. Pasquarello, *Phys. Rev. B* **88**, 115104 (2013).
- [93] I. Souza, J. Íñiguez, and D. Vanderbilt, *Phys. Rev. Lett.* **89**, 117602 (2002).

Paper V

Self-trapped hole and impurity-related broad luminescence in β -Ga₂O₃

Y. K. Frodason, K. M. Johansen, L. Vines, J. B. Varley

Published in *Journal of Applied Physics*, February 2020, volume 127, issue 7, pp. 075–701. DOI: 10.1063/1.5140742.

V

Self-trapped hole and impurity-related broad luminescence in β -Ga₂O₃

Cite as: J. Appl. Phys. 127, 075701 (2020); doi: 10.1063/1.5140742

Submitted: 30 November 2019 · Accepted: 2 February 2020 ·

Published Online: 18 February 2020

Y. K. Frodason,^{1,a)} K. M. Johansen,¹ L. Vines,¹ and J. B. Varley²

AFFILIATIONS

¹Department of Physics/Centre for Materials Science and Nanotechnology, University of Oslo, N-0318 Oslo, Norway

²Lawrence Livermore National Laboratory, Livermore, California 94550, USA

Note: This paper is part of the Special Topic on Defects in Semiconductors 2020.

a) Author to whom correspondence should be addressed: ymirkf@fys.uio.no

ABSTRACT

This work explores the luminescence properties of self-trapped holes and impurity-related acceptors using one-dimensional configuration coordinate diagrams derived from hybrid functional calculations. The photoluminescence spectrum of as-grown β -Ga₂O₃ typically consists of a broad band in the wavelength region from ultraviolet to green and is often dominated by an impurity independent ultraviolet band that is commonly attributed to self-trapped holes. Here, we use the self-trapped hole as a benchmark to evaluate the accuracy of the theoretical defect luminescence spectra and estimate the optical properties of Mg_{Ga}, Be_{Ga}, Ca_{Ga}, Cd_{Ga}, Zn_{Ga}, Li_{Ga}, and N_O acceptor impurities, as well as their complexes with hydrogen donors. We also explore V_{Ga} acceptors complexed with hydrogen and Si_{Ga} donor impurities. The results show that these defects can give rise to broad luminescence bands peaking in the infrared to visible part of the spectrum, making them potential candidates for the defect origin of broad luminescence bands in β -Ga₂O₃.

Published under license by AIP Publishing. <https://doi.org/10.1063/1.5140742>

I. INTRODUCTION

The monoclinic phase of gallium oxide (β -Ga₂O₃) has drawn considerable attention in recent years. Its unique optical and electrical properties, including a wide bandgap (~ 4.9 eV) and a high breakdown field (~ 8 MV/cm), make it a promising material for applications in, e.g., high-power electronics and UV sensors.¹ This technological development will require a good understanding of the defect structure of β -Ga₂O₃, including native defects, impurities, and complexes thereof. To this avail, spectroscopic identification of the ruling defects,^{2,3} e.g., by using photoluminescence (PL) spectroscopy, is essential.

The luminescence spectrum of β -Ga₂O₃ does not exhibit near band-edge emission (NBE), but often consists of several broad luminescence bands in the spectral range between 2.3 and 4.5 eV,¹ which are typically divided into three main spectral components: the ultraviolet (UVL), blue (BL), and green (GL) luminescence bands. These luminescence bands have been extensively characterized in terms of their dependence on temperature, ambient conditions, and dopant concentrations.^{4–12} The lack of NBE has been attributed to self-trapped holes (STHs),^{13,14} which are believed to form self-trapped excitons that recombine and give rise to an

impurity independent, and often dominant, broad UVL band in the emission spectrum.^{4,8–12} This UVL band is only observed for excitation energies above the bandgap and exhibits a large Stokes shift, which is indicative of a strong electron-phonon coupling caused by highly localized charge carriers involved in the recombination.⁴ Recently, the UVL band has been resolved into high and low energy components, where the low band is polarized parallel to the *c* axis of the crystal, and the high band is polarization independent.^{8,12} Donor-acceptor pair recombination involving deep acceptors like V_{Ga} , $V_{Ga}V_O$ complexes, Mg_{Ga}, Be_{Ga}, Li_{Ga}, Zn_{Ga}, and N_O have been suggested as candidates responsible for the luminescence bands peaking in the visible part of the emission spectrum.^{5–8,10,11,15–17} However, the specific defect origins of the majority of PL bands in β -Ga₂O₃ remain a subject of debate.

Defect luminescence lines can be estimated theoretically by using configuration coordinate (CC) diagrams derived from first-principles calculations.^{18–20} This can be highly useful to interpret experimental PL data.²⁰ In the present work, we employ hybrid functional calculations and the effective one-dimensional (1D) CC model to estimate the optical transition energies and luminescence lines of a selection of acceptor impurities in β -Ga₂O₃, namely,

Mg_{Ga}, Be_{Ga}, Ca_{Ga}, Cd_{Ga}, Zn_{Ga}, Li_{Ga}, and N_O. These impurities are typical contaminants in as-grown β -Ga₂O₃ crystals, and/or potentially useful as compensating acceptor dopants to obtain highly-resistive or semi-insulating material.^{21–25} We have also investigated their interaction with hydrogen. Indeed, H_i acts exclusively as a shallow donor in β -Ga₂O₃ and is likely to be trapped by acceptor impurities.^{26–28} Finally, we have explored the optical properties of V_{Ga} acceptors complexed with shallow donor impurities hydrogen and Si_{Ga}. The STH is used as a benchmark to assess the accuracy of our results, as most of the acceptors studied here exhibit a similar polaronic defect state. Our predictions provide useful input for future optical studies on β -Ga₂O₃.

II. METHODOLOGY

All first-principles calculations were based on the generalized Kohn–Sham theory with the projector augmented wave method,^{29,30} as implemented in the VASP code.³¹ The Ga 3*d*, 4*s*, 4*p*; O 2*s*, 2*p*; Mg 2*p*, 3*s*; Be 2*s*; Cd 5*s*, 4*d*; Ca 3*s*, 3*p*, 4*s*; Zn 3*d*, 4*s*; Li 1*s*, 2*s*; and N 2*s*, 2*p* electrons were treated as explicit valence states. To obtain an accurate description of the electronic and structural properties of β -Ga₂O₃, we used the Heyd–Scuseria–Ernzerhof (HSE)³² range-separated hybrid functional. The screening parameter μ was fixed at the standard value,³² and the fraction of screened Hartree–Fock exchange was set to $\alpha = 0.33$, resulting in a direct bandgap of 4.9 eV. The indirect bandgap is only 40 meV lower in energy.³³ This parameterization does not necessarily guarantee an accurate description of defect states, as is evident from the increasing use of Koopmans compliant functionals aiming to ensure that the total energy is a piece-wise linear function of the fractional electron number.^{34–38} For instance, Gake *et al.*³⁹ recently reported that the polaronic defect states of the STH and Mg_{Ga} acceptor in β -Ga₂O₃ exhibit slightly convex behavior, i.e., the single-particle level of the defect state shifts up in energy upon electron occupation. In order to assess how sensitive our results are to the HSE parameterization and elaborate on possible non-Koopmans behavior, some calculations were also performed using the PBE0 functional, as shown in the Appendix, which also yields a direct bandgap of 4.9 eV. We find that the peak positions (PPs) of the calculated luminescence lines change by less than 0.1 eV when PBE0 is used. Both functionals result in slightly convex behavior for the defects studied here, similar to what was reported by Gake *et al.*³⁹

For defect calculations, we employed 160-atom supercells, a plane-wave energy cutoff of 500 eV, and a single special *k*-point at (0.25, 0.25, 0.25). Thermodynamic charge-state transition levels of defects are given by the Fermi level position for which the total energy of the defect-containing supercell in charge-states q and $q \pm 1$ and relaxed configurations $Q(q)$ and $Q(q \pm 1)$ is equal,

$$\epsilon(q/q \pm 1) = E[q \pm 1; Q(q \pm 1)] - E(q; Q(q)) \mp \epsilon_{\text{VBM}}. \quad (1)$$

Here, $\epsilon(q/q \pm 1)$ is given relative to the energy level of the valence band maximum (VBM) ϵ_{VBM} . For vertical charge-state transitions, the configuration is fixed to that of the initial

charge-state $Q(q)$, and the level is given by

$$\mu(q/q \pm 1) = E[q \pm 1; Q(q)] - E(q; Q(q)) \mp \epsilon_{\text{VBM}}. \quad (2)$$

For charged defects, the total energies in Eq. (1) were corrected by using the anisotropic⁴⁰ Freysoldt, Neugebauer, and Van de Walle (FNV) scheme,⁴¹ with the low-frequency dielectric tensor.⁴² For Eq. (2), we used the correction scheme newly developed by Gake *et al.*⁴³ We performed tests to verify the performance of the latter correction scheme for the defects studied in the present work; these tests are shown in the Appendix.

Optical transition energies and luminescence lines were estimated by using the 1D CC model with parameters obtained from the hybrid functional calculations, as described in Refs. 18–20. These parameters include the change in configuration coordinate ΔQ , the zero-phonon line (ZPL) energy E_{ZPL} [given by the thermodynamic charge-state transition level defined in Eq. (1)], and the effective phonon frequencies $\Omega_{g/e}$ in the ground (g) and excited (e) state. In the classical Franck–Condon (FC) approximation, optical transitions are vertical [given by Eq. (2)], which means the emission and absorption energies can be defined as $E_{\text{em}} = E_{\text{ZPL}} - d_{\text{g}}^{\text{FC}}$ and $E_{\text{abs}} = E_{\text{ZPL}} + d_{\text{e}}^{\text{FC}}$, respectively. Here, $d_{\text{g/e}}^{\text{FC}}$ denotes FC relaxation energies. The 1D CC model is a good approximation for defects exhibiting strong electron–phonon coupling,^{18,20} which is the case for all defects studied in the present work.

III. RESULTS AND DISCUSSION

The β -Ga₂O₃ crystal structure contains two inequivalent Ga sites and three inequivalent O sites, as indicated in Fig. 1(a). Ga1 and Ga2 are tetrahedrally and octahedrally coordinated, respectively. Two O sites are threefold-coordinated: O1 (2 $\times$ Ga2, 1 $\times$ Ga1) and O2 (2 $\times$ Ga1, 1 $\times$ Ga2), while the O3 site is fourfold coordinated (3 $\times$ Ga2, 1 $\times$ Ga1).

A. Self-trapped holes

Before addressing the impurities, we consider optical transitions involving the STHs. Photogenerated holes can self-trap onto two different O sites, namely, O1 and O2. As shown in Fig. 1, the hole state is localized at a single O atom for STH_{O1} and shared between two O atoms for STH_{O2}. The calculated hole self-trapping energies (defined in Ref. 13) of 0.48 and 0.49 eV for STH_{O1} and STH_{O2} are nearly equivalent, which can be understood from their similar, nearly planar bonding environments to three Ga neighbors. These self-trapping energies correspond to ZPL energies of 4.38 and 4.37 eV for the capture of an electron at the conduction band minimum (CBM) by STH_{O1} and STH_{O2}. As indicated in the CC diagrams in Fig. 1(b), these transitions result in emission energies of 3.04 and 2.95 eV. When the full luminescence lines are calculated by including vibronic coupling,¹⁸ the corresponding peak positions (PPs) occur at 3.11 and 3.05 eV in the spectrum, as shown in Fig. 1(c). The CC model parameters, PP, and full-width at half maximum (FWHM) for all luminescence lines calculated in the present work are provided in Table I. The calculated PL bands of STH_{O1} and STH_{O2} are broad, with FWHM values of 0.54 and 0.62 eV, respectively. This broadness is caused by the sizable polaronic lattice distortion that accompanies the hole localization.

FIG. 1. (a) Relaxed structure of STH₀₁, STH₀₂, and STH₀₃. The hole (blue isosurface) can be localized at one (STH₀₁ and STH₀₃) or shared between two (STH₀₂) O atoms. STH₀₃ is only metastable and involves breaking the O3–Ga1 bond. (b) CC diagrams for optical transitions involving recombination between STH₀₁ and STH₀₂ with free electrons at the CBM, and (c) the corresponding calculated luminescence lines.

As shown in Fig. 1(a), holes can also localize on the O3 sites. This has not been reported previously. The O3 site has four Ga neighbors and, therefore, occupies a very different bonding environment compared to the O1 and O2 sites. Hole trapping on the O3 site causes significant lattice distortions and breaks the single O3–Ga1 bond. The Ga1 atom is displaced sufficiently to form a new bond with a nearby O2 atom, thus preserving the tetrahedral coordination. However, STH₀₃ is only metastable with a negative self-trapping energy of -0.33 eV and is thus not expected to form relative to the other two STHs.

Experimentally, the STHs have been associated with a broad UVL band peaking in the spectral range 3.1 – 3.6 eV.^{4,7–10,12} The luminescence lines calculated for the STHs peak at the lower end of this range, which may indicate that they are somewhat underestimated. This would reflect the remaining inaccuracy of the hybrid functional calculations (e.g., non-Koopmans behavior), and the

uncertainty of the experimental bandgap of β -Ga₂O₃.⁴⁴ The calculated difference between the PP of STH₀₁ and STH₀₂ is consistent with the difference between the two components of the UV band reported in Ref. 12.

B. Polaronic acceptor impurities

Next, we consider Ga substitutional single acceptor impurities exhibiting polaronic defect states, similar to the STHs, namely, Mg_{Ga2}, Ca_{Ga2}, Cd_{Ga2}, Zn_{Ga1}, and Be_{Ga1}. These impurities, along with N_O, were predicted to have the lowest formation energy in a survey of acceptor impurities performed by Lyons *et al.*²² For each impurity, we have considered the Ga site resulting in the lowest formation energy, as reported elsewhere.^{22,23} For polaronic acceptors, it is important to explore the different possible hole configurations.^{45,46} As shown in Fig. 2(a), the charge-neutral Mg_{Ga2} acceptor corresponds to a small hole polaron localized on a single nearest-neighbor O1 site, in line with experimental magnetic resonance data⁴⁷ and previous theoretical studies,^{22,28} whereas hole localization on the O2 site is 0.12 eV higher in energy. For Ca_{Ga2}, Cd_{Ga2}, Zn_{Ga1}, and Be_{Ga1}, the hole will also most favorably localize on an adjacent O1 site. In general, we find that hole polarons prefer to localize on the nearest-neighbor O site with the lowest coordination number.

Similar to the STHs, optical transitions involving the capture of an electron at the CBM by charge-neutral Mg_{Ga2}, Ca_{Ga2}, Cd_{Ga2}, Zn_{Ga1}, and Be_{Ga1} are estimated. Note that these transitions involve the same type of polaronic defect state as STH₀₁, and thus, assuming that the PPs of the STHs are slightly underestimated, the error could be systematic. The Mg_{Ga2}, Ca_{Ga2}, Cd_{Ga2}, and Zn_{Ga1} acceptors give rise to broad luminescence bands with predicted peak positions in the visible range between 2.15 and 2.62 eV, as shown in Fig. 2(b). In contrast, the calculated luminescence band for Be_{Ga1} peaks significantly lower at 1.71 eV. This is mainly because the thermodynamic $(0/-)$ transition level of Be_{Ga1} is deeper,²² and also because the ground-state relaxation energy is higher. The latter difference is likely related to the relatively small size of the Be ion, which undergoes a comparatively large displacement away from the localized hole, as shown in Fig. 2(a). This is similar to the polaronic Li_{Zn} acceptor in ZnO.⁴⁸ In principle, optical transitions involving metastable hole configurations can also occur. As an example, we have included results for charge-neutral Mg_{Ga2} with the hole localized on the O2 rather than the O1 site, which we label as pO2 (see Table I). Finally, we have studied the double acceptor Li_{Ga2}. The optical transition between the CBM and the $(-/-2-)$ level of Li_{Ga2} results in a luminescence band with a calculated peak position of 1.56 eV. This is significantly lower than those of the single polaronic acceptors, except Be_{Ga1}.

Acceptor impurities present stable trapping sites for H_i donors in β -Ga₂O₃. For instance, the Mg_{Ga2}H complex has been assigned to an infrared (IR) absorption line at 3492 cm⁻¹.²⁸ We find that such complexes are not fully passivated, but rather exhibit a thermodynamic $(+/-0)$ transition level close to the VBM. Note that a donor level is also predicted for the isolated acceptors.⁴⁹ This incomplete passivation means that the complexes can be optically active. We have investigated Mg_{Ga2}H, Ca_{Ga2}H, Be_{Ga1}H, Zn_{Ga1}H, and Cd_{Ga2}H (as shown in Table I). For these complexes, H most favorably binds to one of the O1 ions

TABLE I. Peak position (PP) and full-width at half maximum (FWHM) for the calculated luminescence lines, and CC model parameters obtained from the HSE calculations, including ZPL energy (E_{ZPL}), classical emission (E_{em}) and absorption (E_{abs}) energies, total mass-weighted distortion (ΔQ), and effective normal mode frequencies in the ground/excited state ($\hbar\Omega_{g/e}$).

Optical transition	PP (eV)	FWHM (eV)	E_{ZPL} (eV)	E_{em} (eV)	E_{abs} (eV)	ΔQ (amu ^{1/2} /Å)	$\hbar\Omega_{g/e}$ (meV)
$STH_{O1}^+ + e_{CBM}^-$	3.11	0.54	4.38	3.04	5.58	2.77	38/36
$STH_{O2}^+ + e_{CBM}^-$	3.04	0.62	4.37	2.95	5.56	2.30	47/43
$Mg_{Ga2}^{0,pO1} + e_{CBM}^-$	2.32	0.59	3.69	2.21	4.86	2.67	42/37
$Mg_{Ga2}^{0,pO2} + e_{CBM}^-$	2.53	0.63	3.81	2.41	4.92	2.14	50/44
$Ca_{Ga2}^0 + e_{CBM}^-$	2.40	0.57	3.75	2.30	4.89	2.83	39/34
$Cd_{Ga2}^0 + e_{CBM}^-$	2.62	0.55	3.67	2.52	4.47	2.26	43/36
$Zn_{Ga1}^0 + e_{CBM}^-$	2.15	0.57	3.48	2.04	4.64	2.70	41/36
$Be_{Ga1}^0 + e_{CBM}^-$	1.71	0.64	3.25	1.54	4.63	2.61	46/41
$Li_{Ga2}^- + e_{CBM}^-$	1.56	0.62	2.96	1.37	4.00	2.65	44/35
$(Mg_{Ga2}H)^+ + e_{CBM}^-$	2.71	0.55	4.00	2.63	5.20	2.67	40/37
$(Ca_{Ga2}H)^+ + e_{CBM}^-$	2.76	0.53	4.03	2.68	5.17	2.90	37/34
$(Cd_{Ga2}H)^+ + e_{CBM}^-$	2.90	0.55	3.99	2.81	4.71	2.58	39/30
$(Zn_{Ga1}H)^+ + e_{CBM}^-$	2.75	0.57	3.98	2.66	5.11	2.42	43/40
$(Be_{Ga1}H)^+ + e_{CBM}^-$	2.57	0.60	3.95	2.47	5.28	2.51	44/42
$(V_{Ga}^{ib})^0 + e_{CBM}^-$	1.93	0.62	3.33	1.78	4.46	2.59	44/38
$(V_{Ga2}Si_{Ga1})^- + e_{CBM}^-$	1.17	0.59	2.47	0.93	3.44	2.52	45/36
$(V_{Ga}^{ib}2H)^0 + e_{CBM}^-$	2.12	0.64	3.57	1.97	4.71	2.59	44/38
$(V_{Ga}^{ib}3H)^+ + e_{CBM}^-$	2.54	0.60	3.95	2.43	5.12	2.74	41/36
$(V_{Ga}^{ic}2H)^0 + e_{CBM}^-$	1.95	0.60	3.47	1.82	4.91	2.84	41/38
$(V_{Ga}^{ic}Si_22H)^+ + e_{CBM}^-$	2.55	0.63	3.90	2.43	5.12	2.31	48/44
$N_{O1}^+ + e_{CBM}^-$	2.28	0.58	3.69	2.17	4.99	2.80	40/37
$N_{O2}^+ + e_{CBM}^-$	2.92	0.59	4.25	2.83	5.22	2.77	39/32
$N_{O3}^0 + e_{CBM}^-$	1.44	0.59	2.85	1.27	4.04	2.77	41/36
$N_{O3}^+ + e_{CBM}^-$	1.87	0.55	3.37	1.76	4.74	3.40	34/31
$(N_{O1}H)^+ + e_{CBM}^-$	2.25	0.60	3.91	2.13	5.36	3.32	37/33
$(N_{O2}H)^+ + e_{CBM}^-$	2.65	0.64	4.20	2.53	5.30	3.00	39/32
$(N_{O3}H)^+ + e_{CBM}^-$	2.10	0.49	3.50	2.02	4.92	3.62	31/30

immediately adjacent to the acceptor, as shown in Fig. 2(a). The O–H bond points toward the largest interstitial site, similar to the isolated H_i^+ . The stability of the complexes was assessed by calculating H removal energies, which is defined as the difference in formation energy between the charge-neutral complex and the sum of the two isolated constituents (negatively charged acceptor and H_i^+).¹⁹ The resulting removal energies of 0.68, 0.84, 0.78, 0.79, and 1.01 eV for $Mg_{Ga2}H$, $Ca_{Ga2}H$, $Cd_{Ga2}H$, $Zn_{Ga1}H$, and $Be_{Ga1}H$, respectively, are relatively low considering the modest migration barrier predicted for H_i^+ .²⁶ Initially, these complexes should be stable at room temperature; however, dissociation might occur upon UV light exposure, which would lead to bleaching of their PL bands. Indeed, recombination-enhanced dissociation has been observed, e.g., for the C_NH complex in GaN.⁵⁰ As shown in Fig. 2, optical transitions between the CBM and the

(+/-) level of the H-complexed acceptors results in PL bands peaking between 2.57 and 2.76 eV. Thus, complexing the polaronic acceptors with H will not passivate the luminescence, but rather shift it to higher energies.

Based on our theoretical predictions, isolated and H-complexed polaronic acceptor impurities are potential candidates for luminescence bands observed in the visible part of the spectrum. Indeed, increases in the intensity of BL and GL bands have been reported in experimental cathodoluminescence studies on Mg- and Zn-doped β -Ga₂O₃.^{10,15} We also note that the calculated absorption energies of the polaronic acceptor impurities are very close to the bandgap energy, which means that their luminescence bands could be selectively excited with photon energies slightly below the bandgap. This was observed experimentally for the BL band in Refs. 5 and 7.

FIG. 2. (a) Ground-state configuration of $\text{Mg}_{\text{Ga}2}^0$, $\text{Be}_{\text{Ga}1}^0$, and $(\text{Mg}_{\text{Ga}2}\text{H})^+$. The hole polaron most favorably localizes on a single nearest-neighbor O1 site in all cases. (b) Calculated luminescence lines for optical transitions involving isolated (top) and H-decorated (bottom) polaronic acceptors.

C. Ga vacancies

V_{Ga} acts as a polaronic triple acceptor in $\beta\text{-Ga}_2\text{O}_3$ and could be involved in donor–acceptor pair transitions, similar to the impurities above.⁵ Moreover, the formation energy of V_{Ga} is sufficiently low for it to be incorporated in sizeable concentrations during growth, particularly under O-rich and *n*-type conditions.^{27,51} In addition to the $V_{\text{Ga}1}$ and $V_{\text{Ga}2}$ configurations, there are three split-vacancy configurations where two adjacent vacant Ga sites are complexed with a Ga residing between them in a high-symmetry interstitial site; these are denoted as V_{Ga}^{a} , V_{Ga}^{b} , and V_{Ga}^{c} .⁵¹ The thermodynamic (2−/3−) transition levels of the five different V_{Ga} configurations have been predicted to occur between 1.7 and 2.6 eV below the CBM.⁵¹ We find that optical transitions between the CBM and these (2−/3−) levels result in emission energies between 0.1 and 1.2 eV, which is much lower than the characteristic luminescence bands observed in $\beta\text{-Ga}_2\text{O}_3$. Moreover, these transitions are likely to have significant nonradiative components

FIG. 3. (a) Relaxed structures of the $V_{\text{Ga}}^{\text{b}}3\text{H}$, $V_{\text{Ga}}^{\text{c}}\text{Si}_2\text{H}$, and $V_{\text{Ga}2}\text{Si}_{\text{Ga}1}$ complexes. The Ga vacancies are indicated with dashed translucent circles. (b) Calculated luminescence lines of four V_{Ga} acceptors complexed with H and Si_{Ga} donors.

due to crossing between the ground- and excited-state potential energy curves in their CC diagrams.⁵² In principle, V_{Ga} in the 3− charge state can radiatively capture photogenerated holes from the VB. However, if the lack of NBE is caused by formation of STHs, such transitions are not likely to be observed. Moreover, since both the VB of $\beta\text{-Ga}_2\text{O}_3$ and the polaronic defect states exhibit mostly 2*p* character, the transition dipole moment should be weak. Nevertheless, we obtain emission energies between 1.3 and 2.3 eV for these optical transitions of the five different V_{Ga} acceptors.

However, V_{Ga} can form stable complexes with shallow donor impurities such as H and Si_{Ga} .^{27,53} Notably, the $V_{\text{Ga}}^{\text{b}}2\text{H}$ complex has been assigned to an IR absorption line 3436 cm^{-1} by Weiser *et al.*⁵⁴ Complexing V_{Ga} with shallow single donors will successively passivate its acceptor levels, thereby shifting its luminescence to higher energies, similar to the H-complexed polaronic acceptor impurities in Fig. 2. There is a large number of possible donor-complexed V_{Ga} acceptors to explore. As examples, we have included results for $V_{\text{Ga}2}\text{Si}_{\text{Ga}1}$, $V_{\text{Ga}}^{\text{b}}2\text{H}$, $V_{\text{Ga}}^{\text{b}}3\text{H}$, $V_{\text{Ga}}^{\text{c}}2\text{H}$, and $V_{\text{Ga}}^{\text{c}}\text{Si}_2\text{H}$ in Table I. As shown in Fig. 3(a), the H atoms terminate O dangling bonds at $V_{\text{Ga}1}$ in all cases, while the Si atom goes off-site in the $V_{\text{Ga}}^{\text{c}}\text{Si}_2\text{H}$ complex and occupies a Ga1 site immediately adjacent to $V_{\text{Ga}2}$ in the $V_{\text{Ga}2}\text{Si}_{\text{Ga}1}$ complex. Figure 3(b) shows that the complexes with two and three donor impurities can give rise to luminescence lines with predicted peak positions in the visible range. Hence, such complexes are also potential candidates for the characteristic visible luminescence bands observed in $\beta\text{-Ga}_2\text{O}_3$. It should be noted that, in high-resistive material, the isolated V_{Ga} acceptors could occur in 2− or 1− charge states.^{51,55}

Under such conditions, optical transitions between the CBM and the $(-2/-)$ or $(0/-)$ levels of V_{Ga} might result in luminescence bands peaking in the visible range, similar to the donor-complexed V_{Ga} acceptors above.

D. Nitrogen acceptor impurities

Turning to N impurities substituting on O sites, the most favorable configuration depends on the Fermi level position.²³ In typical unintentionally n -type doped material, N_O will act as a compensating acceptor. Under such conditions, the N_{O3}

configuration exhibits the lowest formation energy. However, a high concentration of N_O will drive the Fermi level toward the $(0/-)$ transition level, where the charge-neutral N_{O1} and N_{O2} may become relevant.²³ All three N_O configurations also exhibit a thermodynamic $(+0)$ transition level located in the lower part of the bandgap. For the N_O acceptors, the neutral and positive charge states correspond to hole states that are localized at the N impurity itself, rather than a neighboring O site, as shown in Fig. 4(a).

We have focused on optical transitions between the CBM and the thermodynamic $(+0)$ charge-state transition level of N_{O1} and N_{O2} , and both the $(+0)$ and $(0/-)$ levels for N_{O3} . As shown in Fig. 4(b), the luminescence lines involving N_O depend strongly on the configuration, and thus the Fermi level position. In n -type material, electron capture from the CBM by charge-neutral N_{O3} results in a broad luminescence band peaking at 1.44 eV. For high-resistive material, where N_O preferably adopts the neutral charge-state, optical transitions between the CBM and the $(+0)$ level of N_{O3} , N_{O2} , and N_{O1} result in bands peaking at 1.87, 2.94, and 2.28 eV, respectively.

As shown in Fig. 4(a), hydrogen can passivate the $(0/-)$ acceptor levels of N_O by forming a bond with the N impurity. The resulting $N_{O1}H$, $N_{O2}H$, and $N_{O3}H$ complexes exhibit H removal energies of 2.18, 1.95, and 0.27 eV, respectively. The latter removal energy is so low that the $N_{O3}H$ complex could be unstable at room temperature. Most likely, this is because N_{O3} is fourfold- and not threefold-coordinated like N_{O1} and N_{O2} [see Fig. 4(a)]. In contrast, the $N_{O1}H$ and $N_{O2}H$ complexes are predicted to be highly stable. The $N_{O1}H$ complex exhibits the lowest formation energy, but it is only 0.13 eV lower than that for $N_{O2}H$. Optical transitions between the CBM and the $(+0)$ transition levels of the $N_{O1}H$, $N_{O2}H$, and $N_{O3}H$ complexes result in broad luminescence bands with calculated PPs of 2.25, 2.65, and 2.10 eV, respectively.

As already mentioned, the emission from N_O -related defects will depend strongly on the configuration, which is important to consider when comparing the predictions with experimental data. Song *et al.*⁵⁶ observed an intense red luminescence (RL) band peaking at 1.67 eV in N-doped β -Ga₂O₃ nanowires. This is close to the luminescence bands calculated for N_{O3} . RL has also been observed in N-doped β -Ga₂O₃ nanoflakes.⁵⁷ In contrast, Harwig and Kellendonk⁵ observed no RL, but a slight increase in the BL band intensity when β -Ga₂O₃ powders were fired in N₂ vs air. In a cathodoluminescence study by Onuma *et al.*,¹⁷ however, the BL band was suppressed in heavily N-doped epitaxial β -Ga₂O₃ films.

IV. CONCLUSION

By using 1D CC diagrams derived from hybrid functional calculations, we have estimated optical transition energies and luminescence lines for acceptor impurities Mg_{Ga2}, Be_{Ga1}, Ca_{Ga2}, Cd_{Ga2}, Zn_{Ga1}, Li_{Ga2}, and N_O , their complexes with H donors, as well as V_{Ga} acceptors complexed with hydrogen and Si_{Ga} donor impurities in β -Ga₂O₃. The results point to these acceptors as possible candidates for the origin of broad PL bands in the infrared to visible part of the emission spectrum. Specifically, the calculated luminescence lines of Mg_{Ga2}, Ca_{Ga2}, Cd_{Ga2}, and Zn_{Ga1} peak in the 2.15–2.62 eV range (green/blue), while those of Be_{Ga1}

FIG. 4. (a) Relaxed structures of N_{O1}^0 , N_{O2}^0 , N_{O3}^0 , $(N_{O1}H)^0$, $(N_{O2}H)^0$, and $(N_{O3}H)^0$. For N_O acceptors, the hole state (blue isosurface) is localized at the N impurity itself, rather than an adjacent O site. (b) Calculated luminescence lines for optical transitions involving N_O and N_OH complexes.

and $\text{Li}_{\text{Ga}2}$ peak at lower energies of 1.71 and 1.56 eV (infrared/red), respectively. V_{Ga} acceptors complexed with shallow donor impurities such as H and Si_{Ga} can similarly give rise to luminescence in the visible range. For N_{O} acceptors, the luminescence depends strongly on the configuration and Fermi level position. The $\text{N}_{\text{O}3}$ configuration, which has the lowest formation energy in n -type material, can give rise to luminescence bands with predicted peak positions at 1.44 and 1.87 eV (infrared/red), whereas the luminescence lines of $\text{N}_{\text{O}1}$ and $\text{N}_{\text{O}2}$ peak at higher energies of 2.28 and 2.92 eV (green and blue), respectively. When the acceptor impurities are complexed with a single H donor, we find that the luminescence band is not passivated, but rather shifted in peak position. These results could be useful for future optical studies seeking to identify the origin of the broad luminescence bands in $\beta\text{-Ga}_2\text{O}_3$.

ACKNOWLEDGMENTS

We wish to thank A. Alkauskas for fruitful collaborations and for providing the code and expertise to calculate luminescence lineshapes, and T. Gake, Y. Kumagai, and F. Oba for helpful discussions. Financial support was kindly provided by the Research Council of Norway and University of Oslo through the frontier research project FUNDAMeNT (No. 251131, FriPro ToppForsk-program). The computations were performed on resources provided by UNINETT Sigma2—the National Infrastructure for High Performance Computing and Data Storage in Norway. This work was partially performed under the auspices of the U.S. Department of Energy (DOE), Lawrence Livermore National Laboratory under Contract No. DE-AC52-07NA27344 and supported by the Critical Materials Institute, an Energy Innovation Hub funded by the U.S. DOE, Office of Energy Efficiency and Renewable Energy, Advanced Manufacturing Office.

APPENDIX: PBE0 calculations and test of finite-size corrections

In order to (i) assess how sensitive our theoretical predictions are to the parameterization of the hybrid functional, i.e., choice of α and μ parameters, and (ii) elaborate on possible non-Koopmans behavior, we have performed calculations using the PBE0 functional, which yields the same direct bandgap value of 4.9 eV. Calculations were performed for a representative subset of the defects studied in the present work, namely, the STHs, two polaronic acceptors ($\text{Mg}_{\text{Ga}2}$ and $\text{Mg}_{\text{Ga}2}\text{H}$) and one O substitutional N

FIG. 5. Dependence of the corrected and uncorrected vertical transition energies of defects on the supercell size. Calculations were performed using the PBE+U functional. The vertical transition energies are given relative to the corrected one in the largest 960 atom supercell.

acceptor ($\text{N}_{\text{O}3}$). The results are listed in Table II. The calculated PPs shift up in energy when the PBE0 functional is used, but the magnitude is only 0.1 eV at most. Based on this, we conclude that the qualitative results do not hinge on the specific HSE parameterization. Regarding the generalized Koopmans condition, our results are similar to those reported by Gake *et al.*,³⁹ i.e., we find that the acceptor impurities exhibit slightly convex behavior when using the HSE functional. If the parameterization is tuned to satisfy the generalized Koopmans condition, the resulting bandgap is overestimated.³⁹ When PBE0 is used, the convexity is only slightly reduced, e.g., for the (0/−) transition of $\text{Mg}_{\text{Ga}2}$ we obtain a non-Koopmans energy (see Ref. 34) of 0.24 eV for HSE and 0.20 eV for PBE0.

Gake *et al.*⁴³ recently proposed a scheme to remedy the spurious supercell-size dependence of vertical transition energies involving defect states. These corrections translate into different effective Franck–Condon relaxation energies that can differ from those evaluated using either no finite-size corrections or those corrected with only the low-frequency dielectric screening.⁵⁸ As shown in Fig. 5, we have evaluated the performance of this finite-size correction by performing supercell-size tests

TABLE II. PP and FWHM for the calculated luminescence lines, and CC model parameters obtained from the PBE0 calculations. The change in PP compared to the value calculated using HSE is given in parenthesis.

Optical transition	PP (eV)	FWHM (eV)	E_{ZPL} (eV)	E_{em} (eV)	E_{abs} (eV)	ΔQ (amu ^{1/2} /Å)	$\hbar\Omega_{g/e}$ (meV)
$\text{STH}_{\text{O}1}^+ + e_{\text{CBM}}^-$	3.18 (+0.07)	0.54	4.38	3.13	5.35	2.69	38/34
$\text{STH}_{\text{O}2}^+ + e_{\text{CBM}}^-$	3.07 (+0.03)	0.59	4.28	2.98	5.30	2.26	46/41
$\text{Mg}_{\text{Ga}2}^0 + e_{\text{CBM}}^-$	2.42 (+0.10)	0.56	3.72	2.30	4.67	2.63	41/34
$(\text{Mg}_{\text{Ga}2}\text{H})^+ + e_{\text{CBM}}^-$	2.80 (+0.09)	0.60	4.02	2.70	5.00	2.65	40/34
$\text{N}_{\text{O}3}^0 + e_{\text{CBM}}^-$	1.54 (+0.10)	0.58	2.88	1.38	3.95	2.75	41/34

of the vertical transitions for a representative set of the defects studied in the present work. We employed the PBE+U functional with an effective U value of 10 eV applied to the O $2p$ orbitals in order to increase the bandgap and ensure well localized defect states, similar in character to those obtained using the hybrid functional, in both the initial and final charge state. Furthermore, the use of the PBE+U functional makes it computationally feasible to employ large supercells. Specifically, we have used supercells with 120, 160, 300, and 960 atoms. Note that, since the cell dimension is not isotropically expanded, we have not performed any extrapolation of the uncorrected energies to the dilute limit. We have used the point charge correction with the alignment term, as explained in Ref. 43. Figure 5 shows that the vertical transition energies are well corrected. The difference between the corrected energy in the 160 and 960 atom supercell is less than 0.03 eV for the transitions involving charge-neutral and singly charged defects, and 0.05 eV for the $\mu(-2-)$ transition of $\text{Li}_{\text{Ga}2}$. We have also confirmed that the formation energies of the defects shown in the supercell-size tests were well corrected.

REFERENCES

- ¹S. Pearton, J. Yang, P. Cary, F. Ren, J. Kim, M. Tadjer, and M. Mastro, *Appl. Phys. Rev.* **5**, 011301 (2018).
- ²M. E. Ingebrigtsen, J. B. Varley, A. Y. Kuznetsov, B. G. Svensson, G. Alfieri, A. Mihaila, U. Badstöbner, and L. Vines, *Appl. Phys. Lett.* **112**, 042104 (2018).
- ³J. F. McGlone, Z. Xia, C. Joishi, S. Lodha, S. Rajan, S. Ringel, and A. R. Arehart, *Appl. Phys. Lett.* **115**, 153501 (2019).
- ⁴T. Harwig, F. Kellendonk, and S. Slappendel, *J. Phys. Chem. Solids* **39**, 675 (1978).
- ⁵T. Harwig and F. Kellendonk, *J. Phys. Chem. Solids* **24**, 255 (1978).
- ⁶G. Blasse and A. Bril, *J. Chem. Phys. Solids* **31**, 707 (1970).
- ⁷L. Binet and D. Gourier, *J. Chem. Phys. Solids* **59**, 1241 (1998).
- ⁸K. Shimamura, E. G. Villora, T. Ujije, and K. Aoki, *Appl. Phys. Lett.* **92**, 201914 (2008).
- ⁹M. Yamaga, T. Ishikawa, M. Yoshida, T. Hasegawa, E. G. Villora, and K. Shimamura, *Phys. Status Solidi C* **8**, 2621 (2011).
- ¹⁰T. Onuma, S. Fujioka, T. Yamaguchi, M. Higashiwaki, K. Sasaki, T. Masui, and T. Honda, *Appl. Phys. Lett.* **103**, 041910 (2013).
- ¹¹T. Onuma, Y. Nakata, K. Sasaki, T. Masui, T. Yamaguchi, T. Honda, A. Kuramata, S. Yamakoshi, and M. Higashiwaki, *J. Appl. Phys.* **124**, 075103 (2018).
- ¹²Y. Wang, P. T. Dickens, J. B. Varley, X. Ni, E. Lotubai, S. Sprawls, F. Liu, V. Lordi, S. Krishnamoorthy, S. Blair, K. G. Lynn, M. Scarpulla, and B. Sensale-Rodriguez, *Sci. Rep.* **8**, 18075 (2018).
- ¹³J. B. Varley, A. Janotti, C. Franchini, and C. G. Van de Walle, *Phys. Rev. B* **85**, 081109 (2012).
- ¹⁴B. E. Kananen, N. C. Giles, L. E. Halliburton, G. K. Foundos, K. B. Chang, and K. T. Stevens, *J. Appl. Phys.* **122**, 215703 (2017).
- ¹⁵X. Wang, F. Zhang, K. Saito, T. Tanaka, M. Nishio, and Q. Guo, *J. Phys. Chem. Solids* **75**, 1201 (2014).
- ¹⁶Q. D. Ho, T. Frauenheim, and P. Deák, *Phys. Rev. B* **97**, 115163 (2018).
- ¹⁷H. Gao, S. Muralidharan, N. Pronin, M. R. Karim, S. M. White, T. Asel, G. Foster, S. Krishnamoorthy, S. Rajan, L. R. Cao, M. Higashiwaki, H. von Wenckstern, M. Grundmann, H. Zhao, D. C. Look, and L. J. Brillson, *Appl. Phys. Lett.* **112**, 242102 (2018).
- ¹⁸A. Alkauskas, J. L. Lyons, D. Steiauf, and C. G. Van de Walle, *Phys. Rev. Lett.* **109**, 267401 (2012).
- ¹⁹C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
- ²⁰A. Alkauskas, M. D. McCluskey, and C. G. Van de Walle, *J. Appl. Phys.* **119**, 181101 (2016).
- ²¹M. Higashiwaki, K. Sasaki, H. Murakami, Y. Kumagai, A. Koukita, A. Kuramata, T. Masui, and S. Yamakoshi, *Semicond. Sci. Technol.* **31**, 034001 (2016).
- ²²J. L. Lyons, *Semicond. Sci. Technol.* **33**, 05LT02 (2018).
- ²³H. Peelaers, J. L. Lyons, J. B. Varley, and C. G. Van de Walle, *APL Mater.* **7**, 022519 (2019).
- ²⁴C. Lin, Y. Yuda, M. H. Wong, M. Sato, N. Takekawa, K. Konishi, T. Watahiki, M. Yamamuka, H. Murakami, Y. Kumagai, and M. Higashiwaki, *IEEE Electron Device Lett.* **40**, 1487 (2019).
- ²⁵Z. Galazka, K. Irmscher, R. Schewski, I. M. Hanke, M. Pietsch, S. Ganschow, D. Klimm, A. Dittmar, A. Fiedler, T. Schroeder, and M. Bickermann, *J. Cryst. Growth* **529**, 125297 (2020).
- ²⁶J. B. Varley, J. R. Weber, A. Janotti, and C. G. Van de Walle, *Appl. Phys. Lett.* **97**, 142106 (2010).
- ²⁷J. B. Varley, H. Peelaers, A. Janotti, and C. G. V. de Walle, *J. Phys. Condens. Matter* **23**, 334212 (2011).
- ²⁸J. R. Ritter, J. Huso, P. T. Dickens, J. B. Varley, K. G. Lynn, and M. D. McCluskey, *Appl. Phys. Lett.* **113**, 052101 (2018).
- ²⁹P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- ³⁰G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- ³¹G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- ³²A. V. Krukau, O. A. Vydrov, A. F. Izmaylov, and G. E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).
- ³³H. Peelaers and C. G. Van de Walle, *Phys. Status Solidi B* **252**, 828 (2015).
- ³⁴S. Lany and A. Zunger, *Phys. Rev. B* **80**, 085202 (2009).
- ³⁵V. Ivády, I. A. Abrikosov, E. Janzén, and A. Gali, *Phys. Rev. B* **87**, 205201 (2013).
- ³⁶B. Sadigh, P. Erhart, and D. Åberg, *Phys. Rev. B* **92**, 075202 (2015).
- ³⁷P. Deák, Q. Duy Ho, F. Seemann, B. Aradi, M. Lorke, and T. Frauenheim, *Phys. Rev. B* **95**, 075208 (2017).
- ³⁸D. O. Demchenko, I. C. Diallo, and M. A. Reshchikov, *Phys. Rev. B* **97**, 205205 (2018).
- ³⁹T. Gake, Y. Kumagai, and F. Oba, *Phys. Rev. Mater.* **3**, 044603 (2019).
- ⁴⁰Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
- ⁴¹C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
- ⁴²M. Schubert, R. Korlacki, S. Knight, T. Hofmann, S. Schöche, V. Darakchieva, E. Janzén, B. Monemar, D. Gogova, Q.-T. Thieu, R. Togashi, H. Murakami, Y. Kumagai, K. Goto, A. Kuramata, S. Yamakoshi, and M. Higashiwaki, *Phys. Rev. B* **93**, 125209 (2016).
- ⁴³T. Gake, Y. Kumagai, C. Freysoldt, and F. Oba, "Finite-size corrections for defect-involving vertical transitions in supercell calculations," *Phys. Rev. B* **101**, 020102 (2020).
- ⁴⁴C. Janowitz, V. Scherer, M. Mohamed, A. Krapf, H. Dwell, R. Manzke, Z. Galazka, R. Uecker, K. Irmscher, R. Fornari, M. Michling, D. Schmeißer, J. R. Weber, J. B. Varley, and C. G. V. de Walle, *New J. Phys.* **13**, 085014 (2011).
- ⁴⁵Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **95**, 094105 (2017).
- ⁴⁶Y. K. Frodason, K. M. Johansen, T. S. Bjørheim, B. G. Svensson, and A. Alkauskas, *Phys. Rev. B* **97**, 104109 (2018).
- ⁴⁷B. E. Kananen, L. E. Halliburton, E. M. Scherrer, K. T. Stevens, G. K. Foundos, K. B. Chang, and N. C. Giles, *Appl. Phys. Lett.* **111**, 072102 (2017).
- ⁴⁸Y. K. Frodason, K. M. Johansen, A. Galeckas, and L. Vines, *Phys. Rev. B* **100**, 184102 (2019).
- ⁴⁹J. L. Lyons, A. Janotti, and C. G. Van de Walle, *J. Appl. Phys.* **115**, 012014 (2014).
- ⁵⁰D. O. Demchenko, I. C. Diallo, and M. A. Reshchikov, *J. Appl. Phys.* **119**, 035702 (2016).

- ⁵¹M. E. Ingebrigtsen, A. Y. Kuznetsov, B. G. Svensson, G. Alfieri, A. Mihaila, U. Badstübner, A. Perron, L. Vines, and J. B. Varley, *APL Mater.* **7**, 022510 (2019).
- ⁵²A. Alkauskas, Q. Yan, and C. G. Van de Walle, *Phys. Rev. B* **90**, 075202 (2014).
- ⁵³S. Lany, *APL Mater.* **6**, 046103 (2018).
- ⁵⁴P. Weiser, M. Stavola, W. B. Fowler, Y. Qin, and S. Pearton, *Appl. Phys. Lett.* **112**, 232104 (2018).
- ⁵⁵B. E. Kananen, L. E. Halliburton, K. T. Stevens, G. K. Foundos, and N. C. Giles, *Appl. Phys. Lett.* **110**, 202104 (2017).
- ⁵⁶Y. P. Song, H. Z. Zhang, C. Lin, Y. W. Zhu, G. H. Li, F. H. Yang, and D. P. Yu, *Phys. Rev. B* **69**, 075304 (2004).
- ⁵⁷G. Pozina, M. Forsberg, M. A. Kaliteevski, and C. Hemmingsson, *Sci. Rep.* **7**, 42132 (2017).
- ⁵⁸E. Farzana, A. Mauze, J. B. Varley, T. E. Blue, J. S. Speck, A. R. Arehart, and S. A. Ringel, *APL Mater.* **7**, 121102 (2019).

Paper VI

Ti- and Fe-related charge transition levels in β -Ga₂O₃

C. Zimmermann, Y. K. Frodason, A. W. Barnard, J. B. Varley, K. Irmischer, Z. Galazka, A. Karjalainen, W. E. Meyer, F. D. Auret, L. Vines

Published in *Applied Physics Letters*, February 2020, volume 116, issue 7, pp. 072–101. DOI: 10.1063/1.5139402.

Ti- and Fe-related charge transition levels in β -Ga₂O₃

Cite as: Appl. Phys. Lett. **116**, 072101 (2020); doi: [10.1063/1.5139402](https://doi.org/10.1063/1.5139402)

Submitted: 19 November 2019 · Accepted: 4 February 2020 ·

Published Online: 18 February 2020

Christian Zimmermann,^{1,a)} Ymir Kalmann Frodason,¹ Abraham Willem Barnard,² Joel Basile Varley,³ Klaus Irmscher,⁴ Zbigniew Galazka,⁴ Antti Karjalainen,⁵ Walter Ernst Meyer,² Francois Danie Auret,² and Lasse Vines¹

AFFILIATIONS

¹Department of Physics/Centre for Materials Science and Nanotechnology, University of Oslo, Blindern, P.O. Box 1048, Oslo N-0316, Norway

²Department of Physics, University of Pretoria, Lynnwood Road, Pretoria 0002, South Africa

³Lawrence Livermore National Laboratory, Livermore, California 94550, USA

⁴Leibniz-Institut für Kristallzüchtung, Max-Born-Straße 2, 12489 Berlin, Germany

⁵Department of Applied Physics, Aalto University, 00076 Aalto, Finland

^{a)}Electronic mail: christian.zimmermann@fys.uio.no

ABSTRACT

Deep-level transient spectroscopy measurements on β -Ga₂O₃ crystals reveal the presence of three defect signatures labeled E_{2a} , E_{2b} , and E_3 with activation energies at around 0.66 eV, 0.73 eV, and 0.95 eV below the conduction band edge. Using secondary ion mass spectrometry, a correlation between the defect concentration associated with E_3 and the Ti concentration present in the samples was found. Particularly, it is found that E_3 is the dominant Ti-related defect in β -Ga₂O₃ and is associated with a single Ti atom. This finding is further corroborated by hybrid functional calculations that predict Ti substituting on an octahedral Ga site, denoted as Ti_{Gall}, to be a good candidate for E_3 . Moreover, the deep level transient spectroscopy results show that the level previously labeled E_2 and attributed to Fe substituting on a gallium site (Fe_{Ga}) consists of two overlapping signatures labeled E_{2a} and E_{2b} . We tentatively assign E_{2a} and E_{2b} to Fe substituting for Ga on a tetrahedral or an octahedral site, respectively.

Published under license by AIP Publishing. <https://doi.org/10.1063/1.5139402>

Monoclinic gallium sesquioxide (β -Ga₂O₃) has attracted considerable attention in recent years due to its wide bandgap and exceptionally high break-down electrical fields,¹ rendering it a potential candidate for applications in UV sensors and power electronics.^{1–6} Defects, however, influence the optical and electrical properties of the material and need to be understood for β -Ga₂O₃ to live up to its potential. For example, defects can pin the Fermi-level in semiconductor–metal or semiconductor–insulator–metal junctions and hence influence the performance of devices for power electronics.^{4,7–9}

Intentional and unintentional impurities are particularly relevant defects in β -Ga₂O₃. For example, iron (Fe) is commonly used to achieve semi-insulating β -Ga₂O₃ needed for obtaining field effect transistors based on β -Ga₂O₃,^{1,6} while titanium (Ti) is often used as Ohmic contact on β -Ga₂O₃.^{1,4,6,10–12} Furthermore, Ti in β -Ga₂O₃ was also proposed as a promising defect for quantum information

processing.^{13,14} Fe and Ti are believed to give rise to deep electronic states in β -Ga₂O₃.^{15–19} Indeed, several defect-related electronic levels have been observed by deep level transient spectroscopy (DLTS). In particular, the defect levels commonly labeled as E_1 , E_2 , and E_3 , with energy level positions at 0.56 eV, 0.78 eV, and 1.01 eV below the conduction band edge, respectively, have all been proposed to be related to impurities due to their lack of response to irradiation.²⁰ Indeed, E_2 has been identified as being related to Fe_{Ga} using DLTS in combination with secondary ion mass spectrometry (SIMS) and hybrid functional calculations.

In this study, we report on a combined DLTS and SIMS study. Using both techniques, we were able to tentatively identify a defect level with an activation energy of 0.95 eV below the conduction band edge to be associated with Ti substituting on an octahedral gallium (Ga) site and denoted as Ti_{Gall}. The corresponding level is commonly observed in commercially available β -Ga₂O₃ and is often labeled

as E_3 . Our identification is corroborated by hybrid functional calculations. Furthermore, we were able to show that the defect signature labeled as E_2 , which is commonly seen in DLTS measurements and associated with Fe_{Ga} , indeed consists of at least two defect signatures.

$\beta\text{-Ga}_2\text{O}_3$ bulk crystals grown by edge-defined film-fed growth (EFG)^{21,22} and the Czochralski method (CZ)^{23,24} were used for this study. The EFG crystals were purchased from *Tamura Corporation*, and the CZ crystals were obtained from the *Leibniz-Institut für Kristallzüchtung (Berlin)*. Furthermore, $\beta\text{-Ga}_2\text{O}_3$ thin-films grown by halide vapor-phase epitaxy (HVPE)⁴ on conductive $\beta\text{-Ga}_2\text{O}_3$ substrates and obtained from *Novel Crystal Technology Inc.* were used as reference materials with a low impurity content. All samples were prepared for DLTS measurements, and hence, Ohmic contacts (Ti/Al or InGa eutectic alloy) and Schottky contacts (Ni or Pt) were deposited on the back and front sides, respectively. The resulting junctions exhibit a rectification of at least two orders of magnitude and a series resistance never exceeding 1 k Ω . The samples displayed donor concentrations ranging from $5 \times 10^{15} \text{ cm}^{-3}$ to $7 \times 10^{18} \text{ cm}^{-3}$. Further details regarding the fabrication of Schottky diodes can be found in Ref. 25 for the CZ crystals and in Refs. 12, 15, and 20 for the EFG and HVPE samples.

DLTS measurements were performed on two different setups described in detail elsewhere,^{20,26} with one setup covering the temperature range from 20 K to 400 K and one high-temperature setup enabling measurements between 150 K and 700 K. In short, a reverse bias of -10 V and a filling pulse of 10 V were deployed for conventional DLTS measurements, while Laplace DLTS was performed at a reverse bias of -2 V and a filling pulse of 1.8 V . Laplace DLTS measurements were analyzed with a software written by Dobaczewski *et al.*^{27,28} A GS4 filter was utilized to construct the conventional DLTS spectra in order to better resolve the defect signatures E_2 and E_3 ,²⁹ and the spectra were simulated with a python-based script. Parameters such as the trap concentration N_t , the activation energy E_A , and the apparent capture cross section σ_{na} of the individual traps were obtained from Laplace DLTS measurements by constructing an Arrhenius plot,^{27,30} while these parameters were extracted from conventional DLTS measurements from the afore-mentioned simulations. In both cases, the extracted value for σ_{na} can be expected to exhibit a large uncertainty. For calculating N_t , the λ -correction was included.^{25,30}

SIMS measurements were performed using a Cameca IMS 7f instrument with a primary beam of 10 ke V O_2^+ ions. For Ti, the absolute concentration was determined using an implanted reference sample. Crater depths were measured using a Dektak Stylus Profilometer to convert sputtering time to depth.

First-principles calculations were performed using the projector augmented wave method^{31,32} and the Heyd-Scuseria-Ernzerhof (HSE)³³ screened hybrid functional, as implemented in the VASP code.³⁴ The fraction of screened Hartree-Fock exchange was adjusted to $\alpha = 0.33$, resulting in a direct bandgap of 4.9 eV .³⁵ The experimentally determined bandgap value can be expected to exhibit an uncertainty of around $\pm 0.1 \text{ eV}$.³⁵ The Ga-3d and Ti-3p, -3d, and -4s electrons were included as valence states. For defect calculations, we used 160-atom supercells, a plane wave energy cutoff of 500 eV , and a single special k -point at $(1/4, 1/4, 1/4)$. Defect formation energies and thermodynamic charge-state transition levels were calculated by following the well-established formalism.³⁶ For charged defects, we adopted the anisotropic³⁷ Freysoldt, Neugebauer, and Van de Walle scheme to correct formation energies³⁸ and the method recently proposed by Gake *et al.* to correct vertical transition energies.³⁹ Nonradiative carrier capture barriers were estimated by using the one-dimensional configuration coordinate (CC) model.⁴⁰ The CC diagrams were derived from the calculated one-dimensional CC model parameters by using a harmonic approximation.⁴¹

Figure 1(a) shows DLTS spectra recorded on an EFG-grown $\beta\text{-Ga}_2\text{O}_3$ crystal. Three defect signatures are observed labeled as E_{2a} ($E_A = 0.66 \text{ eV}$, $\sigma_{\text{na}} = 4 \times 10^{-16} \text{ cm}^2$), E_{2b} ($E_A = 0.73 \text{ eV}$, $\sigma_{\text{na}} = 1 \times 10^{-15} \text{ cm}^2$), and E_3 ($E_A = 0.95 \text{ eV}$, $\sigma_{\text{na}} = 4 \times 10^{-14} \text{ cm}^2$). Defect signatures similar to E_{2a} and E_{2b} were found in EFG- and CZ-grown $\beta\text{-Ga}_2\text{O}_3$ crystals and HVPE-grown $\beta\text{-Ga}_2\text{O}_3$ thin-films, while E_3 was only found in EFG- and CZ-grown $\beta\text{-Ga}_2\text{O}_3$ crystals. Notably, on similar samples, the E_A values of around 1.04 eV (Ref. 25) and 1.01 eV (Ref. 20) have been reported previously for E_3 . Hence, an uncertainty of around 0.1 eV can be assumed for the values of E_A stated here. Considering the previously reported values for σ_{na} of E_2 and E_3 ,^{20,25} an uncertainty of around $\pm$ an order of magnitude can be expected.

Figure 1(b) displays the results obtained performing Laplace DLTS on an EFG-grown $\beta\text{-Ga}_2\text{O}_3$ crystal. The corresponding results corroborate the findings presented above and in Fig. 1(a). Three defect signatures were revealed: E_{2a} ($E_A = 0.56 \text{ eV}$, $\sigma_{\text{na}} = 1 \times 10^{-17} \text{ cm}^2$), E_{2b} ($E_A = 0.70 \text{ eV}$, $\sigma_{\text{na}} = 4 \times 10^{-16} \text{ cm}^2$), and E_3 ($E_A = 0.98 \text{ eV}$, $\sigma_{\text{na}} = 4 \times 10^{-14} \text{ cm}^2$). These parameters match well with the results obtained from simulations of conventional DLTS spectra. The defect parameters extracted from conventional and Laplace DLTS measurements are summarized in Table I.

In previous studies, the signatures E_{2a} and E_{2b} were observed as a single defect signature labeled E_2 ,^{9,15,25,42,43} which was attributed to Fe_{Ga} . E_2 and E_3 are present in a variety of commercially available $\beta\text{-Ga}_2\text{O}_3$ crystals and thin-films.^{9,15,25,42–46} Notably, neither E_2 nor E_3 has been found to be affected by irradiation with protons,^{15,20}

FIG. 1. (a) DLTS spectra recorded on an EFG-grown $\beta\text{-Ga}_2\text{O}_3$ crystal. The data were modeled with a simulation, and three defect signatures labeled as E_{2a} , E_{2b} , and E_3 were unveiled. (b) Results from Laplace DLTS performed on an EFG-grown $\beta\text{-Ga}_2\text{O}_3$ crystal. The Arrhenius plot for the three defect signatures, which are also detected in (a), is shown. The inset shows the emission rate spectrum obtained from the capacitance transient recorded at 400 K .

TABLE I. Overview of the parameters determined for defect signatures observed in a variety of β -Ga₂O₃ crystals. The results were obtained on EFG-, CZ-, and HVPE-grown Ga₂O₃ simulating their conventional DLTS spectra. The results in brackets were derived from Laplace DLTS measurements on an EFG-grown β -Ga₂O₃ crystal.

Defect signature	Activation energy E_A (eV)	Apparent capture cross section σ_{na} (cm ²)
E_{2a}	0.66 (0.56)	4×10^{-16} (1×10^{-17})
E_{2b}	0.73 (0.70)	1×10^{-15} (4×10^{-16})
E_3	0.95 (0.98)	4×10^{-14} (4×10^{-14})

suggesting the involvement of an impurity. After irradiation with protons or α -particles, another level commonly labeled as E_2^* with a charge transition level of around 0.75 eV below the conduction band edge is present in the same temperature region in DLTS measurements.^{15,20,43,47} E_2^* , however, displays a significantly different activation energy and an apparent capture cross section compared to, for example, E_{2a} , suggesting a different origin. Moreover, the trap concentrations associated with E_{2a} and E_{2b} exhibit a ratio of approximately 1:5 (not shown). Notably, a similar ratio is expected for the two configurations of Fe_{Ga}, assuming a difference in the formation energy of 0.3 eV (Ref. 15) at the melting point temperature.^{48,49} Notably, an electron paramagnetic resonance (EPR) study also found a ratio of 1:5 for the two different crystallographic configurations of Fe_{Ga} in β -Ga₂O₃.⁵⁰ Hence, we suggest that E_{2a} and E_{2b} arise from the tetrahedral and octahedral configuration of Fe_{Ga}, respectively.

Figure 2(a) shows an overview over DLTS spectra recorded on a variety of Schottky junctions including CZ-, EFG- and HVPE-grown β -Ga₂O₃. The trap concentration in HVPE-grown β -Ga₂O₃ is generally significantly lower than in CZ- or EFG-grown β -Ga₂O₃ as reported earlier.²⁰ For some CZ-grown β -Ga₂O₃ crystals [see CZ A in Fig. 2(a)], it was not possible to model the region where E_{2a} and E_{2b} are present with only two defect signatures, indicating the presence of additional defect signatures in this temperature region in DLTS measurements. The modeling of conventional DLTS spectra described the signature related to E_3 , suggesting that, indeed, only one defect contributes to this defect signature, as corroborated by Laplace DLTS [see Fig. 1(b)].

A wide range of concentrations associated with E_{2a} , E_{2b} , and E_3 are found in CZ- and EFG-grown samples as reported previously,^{15,25}

rendering them suitable candidates for the identification of impurity-related defects. SIMS measurements reveal that Ti, Fe, Mg, Al, and Si are present in at least some of the investigated samples. In addition to the correlation between E_2 and Fe reported previously,¹⁵ the concentration of E_3 was found to correlate solely with that of Ti. Figure 2(b) displays the correlation between the Ti concentration [Ti] as determined by SIMS and the E_3 trap concentration [E_3] as determined by DLTS (square brackets denote concentration). A linear relationship between [Ti] and [E_3] can be seen. Notably, all data points fall close to the line expected for [Ti] = [E_3], suggesting that E_3 is the dominant Ti-related trap and associated with a single Ti atom. Importantly, in HVPE-grown β -Ga₂O₃, the concentration of both Ti and E_3 was found to be below the detection limit of our systems, further corroborating the correlation between Ti and E_3 .

To gain insights into the formation of defects involving Ti in β -Ga₂O₃ and corroborate the observed correlation between [E_3] and [Ti], we have performed hybrid functional calculations. Only results for the Ti_{Ga} configurations are presented since Ti_O and Ti_i configurations were found to have significantly higher formation energies (not shown). Figure 3(a) displays the formation energy diagram for Ti_{Ga} and Ti_{Gall}, where Gal and Gall denote the tetrahedral and octahedral Ga sites in the β -Ga₂O₃ lattice. Ti_{Gall} has the lowest formation energy regardless of the Fermi level position: the difference is 0.34 eV and 0.86 eV for the positive and neutral charge states, respectively. This means that Ti_{Gall} is expected to be the dominant configuration for Ti_{Ga}, which is consistent with EPR studies performed on β -Ga₂O₃ crystals, where only Ti_{Gall} was identified.^{13,14,16} A recent study reporting first-principles calculations on Ti in β -Ga₂O₃ found very similar results for Ti_{Ga}.¹⁹ Furthermore, the solubility of Ti is expected to be around 1.5 at. % in β -Ga₂O₃,⁵¹ which is consistent with the low formation energy found here for Ti_{Gall}. Notably, the amount of unintentionally incorporated Ti will strongly depend on both the amount of Ti present and the experimental conditions during growth.

Ti_{Ga} is predicted to act as a deep single donor on both lattice sites. In the neutral charge state, the donor electron occupies a localized defect state within the bandgap, showing mainly Ti 3d character. The calculated thermodynamic (+/0) charge state transition level of Ti_{Ga} and Ti_{Gall} occurs at 0.60 eV and 1.13 eV below the conduction band minimum (CBM), respectively. To enable a more direct comparison with the DLTS results, we have estimated the classical capture barrier for electrons E_b by constructing a CC diagram,⁴⁰ as shown in Fig. 3(b). The excited state potential energy surface corresponds to the ionized

FIG. 2. (a) DLTS spectra recorded on various CZ-, EFG- and HVPE-grown β -Ga₂O₃. The corresponding surface orientations are also shown in the legend. The spectra were aligned along the temperature axis with respect to the peak position of the signature labeled E_3 as observed in the sample labeled CZ A (100). The temperature positions of E_{2a} , E_{2b} , and E_3 are marked. (b) Comparison between the titanium concentration obtained from calibrated SIMS measurements and the trap concentration related to E_3 determined by simulating conventional DLTS spectra. Ellipsoidal areas are shown if the uncertainties for [E_3] are larger than the data points displayed. The detection limit for [Ti] as measured by SIMS is estimated to be around 1×10^{15} cm⁻³. [Ti] in HVPE-grown β -Ga₂O₃ is below that limit, and no signal corresponding to E_3 was detected in HVPE-grown β -Ga₂O₃. As a guide, a line corresponding to [E_3] = [Ti] is shown.

FIG. 3. (a) Formation energy of Ti_{Gal} and Ti_{Gall} in dependence of the Fermi level position. The valence and conduction band positions are marked in gray. Formation energies are displayed for O-rich and O-poor conditions. Ti_{Gal} is generally more favorable to form compared to Ti_{Gall} . Ti_{Gal} and Ti_{Gall} are deep single donors and exhibit a charge state transition from $+$ to 0 inside the bandgap of $\beta\text{-Ga}_2\text{O}_3$ at around 0.60 eV and 1.13 eV below the conduction band edge, respectively. The corresponding transition point is marked with a black dot. (b) Configuration coordinate diagrams describing electron capture and emission between the conduction band minimum (CBM) and Ti_{Gal} . The thermal ionization energy E_i is the thermodynamic $(+/-0)$ charge transition level relative to the CBM. The absorption energy E_{abs} is related to the photon energy where the onset of optical absorption is expected within the Franck–Condon approximation. The barrier E_b for the capture of electrons is given by the crossing point between the ground and excited state potential energy surfaces.

donor plus an electron at the CBM ($\text{Ti}_{\text{Gall}}^+ + e_{\text{CBM}}$), and the ground-state curve corresponds to the charge-neutral donor ($\text{Ti}_{\text{Gall}}^0$). The two curves are vertically displaced by the thermal ionization energy E_i , i.e., the Fermi level position of the thermodynamic $(+/-0)$ charge-state transition level relative to the CBM. In this classical picture, the activation energy for electron emission corresponds to the sum of E_i and E_b , which is taken as the energy required to reach the crossing point between the two potential energy curves. For Ti_{Gal} , we obtain a capture barrier of 0.09 eV, whereas no barrier was found for Ti_{Gall} . Note that the activation energy will be lower if its temperature-dependence is taken into account.⁴⁰ Thus, we arrive at 0.69 eV and 1.13 eV as the upper limit for the activation energy of Ti_{Gal} and Ti_{Gall} , respectively. Hence, the calculated transition level for $\text{Ti}_{\text{Gall}}^{(+/-0)}$ agrees within the errors of experiment and theoretical calculation with the activation energy found for E_3 (0.95 eV), further strengthening the assignment of E_3 to Ti. The calculated defect parameters for Ti_{Ga} are summarized in Table II.

In summary, conventional DLTS measurements on selected EFG- and CZ-grown $\beta\text{-Ga}_2\text{O}_3$ crystals reveal the presence of three defect signatures labeled E_{2a} , E_{2b} , and E_3 with activation energies of around 0.66 eV, 0.73 eV, and 0.95 eV below the conduction band edge. E_{2a} and E_{2b} are also found in HVPE-grown $\beta\text{-Ga}_2\text{O}_3$ thin-films, while E_3 was not detected in such samples. It is found that the defect level labeled E_2 , which is attributed to Fe_{Ga} , consists of two distinct defect signatures labeled E_{2a} and E_{2b} . It is proposed that E_{2a} and E_{2b} are associated with Fe substituting for Ga on a tetrahedral or an octahedral site, respectively. The defect concentration associated with E_3 is found to be correlated with the Ti concentration present in the samples as measured by SIMS. Particularly, it is shown that E_3 is the dominant Ti-related defect in $\beta\text{-Ga}_2\text{O}_3$ and is associated with a single Ti atom. This is further supported by hybrid functional calculations where Ti

substituting on an octahedral Ga site denoted as Ti_{Gall} is shown to be an excellent candidate for E_3 .

Financial support from the Research Council of Norway through the FUNDAMENT project (Project No. 251131), the Norwegian Micro- and Nano-Fabrication Facility (NorFab, Project No. 245963), the Faculty of Mathematics and Natural Sciences at the University of Oslo via the strategic research initiative FOXHOUND, and the Norwegian nano-network is acknowledged. This work was partially performed under the auspices of the U.S. DOE by Lawrence Livermore National Laboratory under Contract No. DE-AC52-07NA27344 and partially supported by the Critical Materials Institute funded by the U.S. DOE, Office of Energy Efficiency and Renewable Energy, Advanced Manufacturing Office.

REFERENCES

¹M. Higashiwaki, K. Sasaki, H. Murakami, Y. Kumagai, A. Koukitu, A. Kuramata, T. Masui, and S. Yamakoshi, *Semicond. Sci. Technol.* **31**, 034001 (2016).
²S. Nakagomi, T. Momo, S. Takahashi, and Y. Kokubun, *Appl. Phys. Lett.* **103**, 072105 (2013).
³S. Nakagomi, T. Sato, Y. Takahashi, and Y. Kokubun, *Sens. Actuators, A* **232**, 208 (2015).
⁴M. A. Mastro, A. Kuramata, J. Calkins, J. Kim, F. Ren, and S. Pearton, *ECS J. Solid State Sci. Technol.* **6**, P356 (2017).
⁵Z. Galazka, *Semicond. Sci. Technol.* **33**, 113001 (2018).
⁶S. Pearton, J. Yang, P. H. Cary IV, F. Ren, J. Kim, M. J. Tadjer, and M. A. Mastro, *Appl. Phys. Rev.* **5**, 011301 (2018).
⁷S. Ahn, Y.-H. Lin, F. Ren, S. Oh, Y. Jung, G. Yang, J. Kim, M. A. Mastro, J. K. Hite, C. R. Eddy, Jr. *et al.*, *J. Vac. Sci. Technol., B* **34**, 041213 (2016).
⁸J. F. McGlone, Z. Xia, C. Joishi, S. Lodha, S. Rajan, S. Ringel, and A. R. Arehart, *Appl. Phys. Lett.* **115**, 153501 (2019).
⁹J. F. McGlone, Z. Xia, Y. Zhang, C. Joishi, S. Lodha, S. Rajan, S. A. Ringel, and A. R. Arehart, *IEEE Electron Device Lett.* **39**, 1042 (2018).
¹⁰M.-H. Lee and R. L. Peterson, *APL Mater.* **7**, 022524 (2019).
¹¹M.-H. Lee and R. L. Peterson, *ECS J. Solid State Sci. Technol.* **8**, Q3176 (2019).
¹²M. E. Ingebrigtsen, L. Vines, G. Alfieri, A. Mihaila, U. Badstübner, B. G. Svensson, and A. Kuznetsov, *Mater. Sci. Forum* **897**, 755 (2017).
¹³F. Mentink-Vigier, L. Binet, G. Vignoles, D. Gourier, and H. Vezin, *Phys. Rev. B* **82**, 184414 (2010).
¹⁴F. Mentink-Vigier, L. Binet, D. Gourier, and H. Vezin, *J. Phys.: Condens. Matter* **25**, 316002 (2013).
¹⁵M. E. Ingebrigtsen, J. Varley, A. Y. Kuznetsov, B. G. Svensson, G. Alfieri, A. Mihaila, U. Badstübner, and L. Vines, *Appl. Phys. Lett.* **112**, 042104 (2018).

TABLE II. Summary of the parameters for Ti_{Ga} defects obtained from hybrid functional calculations. The parameters are defined as displayed in Fig. 3(b).

Defect	E_{abs} (eV)	E_i (eV)	E_b (meV)
Ti_{Gal}	2.02	0.60	86
Ti_{Gall}	2.27	1.13	3

- ¹⁶L. Binet, D. Gourier, and C. Minot, *J. Solid State Chem.* **113**, 420 (1994).
- ¹⁷Y. Tomm, J. Ko, A. Yoshikawa, and T. Fukuda, *Sol. Energy Mater. Sol. Cells* **66**, 369 (2001).
- ¹⁸C. Tang, J. Sun, N. Lin, Z. Jia, W. Mu, X. Tao, and X. Zhao, *RSC Adv.* **6**, 78322 (2016).
- ¹⁹M. Saleh, J. B. Varley, J. Jesenovc, A. Bhattacharyya, S. Krishnamoorthy, S. Swain, and K. Lynn, "Degenerate doping in β -Ga₂O₃ single crystals through Hf-doping," preprint [arXiv:2001.11187](https://arxiv.org/abs/2001.11187) (2020).
- ²⁰M. Ingebrigtsen, A. Y. Kuznetsov, B. Svensson, G. Alfieri, A. Mihaila, U. Badstübner, A. Perron, L. Vines, and J. Varley, *APL Mater.* **7**, 022510 (2019).
- ²¹H. Aida, K. Nishiguchi, H. Takeda, N. Aota, K. Sunakawa, and Y. Yaguchi, *Jpn. J. Appl. Phys., Part 1* **47**, 8506 (2008).
- ²²A. Kuramata, K. Koshi, S. Watanabe, Y. Yamaoka, T. Masui, and S. Yamakoshi, *Jpn. J. Appl. Phys., Part 1* **55**, 1202A2 (2016).
- ²³Z. Galazka, K. Irmscher, R. Uecker, R. Bertram, M. Pietsch, A. Kwasniewski, M. Naumann, T. Schulz, R. Schewski, D. Klimm *et al.*, *J. Cryst. Growth* **404**, 184 (2014).
- ²⁴Z. Galazka, R. Uecker, D. Klimm, K. Irmscher, M. Naumann, M. Pietsch, A. Kwasniewski, R. Bertram, S. Ganschow, and M. Bickermann, *ECS J. Solid State Sci. Technol.* **6**, Q3007 (2017).
- ²⁵K. Irmscher, Z. Galazka, M. Pietsch, R. Uecker, and R. Fornari, *J. Appl. Phys.* **110**, 063720 (2011).
- ²⁶B. Svensson, K.-H. Rydén, and B. Lewerentz, *J. Appl. Phys.* **66**, 1699 (1989).
- ²⁷L. Dobaczewski, P. Kaczor, I. D. Hawkins, and A. R. Peaker, *J. Appl. Phys.* **76**, 194 (1994).
- ²⁸See <http://info.ifpan.edu.pl/Dodatki/WordPress/laplacedit/> for "Software Laplace Deep-Level Transient Spectroscopy 2019" (last accessed October 07, 2019).
- ²⁹A. A. Istratov, *J. Appl. Phys.* **82**, 2965 (1997).
- ³⁰P. Blood and J. Orton, *The Electrical Characterization of Semiconductors: Majority Carriers and Electron States* (Academic Press, 1992).
- ³¹P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- ³²G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- ³³A. V. Krukau, O. A. Vydrov, A. F. Izmaylov, and G. E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).
- ³⁴G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- ³⁵C. Janowitz, V. Scherer, M. Mohamed, A. Krapf, H. Dwellk, R. Mancke, Z. Galazka, R. Uecker, K. Irmscher, R. Fornari *et al.*, *New J. Phys.* **13**, 085014 (2011).
- ³⁶C. Freysoldt, B. Grabowski, T. Hickel, J. Neugebauer, G. Kresse, A. Janotti, and C. G. Van de Walle, *Rev. Mod. Phys.* **86**, 253 (2014).
- ³⁷Y. Kumagai and F. Oba, *Phys. Rev. B* **89**, 195205 (2014).
- ³⁸C. Freysoldt, J. Neugebauer, and C. G. Van de Walle, *Phys. Rev. Lett.* **102**, 016402 (2009).
- ³⁹T. Gake, Y. Kumagai, and F. Oba, [arXiv:1907.02380](https://arxiv.org/abs/1907.02380) (2019).
- ⁴⁰D. Wickramaratne, C. E. Dreyer, B. Monserrat, J.-X. Shen, J. L. Lyons, A. Alkauskas, and C. G. Van de Walle, *Appl. Phys. Lett.* **113**, 192106 (2018).
- ⁴¹A. Alkauskas, Q. Yan, and C. G. Van de Walle, *Phys. Rev. B* **90**, 075202 (2014).
- ⁴²A. Polyakov, N. Smirnov, I. Shchemerov, D. Gogova, S. Tarelkin, and S. Pearton, *J. Appl. Phys.* **123**, 115702 (2018).
- ⁴³A. Polyakov, N. Smirnov, I. Shchemerov, E. Yakimov, J. Yang, F. Ren, G. Yang, J. Kim, A. Kuramata, and S. Pearton, *Appl. Phys. Lett.* **112**, 032107 (2018).
- ⁴⁴A. Polyakov, N. Smirnov, I. Shchemerov, E. Yakimov, S. Pearton, C. Fares, J. Yang, F. Ren, J. Kim, P. Lagov *et al.*, *Appl. Phys. Lett.* **113**, 092102 (2018).
- ⁴⁵Z. Zhang, E. Farzana, A. Arehart, and S. Ringel, *Appl. Phys. Lett.* **108**, 052105 (2016).
- ⁴⁶E. Farzana, E. Ahmadi, J. S. Speck, A. R. Arehart, and S. A. Ringel, *J. Appl. Phys.* **123**, 161410 (2018).
- ⁴⁷A. Polyakov, N. Smirnov, I. Shchemerov, S. Pearton, F. Ren, A. Chernykh, P. Lagov, and T. V. Kulevoy, *APL Mater.* **6**, 096102 (2018).
- ⁴⁸K. Hoshikawa, E. Ohba, T. Kobayashi, J. Yanagisawa, C. Miyagawa, and Y. Nakamura, *J. Cryst. Growth* **447**, 36 (2016).
- ⁴⁹Z. Galazka, R. Uecker, K. Irmscher, M. Albrecht, D. Klimm, M. Pietsch, M. Brützam, R. Bertram, S. Ganschow, and R. Fornari, *Cryst. Res. Technol.* **45**, 1229 (2010).
- ⁵⁰R. Büscher and G. Lehmann, *Z. Naturforsch. A* **42**, 67 (1987).
- ⁵¹S. Manandhar and C. V. Ramana, *Appl. Phys. Lett.* **110**, 061902 (2017).

Combining steady-state photo-capacitance spectra with first-principles calculations: the case of Fe and Ti in β -Ga₂O₃

C. Zimmermann, Y. K. Frodason, V. Rønning, J. B. Varley, L. Vines

Published in *New Journal of Physics*, February 2020, volume 22, issue 6, pp. 063–033. DOI: 10.1088/1367-2630/ab8e5b.

PAPER

OPEN ACCESS

RECEIVED
4 March 2020REVISED
19 April 2020ACCEPTED FOR PUBLICATION
29 April 2020PUBLISHED
19 June 2020Original content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](https://creativecommons.org/licenses/by/4.0/).

Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.

Combining steady-state photo-capacitance spectra with first-principles calculations: the case of Fe and Ti in β -Ga₂O₃C Zimmermann^{1,3} , Y Kalmann Frodason¹ , V Rønning¹, J B Varley² and L Vines¹ ¹ Department of Physics/Centre for Materials Science and Nanotechnology, University of Oslo, P.O. Box 1048, Blindern, Oslo N-0316, Norway² Lawrence Livermore National Laboratory, Livermore, CA 94550 United States of America³ Author to whom any correspondence should be addressed.E-mail: christian.zimmermann@fys.uio.no**Keywords:** defects in semiconductors, steady-state photo-capacitance, first-principles calculations, β -Ga₂O₃, deep-level transient spectroscopy, wide band gap semiconductors

Abstract

In this study, we demonstrate an approach to identify defects in wide band gap semiconductors by comparing accumulatively-recorded derivative steady-state photo-capacitance (SSPC) spectra to simulations using results from first-principles calculations. Specifically, we present a method to simulate SSPC spectra which adopts inputs both from first-principles calculations and the experimental conditions. The applicability of the developed method is demonstrated using the cases of substitutional Fe (Fe_{Ga}) and Ti (Ti_{Ga}) defects in β -Ga₂O₃. Using deep-level transient spectroscopy, we identify defect levels associated with Fe_{Ga}^{0/-} ($E_A = 0.66$ eV), Fe_{Ga}^{0/-} ($E_A = 0.79$ eV) and Ti_{Ga}^{+ /0} ($E_A = 1.03$ eV) in the β -Ga₂O₃ samples studied here. Accumulatively-recorded SSPC spectra reveal several defect levels labeled $T_1^{\text{EFG}} - T_6^{\text{EFG}}$ with onsets for optical absorption between 1.5 eV and 4.3 eV. The signature T_1^{EFG} consists of several overlapping defect signatures, and is identified as being related to Fe_{Ga}^{0/-}, Fe_{Ga}^{0/-} and Ti_{Ga}^{+ /0} by comparing measured and simulated accumulatively-recorded derivative SSPC spectra.

1. Introduction

Defects have a pronounced influence on the electrical and optical properties of semiconductors, and are fundamentally important in determining the expected performance of a given semiconductor device. Often, defects are studied by using their charge state transition levels (defect levels) as fingerprints, while their unambiguous identification requires the simultaneous utilization of a number of techniques [1, 2]. In recent years, many wide band gap semiconductors, such as monoclinic gallium sesquioxide (β -Ga₂O₃), have attracted considerable research interest due to promising properties for applications ranging from photo-detectors to power electronics [3–6]. It is, however, a particular challenge to study the electronic properties of defect levels in wide band gap semiconductors.

A widely-used technique to study defect levels in semiconductors is deep-level transient spectroscopy (DLTS) [1, 7], but the accessible part of the band gap is typically limited by the temperature range used for the measurement because DLTS probes defect levels by measuring the thermally-induced emission of charge carriers from defects (traps). For example, in the case of β -Ga₂O₃, defect levels up to 1.4 eV below the conduction band edge can typically be observed using DLTS [8, 9]. Steady-state photo-capacitance (SSPC) measurements and related techniques [1, 10] measure the optically-induced emission of charge carriers from traps, and are complementary to DLTS measurements. Using suitable optical excitation, SSPC measurements can detect defect levels throughout the whole band gap of wide band gap semiconductors. Indeed, SSPC measurements and their transient counter-part deep-level optical spectroscopy have been

used to reveal several deep level defects in β -Ga₂O₃ [11–18]. SSPC measurements, as well as DLTS measurements, also provide the concentration of the traps associated with the observed defect levels. This enables a wide range of study designs suitable for identifying extrinsic as well as intrinsic defects.

First-principles calculations for defect levels in semiconductors have seen significant advancements in recent years, for example, by the introduction of hybrid-functionals, such as the Heyd–Scuseria–Ernzerhof (HSE) functionals [19] which yield an improved description of the atomic and electronic structure of semiconductors, as well as the degree of charge localization at defects [20]. These advances have bridged the gap between calculated defect levels and defect levels observed by techniques like DLTS [21, 22]. For β -Ga₂O₃, specific defect levels observed by DLTS have been identified and assigned to Fe_{GaI} (substitutional Fe on a tetrahedral Ga site), Fe_{GaII} (substitutional Fe on an octahedral Ga site) and Ti_{GaII} (substitutional Ti on an octahedral Ga site) by correlating computational and experimental results [8, 23]. Results from first-principles calculations can also be used to correlate signatures seen in SSPC measurements to specific defects present in a material. Specifically, the optical absorption associated with a defect level can be predicted [22, 24]. However, a clear and corroborated methodology to perform such comparisons is still missing. Particularly, the effect of experimental parameters on the spectral position of signatures seen in SSPC measurements should be taken into account.

Here, we report on a methodology to simulate SSPC spectra from results of first-principles calculations, enabling a comparison between first-principles calculations and SSPC measurements. Fe- and Ti-related charge state transition levels which have recently been identified by DLTS in β -Ga₂O₃ [8, 23] are used to verify the validity of our method, and thereby, we also identify the corresponding SSPC signatures related to Fe_{GaI}, Fe_{GaII} and Ti_{GaII} in β -Ga₂O₃.

2. Experimental details

Bulk β -Ga₂O₃ crystals grown by edge-defined film-fed growth (EFG) [25, 26] with a surface orientation of (−201) were obtained from *Tamura Corporation*. Samples measuring approximately (5×5) mm² were cut with a laser cutter. All samples were prepared for DLTS and SSPC measurements by depositing metal contacts using e-beam evaporation. The samples were cleaned inside an ultrasonic bath using acetone, isopropanol and de-ionized water prior to the metal depositions. Stacks of Ti and Al with a thickness of 10 nm and 120 nm, respectively, were deposited on the back side and used as Ohmic contacts, while front-side Ni contacts were used as semi-transparent Schottky contacts [27, 28]. First, Ni contacts with a thickness of 10 nm were deposited using a shadow mask with diameters of 300 μ m, 600 μ m and 900 μ m. Subsequently, another layer of Ni with a thickness of 150 nm was deposited using a shadow mask with circular openings (diameter = 300 μ m) which aligns with the first deposition such that the thick Ni pads are on top of the semi-transparent Ni pads. The thick Ni parts enable mechanical stability for wire-bonding. Additionally, Pd pads were deposited on top of the thick Ni part to further improve the wire-bonding.

Capacitance–voltage (CV) and current–voltage (IV) measurements were performed using a Keithley 6487 picoammeter/voltage source and either an HP4280 A or Boonton 7200 capacitance meter, respectively. CV measurements were performed at a probing frequency of 1 MHz. CV and IV measurements were performed to ensure device characteristics suitable for DLTS and SSPC measurements as well as to determine the donor concentration (N_D) of the β -Ga₂O₃ samples [1]. For analyzing CV measurements, a relative static dielectric constant (ϵ_s) of 10.2 was assumed for β -Ga₂O₃ [29].

DLTS measurements were performed using a setup described in detail in [23, 30]. The setup allows for DLTS measurements in the temperature range from 150 K to 680 K. DLTS spectra were constructed using a GS4 filter [31]. In order to obtain parameters describing traps, such as trap concentration (N_{tr}), activation energy (E_A) and apparent capture cross section (σ_{na}) DLTS spectra were simulated using a python-based script, where the λ -correction was employed to obtain N_{tr} [1, 32]. E_A is the sum of the classical activation energy for carrier capture (E_b) and the thermodynamic charge-state transition level [1, 21]. σ_{na} depends both on E_b and a prefactor (σ_0) which is, for example, dependent on the charge state of the trap [21, 33–37]. For the samples studied here, larger values for σ_0 can be expected for positively-charged traps as compared to neutral traps, whereas neutral traps are expected to exhibit larger values of σ_0 than negatively-charged traps [34, 37]. More information regarding the simulation of DLTS spectra and the λ -correction can be found in the appendix A.

SSPC measurements were performed with a setup described in detail in [28]. The photo-capacitance (C_{illum}) of the samples is recorded after illuminating the junction at a photon energy E for a time t_{illum} , whereby t_{illum} between 30 s and 1200 s were employed for this study. C_{illum} is referenced to the capacitance

of the junction in the dark (C_{dark}). All capacitance values were measured at a fixed external bias (V_{ext}) of -8 V. SSPC spectra $S(E, t_{\text{illum}})$ were recorded by subsequently measuring $C_{\text{illum}}(E, t_{\text{illum}})$ at different E after t_{illum} . Measurements were performed using steps (ΔE) of 20 meV in-between subsequent E . The spectral distribution of the optical excitation represented by the photon flux ($\Phi(E)$) was determined using a calibrated thermal power meter placed at the sample position, and is shown in figure 1. Typical photon fluxes of $1 \times 10^{17} \text{ m}^{-2} \text{ s}^{-1}$ in the UV and $1 \times 10^{19} \text{ m}^{-2} \text{ s}^{-1}$ in the visible part of the spectrum were found. SSPC spectra were recorded at 120 K.

SSPC measurements can be performed accumulatively [28] or non-accumulatively [1, 13]. For the accumulative SSPC measurements conducted here, $S(E, t_{\text{illum}})$ was recorded at subsequent E without changing V_{ext} , and the measurements were exclusively performed in ascending order of E . In contrast, in non-accumulative SSPC measurements, V_{ext} is set to 0 V in-between measurements at subsequent E .

3. Methodology

3.1. First-principles calculations based on hybrid-functionals

A detailed description of the first-principles methodology and computational details can be found in [23], thus only a brief summary is given here. All calculations were performed using the Heyd–Scuseria–Ernzerhof [19] range-separated hybrid functional, as implemented in the VASP code [38], with the fraction of screened Hartree–Fock exchange set to $\alpha = 0.33$. Defect calculations were performed with 160-atom supercells, a plane-wave energy cutoff of 500 eV and a single k -point at (1/4, 1/4, 1/4). To remedy the spurious supercell-size dependence of thermodynamic and vertical charge state transition energies, we used the correction schemes of Freysoldt *et al* [39, 40], and Gake *et al* [41], respectively.

The optical properties of Fe_{GaI} , Fe_{GaII} and Ti_{GaII} were investigated within the framework of the one-dimensional configuration coordinate (CC) model [20, 22, 42, 43]. CC diagrams were constructed using model parameters from the hybrid-functional calculations, namely the change in configuration coordinate ΔQ , the zero-phonon line (ZPL) energy E_{ZPL} , and the effective vibrational frequencies Ω_g and Ω_e in the ground (g) and excited (e) state, respectively. In the Franck–Condon (FC) approximation, optical transitions are vertical with no change in configuration coordinate. Classical emission and absorption energies can then be defined as $E_{\text{em}} = E_{\text{ZPL}} - d_g^{\text{FC}}$ and $E_{\text{abs}} = E_{\text{ZPL}} + d_e^{\text{FC}}$, respectively, where d_g^{FC} and d_e^{FC} are the so-called FC shifts. The normalized absorption cross-section $\sigma_{i,\text{norm}}^o(E)$, including temperature-dependent vibrational broadening, can be simulated using the effective vibrational frequencies, as outlined in [22, 24].

$\sigma_{n,\text{norm}}^o(E)$ is related to the optically-induced emission of electrons from a defect, while $\sigma_{p,\text{norm}}^o(E)$ is related to the optically-induced emission of holes. Thus, $\sigma_{n,\text{norm}}^o(E)$ is related to processes involving electrons and the conduction band edge, and $\sigma_{p,\text{norm}}^o(E)$ is associated with processes involving electrons and the valence band edge.

3.2. Simulation of steady-state photo-capacitance spectra

The SSPC signal $S(E, t_{\text{illum}})$ is usually presented as [1, 10]:

$$S(E, t_{\text{illum}}) = 2 \frac{C_{\text{illum}}(E, t_{\text{illum}}) - C_{\text{dark}}}{C_{\text{dark}}} N_D = 2 \frac{\Delta C_{\text{illum}}(E, t_{\text{illum}})}{C_{\text{dark}}} N_D = N_{\text{tr,eff}}^*(E, t_{\text{illum}}). \quad (1)$$

Here, $\Delta C_{\text{illum}}(E, t_{\text{illum}})$ denotes the change in (photo-)capacitance during illumination for t_{illum} at E , and C_{dark} represents the capacitance of the junction measured in the dark. $N_{\text{tr,eff}}^*(E, t_{\text{illum}})$ is the change in the

concentration of ionized traps inside the probing volume due to illumination. However the probing volume will usually not be equal to the volume of the space-charge region [1, 28]. Moreover, equation (1) assumes $N_D \ll N_{tr,eff}^*$ to be valid.

$S(E, t_{illum})$ can be expressed with the following empirically-motivated formula [28]:

$$S(E, t_{illum}) = 2N_D \sum_i \frac{\Delta C_{illum,i}}{C_{dark}} \frac{1}{1 + \exp\left(-\frac{E-E_i}{\gamma_i}\right)} \quad (2)$$

where E_i denotes the onset of optical absorption related to trap i , and γ_i describes the steepness of the corresponding step in $S(E, t_{illum})$. $\Delta C_{illum,i}$ is the (photo-)capacitance change related to photo-excitation of trap i . $\Delta C_{illum,i}$ are larger than zero for optically-induced electron emission, and are smaller than zero for optically-induced hole emission. Results of SSPC measurements can also be presented as derivative SSPC spectra $dS(E, t_{illum})/dE$ [10, 28, 44]. Peaks at E_i in $dS(E, t_{illum})/dE$ will represent trap i [28]. Notably, the optically-induced emission of a charge carrier only contributes to the recorded $S(E, t_{illum})$ if the charge carrier is swept out of the space-charge region by the electrical field present in the space-charge region. For many semiconducting oxides, self-trapped holes or electrons can form which may not be sufficiently mobile to leave the space-charge region [45]. In β -Ga₂O₃, self-trapped holes are expected to form with very low mobility below room temperature [45, 46].

In steady-state, i.e., for sufficiently long t_{illum} , $S(E, t_{illum})$ will be constant, and equal to $N_{tr,eff}^{ss}$, representing the steady-state concentration of ionized traps inside the probing volume. $N_{tr,eff}^{ss}$ is a sum of all $N_{tr,eff,i}^{ss}$ representing the concentration of ionized traps i in steady-state. If optically-induced hole emission can be neglected, $N_{tr,i}$ can be computed from $N_{tr,eff,i}^{ss}$ via [1]:

$$N_{tr,i} = N_{tr,eff,i}^{ss} \frac{W^2}{x_{1,i}^2 - W_{o,i}^2} = c N_{tr,eff,i}^{ss}. \quad (3)$$

$N_{tr,i}$ is the actual concentration of trap i . W is the depth of the depletion layer at V_{ext} , $x_{1,i}$ is the depth where the thermodynamic charge state transition level of trap i (E_i^{th}) crosses the Fermi-level E_F , and $W_{o,i}$ represent the fact that electrons from outside the space-charge region can penetrate into the space-charge region and refill photo-ionized traps. The correction factor c represents that during SSPC measurements traps are only photo-ionized in part of the volume of the space-charge region, and will always be larger than 1. Notably, $W_{o,i}$ will be smaller for a trap for which electron capture is more likely [1]. Here, $W_{o,i}$ can be expected to be reduced for donor defects as compared to acceptor defects [34, 37]. Smaller values for $W_{o,i}$ suggest that traps are photo-ionized in a smaller volume inside the space-charge region, and hence the correction factor c will be larger. If hole emission cannot be neglected, an additional factor representing the relative magnitude of optically-induced electron emission as compared to optically-induced hole emission needs to be added to the right hand side of equation (3) [10]. For non-ideal junctions, further corrections in addition to equation (3) are necessary due to leakage currents inside the space-charge region [47]. If leakage currents are present, corrections based on equation (3) will underestimate the actual trap concentration. Generally, traps with larger capture cross-sections for electrons will capture more electrons from the leakage current, and hence a larger deviation from equation (3) can be expected [47].

In order to obtain computational results which can be compared to measured $S(E, t_{illum})$, one needs to compute $N_{tr,eff}^*$ (see equation (1)). The time-evolution of $N_{tr,eff}^*$ is described by the following differential equation [1, 10]:

$$\frac{dN_{tr,eff}^*}{dt} = \sigma_n^o \Phi N_{tr,eff} - \sigma_p^o \Phi N_{tr,eff}^*. \quad (4)$$

Here, $N_{tr,eff}$ denotes the concentration of traps occupied with electrons. σ_i^o are the absorption cross-sections related to the optically-induced emission of electrons ($i = n$) or holes ($i = p$) from a trap [22]. Often, optically-induced hole emission can be neglected, and one obtains:

$$\frac{dN_{tr,eff}^*}{dt} = \sigma_n^o \Phi N_{tr,eff}. \quad (5)$$

Here, $N_{tr,eff}$ is equal to $N_{tr,eff}^{ss} - N_{tr,eff}^*$. Equation (5) can be solved for the experimental conditions encountered in accumulative or non-accumulative SSPC measurements. In the following, E^k denotes a specific photon energy used for illumination during an SSPC measurements. The E^k are ordered in ascending order, and hence $E^k > E^{k-1}$ is valid. For accumulative SSPC measurements, one obtains the following expression for equation (1) when solving equation (5):

$$S_{acc}(E^k, t_{illum}) = S(E^{k-1}, t_{illum}) + [N_{tr,eff}^{ss} - S(E^{k-1}, t_{illum})] [1 - \exp(-\sigma_n^o(E^k) \Phi(E^k) t_{illum})], \quad (6)$$

Table 1. Summary of parameters describing the CC diagrams for $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$ [8, 23].

Defect	E_{ZPL} (eV)	$d_{\text{g/c}}^{\text{FC}}$ (eV)	ΔQ (amu ^{1/2} /Å)	$\Omega_{\text{g/c}}$ (meV)
$\text{Fe}_{\text{Gal}}^{0/-}$	0.62	1.10/1.02	1.63	59/57
$\text{Fe}_{\text{Gal}}^{0/+}$	0.72	1.04/0.93	1.22	76/72
$\text{Ti}_{\text{Gal}}^{+/0}$	1.13	1.01/1.14	1.35	68/72

if one specific trap is assumed to be present in the space-charge region. Notably, k starts at 1, and $S(E^0, t_{\text{illum}})$ is set to zero.

For non-accumulative SSPC measurements, the corresponding expression is:

$$S_{\text{non-acc}}(E^k, t_{\text{illum}}) = N_{\text{tr,eff}}^{\text{ss}} [1 - \exp(-\sigma_n^0(E^k) \Phi(E^k) t_{\text{illum}})], \quad (7)$$

if one specific trap is assumed to be present in the space-charge region. To solve equations (6) and (7), one needs to know $\sigma_n^0(E^k)$ and $\Phi(E^k)$. $\sigma_n^0(E^k)$ can be defined as:

$$\sigma_n^0(E^k) = \sum_n^0 \sigma_{n,\text{norm}}^0(E^k). \quad (8)$$

$\sigma_{n,\text{norm}}^0$ can be obtained from first-principles calculations for a specific defect. The absolute value $\sum_n^0$, however, is challenging to extract from first-principles calculations, and is considered a free parameter of the simulation. $\Phi(E^k)$ was measured for the optical excitation of the setup used for SSPC measurements (see figure 1). If several traps i are present, $S_{\text{acc}}(E^k, t_{\text{illum}})$ and $S_{\text{non-acc}}(E^k, t_{\text{illum}})$ are superpositions of contributions $S_{\text{acc},i}(E^k, t_{\text{illum}})$ and $S_{\text{non-acc},i}(E^k, t_{\text{illum}})$ from the individual traps i , assuming no interaction between traps, which is a viable assumption in the dilute regime.

The main difference between accumulative and non-accumulative SSPC measurements is the starting point for SSPC measurements performed at subsequent E^k . Accumulative SSPC measurements will exhibit a steeper rise of $S_{\text{acc}}(E^k, t_{\text{illum}})$ in the vicinity of defect-related optical absorption. Thus, accumulative SSPC measurements are more suitable for reaching steady-state conditions for a given trap. In the appendix A, a detailed derivation of equations (6) and (7) as well as comparisons between the theoretical expressions of $S_{\text{acc}}(E^k, t_{\text{illum}})$ (see equation (6)) and $S_{\text{non-acc}}(E^k, t_{\text{illum}})$ (see equation (7)) are shown.

4. Results and discussion

The CC diagrams for the charge state transitions $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$ were calculated using hybrid-functionals, and the parameters describing $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$ are summarized in table 1 [8, 23]. The computed values are in accordance with other recent studies regarding $\text{Fe}_{\text{Gal}}^{0/-}$ and $\text{Fe}_{\text{Gal}}^{0/+}$ [48] as well as $\text{Ti}_{\text{Gal}}^{+/0}$ [49]. Figure 2 displays results for $\sigma_{n,\text{norm}}^0$ and $\sigma_{p,\text{norm}}^0$ related to $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$ in β -Ga₂O₃. A temperature of 120 K was assumed for the computations. For $\sigma_{n,\text{norm}}^0$, calculated absorption cross-section spectra are shown with and without taking vibrational broadening into account, whereas only results including vibrational broadening are shown for $\sigma_{p,\text{norm}}^0$. Calculated absorption cross-section spectra without vibrational broadening exhibit sharp onsets of absorption, and particularly, exhibit no absorption below the classical absorption energy E_{abs} [22], in contrast to what is expected in experiments. Hence, absorption cross-sections with vibrational broadening are used in the following. The calculated $\sigma_{n,\text{norm}}^0$ and $\sigma_{p,\text{norm}}^0$ are broad which is in accordance with previous computational results for $\sigma_{n,\text{norm}}^0$ related to primary intrinsic defects in β -Ga₂O₃ [28]. Note that the $\sigma_{n,\text{norm}}^0$ related to $\text{Fe}_{\text{Gal}}^{0/-}$ and $\text{Fe}_{\text{Gal}}^{0/+}$ show a significant overlap, while $\sigma_{n,\text{norm}}^0$ related to $\text{Ti}_{\text{Gal}}^{+/0}$ occurs at higher photon energies. Our computational results for $\sigma_{n,\text{norm}}^0$ of $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Fe}_{\text{Gal}}^{0/-}$ are in accordance with experimental photo-electron paramagnetic resonance studies performed by Bhandari *et al* [48, 50]. For $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$, optically-induced hole emission is only seen for photon energies close to E_{g} , i.e., optically-induced hole emission does not occur in the photon energy range where the onset of optically-induced electron emission is observed for these charge-state transitions. Thus, optically-induced hole emission related to $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gal}}^{0/+}$ and $\text{Ti}_{\text{Gal}}^{+/0}$ can be neglected when modeling SSPC spectra for photon energies lower than 4.0 eV.

Figure 3 shows DLTS spectra recorded on a EFG-grown β -Ga₂O₃ crystal. Three defect signatures labeled as E_{2a} ($E_{\text{A}} = 0.66$ eV, $\sigma_{\text{na}} = 4 \times 10^{-16}$ cm²), E_{2b} ($E_{\text{A}} = 0.79$ eV, $\sigma_{\text{na}} = 3 \times 10^{-15}$ cm²) and E_3 ($E_{\text{A}} = 1.03$ eV, $\sigma_{\text{na}} = 1 \times 10^{-13}$ cm²) are found to be present, in accordance with previous studies on EFG-grown β -Ga₂O₃ crystals [8, 23]. No other defect levels with smaller activation energies than 1.2 eV were present in

Figure 2. Absorption cross-sections $\sigma_{n,norm}^o$ and $\sigma_{p,norm}^o$ related to $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gall}}^{0/-}$ and $\text{Ti}_{\text{Gall}}^{+/0}$. For $\sigma_{n,norm}^o$, results are shown with and without taking vibrational broadening into account, while for $\sigma_{p,norm}^o$ results are only shown with vibrational broadening. A temperature of 120 K was assumed.

Figure 3. DLTS spectra recorded on a EFG-grown $\beta\text{-Ga}_2\text{O}_3$ crystal. The DLTS spectra were constructed with a GS4 filter and compared to simulations (solid lines). Three defect signatures $\text{Fe}_{\text{Gal}}^{0/-}$ (E_{2a}), $\text{Fe}_{\text{Gall}}^{0/-}$ (E_{2b}) and $\text{Ti}_{\text{Gall}}^{+/0}$ (E_3) are observed and labeled.

concentrations exceeding $1 \times 10^{15} \text{ cm}^{-3}$ in this sample. E_{2a} and E_{2b} have been assigned to $\text{Fe}_{\text{Gal}}^{0/-}$ and $\text{Fe}_{\text{Gall}}^{0/-}$, respectively [8, 23, 51], while E_3 is proposed to be related to $\text{Ti}_{\text{Gall}}^{+/0}$ [23]. This identification is consistent with a recent DLTS study that associated E_{2a}/E_{2b} with a deep acceptor and E_3 with a deep donor [52]. Taking the λ -correction [1, 32] into account, the concentrations of the corresponding traps were determined to be $2.54 \times 10^{15} \text{ cm}^{-3}$ (E_{2a} or Fe_{Gal}), $2.32 \times 10^{16} \text{ cm}^{-3}$ (E_{2b} or Fe_{Gall}) and $5.45 \times 10^{15} \text{ cm}^{-3}$ (E_3 or Ti_{Gall}), respectively (see table 2). Thus, using DLTS measurements, we are able to establish the presence and concentration of Fe_{Gal} , Fe_{Gall} and Ti_{Gall} in the sample.

Accumulative SSPC measurements were performed on the same EFG-grown $\beta\text{-Ga}_2\text{O}_3$ sample for which DLTS spectra are shown in figure 3. Figure 4(a) displays the recorded SSPC spectrum represented as conventional SSPC spectrum ($S_{\text{acc}}(E)$) and as derivative SSPC spectrum ($dS_{\text{acc}}(E)/dE$). Optically-induced emission of electrons is observed with onsets at 2.2–2.3 eV (T_1^{EFG}), 2.8–2.9 eV (T_2^{EFG}), 3.7–3.8 eV (T_3^{EFG}), 3.8–4.0 eV (T_4^{EFG}), 4.0–4.2 eV (T_5^{EFG}) and 4.2–4.3 eV (T_6^{EFG}). Furthermore, a signature originating from the band gap (E_g) of $\beta\text{-Ga}_2\text{O}_3$ can be seen. The features T_1^{EFG} and T_2^{EFG} are broad and partially overlap, and hence it is difficult to establish the respective onset position accurately. Interestingly, T_1^{EFG} and T_2^{EFG} can be properly distinguished in $dS_{\text{acc}}(E)/dE$ (see upper panel in figure 4(a)) which demonstrates the applicability of derivative SSPC spectra [28].

Table 2. Summary of the parameters used for the model displayed in figure 5. The values for $N_{\text{tr,eff}}^{\text{ss}}$ were determined from modeling accumulative SSPC spectra (see figure 5), while the values for N_{tr} were obtained from DLTS measurements (see figure 3).

Defect level	Σ_n^0 (10^{-18} cm^{-2})	$N_{\text{tr,eff}}^{\text{ss}}$ (10^{15} cm^{-3})	N_{tr} (10^{15} cm^{-3})
$\text{Fe}_{\text{GaI}}^{0/-}$	0.3	1.5	2.6
$\text{Fe}_{\text{GaII}}^{0/-}$	0.3	9.5	23.2
$\text{Ti}_{\text{GaII}}^{+/0}$	9.6	1.1	5.5

Figure 4(b) displays a comparison between derivative SSPC spectra recorded accumulatively as well as non-accumulatively on the same EFG-grown β -Ga₂O₃ crystal. The spectra were recorded using two different t_{illum} . Data are only shown for the photon energy range where T_1^{EFG} and T_2^{EFG} can be seen. Features in $dS_{\text{acc}}(E)/dE$ are narrower than the corresponding features seen in $dS_{\text{non-acc}}(E)/dE$. Indeed, it is not possible to distinguish T_1^{EFG} and T_2^{EFG} in $dS_{\text{non-acc}}(E)/dE$. With increasing t_{illum} , the signatures associated with T_1^{EFG} and T_2^{EFG} become significantly more narrow and shift to lower photon energies in $dS_{\text{acc}}(E)/dE$, while only minor changes are seen in $dS_{\text{non-acc}}(E)/dE$. Thus, using accumulative SSPC measurements with long t_{illum} , the spectral resolution can be significantly improved. The spectral shape seen for T_1^{EFG} and T_2^{EFG} in $dS_{\text{acc}}(E)/dE$ recorded with $t_{\text{illum}} = 1200 \text{ s}$ clearly suggests the presence of several overlapping defect signatures.

As mentioned before, DLTS measurements confirm the presence of $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$ in this EFG-grown β -Ga₂O₃ sample, and are thus expected to appear in SSPC spectra as well. It is possible to estimate the onset of defect-related optical absorption by adding the Franck–Condon shift for a specific charge-state transition of a defect to the corresponding activation energy determined by DLTS [21, 22]. Assuming typical Franck–Condon shifts of 0.4–1.2 eV as reported in β -Ga₂O₃ previously [11, 12, 28], one expects the optical absorption related to $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$ to occur at around 1.1–2.2 eV. Thus, $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$ are all plausible candidates for T_1^{EFG} . Further, the amplitude of T_1^{EFG} suggests an associated trap concentration in the range of $1 \times 10^{16} \text{ cm}^{-3}$, corroborating the relation to $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$. Notably, we observed no other defect signatures in DLTS measurements with concentrations above $1 \times 10^{15} \text{ cm}^{-3}$ that are likely candidates for contributing to T_1^{EFG} .

In order to assign T_1^{EFG} to $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$, however, it is necessary to compare the calculated results for $\sigma_{n,\text{norm}}^0$ (see figure 2) to the recorded SSPC spectra. Particularly, it is necessary to take experimental parameters such as t_{illum} into account (see figure 4(b)). One approach is the method presented above, by comparing the experimental data with SSPC spectra simulated by utilizing the absorption cross sections obtained from first-principles calculations. In figure 5, SSPC spectra recorded accumulatively on the same EFG-grown β -Ga₂O₃ crystal for which results are shown in figure 3 are compared to simulations based on equation (6). Importantly, the overall trap concentration is found to be lower than 20% of N_{D} . The simulations were performed assuming only the presence of $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$. The simulation has two free parameters for each defect signature: one pair of Σ_n^0 and $N_{\text{tr,eff}}^{\text{ss}}$ for $\text{Fe}_{\text{GaI}}^{0/-}$, $\text{Fe}_{\text{GaII}}^{0/-}$ and $\text{Ti}_{\text{GaII}}^{+/0}$, respectively. Increasing Σ_n^0 will lead to a narrowing of the simulated defect signature and shift it to lower

Figure 5. Accumulative SSPC spectra recorded on a EFG-grown β -Ga₂O₃ crystal using different t_{illum} . The spectra were modeled with equation (6), and the models are shown in solid lines. The model parameters are shown in table 2. A feature related to the spectral shape of Φ is marked in gray (see figure 1).

photon energies (see appendix A). Changing $N_{\text{tr,eff}}^{\text{ss}}$ will scale the simulated defect signature (see appendix A). The parameters which give the model curve shown in figure 4(a) are shown in table 2. The model parameters yield an excellent fit to the recorded data even when modeling different t_{illum} simultaneously, corroborating the validity of employing equation (6). Notably, it was not possible to model T_2^{EFG} using the absorption cross-sections calculated for $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gall}}^{0/-}$ and $\text{Ti}_{\text{Gall}}^{+/0}$ (not shown). Thus, we tentatively assign T_1^{EFG} to $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gall}}^{0/-}$ and $\text{Ti}_{\text{Gall}}^{+/0}$. However, it is possible that other defects contribute to T_1^{EFG} to a minor extent, i.e., from DLTS measurements, it cannot be ruled out that defects with a concentration below $1 \times 10^{15} \text{ cm}^{-3}$ are present in addition to Fe_{Gal} , Fe_{Gall} and Ti_{Gall} that might contribute to T_1^{EFG} .

The simulation takes the spectral shape of the optical excitation represented by $\Phi(E)$ explicitly into account. In the recorded as well as simulated spectra shown in figure 5, an artifact can be seen at around 1.5 eV which is related to a structure in $\Phi(E)$ (see figure 1). The corresponding structure can be identified as an artifact in the data as well as the simulation because it does not shift to lower photon energies with increasing t_{illum} as can be expected from features related to optical absorption associated with traps. The fact that modeling based on the measured $\Phi(E)$ accurately reproduces the artifact as seen in the data further corroborates the validity of the model described in equation (6).

Table 2 shows the comparison of values determined for $N_{\text{tr,eff}}^{\text{ss}}$ and N_{tr} of Fe_{Gal} , Fe_{Gall} and Ti_{Gall} from SSPC and DLTS measurements, respectively. Notably, all values obtained for $N_{\text{tr,eff}}^{\text{ss}}$ are lower than the values determined for N_{tr} by a factor of 2–5. Applying a probing volume correction to $N_{\text{tr,eff}}^{\text{ss}}$ (see equation (3)) will bring the values determined from SSPC measurements closer to the ones obtained from DLTS measurements. Interestingly, a larger deviation between $N_{\text{tr,eff}}^{\text{ss}}$ and N_{tr} is seen for Ti_{Gall} , as expected for defects more likely to capture electrons. Indeed, Ti_{Gall} is a donor, and hence more prone to capture electrons compared to the acceptor defects Fe_{Gal} and Fe_{Gall} [34, 37]. In accordance, using DLTS, comparatively large apparent cross-sections for electron capture are determined for $\text{Ti}_{\text{Gall}}^{+/0}$ in contrast to $\text{Fe}_{\text{Gal}}^{0/-}$ and $\text{Fe}_{\text{Gall}}^{0/-}$ [8, 9, 23].

5. Summary and conclusion

In summary, we presented a new method to combine SSPC measurements with first-principles calculations which can be used to reveal the identity of optical charge-state transition levels related to defects in wide band gap semiconductors. A method to simulate SSPC spectra using defect-related optical absorption spectra obtained from first-principles calculations based on hybrid-functionals was proposed. The simulations take the experimental conditions for the accumulative SSPC measurements explicitly into account. The thermodynamic charge-state transition levels of $\text{Fe}_{\text{Gal}}^{0/-}$, $\text{Fe}_{\text{Gall}}^{0/-}$ and $\text{Ti}_{\text{Gall}}^{+/0}$ in β -Ga₂O₃ were recently identified [8, 9, 23], and thus served as a test case for the method we developed. Accumulative SSPC measurements were performed on EFG-grown β -Ga₂O₃ crystals and several defect signatures labeled $T_1^{\text{EFG}} - T_6^{\text{EFG}}$ with onsets for optical absorption between 1.5 eV and 4.3 eV were unveiled. Indeed, we demonstrated how the simulation of accumulatively-recorded derivative SSPC spectra can be used to

Table A1. Overview over standard parameters used for the simulation of SSPC spectra presented here.

Σ_n^0 (m ²)	Φ (m ⁻² s ⁻¹)	t_{illum} (s)	ΔE (meV)	$N_{\text{tr,eff}}^{\text{ss}}$ (cm ⁻³)
2×10^{-20}	10^{18}	10/300	20	10^{16}

identify the optical charge-state transition levels related to $\text{Fe}_{\text{Ga}}^{0/-}$, $\text{Fe}_{\text{Ga}}^{0/-}$ and $\text{Ti}_{\text{Ga}}^{+/0}$ in $\beta\text{-Ga}_2\text{O}_3$. Thus, we were able to assign the signature labeled T_1^{EFG} to $\text{Fe}_{\text{Ga}}^{0/-}$, $\text{Fe}_{\text{Ga}}^{0/-}$ as well as $\text{Ti}_{\text{Ga}}^{+/0}$. Future applications of this approach, as well as its extension to account for optically-induced hole emission processes, may help elucidate the origins of other deep level signatures in $\beta\text{-Ga}_2\text{O}_3$ and other wide-band-gap semiconductors.

Acknowledgments

Financial support is acknowledged from the Research Council of Norway through the FUNDAMENT project (project number: 251131), the Norwegian Micro- and Nano-Fabrication Facility (NorFab, project number: 245963) and the Faculty of Mathematics and Natural Sciences at the University of Oslo via the strategic research initiative FOXHOUND. This work was partially performed under the auspices of the U.S. DOE by Lawrence Livermore National Laboratory under contract DE-AC52-07NA27344, and supported by the Critical Materials Institute, an Energy Innovation Hub funded by the U.S. DOE, Office of Energy Efficiency and Renewable Energy, Advanced Manufacturing Office. We wish to thank Audrius Alkauskas for fruitful collaboration and discussion. We further thank Robert Karsthof, Ole Myren Röhne and Ole Dorholt for wire-bonding of our samples.

Appendix A. Simulation of deep-level transient and steady-state photo-capacitance spectra

A.1. Simulation of deep-level transient spectra

In deep-level transient spectroscopy (DLTS) [1, 7], a rectifying junction is kept a reverse-bias voltage ($V_{\text{rev}} < 0$ V) and subjected to a voltage pulse ($V_{\text{pulse}} > 0$ V) at a time t_0 which lasts for a duration t_{pulse} . In the following, it is assumed that DLTS measurements are performed on a Schottky junction comprising an n-type semiconductor. Moreover, we assume that a trap exhibiting a concentration of N_{tr} and a single thermodynamic charge-state transition level (E_t) is present in the semiconductor. Prior to applying the voltage pulse, the trap will be empty of electrons in-between the surface of the semiconductor and a depth x_1 . x_1 is the depth where the Fermi level (E_F) crosses E_t , and its value will depend on V_{rev} . During the voltage pulse, an additional amount of traps will be filled with electrons, i.e., traps in-between x_1 and a depth x_2 will also be filled with electrons. x_2 is the depth where E_F crosses E_t when the applied bias voltage is equal to $V_{\text{rev}} + V_{\text{pulse}}$. After the end of the voltage pulse at $t_0 + t_{\text{pulse}}$, the charge-state transition level of traps in-between x_2 and x_1 will be above E_F , and thus electron emission will occur until all traps in-between x_2 and x_1 are void of electrons.

The corresponding electron emission is a thermally-activated process, and its rate e_n^{th} can be expressed by [1, 7]:

$$e_n^{\text{th}} = \beta \sigma_{\text{na}} T^2 \exp\left(-\frac{E_A}{k_B T}\right). \quad (\text{A.1})$$

Here, T is the sample temperature, E_A is the activation energy for thermally-induced electron emission from the trap, σ_{na} is the apparent capture cross section, k_B is Boltzmann's constant and β is a material-specific constant. E_A is the sum of E_t and the corresponding energetic barrier for electron capture (E_b) [1, 21]. Assuming parabolic bands, β can be computed by [1]:

$$\beta = 2\sqrt{3} \left(\frac{2\pi}{h^2}\right)^{\frac{3}{2}} k_B^2 m_{\text{n,eff}}. \quad (\text{A.2})$$

Here, h is Planck's constant and $m_{\text{n,eff}}$ is the effective mass of electrons in the conduction band. For $\beta\text{-Ga}_2\text{O}_3$, a value of $0.28 m_e$ was used for $m_{\text{n,eff}}$ [53, 54], whereby m_e is the electron mass.

In DLTS, the thermally-induced electron emission is probed by recording the capacitance of the rectifying junction. Particularly, the capacitance transient ($C(t)$) is recorded after the end of the voltage pulse, and is described by [1]

$$C(t) = C_0 \left[1 - \frac{N_{\text{tr,probe}}}{2N_D} \exp(-e_n^{\text{th}} t) \right], \quad (\text{A.3})$$

assuming $N_{\text{tr}} \ll N_{\text{D}}$ to be valid. Here, C_0 is the capacitance of the rectifying junction measured prior to the voltage pulse, i.e., the capacitance of the rectifying junction when V_{rev} is applied. N_{D} is the donor concentration and $N_{\text{tr,probe}}$ is the effective trap concentration in the probing volume, i.e., the effective concentration of traps in-between x_2 and x_1 . Following the approach outlined by Lang, the DLTS spectra $S_j(T)$ can be constructed, and $S_j(T)$ is defined as [1, 7, 31]:

$$S_j(T) = \frac{1}{t_j} \int_{t_{\text{delay}}}^{t_{\text{delay}} + t_j} C(t) w(t) dt. \quad (\text{A.4})$$

Here, t_{delay} is the time at which the recording of $C(t)$ starts after the end of the voltage pulse, whereas t_j is the duration for which $C(t)$ is recorded/analyzed. $w(t)$ is the weighting function, e.g., a lock-in function [1] or a GS4 filter function [31]. To analyze DLTS measurements, one needs to use more than one specific t_j . Often, $C(t)$ is recorded for a duration $t_{\text{transient}}$, and different parts of the transient, represented by t_j , are analyzed in order to obtain different $S_j(T)$. Different $S_j(T)$ essentially correspond to analyzing the recorded $C(t)$ for different values of e_n^{th} (see figure 3 in the manuscript). The recorded $S_j(T)$ can be compared to simulations when combining equation (A.4) with equations (A.1) and (A.3). The free parameters of the simulation are the quantities $N_{\text{tr,probe}}$, E_A and σ_{na} which describe the concentration and properties of the trap. Often, one represents DLTS spectra as $2N_{\text{D}}\Delta C/C_0$, whereby $\Delta C = C_0 - C(t = 0 \text{ s})$ can be calculated from $S_j(T)$ as outlined in [1, 55].

As mentioned above, $N_{\text{tr,probe}}$ represents the effective trap concentration in-between x_2 and x_1 . The actual trap concentration N_{tr} can be determined by using [1]:

$$N_{\text{tr}} = \frac{W^2}{x_1^2 - x_2^2} N_{\text{tr,probe}}. \quad (\text{A.5})$$

Here, W is the width of the space-charge region when applying V_{rev} . The correction performed in equation (A.5) is often referred to as λ -correction [1, 32].

A.2. Simulation of steady-state photo-capacitance spectra from first-principles calculations

Steady-state photo-capacitance (SSPC) measurements are performed by measuring the photo-capacitance of a rectifying junction after illumination at the photon energy E^k for a duration t_{illum} . In the following, it is assumed that SSPC measurements are performed on a Schottky junction comprising an n-type semiconductor. Moreover, we assume that a trap exhibiting a concentration of N_{tr} and a single thermodynamic charge-state transition level (E_t) is present in the semiconductor.

SSPC spectra ($S(E^k, t_{\text{illum}})$) are constructed by recording the photo-capacitance ($C_{\text{illum}}(E^k, t_{\text{illum}})$) of the junction at subsequent E^k . $S(E^k, t_{\text{illum}})$ is usually expressed as [1, 10]:

$$S(E^k, t_{\text{illum}}) = 2 \frac{C_{\text{illum}}(E^k, t_{\text{illum}}) - C_{\text{dark}}}{C_{\text{dark}}} N_D = 2 \frac{\Delta C_{\text{illum}}(E^k, t_{\text{illum}})}{C_{\text{dark}}} N_D = N_{\text{tr,eff}}^*(E^k, t_{\text{illum}}). \quad (\text{A.6})$$

Here, $\Delta C_{\text{illum}}(E^k, t_{\text{illum}})$ denotes the change in (photo-)capacitance during illumination for t_{illum} at E^k , and C_{dark} represents the capacitance of the junction measured in the dark. $N_{\text{tr,eff}}^*(E^k, t_{\text{illum}})$ is the change in the concentration of ionized traps inside the probing volume due to illumination. Notably, the probing volume will usually not be equal to the volume of the space-charge region [1, 28]. Moreover, equation (A.6) assumes $N_D \ll N_{\text{tr}}$ to be valid.

$N_{\text{tr,eff}}^*(E^k, t_{\text{illum}})$ is described by the following differential equation [10]:

$$\frac{dN_{\text{tr,eff}}^*}{dt} = \sigma_n^{\circ} \Phi N_{\text{tr,eff}}, \quad (\text{A.7})$$

when assuming that the photo-ionization process only involves the defect and the conduction band (optically-induced electron emission), i.e., optically-induced hole emission (photo-ionization processes

Figure A3. Graphical representation of equations (A.14) and (A.18) for various t_{illum} . Results are shown for (a) conventional and (b) derivative SSPC spectra. Here, the σ_n^o calculated for $\text{Ti}_{\text{Ga}}^{+/0}$ was used. Moreover, the following parameters were used: $\Delta E = 20 \text{ meV}$, $\Sigma_n^o = 2 \times 10^{-20} \text{ m}^2$, $\Phi = 1 \times 10^{15} \text{ m}^{-2} \text{ s}$ and $N_{\text{tr,eff}}^s = 1 \times 10^{16} \text{ cm}^{-3}$.

involving the defect and the valence band) can be neglected. Optically-induced hole emission can be neglected if (i) holes are not sufficiently mobile to leave the space-charge region, or (ii) optically-induced hole emission does not occur in the spectral region of interest [10, 28]. In equation (A.7), σ_n^o represents the absorption cross-section related to the optically-induced electron emission from the defect, whereas Φ denotes the spectral photon flux used for illumination. σ_n^o and Φ will be functions of E^k . $N_{\text{tr,eff}}$ is the concentration of defects inside the probing volume which are not ionized, and hence $N_{\text{tr,eff}}$ is equal to $N_{\text{tr,eff}}^{\text{ss}} - N_{\text{tr,eff}}^*$. $N_{\text{tr,eff}}^{\text{ss}}$ is the effective concentration of the defect inside the probing volume. Using this, equation (A.7) becomes:

$$\frac{dN_{\text{tr,eff}}^*}{dt} = \sigma_n^o \Phi N_{\text{tr,eff}}^{\text{ss}} - \sigma_n^o \Phi N_{\text{tr,eff}}^* \quad (\text{A.8})$$

Equation (A.8) describes a first-order, non-homogeneous differential equation. The associated homogeneous differential equation is:

$$\frac{dN_{\text{tr,eff}}^*}{dt} = -\sigma_n^o \Phi N_{\text{tr,eff}}^* \quad (\text{A.9})$$

This differential equation is solved by:

$$N_{\text{tr,eff}}^* = A \exp(-\sigma_n^o \Phi t) \quad (\text{A.10})$$

Here, A is a constant which needs to be chosen according to the boundary condition. A particular solution for equation (A.8) is

$$N_{\text{tr,eff}}^* = N_{\text{tr,eff}}^{\text{ss}} \quad (\text{A.11})$$

The overall solution to equation (A.8) is obtained by adding equations (A.10) and (A.11) together, and hence:

$$N_{\text{tr,eff}}^* = N_{\text{tr,eff}}^{\text{ss}} + A \exp(-\sigma_n^o \Phi t) \quad (\text{A.12})$$

As mentioned above, A needs to be determined from the boundary condition which will depend on the way SSPC measurements are performed. In non-accumulative SSPC measurements, the defect is re-filled with electrons prior to illumination at E^k , and hence the concentration of (photo-)ionized defects prior to illumination at E^k inside the probing volume ($N_{\text{tr,eff}}^*(E^k, t = 0 \text{ s})$) will be expressed by:

$$N_{\text{tr,eff}}^*(E^k, t = 0 \text{ s}) = 0. \quad (\text{A.13})$$

Thus, A will be equal to $-N_{\text{tr,eff}}$, and hence:

$$\begin{aligned} S_{\text{non-acc}}(E^k, t_{\text{illum}}) &= N_{\text{tr,eff}}^{\text{ss}} - N_{\text{tr,eff}}^{\text{ss}} \exp(-\sigma_n^0 \Phi t) \\ &= N_{\text{tr,eff}}^{\text{ss}} [1 - \exp(-\sigma_n^0 \Phi t_{\text{illum}})] . \end{aligned} \quad (\text{A.14})$$

Notably, for t_{illum} approaching ∞ s, $S_{\text{non-acc}}(E^k, t_{\text{illum}})$ approaches $N_{\text{tr,eff}}^{\text{ss}}$. $t_{\text{illum}} \rightarrow \infty$ s is equivalent to reaching steady-state conditions, and hence the superscript ss was used for denoting $N_{\text{tr,eff}}^{\text{ss}}$.

In accumulative SSPC measurements, the rectifying junction under illumination is kept at a fixed reverse-bias voltage while illuminating the junction at different E^k . Importantly, measurements are performed in ascending order of E^k , i.e., $E^k < E^{k+1}$ is valid. For the first measurement performed at E^0 , the boundary condition stated in equation (A.13) holds, and thus

$$S_{\text{acc}}(E^0, t_{\text{illum}}) = N_{\text{tr,eff}}^{\text{ss}} [1 - \exp(-\sigma_n^0 \Phi t_{\text{illum}})] . \quad (\text{A.15})$$

For illumination at subsequent E^k , the following boundary condition holds:

$$\begin{aligned} N_{\text{tr,eff}}^*(E^k, t = 0 \text{ s}) &= N_{\text{tr,eff}}^*(E^{k-1}, t_{\text{illum}}) \\ &= S_{\text{acc}}(E^{k-1}, t_{\text{illum}}) \end{aligned} \quad (\text{A.16})$$

reflecting that when illumination starts, a certain concentration of defects is already photo-ionized due to illumination at E^{k-1} . Thus A is equal to $S_{\text{acc}}(E^{k-1}, t_{\text{illum}}) - N_{\text{tr,eff}}^{\text{ss}}$ and hence:

$$S_{\text{acc}}(E^k, t_{\text{illum}}) = N_{\text{tr,eff}}^{\text{ss}} + [S_{\text{acc}}(E^{k-1}, t_{\text{illum}}) - N_{\text{tr,eff}}^{\text{ss}}] \exp(-\sigma_n^0 \Phi t_{\text{illum}}) \quad (\text{A.17})$$

is valid for $E^k \neq E^0$. Adding $0 = S_{\text{acc}}(E^{k-1}, t_{\text{illum}}) - S_{\text{acc}}(E^{k-1}, t_{\text{illum}})$ on the right hand side, equation (A.17) can be re-written as:

$$\begin{aligned}
 S_{acc}(E^k, t_{illum}) &= S_{acc}(E^{k-1}, t_{illum}) - S_{acc}(E^{k-1}, t_{illum}) + N_{tr,eff}^{ss} + [S_{acc}(E^{k-1}, t_{illum}) - N_{tr,eff}^{ss}] \exp(-\sigma_n^o \Phi t_{illum}) \\
 &= S_{acc}(E^{k-1}, t_{illum}) + [N_{tr,eff}^{ss} - S_{acc}(E^{k-1}, t_{illum})] [1 - \exp(-\sigma_n^o \Phi t_{illum})].
 \end{aligned} \quad (A.18)$$

This equation is valid for all E^k if $S_{acc}(E^0, t_{illum})$ is set to 0.

Equations (A.14) and (A.18) can be expressed more general in the form $S_{acc}(E^k, t_{illum}, t)$ and $S_{non-acc}(E^k, t_{illum}, t)$. $S_{acc}(E^k, t_{illum}, t)$ and $S_{non-acc}(E^k, t_{illum}, t)$ describe the recorded SSPC spectrum after illumination for a time t at E^k while the junction was illuminated for a duration t_{illum} at all photon energies E' for which $j < k$ is valid. $S_{acc}(E^k, t_{illum}, t)$ can be expressed as:

$$162 \quad S_{acc}(E^k, t_{illum}, t) = S(E^{k-1}, t_{illum}, t_{illum}) + [N_{tr,eff}^{ss} - S(E^{k-1}, t_{illum}, t_{illum})] [1 - \exp(-\sigma_n^o \Phi t)], \quad (A.19)$$

while $S_{\text{non-acc}}(E^k, t_{\text{illum}}, t)$ can be calculated by:

$$S_{\text{non-acc}}(E^k, t_{\text{illum}}, t) = N_{\text{tr,eff}}^{\text{ss}} [1 - \exp(-\sigma_n^0 \Phi t)] . \quad (\text{A.20})$$

σ_n^0 is defined by:

$$\sigma_n^0 = \Sigma_n^0 \sigma_{n,\text{norm}}^0 . \quad (\text{A.21})$$

Here, $\sigma_{n,\text{norm}}^0$ can be obtained from first-principles calculations for a specific trap, while Σ_n^0 is a free parameter of the simulation.

In the following, graphical representations of equations (A.14), (A.18–A.20) will be shown. Hereby, the calculated $\sigma_{n,\text{norm}}^0$ of $\text{Ti}_{\text{Ga}}^{+/0}$ was used. In table A1, the standard values for the simulation parameters are stated. Φ is assumed to be constant for all photon energies, and ΔE is the energy step between two subsequent E^k , i.e., $\Delta E = E^{k+1} - E^k$ is valid.

Figure A1 displays graphical representations of equations (A.19) and (A.20). Figure A1(a) shows the dependence on t , while figures A1(b) and (c) show the corresponding dependence on E^k . Notably, for the same experimental conditions, non-accumulative SSPC measurements will reach steady-state conditions for longer t_{illum} compared to accumulative SSPC measurements. Generally, longer t_{illum} are associated with steps in SSPC spectra shifting to lower photon energies and becoming steeper.

In figures A2–A5, the influence of a particular parameter on equations (A.14) and (A.18) is shown. For longer t_{illum} and higher Φ , steps in S_{acc} as well as $S_{\text{non-acc}}$ will shift to lower photon energies and become steeper. The corresponding changes are more notable for accumulative SSPC spectra under the same experimental conditions. Only S_{acc} exhibits a change depending on ΔE . For S_{acc} as well as $S_{\text{non-acc}}$, $N_{\text{tr,eff}}^{\text{ss}}$ is a scaling factor.

ORCID iDs

C Zimmermann <https://orcid.org/0000-0003-3708-6074>

Y Kalmann Frodason <https://orcid.org/0000-0001-9151-2084>

J B Varley <https://orcid.org/0000-0002-5384-5248>

L Vines <https://orcid.org/0000-0001-5759-7192>

References

- [1] Blood P and Orton J W 1992 *The Electrical Characterization of Semiconductors: Majority Carriers and Electron States* (Techniques of Physics) (New York: Academic)
- [2] Van de Walle C G and Neugebauer J 2004 First-principles calculations for defects and impurities: applications to III-nitrides *J. Appl. Phys.* **95** 3851–79
- [3] Pearton S J, Yang J, Cary P HIV, Ren F, Kim J, Tadjer M J and Mastro M A 2018 A review of Ga_2O_3 materials, processing, and devices *Appl. Phys. Rev.* **5** 011301
- [4] Higashiwaki M, Sasaki K, Murakami H, Kumagai Y, Koukitu A, Kuramata A, Masui T and Yamakoshi S 2016 Recent progress in Ga_2O_3 power devices *Semicond. Sci. Technol.* **31** 034001
- [5] Nakagomi S, Momo T, Takahashi S and Kokubun Y 2013 Deep ultraviolet photodiodes based on $\beta\text{-Ga}_2\text{O}_3/\text{SiC}$ heterojunction *Appl. Phys. Lett.* **103** 072105
- [6] Nakagomi S, Sato T, Takahashi Y and Kokubun Y 2015 Deep ultraviolet photodiodes based on the $\beta\text{-Ga}_2\text{O}_3/\text{GaN}$ heterojunction *Sensors Actuators A* **232** 208–13
- [7] Lang D V 1974 Deep-level transient spectroscopy: a new method to characterize traps in semiconductors *J. Appl. Phys.* **45** 3023–32
- [8] Eide Ingebrigtsen M, Varley J B, Kuznetsov A Y, Svensson B G, Alfieri G, Mihaila A, Badstübner U and Vines L 2018 Iron and intrinsic deep level states in Ga_2O_3 *Appl. Phys. Lett.* **112** 042104
- [9] Ingebrigtsen M E, Kuznetsov A Y, Svensson B G, Alfieri G, Mihaila A, Badstübner U, Perron A, Vines L and Varley J B 2019 Impact of proton irradiation on conductivity and deep level defects in $\beta\text{-Ga}_2\text{O}_3$ *APL Mater.* **7** 022510
- [10] Chantre A, Vincent G and Bois D 1981 Deep-level optical spectroscopy in GaAs *Phys. Rev. B* **23** 5335
- [11] Farzana E, Ahmadi E, James S S, Arehart A R and Ringel S A 2018 Deep level defects in Ge-doped (010) $\beta\text{-Ga}_2\text{O}_3$ layers grown by plasma-assisted molecular beam epitaxy *J. Appl. Phys.* **123** 161410
- [12] Zhang Z, Farzana E, Arehart A R and Ringel S A 2016 Deep level defects throughout the bandgap of (010) $\beta\text{-Ga}_2\text{O}_3$ detected by optically and thermally stimulated defect spectroscopy *Appl. Phys. Lett.* **108** 052105
- [13] Farzana E, Chaiken M F, Blue T E, Arehart A R and Ringel S A 2019 Impact of deep level defects induced by high energy neutron radiation in $\beta\text{-Ga}_2\text{O}_3$ *APL Mater.* **7** 022502
- [14] Polyakov A Y, Smirnov N B, Shchemerov I V, Yakimov E B, Yang J, Ren F, Yang G, Kim J, Kuramata A and Pearton S J 2018 Point defect induced degradation of electrical properties of Ga_2O_3 by 10 MeV proton damage *Appl. Phys. Lett.* **112** 032107
- [15] Polyakov A Y et al 2018 Defects responsible for charge carrier removal and correlation with deep level introduction in irradiated $\beta\text{-Ga}_2\text{O}_3$ *Appl. Phys. Lett.* **113** 092102
- [16] Polyakov A Y, Smirnov N B, Shchemerov I V, Gogova D, Tarelkin S A and Pearton S J 2018 Compensation and persistent photocapacitance in homoepitaxial Sn-doped $\beta\text{-Ga}_2\text{O}_3$ *J. Appl. Phys.* **123** 115702

- [17] Polyakov A Y, Smirnov N B, Shchemerov I V, Pearton S J, Fan R, Chernykh A V and Kochkova A I 2018 Electrical properties of bulk semi-insulating β -Ga₂O₃ (Fe) *Appl. Phys. Lett.* **113** 142102
- [18] Nakano Y 2017 Electrical characterization of β -Ga₂O₃ single crystal substrates *ECS J. Solid State Sci. Technol.* **6** P615–7
- [19] Krukau A V, Vydrov O A, Izmaylov A F and Scuseria G E 2006 Influence of the exchange screening parameter on the performance of screened hybrid functionals *J. Chem. Phys.* **125** 224106
- [20] Freysoldt C, Grabowski B, Hickel T, Neugebauer J, Kresse G, Anderson J and Van de Walle C G 2014 First-principles calculations for point defects in solids *Rev. Mod. Phys.* **86** 253
- [21] Wickramaratne D, Dreyer C E, Monserrat B, Shen J-X, Lyons J L, Alkauskas A and Van de Walle C G 2018 Defect identification based on first-principles calculations for deep level transient spectroscopy *Appl. Phys. Lett.* **113** 192106
- [22] Alkauskas A, McCluskey M D and Van de Walle C G 2016 Tutorial: Defects in semiconductors - combining experiment and theory *J. Appl. Phys.* **119** 181101
- [23] Zimmermann C, Frodason Y K, Barnard A W, Varley J B, Irmscher K, Galazka Z, Karjalainen A, Meyer W E, Auret F D and Vines L 2020 Ti- and Fe-related charge transition levels in β -Ga₂O₃ *Appl. Phys. Lett.* **116** 072101
- [24] Kopylov A A and Pikhin A N 1975 Influence of temperature on spectra of optical absorption by deep levels in semiconductors *Sov. Phys. - Solid State* **16** 1200–3
- [25] Aida H, Nishiguchi K, Takeda H, Aota N, Sunakawa K and Yaguchi Y 2008 Growth of β -Ga₂O₃ single crystals by the edge-defined, film fed growth method *Jpn. J. Appl. Phys.* **47** 8506–9
- [26] Kuramata A, Koshi K, Watanabe S, Yu Y, Masui T and Yamakoshi S 2016 High-quality single crystals grown by edge-defined film-fed growth *Japan. J. Appl. Phys.* **55** 1202A2
- [27] Ingebrigtsen M E, Vines L, Alfieri G, Mihaila A, Badstübner U, Svensson B G and Kuznetsov A 2017 Bulk β -Ga₂O₃ with (010) and (201) surface orientation: Schottky contacts and point defects *Mater. Sci. Forum* **897** 755–8
- [28] Zimmermann C, Rönning V, Frodason Y K, Varley J B, Bobal V and Vines L 2020 Primary intrinsic defects and their charge transition levels in β -Ga₂O₃ *Phys. Rev. Mater.* (submitted)
- [29] Passlack M, Hunt N E J, Schubert E F, Zyzdzik G J, Hong M, Mannaerts J P, Opila R L and Fischer R J 1994 Dielectric properties of electron beam deposited Ga₂O₃ films *Appl. Phys. Lett.* **64** 2715–7
- [30] Svensson B G, Rydén K-H and Lewerentz B M S 1989 Overlapping electron traps in n-type silicon studied by capacitance transient spectroscopy *J. Appl. Phys.* **66** 1699–704
- [31] Istratov A A 1997 New correlation procedure for the improvement of resolution of deep level transient spectroscopy of semiconductors *J. Appl. Phys.* **82** 2965–8
- [32] Irmscher K, Galazka Z, Pietsch M, Uecker R and Fornari R 2011 Electrical properties of β -Ga₂O₃ single crystals grown by the czochralski method *J. Appl. Phys.* **110** 063720
- [33] Ridley B K 1978 Multiphonon, non-radiative transition rate for electrons in semiconductors and insulators *J. Phys. C: Solid State Phys.* **11** 2323–41
- [34] Alkauskas A, Yan Q and Van de Walle C G 2014 First-principles theory of nonradiative carrier capture via multiphonon emission *Phys. Rev. B* **90** 075202
- [35] Bonch-Bruевич V L 1959 *Fiz. Tverd. Tella* **182**
- [36] Gummel H and Lax M 1955 Thermal ionization and capture of electrons trapped in semiconductors *Phys. Rev.* **97** 1469
- [37] Pässler R 1976 Relationships between the nonradiative multiphonon carrier-capture properties of deep charged and neutral centres in semiconductors *Phys. Status Solidi B* **78** 625–35
- [38] Kresse G and Furthmüller J 1996 Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set *Phys. Rev. B* **54** 11169
- [39] Freysoldt C, Neugebauer J and Van de Walle C G 2009 Fully ab initio finite-size corrections for charged-defect supercell calculations *Phys. Rev. Lett.* **102** 016402
- [40] Kumagai Y and Oba F 2014 Electrostatics-based finite-size corrections for first-principles point defect calculations *Phys. Rev. B* **89** 195205
- [41] Gake T, Kumagai Y, Freysoldt C and Oba F 2020 Finite-size corrections for defect-involving vertical transitions in supercell calculations *Phys. Rev. B* **101** 020102
- [42] Stoneham A M 1975 *Theory of Defects in Solids* (Oxford: Oxford University Press)
- [43] Alkauskas A, Lyons J L, Steiauf D and Van de Walle C G 2012 First-principles calculations of luminescence spectrum line shapes for defects in semiconductors: the example of GaN and ZnO *Phys. Rev. Lett.* **109** 267401
- [44] White A M, Dean P J and Porteous P 1976 Photocapacitance effects of deep traps in epitaxial GaAs *J. Appl. Phys.* **47** 3230–9
- [45] Varley J B, Janotti A, Franchini C and Van de Walle C G 2012 Role of self-trapping in luminescence and p-type conductivity of wide-band-gap oxides *Phys. Rev. B* **85** 081109
- [46] Kananen B E, Giles N C, Halliburton L E, Foundos G K, Chang K B and Stevens K T 2017 Self-trapped holes in β -Ga₂O₃ crystals *J. Appl. Phys.* **122** 215703
- [47] Furukawa Y 1967 Trap levels in gallium arsenide *Japan. J. Appl. Phys.* **6** 675
- [48] Bhandari S, Zvanut M E and Varley J B 2019 Optical absorption of Fe in doped Ga₂O₃ *J. Appl. Phys.* **126** 165703
- [49] Saleh M, Varley J B, Jesenovc J, Bhattacharyya A, Krishnamoorthy S, Swain S and Lynn K 2020 Degenerate doping in β -Ga₂O₃ single crystals through Hf-doping *Semicond. Sci. Technol.* **35** 04LT01
- [50] Bhandari S and Zvanut M E 2020 Optical transitions for impurities in Ga₂O₃ as determined by photo-induced electron paramagnetic resonance spectroscopy *J. Appl. Phys.* **127** 065704
- [51] Lenyk C A, Gustafson T D, Halliburton L E and Giles N C 2019 Deep donors and acceptors in β -Ga₂O₃ crystals: determination of the Fe^{2+/3+} level by a noncontact method *J. Appl. Phys.* **126** 245701
- [52] Polyakov A Y, Lee I-H, Smirnov N B, Shchemerov I V, Vasilev A, Chernykh A V and Pearton S J 2020 Electric field dependence of major electron trap emission in bulk β -Ga₂O₃: Poole-frenkel effect versus phonon-assisted tunneling *J. Phys. D: Appl. Phys.* **53** 304001
- [53] Janowitz C *et al* 2011 Experimental electronic structure of In₂O₃ and Ga₂O₃ *New J. Phys.* **13** 085014
- [54] Mock A, Korlacki R, Briley C, Darackchieva V, Monemar B, Kumagai Y, Goto K, Higashiwaki M and Schubert M 2017 Band-to-band transitions, selection rules, effective mass, and excitonic contributions in monoclinic β -Ga₂O₃ *Phys. Rev. B* **96** 245205
- [55] Åberg D 2001 Capacitance spectroscopy of point defects in silicon and silicon carbide *PhD Thesis KTH*, Royal Institute of Technology Stockholm

Paper VIII

Formation and control of the E_2^* center in implanted β -Ga₂O₃ by reverse-bias and zero-bias annealing

C. Zimmermann, E. F. Verhoeven, Y. K. Frodason, P. M. Weiser, J. B. Varley, L. Vines

Published in *Journal of Physics D: Applied Physics*, July 2020, volume , issue , pp. . DOI: 10.1088/1361-6463/aba64d.

VIII

Formation and control of the E_2^* center in implanted β -Ga₂O₃ by reverse-bias and zero-bias annealing

C Zimmermann¹ , E Førdestrøm Verhoeven¹, Y Kalmann Frodason¹, P M Weiser¹, J B Varley² and L Vines¹

¹ Department of Physics, Centre for Materials Science and Nanotechnology, University of Oslo, Blindern Box 1048, Norway

² Lawrence Livermore National Laboratory, Livermore, CA 94550, United States of America

E-mail: christian.zimmermann@fys.uio.no

Received 17 April 2020, revised 1 July 2020

Accepted for publication 15 July 2020

Published 20 August 2020

Abstract

Deep-level transient spectroscopy measurements are conducted on β -Ga₂O₃ thin-films implanted with helium and hydrogen (H) to study the formation of the defect level E_2^* ($E_A = 0.71$ eV) during heat treatments under an applied reverse-bias voltage (reverse-bias annealing). The formation of E_2^* during reverse-bias annealing is a thermally-activated process exhibiting an activation energy of around 1.0 eV to 1.3 eV, and applying larger reverse-bias voltages during the heat treatment results in a larger concentration of E_2^* . In contrast, heat treatments without an applied reverse-bias voltage (zero-bias annealing) can be used to decrease the E_2^* concentration. The removal of E_2^* is more pronounced if zero-bias anneals are performed in the presence of H. A scenario for the formation of E_2^* is proposed, where the main effect of reverse-bias annealing is an effective change in the Fermi-level position within the space-charge region, and where E_2^* is related to a defect complex involving intrinsic defects that exhibits several different configurations whose relative formation energies depend on the Fermi-level position. One of these configurations gives rise to E_2^* , and is more likely to form if the Fermi-level position is further away from the conduction band edge. The defect complex related to E_2^* can become hydrogenated, and the corresponding hydrogenated complex is likely to form when the Fermi level is close to the conduction band edge. Di-vacancy defects formed by oxygen and gallium vacancies ($V_O - V_{Ga}$) fulfill several of these requirements, and are proposed as potential candidates for E_2^* .

Keywords: β -Ga₂O₃, deep-level transient spectroscopy, hydrogen, irradiation, implantation, reverse-bias annealing, intrinsic defects

(Some figures may appear in colour only in the online journal)

1. Introduction

Monoclinic gallium sesquioxide (β -Ga₂O₃) has emerged in recent years as a promising material for applications in power electronics and UV photo-detectors due to its wide band gap and exceptionally high break-down electrical field [1–6]. There has been significant progress in improving the quality of β -Ga₂O₃ bulk crystals and thin-films [4, 7–13]. However, point defects are still a limiting factor for device

Original Content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](https://creativecommons.org/licenses/by/4.0/). Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.

performance, and influence the operation of devices for power electronics due to, for example, Fermi-level pinning [14–16] or an increase in the on-resistance [17]. Indeed, McGlone *et al* recently showed that a defect level commonly labeled as E_2^* is limiting the device performance of metal-semiconductor field-effect transistors (MESFETs) based on β -Ga₂O₃ [14].

E_2^* is associated with a defect level at around 0.75 eV below the conduction band edge (E_C) as determined by deep-level transient spectroscopy (DLTS) [14, 15, 18–20]. The defect level has been observed in as-grown β -Ga₂O₃ thin-films deposited by plasma-assisted molecular beam epitaxy [14, 15], and is suggested to be associated with intrinsic defects due to its formation in β -Ga₂O₃ bulk crystals and thin-films upon proton irradiation [18–20]. Furthermore, the concentration of E_2^* in proton-irradiated β -Ga₂O₃ bulk crystals and thin-films increases upon heat treatments in the range of 650 K, indicating the formation of E_2^* through a thermally-activated process [19]. However, no structural origin has so far been attributed to E_2^* .

The position of the Fermi level can have a pronounced influence on defect formation processes via the contribution of the electron chemical potential to defect formation energies [21–23]. Particularly, it has been shown that several defect signatures are introduced in the space-charge region of β -Ga₂O₃ Schottky barrier diodes (SBDs) when the diodes are exposed to elevated temperatures in conjunction with an applied bias voltage, causing a change in the Fermi-level position within the space-charge region [24]. Moreover, hydrogen (H) can play an important role in defect formation because H is expected to be mobile at or slightly above room temperature in β -Ga₂O₃, and has been shown to form complexes with various acceptor defects [23, 25–27].

Here, we report on the formation of the defect level E_2^* in β -Ga₂O₃ thin-films subjected to helium- (He) and H-implantation using deep level transient spectroscopy (DLTS). We observe that the introduction of E_2^* is promoted by annealing samples subjected to H- or He-implantation under an applied reverse-bias voltage. Annealing the corresponding samples without an applied reverse-bias voltage leads to a decrease in the E_2^* concentration. Thus, annealing implanted β -Ga₂O₃ thin-films with and without an applied reverse-bias voltage can be used to control the concentration of E_2^* . Notably, a more pronounced decrease in the E_2^* concentration is seen for heat treatments without an applied reverse-bias voltage in the presence of H. We propose that E_2^* is associated with a defect complex forming more preferably when the Fermi level is further away from E_C . Importantly, at Fermi-level positions closer to E_C , a different defect complex or configuration is more likely to form that does not give rise to a charge-state transition level accessible for our DLTS measurements. Moreover, for Fermi-level positions close to E_C , H is proposed to form a hydrogenated defect complex that competes with the defect giving rise to E_2^* . Finally, based on a discussion of the present results in light of first-principles defect calculations available in the literature, di-vacancy complexes

formed by oxygen vacancies (V_O) and gallium vacancies (V_{Ga}) are proposed as a promising class of candidates for E_2^* .

2. Experimental

β -Ga₂O₃ thin-films (thickness $\approx 10 \mu\text{m}$) grown by halide vapor-phase epitaxy (HVPE) [4] on conductive β -Ga₂O₃ substrates were obtained from Novel Crystal Technology, Inc. [28]. More information regarding the morphology and microstructure of the HVPE grown β -Ga₂O₃ thin-films can be found in [4, 29, 30]. Samples measuring $(5 \times 5) \text{ mm}^2$ were cut with a laser cutter, and cleaned inside an ultrasonic bath using acetone, isopropanol and de-ionized water prior to fabricating SBDs by depositing suitable metals. The metals were deposited using e-beam evaporation, with Ti/Al (thickness = 10 nm/120 nm) serving as the Ohmic area back contact, whereas circular Ni pads (thickness = 150 nm) with diameters of 480 μm or 830 μm , respectively, were used as Schottky front contacts [31]. Per sample, around 10–15 Ni pads were deposited, i.e. 10–15 SBDs were obtained per sample.

Capacitance–voltage (CV), current–voltage (IV) and DLTS measurements were performed using a setup described in detail in [32, 33]. CV and IV measurements were performed in the dark and at room temperature. Generally, all investigated SBDs exhibited a rectification of several orders of magnitude when comparing the current at reverse and forward bias as well as very low conductance values. The depth distribution of the charge-carrier concentration (n) was computed from CV measurements [34] and is denoted as n -profile. A relative static dielectric constant (ϵ_s) of 10.2 was assumed for β -Ga₂O₃ [35].

DLTS measurements were performed in the temperature range from 290 K to 450 K during heating of the sample with 2 K min^{-1} . DLTS spectra were constructed using a lock-in (GS2) filter [34, 36]. All DLTS measurements were performed at a reverse-bias voltage of -8 V or -4 V and utilized pulse voltages of 8 V or 4 V. Parameters describing the traps present in the space-charge region, such as the trap concentration (N_t), the activation energy (E_A) and the apparent capture cross section (σ_{na}) were extracted by simulating the recorded DLTS spectra with a python-based script. From results obtained on various SBDs comprising HVPE-grown β -Ga₂O₃ thin-films, the uncertainty in E_A is estimated to be around 0.10 eV, whereas the uncertainty in σ_{na} can be expected to be within $\pm$ an order of magnitude. Notably, using DLTS measurements, it is possible to observe comparatively low defect concentrations present in the space-charge region of SBDs [34]. Thus, DLTS measurements are particularly suitable to study the introduction of defects upon ion implantation and subsequent reverse-bias and zero-bias anneals performed on SBDs.

The setup utilized for DLTS measurements was also used for heat treatments of SBDs up to 680 K. Specifically, the heat treatments were conducted inside a metal cylinder which was evacuated using a roughing pump and a turbo pump. Thus, the anneals were performed in vacuum and in the dark. Inside

the metal cylinder, the sample was placed on a ceramic sample stage with a conductive wire in its center. For electrical contact, the sample's Ohmic area back contact was placed on top of the conductive wire, whereas one of the sample's circular Schottky front contact pads was electrically connected by placing a needle on top of the contact to be annealed. A Boonton 7200 capacitance meter was used to apply a bias voltage during the heat treatments if desired. Typical annealing experiments (annealing cycle) consisted of (i) heating the sample with a specific heating ramp to the desired annealing temperature, (ii) keeping the sample at the annealing temperature for a specific time and (iii) a cool-down of the sample with a specific cooling ramp to room temperature. The duration of the anneal refers to the time the sample was kept at the annealing temperature, excluding the time it took for heating and cooling. The heating was performed using a resistive heating element thermally connected to the sample stage, whereby the sample temperature was recorded with a calibrated thermistor placed on top of the sample stage in the vicinity of the sample. For cooling, the sample stage was brought in thermal contact with liquid nitrogen (LN₂) while the resistive heater was used to obtain the desired cooling rate. Typically, heating and cooling rates of approximately 6 K min⁻¹ were utilized. Heat treatments with an applied reverse-bias voltage are denoted as reverse-bias anneals, whereas heat treatments without an applied bias voltage are referred to as zero-bias anneals. For reverse-bias anneals, a reverse bias voltage was applied during the whole annealing cycle. Unless stated otherwise, reverse-bias anneals were performed using an applied reverse-bias voltage of -8 V.

All H- and He-implantations were performed at room temperature through the Ni contacts, using kinetic energies (E) of 180 keV to 220 keV for H and 500 keV for He. The projected range (R_p) for defect generation due to the ion implantation was computed utilizing Monte-Carlo simulations as implemented within the *The Stopping and Range of Ions in Matter* package [37] using default displacement energies for Ga and O of 25 eV and 28 eV, respectively. For H implantation, R_p^H is between 850 nm and 1050 nm, whereas for He implantation, R_p^{He} is around 1150 nm. Typical ion fluences for implantation (Φ) were in the range of $5 \times 10^{12} \text{ cm}^{-2}$ – $1 \times 10^{13} \text{ cm}^{-2}$ for H and $1 \times 10^{10} \text{ cm}^{-2}$ – $1 \times 10^{11} \text{ cm}^{-2}$ for He.

3. Results and discussion

Figures 1 (a) and (b) display n -profiles recorded on a HVPE-grown β -Ga₂O₃ thin-film after He implantation, and subsequent reverse-bias and zero-bias anneals at 650 K. In figure 1 (a), results are shown for a SBD immediately after He implantation, and after reverse-bias and zero-bias anneals. After He implantation, the region around R_p^{He} is partly compensated, as evidenced by a reduction in the charge-carrier concentration. The first heat treatment leads to a restoration of the charge-carrier concentration, whereas subsequent heat treatments result only in minor changes in the

n -profile, in accordance with previous reports [19, 38, 39]. In figure 1 (b), n -profiles for a second SBD on the same HVPE-grown β -Ga₂O₃ thin-film are shown. Here, results are displayed after an initial zero-bias anneal, and for subsequent reverse-bias and zero-bias anneals. The n -profiles do not change significantly after the heat treatments, which indicates that the probing depth expected for DLTS measurements (W) does not change significantly during subsequent DLTS measurements.

Figures 1 (c) and (d) show DLTS spectra recorded on the same SBDs whose n -profiles are shown in panels (a) and (b), respectively. Immediately after He implantation (see figure 1 (c)), a defect signature commonly labeled as E_2 ($E_A = 0.74$ eV, $\sigma_{na} = 1 \times 10^{-16} \text{ cm}^2$) can be seen which has previously been identified as $\text{Fe}_{\text{Ga}}^{0/-}$ (charge-state transition from neutral Fe^{3+} to an Fe^{2+} acceptor state substituting on an octahedral Ga site) [18, 33]. E_2 was also present in as-received HVPE-grown β -Ga₂O₃ thin-films (not shown), and no change is observed during the subsequent heat treatments, in accordance with previous reports [19]. Additionally, in figure 1 (c), a shoulder can be seen on the low temperature side of E_2 , indicating the presence of another defect level where one would expect E_2^* to occur [18, 19]. After a subsequent reverse-bias anneal at 650 K, E_2^* ($E_A = 0.71$ eV, $\sigma_{na} = 1 \times 10^{-19} \text{ cm}^2$) is introduced with a significantly higher concentration, in accordance with the observations reported in [19]. Notably, the simulations performed to extract E_A , σ_{na} and N_t do not capture the corresponding signature entirely, indicating the presence of several overlapping defect signatures. The E_2^* concentration decreases after a subsequent zero-bias anneal at 650 K. Notably, the E_2^* concentration observed using DLTS measurements is very low, i.e. we do not expect detectable changes in the microstructure of our samples related to the formation and removal of E_2^* .

Importantly, reversing the order of the heat treatment sequence by starting with a zero-bias anneal at 650 K (see figure 1 (d)) results in a reduced introduction of E_2^* upon the initial heat treatment. The effect of reverse-bias annealing is further demonstrated by the subsequent reverse-bias anneal at 650 K, where a considerable increase in the E_2^* concentration can be observed. Interestingly, the concentration of E_2^* does not increase further when the sample is subjected to an additional reverse-bias anneal at 650 K (not shown). Moreover, the concentration associated with E_2^* can be altered by additional heat treatments: subsequent zero-bias and reverse-bias anneals at 650 K cause the concentration to decrease and increase, respectively. However, the E_2^* concentration after the second reverse-bias anneal is lower than what was observed after the first reverse-bias anneal, suggesting that the formation and removal of E_2^* is not entirely reversible. Importantly, it is not possible to decrease the E_2^* concentration by zero-bias annealing to the value which had been observed prior to the first reverse-bias anneal. This strong dependence on device history should be considered in the context of understanding the formation of E_2^* across the literature [14, 15, 18–20].

Figure 1. (a), (b) n -profiles and (c), (d) DLTS spectra recorded on a HVPE-grown β -Ga₂O₃ thin-film after He implantation ($E = 500 \text{ keV}$, $\Phi = 2.5 \times 10^{10} \text{ cm}^{-2}$). Data (filled circles and triangles) are shown for two different SBDs located on the same HVPE-grown β -Ga₂O₃ thin-film. The SBDs were subjected to a different order of heat treatments after He implantation as listed in (a) and (b), where the order is indicated by roman letters. DLTS spectra were recorded using a reverse-bias voltage of -8 V and a pulse voltage of 8 V . R_p^{He} and the probing depth W expected in DLTS measurements are marked in (a) and (b). In (c) and (d) simulated DLTS spectra are shown as solid lines and the positions of the defect levels E_2^* and E_2 are indicated.

Next, we investigated the impact of H on the formation of E_2^* . Figure 2 shows DLTS spectra recorded on two different SBDs located on a HVPE-grown β -Ga₂O₃ thin-film subjected to H implantation and subsequent heat treatments. Figure 2 (a) shows DLTS spectra for one of the SBDs after H implantation and subsequent heat treatments at 650 K in the order: reverse-bias, zero-bias, and reverse-bias anneal. After the first reverse-bias anneal, E_2^* is seen in pronounced concentration. Subsequently, the SBD was subjected to a zero-bias anneal, and the concentration related to E_2^* is significantly lowered. Finally, the SBD was subjected to a reverse-bias anneal, and the concentration associated with E_2^* increases yet again. Interestingly, the E_2^* concentration after the second reverse-bias anneal is not as large as after the first one, and hence it seems like the introduction and removal of E_2^* is not entirely reversible regardless whether H is present or not (see figure 1). Notably, the response of E_2^* to reverse-bias and zero-bias anneals is similar for He- and H-implantation, i.e. the E_2^* concentration increases upon reverse-bias annealing, whereas it decreases due to zero-bias annealing. However, the decrease of the E_2^* concentration upon zero-bias anneals is more pronounced for the case of H implantation (see figure 2) compared to the case of He implantation (see figure 1).

In contrast to what has been observed for He implantation (see figure 1), anneals affect the E_2 concentration for H-implanted HVPE-grown β -Ga₂O₃ thin-films. Particularly, the E_2 concentration decreases due to zero-bias anneals, and increases during subsequent reverse-bias anneals. This behavior could be related to the formation and dissociation of complexes involving Fe and H [40].

Figure 2 (b) shows DLTS spectra for the H-implanted sample recorded on a second SBD subjected to a reversed order of heat treatments: zero-bias, reverse-bias, and zero-bias anneal. E_2^* is not observed when the first heat treatment is performed without an applied reverse-bias voltage. Subsequent reverse- and zero-bias anneals at 650 K cause the concentration associated with E_2^* to increase and decrease, respectively.

Further investigations were conducted by He- and subsequent H-implantation to further study the role of H, and the corresponding results are displayed in figure 3. Figure 3 (a) shows DLTS spectra recorded on a HVPE-grown β -Ga₂O₃ thin-film subjected to He- and H-implantation, and subsequent heat treatments at temperatures between 625 K and 680 K . Although E_2^* was not observed after the ion implantations or the subsequent zero-bias anneal, its concentration can be enhanced considerably by reverse-bias annealing at 625 K .

Figure 2. DLTS spectra recorded on a HVPE-grown β -Ga $_2$ O $_3$ thin-film after H implantation ($E = 180$ keV, $\Phi = 1 \times 10^{13}$ cm $^{-2}$). Data (filled circles) are shown for two different SBDs located on the same HVPE-grown β -Ga $_2$ O $_3$ thin-film. The SBDs were subjected to a different order of heat treatments after the H implantation and the order is indicated by roman letters. Simulated DLTS spectra are shown as solid lines and the positions of the defect levels E_2^* and E_2 are indicated. DLTS spectra were recorded using a reverse-bias voltage of -8 V and a pulse voltage of 8 V. The probing depth expected for the DLTS measurements did not change significantly for the different heat treatments.

Figure 3. (a) DLTS spectra recorded on a HVPE-grown β -Ga $_2$ O $_3$ thin-film after He- ($E = 500$ keV, $\Phi = 1.25 \times 10^{10}$ cm $^{-2}$) and H-implantation ($E = 220$ keV, $\Phi = 5 \times 10^{12}$ cm $^{-2}$). Data (filled circles) are shown for a SBD subjected to different heat treatments after the ion implantations and their order is indicated by roman letters. Notably, the annealing duration stated for step III is the accumulated annealing duration, i.e. no zero-bias anneal was performed in-between step II and III. Simulated DLTS spectra are shown as solid lines and the positions of the defect levels E_2^* and E_2 are indicated. DLTS spectra were recorded using a reverse-bias voltage of -8 V and a pulse voltage of 8 V. The probing depth expected for the DLTS measurements did not change significantly for the different heat treatments. (b) Arrhenius plot constructed using the steady-state concentrations related to E_2^* ($[E_2^*]_{ss}$) obtained by heat-treating a HVPE-grown β -Ga $_2$ O $_3$ thin-film subjected to He- and H-implantation at different temperatures T_{ann} under an applied reverse-bias voltage of -8 V. From linear fits to the data (solid lines), the corresponding activation energy is estimated to be around 1.0 eV to 1.3 eV.

Subsequent reverse-bias and zero-bias anneals for the He- and H-implanted sample cause changes in the concentration of E_2^* similar to the changes observed in the H- or He-implanted samples, i.e. the concentration related to E_2^* can be increased by reverse-bias annealing and decreased by zero-bias annealing. Furthermore, the introduction of E_2^* exhibits a pronounced dependence on the duration of the reverse-bias anneal, as evidenced by the increased E_2^* concentration for the 40 min - long reverse-bias anneal as compared to the 20 min - long reverse-bias anneal. When the sample receives a subsequent zero-bias anneal at 650 K, the concentration associated with E_2^* decreases. Similar to what has been observed for H implantation (see figure 2), the zero-bias anneal decreases the concentration of E_2^* to the same value that was observed prior to the initial reverse-bias anneal. Notably, no changes in the

E_2 concentration are observed during zero-bias or reverse-bias anneals.

Reverse-bias anneals similar to the ones shown in figure 3 (a) were performed for annealing temperatures (T_{ann}) of 580 K, 600 K and 625 K using an applied reverse-bias voltage of -8 V. The reverse-bias anneals were conducted using different accumulated annealing durations (t_{ann}) without performing zero-bias anneals in-between the reverse-bias anneals performed at the same T_{ann} . However, zero-bias anneals were performed when switching to a different T_{ann} , i.e. the initial E_2^* concentration is nearly the same for each T_{ann} . The corresponding results were used to study the thermally-activated introduction of E_2^* assuming first order kinetics: $[E_2^*] = [E_2^*]_{ss} [1 - \exp(-kt_{ann})]$, where $[E_2^*]_{ss}$ denotes the E_2^* concentration ($[E_2^*]_1$) in steady-state and k denotes the

Figure 4. DLTS spectra recorded on a HVPE-grown β -Ga₂O₃ thin-film after He implantation ($E = 500$ keV, $\Phi = 1.25 \times 10^{10}$ cm⁻²) and H implantation ($E = 220$ keV, $\Phi = 5 \times 10^{12}$ cm⁻²) and subsequent reverse-bias anneals at 600 K for 90 min. The reverse-bias anneals were performed at -4 V (filled blue circles) and -8 V (filled black circles). Different parts of the space-charge region were probed by performing DLTS measurements using different combinations of reverse bias (V_{bias}) and pulse voltages (V_{pulse}). The respective pairs of V_{bias} and V_{pulse} are stated in the subplots. Simulated DLTS spectra are shown as solid lines and the positions of the defect levels E_2^* and E_2 are indicated.

introduction rate. Interestingly, k was found to be similar for all T_{ann} and exhibited values of around $1/3000$ s⁻¹. The resulting Arrhenius plot for $[E_2^*]_{\text{ss}}$ is shown in figure 3 (b), and an activation energy of 1.0 eV to 1.3 eV was derived from linear fits to the data for the introduction of E_2^* under an applied reverse-bias voltage of -8 V. No change in the E_2^* concentration was observed for heat treatments below 500 K regardless of the kind of ion implantation or whether an external bias voltage was applied or not.

Further experiments were conducted to investigate the influence of the magnitude of the reverse-bias voltage applied during reverse-bias anneals. Figure 4 shows DLTS spectra recorded on a HVPE-grown β -Ga₂O₃ thin-film after implantation with He and H, and subsequent reverse-bias anneals at 600 K for 90 min using an applied reverse-bias voltage of either -4 V or -8 V. The reverse-bias anneal at -4 V was performed prior to the one at -8 V, and the SBD was subjected to a zero-bias anneal before performing the reverse-bias anneal at -8 V. Thus, the concentration associated with E_2^* was low prior to both reverse-bias anneals. When performing the heat treatment under a reverse-bias voltage of -8 V, the Fermi level is shifted further away from E_C inside the corresponding space-charge region, and hence in-between the surface of the HVPE-grown β -Ga₂O₃ thin-film and $W(-8$ V). Consequently, the Fermi level is affected up to a depth of $W(-4$ V) for a heat treatment under an applied reverse-bias voltage of -4 V. In figure 4 (a), DLTS measurements were performed that probe mainly the region from $W(-8$ V) to $W(-4$ V), and E_2^* is only detected in significantly increased concentration for the heat treatment performed under an applied reverse-bias voltage of -8 V. This suggests that E_2^* is only introduced inside the space-charge region established during the heat treatment. Figure 4 (b) shows DLTS spectra recorded for a probing depth between $W(-4$ V) and the surface of the HVPE-grown β -Ga₂O₃ thin-film. An increased concentration of E_2^* can be seen for the reverse-bias anneals performed at -8 V and -4 V. Importantly, the concentration related to E_2^* is significantly higher for the reverse-bias anneal performed at -8 V. In

figure 4 (c), DLTS spectra are shown for a probing depth of $W(-8$ V) to the surface. Although both reverse-bias anneals increase the concentration of E_2^* , the reverse-bias anneal at -8 V produces a larger concentration than the anneal at -4 V. The results presented in figure 4 show that E_2^* is introduced inside the space-charge region of SBDs subjected to reverse-bias anneals, and that applying a larger reverse-bias voltage during the heat treatments leads to the introduction of a larger amount of E_2^* , suggesting that the defect associated with E_2^* forms more preferably the further away the Fermi-level position is from E_C . The E_2 concentration is not influenced by the reverse-bias anneals. Its concentration depends, however, on the probing depth of the DLTS measurement which is most likely related to the λ -correction [34] and/or a slightly inhomogeneous depth distribution of Fe.

To summarize our findings, the formation of E_2^* after ion implantation due to a thermally-activated process suggests a relation of E_2^* to a defect complex comprising at least one intrinsic defect. This is in accordance with a previous study on proton-irradiated β -Ga₂O₃ single crystals and thin-films [19]. The formation of E_2^* is considerably enhanced by reverse-bias anneals at temperatures of around 600 K, and its formation is seen to occur inside the space-charge region of SBDs. Notably, E_2^* is introduced to a larger extent when applying larger reverse-bias voltages during reverse-bias anneals. Zero-bias anneals can be used to decrease the concentration of E_2^* . The presence of H does not significantly affect the observed introduction of E_2^* , but seems to aid the removal of E_2^* when performing zero-bias anneals.

The formation and removal behavior of E_2^* upon reverse-bias and zero-bias anneals can be explained by at least two scenarios: (i) the defect complex giving rise to E_2^* consists of constituent defects, which have a barrier for migration that depends strongly on their charge states, and hence the Fermi-level position, or (ii) the defect complex associated with E_2^* has several configurations, where only one (or a few) have a charge-state transition level giving rise to E_2^* . The configuration associated with E_2^* is more likely to form when

the Fermi level is far away from E_C , whereas configurations that do not exhibit a charge-state transition level accessible for our DLTS measurements are more favorable for Fermi-level positions close to E_C .

Scenario (i) is supported by computational studies reporting a strong dependence of the migration barrier of intrinsic defects in β -Ga₂O₃ on their respective charge state [19, 41, 42]. For example, V_O exhibits a lower migration barrier in the +2 charge state compared to the one found for the neutral charge state [42]. However, the observation of a reversible formation and removal of the defect giving rise to E_2^* is challenging to reconcile with scenario (i). Rather, one would expect that the mobile defect either leaves or enters the space-charge region during the heat treatment, and thus either the removal or formation of a defect will be observed within the space-charge region. Additionally, the dependence of the introduction of E_2^* on the magnitude of the applied reverse-bias voltage is inconsistent with scenario (i). For example, for the situation displayed in figure 4 (b), one would expect a similar E_2^* concentration to be introduced regardless of the reverse-bias voltage applied during the reverse-bias anneal. In contrast, we observed a dependence of the introduced concentration of E_2^* on the magnitude of the applied reverse-bias voltage.

Scenario (ii), however, seems to be in better agreement with the experimental observations. Within scenario (ii), it is expected that the formation and removal of E_2^* will be reversible. The degree of reversibility will, however, be influenced by other factors, e.g. the presence of other defects and the transformation dynamics between different defect configurations. The observation of a thermally-activated steady-state concentration of E_2^* also agrees with scenario (ii) where the formation and removal of E_2^* is related to a Fermi-level-dependent difference in formation energy, i.e. the equilibrium concentration of E_2^* will depend on the Fermi-level position. Thus, we also expect the formation of E_2^* to gradually depend on the magnitude of the applied reverse-bias voltage, in accordance with our observations. We derived an activation energy on the order of around 1.0 eV–1.3 eV for the thermally-activated formation of E_2^* (see figure 3 (b)). Within scenario (ii), this activation energy can be interpreted as the difference in relative formation energy between the defect configuration giving rise to E_2^* and competing defect configurations without a charge-state transition level accessible for our DLTS measurements.

The introduction of E_2^* does not seem to be influenced by the presence of H. In contrast, the removal of E_2^* due to zero-bias anneals is promoted in the presence of H. Within scenario (ii), H is proposed to form a hydrogenated version of the defect complex being connected to E_2^* , and this hydrogenated defect complex is more likely to form than the non-hydrogenated version for Fermi-level positions close to E_C . Thus, H promotes the removal of E_2^* during zero-bias annealing. For Fermi-level positions further away from E_C , the hydrogenated defect complex is not as likely to form, and thus plays only a minor or no role in the actual formation of E_2^* . Notably, for scenario (ii) to be able to explain the experimental results, the transformation between different defect configurations needs to be possible

at the temperatures used for the heat treatments, whereby the kinetics of transformation may depend on the charge states of the involved defects.

Further work is necessary to identify the specific defect(s) giving rise to E_2^* . However, the formation and removal behavior of E_2^* after ion implantation and proton irradiation and the similarity in behavior seen for a wide range of different β -Ga₂O₃ samples implies the association with a defect complex either involving only intrinsic defects or comprising an intrinsic defect and an ubiquitous impurity [19]. Based on these observations, one may speculate about the origin of E_2^* . For example, di-vacancy complexes formed by V_{Ga} and V_O (V_{Ga}–V_O) possess many of the proposed features; they are intrinsic defect complexes that are expected to exhibit one or more charge-state transition levels in the proposed energy range, and they have a multitude of different configurations [19, 23]. Notably, the formation energies of various V_{Ga}–V_O complexes have been found to be comparatively low in β -Ga₂O₃, and can be expected to strongly depend on the Fermi-level position [19]. Moreover, V_{Ga}–V_O complexes display acceptor behavior for Fermi-level positions close to E_C [19], and thus hydrogenation is likely [23]. Importantly, the migration barriers computed for isolated V_{Ga} and V_O suggest that defect transformation involving vacancies will be possible at temperatures around 600 K [23, 42]. However, first-principles calculations are only reported for a few V_{Ga}–V_O configurations so far, and are not sufficient to explain the experimental observations entirely [19], which warrants further investigations.

4. Summary and conclusion

The formation and removal of E_2^* ($E_A = 0.71$ eV, $\sigma_{na} = 1 \times 10^{-19}$ cm²) in HVPE-grown β -Ga₂O₃ thin-films subjected to ion implantation and subsequent heat treatments was studied using DLTS. The introduction of E_2^* is promoted by reverse-bias anneals at temperatures in the range of 600 K within the space-charge region of SBDs comprising the β -Ga₂O₃ thin-films subjected to He- and/or H-implantation. Subsequent zero-bias anneals at temperatures in the range of 600 K cause the concentration of E_2^* to decrease, whereby the removal of E_2^* is more pronounced if H is present in the space-charge region of the SBD. The formation of E_2^* by reverse-bias annealing is a thermally-activated process with an activation energy of 1.0 eV–1.3 eV. In summary, our results show how reverse-bias and zero-bias anneals can be used to control the concentration of E_2^* in SBDs comprising He- and/or H-implanted β -Ga₂O₃ thin-films. Importantly, it is shown that H can aid the removal of E_2^* . The results presented here strongly suggest that E_2^* is likely to form in the space-charge region of β -Ga₂O₃-based devices for power electronics if the constituent defects of E_2^* are present. Moreover, it can be expected that the E_2^* concentration will change during device operation, which suggests the importance of device preparation and measurement history in the growing number of reports about E_2^* in β -Ga₂O₃. These points are particularly relevant taking into account that E_2^* has

been shown to influence the performance of β -Ga₂O₃-based MESFETs [14, 15].

The observed formation behavior of E_2^* is explained by a change in the Fermi-level position inside the space-charge region when applying a reverse-bias voltage. Thus, we propose that E_2^* is related to a defect complex involving intrinsic defects that exhibits different configurations whose relative formation energies depend strongly on the Fermi-level position. Configurations giving rise to E_2^* are more likely to form for Fermi-level positions further away from E_C (reverse-bias annealing), whereas configurations that are preferred for Fermi-level positions close to E_C (zero-bias annealing) do not exhibit defect levels accessible for our DLTS measurements. Furthermore, E_2^* can be passivated by H, and the hydrogenated defect complex is proposed to be more likely to form for Fermi-level positions close to E_C . Divacancy complexes of the form $V_{Ga}-V_O$ are proposed as potential candidates for E_2^* , but further experimental and computational investigations are required for an unambiguous identification of the specific structural defect associated with E_2^* .

Acknowledgment

Financial support is acknowledged from the Research Council of Norway through the FUNDAMENT project (project number: 251131), the Norwegian Micro- and Nano-Fabrication Facility (NorFab, project number: 245963) and the Faculty of Mathematics and Natural Sciences at the University of Oslo via the strategic research initiative FOXHOUND. This work was partially performed under the auspices of the U.S. DOE by Lawrence Livermore National Laboratory under contract DE-AC52-07NA27344, and supported by the Critical Materials Institute, an Energy Innovation Hub funded by the U.S. DOE, Office of Energy Efficiency and Renewable Energy, Advanced Manufacturing Office.

ORCID iDs

C Zimmermann <https://orcid.org/0000-0003-3708-6074>
L Vines <https://orcid.org/0000-0001-5759-7192>

References

- [1] Higashiwaki M, Sasaki K, Murakami H, Kumagai Y, Koukitu A, Kuramata A, Masui T and Yamakoshi S 2016 Recent progress in Ga₂O₃ power devices *Semicond. Sci. Technol.* **31** 034001
- [2] Nakagomi S, Momo T, Takahashi S and Kokubun Y 2013 Deep ultraviolet photodiodes based on β -Ga₂O₃/SiC heterojunction *Appl. Phys. Lett.* **103** 072105
- [3] Nakagomi S, Sato T, Takahashi Y and Kokubun Y 2015 Deep ultraviolet photodiodes based on the β -Ga₂O₃/GaN heterojunction *Sensors Actuators A* **232** 208–13
- [4] Mastro M A, Kuramata A, Calkins J, Kim J, Ren F and Pearton S J 2017 Perspective - Opportunities and future directions for Ga₂O₃ *ECS J. Solid State Sci. Technol.* **6** P356–9
- [5] Galazka Z 2018 β -Ga₂O₃ for wide-bandgap electronics and optoelectronics *Semicond. Sci. Technol.* **33** 113001
- [6] Pearton S J, Yang J, Cary P H, Ren F, Kim J, Tadjer M J and Mastro M A 2018 A review of Ga₂O₃ materials, processing and devices *Appl. Phys. Rev.* **5** 011301
- [7] Galazka Z et al 2014 On the bulk β -Ga₂O₃ single crystals grown by the Czochralski method *J. Cryst. Growth* **404** 184–91
- [8] Galazka Z et al 2017 Scaling-up of bulk β -Ga₂O₃ single crystals by the Czochralski method *ECS J. Solid. State. Sc.* **6** Q3007–Q3011
- [9] Aida H, Nishiguchi K, Takeda H, Aota N, Sunakawa K and Yaguchi Y 2008 Growth of β -Ga₂O₃ single crystals by the edge-defined, film fed growth method *Japan. J. Appl. Phys.* **47** 8506–9
- [10] Kuramata A, Koshi K, Watanabe S, Yamaoka Y, Masui T and Yamakoshi S 2016 High-quality β -Ga₂O₃ single crystals grown by edge-defined film-fed growth *Japan. J. Appl. Phys.* **55** 1202A2
- [11] Ahmadi E, Koksaldi O S, Zheng X, Mates T, Oshima Y, Mishra U K and Speck J S 2017 Demonstration of β -(Al_{1-x}Ga_x)₂O₃/ β -Ga₂O₃ modulation doped field-effect transistors with Ge as dopant grown via plasma-assisted molecular beam epitaxy *Appl. Phys. Express* **10** 071101
- [12] Krishnamoorthy S, Xia Z, Bajaj S, Brenner M and Rajan S 2017 Delta-doped β -gallium oxide field-effect transistor *Appl. Phys. Express* **10** 051102
- [13] Krishnamoorthy S et al 2017 Modulation-doped β -(Al_{0.2}Ga_{0.8})₂O₃/ β -Ga₂O₃ field-effect transistor *Appl. Phys. Lett.* **111** 023502
- [14] McGlone J F, Xia Z, Joishi C, Lodha S, Rajan S, Ringel S and Arehart A R 2019 Identification of critical buffer traps in Si δ -doped β -Ga₂O₃ MESFETs *Appl. Phys. Lett.* **115** 153501
- [15] McGlone J F, Xia Z, Zhang Y, Joishi C, Lodha S, Rajan S, Ringel S A and Arehart A R 2018 Trapping effects in Si δ -doped β -Ga₂O₃ MESFETs on an Fe-doped β -Ga₂O₃ substrate *IEEE Electron Device Lett.* **39** 1042–5
- [16] Huang S-S, Lopez R, Paul S, Neal A T, Mou S, Hwang M-P and Li J V 2018 β -Ga₂O₃ defect study by steady-state capacitance spectroscopy *Japan. J. Appl. Phys.* **57** 091101
- [17] Neal A T, Mou S, Lopez R, Li J V, Thomson D B, Chabak K D and Jessen G H 2017 Incomplete ionization of a 110 meV unintentional donor in β -Ga₂O₃ and its effect on power devices *Sci. Rep.* **7** 13218
- [18] Ingebrigtsen M E, Varley J B, Yu Kuznetsov A, Svensson B G, Alfieri G, Mihaila A, Badstübner U and Vines L 2018 Iron and intrinsic deep level states in Ga₂O₃ *Appl. Phys. Lett.* **112** 042104
- [19] Ingebrigtsen M E, Yu Kuznetsov A, Svensson B G, Alfieri G, Mihaila A, Badstübner U, Perron A, Vines L and Varley J B 2019 Impact of proton irradiation on conductivity and deep level defects in β -Ga₂O₃ *APL Mater.* **7** 022510
- [20] Polyakov A Y et al 2018 Point defect induced degradation of electrical properties of Ga₂O₃ by 10 MeV proton damage *Appl. Phys. Lett.* **112** 032107
- [21] Chantre A 1989 Introduction to defect bistability *Appl. Phys. Rev. A* **48** 3–9
- [22] Van de Walle C G and Neugebauer Jorg 2004 First-principles calculations for defects and impurities: Applications to III-nitrides *J. Appl. Phys.* **95** 3851–79
- [23] Varley J B, Peelaers H, Janotti A and Van de Walle C G 2011 Hydrogenated cation vacancies in semiconducting oxides *J. Phys.: Condens. Matter* **23** 334212
- [24] Ingebrigtsen M E, Yu Kuznetsov A, Svensson B G, Alfieri G, Mihaila A and Vines L 2019 Generation and metastability of deep level states in β -Ga₂O₃ exposed to reverse bias at elevated temperatures *J. Appl. Phys.* **125** 185706
- [25] Qin Y, Stavola M, Beall Fowler W, Weiser P and Pearton S J 2019 Hydrogen centers in β -Ga₂O₃: Infrared spectroscopy

- and density functional theory *ECS J. Solid. State. Sc.* **8** Q3103–Q3110
- [26] Weiser P, Stavola M, Beall Fowler W, Qin Y and Pearton S 2018 Structure and vibrational properties of the dominant OH center in β -Ga₂O₃ *Appl. Phys. Lett.* **112** 232104
- [27] Ritter J R, Huso J, Dickens P T, Varley J B, Lynn K G and McCluskey M D 2018 Compensation and hydrogen passivation of magnesium acceptors in β -Ga₂O₃ *Appl. Phys. Lett.* **113** 052101
- [28] Novel Crystal Technology, Inc 2020 www.novelpcrystal.co.jp/eng/ (Accessed: 12 February 2020)
- [29] Mahadik N A, Tadjer M J, Bonanno P L, Hobart K D, Stahlbush R E, Anderson T J and Kuramata A 2019 High-resolution dislocation imaging and micro-structural analysis of HVPE- β Ga₂O₃ films using monochromatic synchrotron topography *APL Mater.* **7** 022513
- [30] Murakami H et al 2014 Homoepitaxial growth of β -Ga₂O₃ layers by halide vapor phase epitaxy *Appl. Phys. Express* **8** 015503
- [31] Ingebrigtsen M E, Vines L, Alfieri G, Mihaila A, Badstübner U, Svensson B G and Kuznetsov A 2017 Bulk β -Ga₂O₃ with (010) and (201) surface orientation: Schottky contacts and point defects *Mater. Sci. Forum* **897** 755–8
- [32] Svensson B G, Rydén K-H and Lewerentz B M S 1989 Overlapping electron traps in n-type silicon studied by capacitance transient spectroscopy *J. Appl. Phys.* **66** 1699–704
- [33] Zimmermann C et al 2020 Ti- and Fe-related charge transition levels in β -Ga₂O₃ *Appl. Phys. Lett.* **116** 072101
- [34] Blood P and Orton J W 1992 *The Electrical Characterization of Semiconductors: Majority Carriers and Electron States* (New York: Academic)
- [35] Passlack M, Hunt N E J, Schubert E F, Zydzik G J, Hong M, Mannaerts J P, Opila R L and Fischer R J 1994 Dielectric properties of electron beam deposited Ga₂O₃ films *Appl. Phys. Lett.* **64** 2715–17
- [36] Istratov A A 1997 New correlation procedure for the improvement of resolution of deep level transient spectroscopy of semiconductors *J. Appl. Phys.* **82** 2965–8
- [37] Ziegler J F, Ziegler M D and Biersack J P 2010 SRIM – The stopping and range of ions in matter *Nucl. Instrum. Meth. Phys. Res. B* **268** 1818–23
- [38] Wong M H, Takeyama A, Makino T, Ohshima T, Sasaki K, Kuramata A, Yamakoshi S and Higashiwaki M 2018 Radiation hardness of β -Ga₂O₃ metal-oxide-semiconductor field-effect transistors against gamma-ray irradiation *Appl. Phys. Lett.* **112** 023503
- [39] Kim J, Pearton S J, Fares C, Yang J, Ren F, Kim S and Polyakov A Y 2019 Radiation damage effects in Ga₂O₃ materials and devices *J. Mater. Chem. C* **7** 10–24
- [40] Higashiwaki M and Fujita S 2020 *Gallium Oxide* (Berlin: Springer)
- [41] Zimmermann C, Rønning V, Frodason Y K, Varley J B, Bobal V and Vines L 2020 Primary intrinsic defects and their charge transition levels in β -Ga₂O₃ *Phys. Rev. Mater.* **4** 074605
- [42] Kyrtos A, Matsubara M and Bellotti E 2017 Migration mechanisms and diffusion barriers of vacancies in Ga₂O₃ *Phys. Rev. B* **95** 245202